

American National Standard

designation system

for unalloyed aluminum

Approved November 7, 2013

Secretariat: The Aluminum Association, Inc.

1. Scope

1.1 This standard provides a system for designating unalloyed aluminum not made by a refining process and used primarily for remelting.

1.2 Unalloyed wrought aluminum designations (10xx series with specified minimum aluminum and limits for natural impurities), are assigned and registered in accordance with ANSI H35.1.

2. Unalloyed Aluminum Designation System^①

2.1 This system consists of four digit numerical designations prefixed by the letter P and suffixed by a serial letter. The first two numerical digits, XX, indicate the two digits to the right of the decimal place in the limit for maximum silicon, 0.XX. The last two numerical digits, YY, indicate the two digits to the right of the decimal place in the limit for maximum iron, 0.YY.

2.1.1 Each basic unalloyed aluminum designation is identified by the letter A following the numerical designation, i.e., PXXYYA.

2.1.2 Variations of a basic unalloyed aluminum, i.e., having the same individual silicon and iron limits but having different individual limits for elements other than silicon and iron are identified by substituting a serial letter in place of the letter A. The serial letters are assigned in alphabetical sequence starting with B but omitting I, O, and Q.

2.2 Maximum limits for the following, expressed as a multiple of 0.01 percent are registered for each designation: Silicon; Iron; Other Elements, Each^②; Other Elements, Total^②; Aluminum, remainder^③. Maximum limits for individual elements other than silicon and iron may be registered^④.

^① Chemical composition limits and designations conforming to this standard may be registered with the Aluminum Association provided (a) the unalloyed aluminum is offered for sale currently and shall have been sold within the 12 months immediately preceding the date of registration request, in both cases in commercial quantities, (b) the complete chemical composition limits are registered, (c) the composition is different from that of any other unalloyed aluminum for which a numerical designation already has been assigned.

^② Excluding aluminum and other element(s), singly or in combination, that have a specified limit.

^③ The aluminum content for unalloyed aluminum not made by a refining process is the difference between 100.00 percent and the sum of all the other analyzed metallic elements including silicon present in the amounts of 0.010 percent or more each expressed to the second decimal before determining the sum. When an element's specified maximum limit is 0.XX, an observed value or a calculated value greater than 0.005 but less than 0.010% is rounded off and shown as "less than 0.01."

^④ Standard limits for impurities are arranged in the following sequence: Silicon; Iron; Zinc; Gallium; Vanadium; Additional specified elements in alphabetical order of their chemical symbols; Other Elements, Each; Other Elements, Total; Aluminum, remainder.

An American National Standard implies a consensus of those substantially concerned with its scope and provisions. An American National Standard is intended as a guide to aid the manufacturer, the consumer, and the general public. The existence of an American National Standard does not in any respect preclude anyone, whether he has approved the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not conforming to the standard. American National Standards are subject to periodic review and users are cautioned to obtain the latest editions.

The American National Standards Institute does not develop standards and will in no circumstances give an interpretation of any American National Standard. Moreover, no person shall have the right or authority to issue an interpretation of an American National Standard in the name of the American National Standard.

CAUTION NOTICE: This American National Standard may be revised or withdrawn at any time. The procedures of the American National Standards Institute require that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of approval. Purchasers of American National Standards may receive current information on all standards by calling or writing the American National Standards Institute.