

ANSI H35.1 / H35.1(M)-2017
Revision of H35.1/ H35.1(M)-2013

American National Standard Alloy and Temper Designation Systems for Aluminum

Secretariat
The Aluminum Association
Incorporated

American National Standard

Approval of an American National Standard requires verification by **the American National Standards Institute (ANSI)** that the requirements for due process, consensus, and other criteria for approval have been met by the standards developer.

Consensus is established when, in the judgment of the ANSI Board of Standards Review, substantial agreement has been reached by directly and materially affected interests. Substantial agreement means much more than a simple majority, but not necessarily unanimity. Consensus requires that all views and objections be considered, and that a concerted effort be made toward their resolution.

The use of American National Standards is completely voluntary; their existence does not in any respect preclude anyone, whether he has approved the standards or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not conforming to the standards.

The American National Standards Institute does not develop standards and will under no circumstances give an interpretation of any American Standard. Moreover, no person shall have the right or authority to issue an interpretation of an American National Standard in the name of the American National Standards Institute. Requests for interpretation should be addressed to the secretariat or sponsor whose name appears on the title page of this standard.

CAUTION NOTICE: This American National Standard may be revised or withdrawn at any time. The procedures of the American National Standards Institute require that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of approval. Purchasers of American National Standards may receive current information on all standards by calling or writing the American National Standards Institute, 25 West 43rd Street, New York, NY 10036.

ANSI H35.1 / H35.1(M)-2017
Revision of H35.1/ H35.1(M)-2013

American National Standard Alloy and Temper Designation Systems for Aluminum

Secretariat

The Aluminum Association, Inc.
1400 Crystal Drive, Suite 430
Arlington, VA **22202**

Approved May 12, 2017
American National Standards Institute

**ACCREDITED STANDARDS COMMITTEE H35
ON
ALUMINUM AND ALUMINUM ALLOYS**

OFFICERS

Francine Bovard, Chairman
John Weritz, Secretary

COMMITTEE MEMBERS

THE ALUMINUM ASSOCIATION

FRANCINE BOVARD, Arconic, New Kensington, Pennsylvania

AEROSPACE INDUSTRIES ASSOCIATION OF AMERICA

JAMES R. RENTSCH, *Aerospace Industries Association of America*, Arlington, Virginia

ALUMINUM EXTRUDERS COUNCIL

OLIVIER GABIS, Wagstaff, Saint Clairsville, Ohio

AMERICAN FOUNDRY SOCIETY

STEVE ROBISON, *American Foundry Society*, Schaumburg, Illinois

ASTM INTERNATIONAL

BRIAN P. COCHRAN, *ASTM B07*, Wabash, Indiana

METAL SERVICE CENTER INSTITUTE

JULIE S. THANE, *Metal Service Center Institute*, Chicago, Illinois

NATIONAL ELECTRICAL MANUFACTURERS ASSOCIATION

VINCE BACLAWSKI, *National Electrical Manufacturers Association*, Arlington, Virginia

SAE INTERNATIONAL (SOCIETY OF AUTOMOTIVE ENGINEERS)

ROBERT STEFFEN, *Raytheon Precision Manufacturing*, Dallas, Texas

U.S. DEPARTMENT OF COMMERCE

FRANK W. GAYLE, *National Institute of Standards and Technology*, Gaithersburg, Maryland

U.S. DEPARTMENT OF THE NAVY

CARL LEVANDUSKY, *Naval Air Warfare Center Aircraft Division*, Lakehurst, New Jersey

U.S. DEPARTMENT OF THE AIRFORCE

JEFFREY CALCATERRA, US Airforce Systems Support Division, Dayton, Ohio

ANSI H35.1 / H35.1(M)-2017

Foreword

This Standard is a revision of ANSI Standard H35.1/H35.1(M)-2013 Alloy and Temper Designation Systems for Aluminum.

Initially, the Standard consisted of only the alloy designation system for wrought aluminum developed by The Aluminum Association and adopted by that organization in 1954. A booklet describing the system was issued in July 1954 and was approved under the existing standards procedure of the American Standards Association as American Standard H35.1-1957.

All major producers of wrought aluminum alloys in the United States adopted the Aluminum Association Alloy Designation System for Wrought Aluminum on October 1, 1954. A Military Standard (MIL-STD-192) covering the new system was issued in October 1955. The Society of Automotive Engineers began using the designations in 1956, and the American Society for Testing and Materials in 1958.

The Standard was reissued in 1962 to add the temper designation system that had been in effect in the United States since 1948. Subsequently, MIL-STD-192 was cancelled, since it was the equivalent to American Standard H35.1-1962.

This Standard was originally developed and subsequently revised using the "canvas" method and published under the proprietary sponsorship of the Aluminum Association. At the request of the Aluminum Association, the establishment of Standards Committee H35 on Aluminum Alloys was authorized by the American National Standards Institute on 17 February 1970, with the Association serving as Secretariat.

The 1971 revision of ANSI H35.1 was the first revision developed by Standards Committee H35, under the "Standards Committee" procedures, and the 1972, 1975, 1978, and 1982 revisions were developed under the auspices of that Committee.

Standards Committee H35 was transferred to an Accredited Standards Committee on December 28, 1983, and this revision was developed under the Accredited Standards Committee method.

The latest 2017 edition includes revisions to the definitions of basic H and T tempers, discontinuation of the practice of assigning experimental alloy designations, a revision to the variation requirements, revisions to footnotes 4 and 5 and clarification in section 3.2.1. These changes are indicated by highlights in the text.

ANSI H35.1 / H35.1(M)-2017

Alloy and Temper Designation Systems for Aluminum (ANSI H35.1/H35.1(M)-2017)

1. Scope

This standard provides systems for designating wrought aluminum and wrought aluminum alloys, aluminum and aluminum alloys in the form of castings and foundry ingot, and the tempers in which aluminum and aluminum alloy wrought products and aluminum alloy castings are produced. Specific limits for chemical compositions and for mechanical and physical properties to which conformance is required are provided by applicable product standards.

NOTE: A numerical designation assigned in conformance with this standard should only be used to indicate an aluminum or an aluminum alloy having chemical composition limits identical to those registered with the Aluminum Association and, for wrought aluminum and wrought aluminum alloys, with the signatories of the Declaration of Accord on an International Alloy Designation System for Wrought Aluminum and Wrought Aluminum Alloys.

2. Wrought Aluminum and Aluminum Alloy Designation System ^{① ② ③ ④ ⑤}

A system of four-digit numerical designations is used to identify wrought aluminum and wrought aluminum alloys. The first digit indicates the alloy group as follows:

Aluminum, 99.00 percent and greater	1xxx
Aluminum alloys grouped by major alloying elements	
Copper	2xxx
Manganese	3xxx
Silicon	4xxx
Magnesium	5xxx
Magnesium and silicon	6xxx
Zinc	7xxx
Other element	8xxx
Unused series	9xxx

① Chemical composition limits and designations conforming to this standard for wrought aluminum and wrought aluminum alloys, and aluminum and aluminum alloy castings and foundry ingot may be registered with the Aluminum Association provided: (1) the aluminum or aluminum alloy is offered for sale, (2) the complete chemical composition limits are registered, and (3) the composition is significantly different from that of any aluminum or aluminum alloy for which a numerical designation already has been assigned.

② For codification purposes an alloying element is any element that is intentionally added for any purpose other than grain refinement and for which minimum and maximum limits are specified.

③ Standard limits for alloying elements and impurities are expressed to the following places:

Less than 0.001 percent	0.000X
0.001 but less than 0.01 percent	0.00X
0.01 but less than 0.10 percent	
Unalloyed aluminum made by a refining process	0.0XX
Alloys and unalloyed aluminum not made by a refining process	0.0X
0.10 through 0.55 percent	0.XX
(It is customary to express limits of 0.30 percent through 0.55 percent as 0.X0 or 0.X5)	
Over 0.55 percent	0.X, X.X, etc.
(except that combined Si + Fe limits for 1xxx designations must be expressed as 0.XX or 1.XX)	

④ Standard limits for alloying elements and impurities are expressed in the following sequence: Silicon; Iron; Copper; Manganese; Magnesium; Chromium; Nickel; Zinc; Titanium (see Note 1); Other (see Note 2) Elements, Each; Other (see Note 2) Elements, Total; Aluminum (see Note 3).

⑤ The aluminum content for unalloyed aluminum made by a refining process is the difference between 100.00 percent and the sum of all other metallic elements together with silicon present in amounts of 0.0010

The designation assigned shall be in the 1xxx group whenever the minimum aluminum content is specified as 99.00 percent or higher. The alloy designation in the 2xxx through 8xxx groups is determined by the alloying element (Mg₂Si for 6xxx alloys) present in the greatest mean percentage, except in cases in which the alloy being registered qualifies as a modification or variation of a previously registered alloy. If the greatest mean percentage is common to more than one alloying element, choice of group shall be in order of group sequence Cu, Mn, Si, Mg, Mg₂Si, Zn or others.

The last two digits identify the aluminum alloy or indicate the aluminum purity. The second digit indicates modifications of the original alloy or impurity limits.

2.1 Aluminum

In the 1xxx group for minimum aluminum purities of 99.00 percent and greater, the last two of the four digits in the designation indicate the minimum aluminum percentage^⑤. These digits are the same as the two digits to the right of the decimal point in the minimum aluminum percentage when it is expressed to the nearest 0.01 percent. The second digit in the designation indicates modifications in impurity limits or alloying elements. If the second digit in the designation is zero, it indicates unalloyed aluminum having natural impurity limits; integers 1 through 9, which are assigned consecutively as needed, indicate special control of one or more individual impurities or alloying elements.

Note 1—Additional specified elements having limits are inserted in alphabetical order according to their chemical symbols between Titanium and Other Elements, Each, or are listed in footnotes.

Note 2—"Other" includes listed elements for which no specific limit is shown as well as unlisted metallic elements. **"Total" is the sum of those "Others" metallic elements 0.010 or more each, expressed to the second decimal before determining the sum.** The producer may analyze samples for trace elements not specified in the registration or specification. However, such analysis is not required and may not cover all metallic "other" elements. Should any analysis by the producer or the purchaser establish that an "other" element exceeds the limit of "Each" or that the aggregate of several "other" elements exceeds the limit of "Total", the material shall be considered non-conforming.

Note 3—Aluminum is specified as minimum for unalloyed aluminum, and as a remainder for aluminum alloys.

⑤ (Continued) percent or more each, expressed to the third decimal before determining the sum, which is rounded to the second decimal before subtracting; for unalloyed aluminum not made by a refining process it is the difference between 100.00 percent and the sum of all other analyzed metallic elements together with silicon present in amounts of 0.010 percent or more each, expressed to the second decimal before determining the sum. For unalloyed aluminum made by a refining process, when the specified maximum limit is 0.0XX, an observed value or a calculated value greater than 0.0005 but less than 0.0010% is rounded off and shown as "less than 0.001"; for alloys and unalloyed aluminum not made by a refining process, when the specified maximum limit is 0.XX, an observed value or a calculated value greater than 0.005 but less than 0.010% is rounded off and shown as "less than 0.01".

⑥ Individual element limits (i.e. a maximum limit or a range) are required for elements having a combined maximum limit in excess of 0.10%. Individual element limits are not required for elements having a combined maximum limit of 0.10% or less.