

This is a preview of "ANSI/ABMA 11-1990 (R...)". Click here to purchase the full version from the ANSI store.



**Accredited Standards
Committee B3**

Load Ratings and Fatigue Life for Roller Bearings ANSI/ABMA 11:1990



Secretariat

**American Bearing
Manufacturers Association**

ANSI/ABMA 11:1990

Reaffirmed 2008



ABMA
2025 M Street, NW
Suite 800
Washington, DC 20036
Ph: 202-367-1155
Fax: 202-367-2155

E-mail: info@americanbearings.org
www.americanbearings.org

This is a preview of "ANSI/ABMA 11-1990 (R...)". [Click here to purchase the full version from the ANSI store.](#)

AMERICAN NATIONAL STANDARD
(This is not an approved part of the standard)

Approval of an American National Standard requires verification by ANSI that the requirements for due process, consensus, and other criteria for approval have been met by the standards developer.

Consensus means substantial agreement has been reached by directly and materially affected interests. This signifies the concurrence of more than a simple majority, but not necessarily unanimity. Consensus requires that all views and objections be considered, and that an effort be made toward their resolution.

The use of an American National Standard is completely voluntary; their existence does not in any respect preclude anyone, whether they approved the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not conforming to the standard.

The American National Standards Institute does not develop standards and will in no circumstances give an interpretation of any American National Standard. Moreover, no person shall have the right or authority to issue an interpretation of an American National Standard in the name of the American National Standards Institute. Requests for interpretations should be addressed to the secretariat of the sponsor whose name appears on the title page of this standard.

CAUTION NOTICE: This American National Standard may be revised or withdrawn at any time.

Purchasers of American National Standards may receive current information on all standards by calling or writing the American National Standards Institute or online at www.ANSI.org.
Published by

American Bearing Manufacturers Association
2025 M Street, N.W., Suite 800
Washington, DC 20036
Copyright © 2011 by American Bearing Manufacturers Association

All rights reserved.

No part of this publication may be reproduced in any form, in an electronic retrieval system or otherwise, without prior written permission of the publisher.

Printed in the United States of America

Load Ratings and Fatigue Life For Roller Bearings

CONTENTS

SECTION	PAGE
1. Introduction	1
1.1 Purpose of Standard	1
1.2 Life Criterion	1
1.3 Static Load Criterion	1
2. Symbols	2
3. Definitions	3
3.1 Life	3
3.2 Reliability	3
3.3 Static Load	3
3.4 Pitch Diameter of a Roller Set, D_{pw}	3
3.5 Basic Rating Life, L_{10}	3
3.6 Adjusted Rating life, L_{na}	3
3.7 Basic Dynamic Radial Load Rating, C_r	3
3.8 Basic Static Radial Load Rating, C_{or}	3
3.9 Basic Dynamic Axial Load Rating, C_a	3
3.10 Basic Static Axial Load Rating, C_{oa}	4
3.11 Dynamic Equivalent Radial Load, P_r	4
3.12 Static Equivalent Radial Load, P_{oa}	4
3.13 Dynamic Equivalent Axial Load, P_a	4
3.14 Static Equivalent Axial Load, P_{oa}	4
3.15 Roller Diameter, D_{we}	4
3.16 Roller Length, L_{we}	4
3.17 Nominal Contact Angle, α	4
3.18 Line Contact	4
3.19 Point Contact	4
3.20 Optimized Contact	4
3.21 Conventional Operating Conditions	5
4. Scope	5
4.1 Bearing Types	5
4.1.1 General	5
4.1.2 Basic Types	5
4.1.3 Double Row	5
4.2 Limitations	5
4.2.1 Truncated Contact Area	5
4.2.2 Materials	5
4.2.3 Bearing Types	5
4.2.4 Lubrication	5
4.2.5 Ring Support and Alignment	5
4.2.6 Internal Clearance	5
4.2.7 High Speed Effects	6
4.2.8 Stress Concentrations	6
4.2.9 Tolerances	6
4.2.10 Plastic Deformation in the Contact Area	6
4.3 Operating Parameters	6
5 Radial Roller Bearings	6
5.1 Basic Dynamic Radial Load Rating	6
5.1.1 Bearing Combinations	7
5.2 Dynamic Equivalent Radial Load	7
5.2.1 Bearing Combinations	10

This is a preview of "ANSI/ABMA 11-1990 (R...)". [Click here to purchase the full version from the ANSI store.](#)

5.3	Basic Rating Life	10
5.4	Basic Static Radial Load Rating	10
5.4.1	Bearing Combinations	10
5.5	Static Equivalent Radial Load	11
5.5.1	Bearing Combinations	11
6	Thrust Roller Bearings	11
6.1	Basic Dynamic Axial Load Rating	11
6.1.1	Single Row Bearings	11
6.1.2	Bearings with Two or More Rows of Rollers	12
6.2	Dynamic Equivalent Axial Load	12
6.3	Basic Rating Life	12
6.4	Basic Static Axial Load Rating	19
6.5	Static Equivalent Axial Load	19
7	Life Adjustment Factors	19
7.1	General	19
7.2	Limitations	20
7.3	Life Adjustment Factor for Reliability, a_1	20
7.4	Life Adjustment Factor for Special Bearing Properties, a_2	20
7.5	Life Adjustment Factor for Operating Conditions, a_3	20

LIST OF TABLES

TABLE NO.	TITLE	PAGE
RADIAL ROLLER BEARINGS		
1	Values of f_{cm}	8
2	Values of X and Y	10
3	Values of X_o and Y_o	11
THRUST ROLLER BEARINGS		
4	Values of f_{cm} for cylindrical roller bearings, tapered roller bearings and needle roller bearings with machined rings	13
5	Values of f_{cm} for drawn cup needle roller bearings	15
6	Values of f_{cm} for spherical roller bearings	17
7	Values of X and Y	19
8	Life Adjustment Factors for Reliability	20

Load Ratings and Fatigue Life for Roller Bearings

1. INTRODUCTION

1.1 Purpose of Standard

Roller bearing performance is a function of many variables. These include the bearing design, the characteristics of the material from which the bearings are made, the way in which they are manufactured, as well as many variables associated with their application. The only sure way to establish the satisfactory operation of a bearing selected for a specific application is by actual performance in the application. As this is often impractical, another basis is required to estimate the suitability of a particular bearing for a given application. This is the purpose of this standard.

This standard specifies the method of calculating the basic dynamic load rating of rolling bearings within the size ranges shown in the relevant ANSI/ABMA standards, manufactured from contemporary, commonly used, good quality hardened steel in accordance with good manufacturing practice and basically of conventional design as regards the shape of rolling contact surfaces.

This standard also specifies the method of calculating the basic rating life, which is the life associated with 90% reliability, with commonly used material and manufacturing quality, and with conventional operating conditions. In addition, it specifies the method of calculating adjusted rating life, in which various reliabilities, special bearing properties and specific operating conditions are taken into account by means of life adjustment factors.

Furthermore, this standard specifies the method of calculating the basic static load rating and the static equivalent load for roller bearings within the size ranges shown in the relevant ANSI/ABMA Standards, manufactured from good quality hardened steel, in accordance with good manufacturing practice and basically of conventional design as regards the shape of rolling contact surfaces.

1.2 Life Criterion

Even if roller bearings are properly mounted, adequately lubricated, protected from foreign matter, and are not subjected to extreme operating conditions, they can ultimately fatigue. Under ideal conditions, the repeated stresses developed in the contact areas between the roller and the raceways eventually can result in fatigue of the material which

manifests itself as spalling of the load carrying surfaces. In most applications the fatigue life is the maximum useful life of a bearing. This fatigue is the criterion of life used as the basis for the first part of this standard.

Fatigue life calculated in accordance with this standard does not represent the maximum that can be attained by applying all known technology to roller bearing design and application. Neither does it represent the minimum that should be expected of a bearing made by a producer lacking skill and experience in the design and manufacture of roller bearings, even though the bearing meets the geometric parameters given below. The calculated fatigue life represents the performance normally expected from high quality bearings made by reputable manufacturers. Manufacturers can supply longer lived bearings by the application of advanced materials and manufacturing processes. The present standard has evolved as a means for bearing users to specify a reasonable standard of performance for the bearing they wish to purchase.

1.3 Static Load Criterion

A static load is a load acting on a non-rotating bearing. Permanent deformations appear in rollers and raceways under a static load of moderate magnitude and increase gradually with increasing load.

It is often impractical to establish whether the deformations appearing in a bearing in a specific application are permissible by testing the bearing in that application. Other methods are therefore required to establish the suitability of the bearing selected.

Experience shows that a total permanent deformation of 0.0001 of the rolling element diameter, at the center of the most heavily loaded roller/raceway contact, can be tolerated in most bearing applications without the subsequent bearing operation being impaired. The basic static load rating is, therefore, given a magnitude such that approximately this deformation occurs when the static equivalent load is equal to the load rating.

Tests indicate that a load of the magnitude in question may be considered to correspond to a calculated contact stress of

— 4000 MPa (580,000 psi) for all roller bearings