


AMERICAN NATIONAL STANDARD

Tooth Proportions for Plastic Gears

ANSI/AGMA 1106-A97



AGMA STANDARD



Reproduced By GLOBAL
ENGINEERING DOCUMENTS
With The Permission Of AGMA
Under Royalty Agreement

American National Standard

Tooth Proportions for Plastic Gears

ANSI/AGMA 1106-A97

[Metric edition of ANSI/AGMA 1006-A97]

Approval of an American National Standard requires verification by ANSI that the requirements for due process, consensus, and other criteria for approval have been met by the standards developer.

Consensus is established when, in the judgment of the ANSI Board of Standards Review, substantial agreement has been reached by directly and materially affected interests. Substantial agreement means much more than a simple majority, but not necessarily unanimity. Consensus requires that all views and objections be considered, and that a concerted effort be made toward their resolution.

The use of American National Standards is completely voluntary; their existence does not in any respect preclude anyone, whether he has approved the standards or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not conforming to the standards.

The American National Standards Institute does not develop standards and will in no circumstances give an interpretation of any American National Standard. Moreover, no person shall have the right or authority to issue an interpretation of an American National Standard in the name of the American National Standards Institute. Requests for interpretation of this standard should be addressed to the American Gear Manufacturers Association.

CAUTION NOTICE: AGMA technical publications are subject to constant improvement, revision, or withdrawal as dictated by experience. Any person who refers to any AGMA Technical Publication should be sure that the publication is the latest available from the Association on the subject matter.

[Tables or other self-supporting sections may be quoted or extracted. Credit lines should read: Extracted from ANSI/AGMA 1106-A97, *Tooth Proportions for Plastic Gears*, with the permission of the publisher, the American Gear Manufacturers Association, 1500 King Street, Suite 201, Alexandria, Virginia 22314.]

Approved August 7, 1997

ABSTRACT

This standard presents a new basic rack, AGMA PT, which, with its full round fillet, may be preferred in many applications of gears made from plastic materials. It also explains and illustrates the general concept of the basic rack. It contains a description, with equations and sample calculation, of how the proportions of a spur or helical gear may be derived from the design tooth thickness and the basic rack data. These equations and calculations use ISO based symbols and metric units. In several annexes, there are discussions of possible variations from this basic rack and also a procedure for defining tooth proportions without using the basic rack concept.

Published by

**American Gear Manufacturers Association
1500 King Street, Suite 201, Alexandria, Virginia 22314**

Copyright © 1997 by American Gear Manufacturers Association
All rights reserved.

No part of this publication may be reproduced in any form, in an electronic retrieval system or otherwise, without prior written permission of the publisher.

Printed in the United States of America

ISBN: 1-55589-685-5

Contents

	Page
Foreword	iv
1 Scope	1
2 Definitions and symbols	1
3 Tooth proportions and basic rack	3
4 Standard basic rack for plastic gears	3
5 Gear tooth proportions from basic rack data	8

Tables

1 Nomenclature: symbols and terms	1
2 Standard basic racks (based on unit module)	4

Figures

1 AGMA PT basic rack (for m or $m_n = 1$)	3
2 Example of AGMA PT basic rack modified with tip relief	5
3 Comparison of calculated bending stresses at fillets from AGMA Fine-Pitch and AGMA PT basic racks	6
4(a) Effect of fillet shape on mold flow	7
4(b) Effect of fillet shape on fiber orientation close to surface (at mid-facewidth location)	7
4(c) Effect of fillet shape on fillet surface temperature during freezing	7
4(d) Comparison of shrinkage effect in undercut pinion with sharp and rounded fillets	8
5 Tooth outline features introduced by tip rounding on external gears	11

Annexes

A Basic rack description and application	13
B Experimental basic racks for plastic gears	21
C Determination of tooth thickness and other design variables	23
D Gear tip relief from a modified basic rack	27
E Alternate practices for defining tooth proportions	31
F Generating gear geometry without racks	37
G Sample calculations	43
Bibliography	47

Foreword

[The foreword, footnotes, and annexes are provided for informational purposes only and should not be construed as a part of ANSI/AGMA 1106–A97, *Tooth Proportions for Plastic Gears*.]

AGMA has issued standards for gear tooth proportions over a period of many years. The most recent versions have been AGMA 201.02 (withdrawn 1995), *Tooth Proportions for Coarse–Pitch Involute Spur Gears*, and ANSI/AGMA 1003–G93, *Tooth Proportions for Fine–Pitch Involute Spur and Helical Gears*. These standards and their predecessors were prepared in response to the need to standardize gear generating cutting tools such as hobs and shaper cutters. Without such standards, the variety of tools needed by gear shops would have become unlimited.

The manufacture of gears by the molding process is not subject to the same practical constraints as manufacture by the gear cutting process. Every mold is inherently “non–standard”. The geometry of the mold cavity cannot follow a standard because of varying allowances for shrinkage. Furthermore, there are some methods for manufacturing the mold cavity which do not depend on cutting tools and, even for those that do, special tools are generally required. Thus, tooth proportions for molded plastic gears need not follow those established for machined gears.

Some of the special properties of plastic materials influence the selection of gear tooth proportions as the two following examples illustrate:

- The structure and orientation of plastic molecules, regardless of processing method, makes the strengths of the materials particularly sensitive to sharp internal corners. A substantially stronger tooth will result if sharp fillets at the base of the tooth are avoided. The tooth proportions for gears made according to the AGMA fine–pitch standard noted above generally result in relatively sharp fillets.
- In certain applications, the higher expansion properties of plastic materials may create the need for a greater depth of engagement between mating gears than permitted by the other standard tooth forms.

As a result of this preference for a different tooth form, members of the plastic gear molding industry have adopted their own individual sets of tooth proportions. One set that has gained wide usage by plastic gear designers, and is often specified in place of the AGMA Fine–Pitch Standard, has been developed by William McKinley [1]. Because these tooth forms contain the preferential features for molded plastic gears and because they are already well recognized in the industry, they were used, with some changes, as models in the preparation of this standard. The first of the four variations in this set has a depth of engagement, or working depth, that is the same as in the above mentioned AGMA standards. The other three have increased depths of engagement in varying degrees. This standard has selected only the first variation, which is the one in widest use, as the model for the new tooth proportions. However, data similarly based on the other three variations are included in annex B.

The tooth forms in this standard are defined with the use of the basic rack concept. For those that might be unfamiliar with this concept, a detailed description of the basic rack is included as annex A.

Suggestions for the improvement of this standard will be welcome. They should be sent to the American Gear Manufacturers Association, 1500 King Street, Suite 201, Alexandria, Virginia, 22314.

PERSONNEL of the AGMA Plastic Gearing Committee

Chairman: I. Laskin Irving Laskin, P.E.
Vice Chairman: H. Yelle Ecole Polytechnique de Montréal

ACTIVE MEMBERS

M.A. Bennick	RTP Company	S.D. Pierson	ABA-PGT, Inc.
R. Casavant	GW Plastics, Inc.	J.T. Rill	Black & Decker, Inc.
D. Castor	Eastman Kodak Company	M. Schireson	DSM Engng. Plastics, Inc.
C.M. Denny	Consultant	L. Siders	Lexmark
D.S. Ellis	ABA-PGT, Inc.	Z. Smith	Hoechst Celanese Corp.
K. GitcheI	Universal Tech. Systems, Inc.	M. Thompson	UFE, Inc.
J.W. Kelley	Shell Chemical Company	A. Ulrich	UFE, Inc.
R. Kleiss	Kleiss Engineering	M. Wichmann	DuPont Polymers
S. Legault	Seitz Corporation	E.H. Williams, III	...	LNP Engng. Plastics, Inc.
A. Milano	Seitz Corporation	J.H. Winzeler, Jr.	..	Winzeler, Inc.

ASSOCIATE MEMBERS

J. Ambrosina	IDEO Product Development	R.B. Lewis	Lewis Research, Inc.
M.K. Anwar	Allied Devices Corporation	J. Lovell	Spaulding Composites Co.
D. Bailey	Rochester Gear, Inc.	G. Martello	BF Goodrich Spec. Chem.
R.E. Bergmann	Gear Research Institute	J.H. Monger	Process Gear Company
F. Boss	DSM Engineering Plastics	M. Octrue	CETIM
K. Buyukataman	...	UTC Pratt & Whitney	M. Oliveto	DSM Engng. Plastics, Inc.
A. Conrad	GW Plastics, Inc.	K.R. Price	Eastman Kodak Company
P. Danish	ITT Automotive	E. Reiter	ATS Precision Comp. Div.
P. Davoli	Politecnico di Milano	D. Rosenfeld	DSM Engng. Plastics, Inc.
W.T. Derry	Lewis Research, Inc.	R. Santandreu	Consultant
E. Dornan	Winzeler, Inc.	N.R. Schott	Institute for Plastic Innovation
L. Faure	C.M.D.	J. Simonelli	Emerson Power Trans. Co.
C. Fleenor	Bay Designs, Inc.	L.J. Smith	Invincible Gear Company
M. Fletcher	Hoechst Celanese	R.E. Smith	R.E. Smith & Company, Inc.
D. Fritzinger	Power Wheels	Z. Solstarecz	Seitz Corporation
R.J. Galipeau	Plastics Technology	C. Tacey	DuPont Polymers
T. Guala	DuPont Company	R. Weder	C.W. Tool - Mikron
P.M. Hughes	Hoechst Celanese	M. Wilkinson	GW Plastics
S LeGault	Seitz Corporation	P. Wyluda	Hoechst Celanese

(This page is intentionally blank)

American National Standard – Tooth Proportions for Plastic Gears

1 Scope

1.1 Basic rack

This standard defines a basic rack for spur and helical plastic gears. However, the specific basic rack can be applied to any type of gear which employs the basic rack concept to help define its geometry.

NOTE: This basic rack is an optional alternative to other AGMA basic racks. It will often be preferred for those applications in which tooth bending strength is a major factor in the design of plastic gears.

A detailed description of the basic rack concept, including its features and its application to various types of gears, is given in annex A.

The data for three other basic racks, differing primarily in depth of engagement, are given in annex B.

1.2 Gear tooth proportions

This standard shows how basic rack dimensions determine the tooth proportions of the gear once the tooth thickness has been established. Specific values of the gear tooth thickness and the resulting gear tooth proportions are not covered by this standard. However, many of the considerations that go into such a selection are discussed in annex C.

The tip relief from a modified basic rack is discussed in annex D.

1.3 Non-traditional practices for defining tooth proportions

Annexes E and F describe some non-traditional practices currently used to help achieve gear designs that are optimum for their applications. Their use with molded plastic gears has been made more convenient by modern methods of mold cavity manufacture. These practices include modifying standard basic racks, creating custom designed basic racks, and designing tooth proportions without reference to basic racks. In the annexes, the description of each method is accompanied by potential advantages and design cautions. An example of one procedure for the last method, designing without reference to basic racks, is presented in annex F.

2 Definitions and symbols

2.1 Definitions

The terms used in this standard conform to ANSI/AGMA 1012-F90, *Gear Nomenclature, Definition of Terms with Symbols* and AGMA 904-B89, *Metric Usage*.

Terms used in this standard which require elaboration and concepts which are specific to plastic gears are covered where they are first used.

2.2 Symbols

The symbols used in the tables and formulas are shown in table 1.

NOTE: The symbols and definitions used in this standard may differ from similar items in other AGMA standards. The user should not assume that familiar symbols can be used without a careful study of these definitions.

Table 1 – Nomenclature: symbols and terms

Symbol	Term	First Used
c_{BR}	Clearance of basic rack	Figure 1
d	Reference diameter (standard pitch diameter) of gear	Eq 1
d_F	Form diameter of gear	Eq 6
d_{ai}	Inside diameter of internal gear	Eq 9

(continued)