



Measurement of the Leachability of Solidified Low- Level Radioactive Wastes by a Short-Term Test Procedure

An American National Standard

ANSI/ANS-16.1-2019

Published by the
American Nuclear Society
555 N. Kensington Ave
La Grange Park, IL 60526



ANSI/ANS-16.1-2019

**American National Standard
Measurement of the Leachability of
Solidified Low-Level Radioactive Wastes
by a Short-Term Test Procedure**

Secretariat
American Nuclear Society

Prepared by the
**American Nuclear Society
Standards Committee
Working Group ANS-16.1**

Published by the
**American Nuclear Society
555 North Kensington Avenue
La Grange Park, Illinois 60526 USA**

Approved February 22, 2019
by the
American National Standards Institute, Inc.

American National Standard

Designation of this document as an American National Standard attests that the principles of openness and due process have been followed in the approval procedure and that a consensus of those directly and materially affected by the standard has been achieved.

This standard was developed under the procedures of the Standards Committee of the American Nuclear Society; these procedures are accredited by the American National Standards Institute, Inc., as meeting the criteria for American National Standards. The consensus committee that approved the standard was balanced to ensure that competent, concerned, and varied interests have had an opportunity to participate.

An American National Standard is intended to aid industry, consumers, governmental agencies, and general interest groups. Its use is entirely voluntary. The existence of an American National Standard, in and of itself, does not preclude anyone from manufacturing, marketing, purchasing, or using products, processes, or procedures not conforming to the standard.

By publication of this standard, the American Nuclear Society does not insure anyone utilizing the standard against liability allegedly arising from or after its use. The content of this standard reflects acceptable practice at the time of its approval and publication. Changes, if any, occurring through developments in the state of the art, may be considered at the time that the standard is subjected to periodic review. It may be reaffirmed, revised, or withdrawn at any time in accordance with established procedures. Users of this standard are cautioned to determine the validity of copies in their possession and to establish that they are of the latest issue.

The American Nuclear Society accepts no responsibility for interpretations of this standard made by any individual or by any ad hoc group of individuals. Responses to inquiries about requirements, recommendations, and/or permissive statements (i.e., "shall," "should," and "may," respectively) should be sent to the Publications and Standards Department at Society Headquarters. Action will be taken to provide appropriate response in accordance with established procedures that ensure consensus.

Comments on this standard are encouraged and should be sent to Society Headquarters.

Published by

American Nuclear Society
555 North Kensington Avenue
La Grange Park, Illinois 60526 USA



This document is copyright protected.

Copyright © 2019 by American Nuclear Society. All rights reserved.

Any part of this standard may be quoted. Credit lines should read "Extracted from American National Standard ANSI/ANS-16.1-2019 with permission of the publisher, the American Nuclear Society." Reproduction prohibited under copyright convention unless written permission is granted by the American Nuclear Society.

Printed in the United States of America

Inquiry Requests

The American Nuclear Society (ANS) Standards Committee will provide responses to inquiries about requirements, recommendations, and/or permissive statements (i.e., “shall,” “should,” and “may,” respectively) in American National Standards that are developed and approved by ANS. Responses to inquiries will be provided according to the Policy Manual for the ANS Standards Committee. Nonrelevant inquiries or those concerning unrelated subjects will be returned with appropriate explanation. ANS does not develop case interpretations of requirements in a standard that are applicable to a specific design, operation, facility, or other unique situation only and therefore is not intended for generic application.

Responses to inquiries on standards are published in ANS’s magazine, *Nuclear News*, and are available publicly on the ANS Web site or by contacting the Publications and Standards Department.

Inquiry Format

Inquiry requests shall include the following:

- (1) the name, company name if applicable, mailing address, and telephone number of the inquirer;
- (2) reference to the applicable standard edition, section, paragraph, figure, and/or table;
- (3) the purpose(s) of the inquiry;
- (4) the inquiry stated in a clear, concise manner;
- (5) a proposed reply, if the inquirer is in a position to offer one.

Inquiries should be addressed to

American Nuclear Society
Publications and Standards Department
555 N. Kensington Avenue
La Grange Park, IL 60526

or standards@ans.org

This is a preview of "ANSI/ANS-16.1-2019". [Click here to purchase the full version from the ANSI store.](#)

American National Standard ANSI/ANS-16.1-2019

Foreword (This foreword is not a part of American National Standard “Measurement of the Leachability of Solidified Low-Level Radioactive Wastes by a Short-Term Test Procedure,” ANSI/ANS-16.1-2019, but is included for informational purposes.)

Contact of solid radioactive wastes with water is the initial step of a potentially major pathway for radionuclide release and migration off-site. The release of radionuclides from a waste form through contact with water, referred to as leaching, must occur before they migrate through groundwater and off the disposal site. It follows that the resistance of a waste form to leaching is of fundamental interest in low-level radioactive waste disposal and that the measurement of the leach resistance of potential waste forms is important in low-level radioactive waste management. The low-level radioactive wastes addressed in this standard are those defined in Title 10, Code of Federal Regulations, Part 61, “Licensing Requirements for Land Disposal of Radioactive Waste.”¹⁾

This standard provides a simple method for the quantitative comparison of the leach resistance of different radionuclides from different materials. The method is not intended to provide information suitable for assessing waste form performance or qualification for disposal. Rather, it provides a rapid and economical means for screening optional materials, formulations, and processing methods to develop and select waste forms for more extensive testing. Although the test results might provide basic insights regarding the leaching mechanism and performance, those insights should be evaluated using process-specific test methods and site-specific test conditions (e.g., by following the approach recommended in ASTM C1174-17²⁾). Other methods appropriate for evaluating release mechanisms and long-term performance of low-level waste forms have been developed (e.g., ASTM C1308-08³⁾ and EPA SW-846 Methods 1311 and 1312^{4),5)}). EPA SW-846 Methods 1313 and 1315^{6),7)} may be used to determine additional information. EPA SW-846 Method 1315 has been used with prepared glass coupons and at multiple controlled temperatures to evaluate dissolution and leaching kinetics.⁸⁾ EPA Methods 1313 and 1315 have also been used to understand the susceptibility of cement mortars and low-activity nuclear waste forms to carbonation and carbonation front ingress rates and to understand the impact of carbonation on the leaching of material constituents.^{9),10),11)}

¹⁾ Code of Federal Regulations, Title 10, “Energy,” Part 61, “Licensing Requirements for Land Disposal of Radioactive Waste,” U.S. Nuclear Regulatory Commission, Washington, D.C.

²⁾ ASTM C1174-17, “Standard Practice for Evaluation of the Long-Term Behavior of Materials Used in Engineered Barrier Systems (EBS) for Geological Disposal of High-Level Radioactive Waste,” ASTM International (2017).

³⁾ ASTM C1308-08(2017), “Standard Test Method for Accelerated Leach Test for Diffusive Releases from Solidified Waste and a Computer Program to Model Diffusive, Fractional Leaching from Cylindrical Waste Forms,” ASTM International (2008).

⁴⁾ EPA SW-846, “Test Method 1311: Toxicity Characteristic Leaching Procedure,” part of Test Methods for Evaluating Solid Waste, Physical/Chemical Methods, Environmental Protection Agency (1992); available at <https://www.epa.gov/hw-sw846/sw-846-test-method-1311-toxicity-characteristic-leaching-procedure> (current as of March 14, 2019).

⁵⁾ EPA SW-846, “Test Method 1312: Synthetic Precipitation Leaching Procedure,” part of Test Methods for Evaluating Solid Waste, Physical/Chemical Methods, Environmental Protection Agency (1994); available at <https://www.epa.gov/hw-sw846/sw-846-test-method-1312-synthetic-precipitation-leaching-procedure> (current as of March 14, 2019).

⁶⁾ EPA SW-846, “Validated Test Method 1313: Liquid-Solid Partitioning as a Function of Extract pH Using a Parallel Batch Extraction Procedure,” Environmental Protection Agency (2017); available at <https://www.epa.gov/hw-sw846/validated-test-method-1313-liquid-solid-partitioning-function-extract-ph-using-parallel> (current as of March 14, 2019).

⁷⁾ EPA SW-846, “Validated Test Method 1315: Mass Transfer Rates of Constituents in Monolithic or Compacted Granular Materials Using a Semi-Dynamic Tank Leaching Procedure,” Environmental Protection Agency (2017); available at <https://www.epa.gov/hw-sw846/validated-test-method-1315-mass-transfer-rates-constituents-monolithic-or-compacted> (current as of March 14, 2019).

⁸⁾ C. CORKHILL et al., “Evaluation of Novel Leaching Assessment for Nuclear Waste Glasses,” *Proc. Waste Management 2018*, Phoenix, Arizona, March 18–22, 2018, paper 18314 (2018).

⁹⁾ J. L. BRANCH et al., “The Impact of Carbonation on the Microstructure and Solubility of Major Constituents in Microconcrete Materials with Varying Alkalinities due to Fly Ash Replacement of Ordinary Portland Cement,” *Cem. Concr. Res.*, **89**, 297 (2016); <https://doi.org/10.1016/j.cemconres.2016.08.019>.

¹⁰⁾ O. KLEIN-BENDAVID et al., “Retention of Cr in Metakaolin-Based Geopolymeric Materials Under Oxidation and Carbonation,” *Proc. Waste Management 2017*, Phoenix, Arizona, March 5–7, 2017, paper 17453 (2017).

¹¹⁾ J. L. BRANCH et al., “Evaluating the Impacts of Reactive Gas (Carbon Dioxide and Oxygen) Ingress on Leaching from Cementitious Waste Forms,” *Proc. Waste Management 2017*, Phoenix, Arizona, March 5–7, 2017, paper 17482 (2017).

Low-level radioactive wastes are generated as combustible, non-combustible, compactible, and non-compactible solids (e.g., cloth, metal, paper, wood), liquids (e.g., evaporator bottoms, decontamination solutions), slurries (e.g., filter sludges, ion-exchange resins), and powders (e.g., incinerator ash, salts). This standard was designed principally for comparisons of solid monolithic low-level radioactive waste forms generated from non-self-heating radioactive fluid (e.g., liquids, slurries, free-flowing powders) waste streams.

An accepted method for managing these liquids, slurries, and powders is solidification, packaging, and subsequent shipment for disposal by shallow land burial. Solidification restricts dispersal during handling and transportation and provides a non-changing volume during the residence time of the waste in the burial trench.

At present, generators of low-level radioactive wastes (e.g., nuclear power plants, U.S. Department of Energy reservations and national laboratories, research and development laboratories, and hospitals) need a common basis for comparing the alternatives for packaging, handling, storing, and shipping their radioactive wastes. Vendors and developers of solidification systems need a common basis for comparing the leachability of the waste forms made by their solidification processes. The test presented in this standard provides a relative measure of leach resistance within a reasonable time period to provide comparative results for alternative low-level waste forms.

Although leach testing has been recognized as a primary technique for the comparison of solidified waste forms, the determination of release rates from different waste form materials remains complex for the following reasons:

- (1) Leaching can proceed by several concurrent mechanisms, such as diffusion, dissolution, and erosion. The relative importance of each process can be different for each radionuclide of interest, matrix material, and set of processing conditions and can change with time, temperature, pH, substances dissolved in the water, and other environmental variables.
- (2) Actual leaching conditions that might occur during the sound life of a solidified waste form (i.e., the time over which the waste form meets the specifications for all applicable performance parameters) are imprecisely known, and postulated conditions can vary widely over time.

The test method described in this standard cannot be used for performance assessment of waste forms because it does not address the radionuclide release mechanisms or effects of environmental conditions on the test response. Instead, it provides an economical and rapid method for comparing the leachability of alternative waste forms.

This standard was originally published as ANS-16.1-1986, which was informed by a method published by the International Atomic Energy Agency in 1971¹²⁾ and ISO 6961:1982(E), published in 1982.¹³⁾ ANS-16.1-2003 (R2017) was reaffirmed in 2017 with the understanding that it would be revised to update its technical content and clarify its purpose and application. While the leach test procedure and definition of the leachability index remain consistent with previous versions, this revision provides specific instructions regarding test variables, execution, presentation and analysis of test data, and interpretation of the test results. The most significant changes are that the revised procedure requires constant 1-day replacement

¹²⁾ "Leach Testing of Immobilized Radioactive Waste Solids, A Proposal for a Standard Method," E. D. HESPE, Ed., International Atomic Energy Agency, *At. Energy Rev.*, **9**, 1, 195 (1971).

¹³⁾ ISO 6961:1982(E), "Long-Term Leach Testing of Solidified Radioactive Waste Forms," International Organization for Standardization (1982).

intervals, eliminates the option for long-term test intervals, and quantifies the uncertainty in the leachability index to objectively compare values for different materials.

Working Group ANS-16.1 of the Standards Committee of the American Nuclear Society had the following membership at the time it approved this standard:

A. Garrabrants (Co-Chair), *Vanderbilt University*
D. S. Kosson (Co-Chair), *Vanderbilt University*
L. Parks (Vice Chair), *U.S. Nuclear Regulatory Commission*

G. Alexander, *U.S. Nuclear Regulatory Commission*
K. Brown, *Vanderbilt University*
W. L. Ebert, *Argonne National Laboratory*
M. Fuhrmann, *U.S. Nuclear Regulatory Commission*
A. Kruger, *U.S. Department of Energy*
H. van der Sloot, *Individual*

The Siting: General and Monitoring Subcommittee had the following membership at the time of its approval of this standard as follows:

L. Parks (Chair), *U.S. Nuclear Regulatory Commission*

T. Bellinger, *Consolidated Nuclear Security, LLC*
D. A. Bruggeman, *Los Alamos National Laboratory*
A. Garrabrants, *Vanderbilt University*
G. T. Jannik, *Savannah River National Laboratory*
D. S. Kosson, *Vanderbilt University*
D. C. Mussatti, *U.S. Nuclear Regulatory Commission*

The Environmental and Siting Consensus Committee (ESCC) had the following membership at the time of its approval of this standard:

C. A. Mazzola (Chair), *Project Enhancement Corporation*
J. Call, (Vice Chair), *Oasys, Inc.*

T. Bellinger, *Consolidated Nuclear Security, LLC*
D. A. Bruggeman, *Los Alamos National Laboratory*
K. R. Bryson, *Individual*
W. L. Ebert, *Argonne National Laboratory*
Y. Gao, *Westinghouse Electric Company, LLC*
B. J. Gutierrez, *U.S. Department of Energy*
R. J. Hunt, *Consolidated Nuclear Security, LLC*
Y. Li, *Defense Nuclear Facilities Safety Board*
K. Y. Ng, *Bechtel Power Corporation*
J. O'Brien, *U.S. Department of Energy*
L. Parks, *U.S. Nuclear Regulatory Commission*
S. A. Rosenbloom, *U.S. Department of Energy*
J. B. Savy, *Individual*
A. Simpkins, *Dade Moeller*
P. B. Snead, *Duke Energy*
J. Xu, *U.S. Nuclear Regulatory Commission*

This is a preview of "ANSI/ANS-16.1-2019". [Click here to purchase the full version from the ANSI store.](#)

American National Standard ANSI/ANS-16.1-2019

Contents

Section	Page
1 Scope, purpose, and application.....	1
1.1 Scope	1
1.2 Purpose	1
1.3 Application.....	1
2 Definitions	2
2.1 Shall, should, and may	2
2.2 Definitions.....	2
3 Leach test preparation	3
3.1 Specimen preparation	3
3.2 Leach test vessel	4
3.3 Environmental and radiological controls	5
3.4 Leachant	5
4 Leach test procedure	5
4.1 Specimen characterization	6
4.2 Determining initial amounts of radionuclides.....	6
4.3 Specimen rinse.....	7
4.4 Test initiation	7
4.5 Test interval.....	7
4.5.1 Leachate replacement.....	8
4.5.2 Inspection for solids	8
4.5.3 Vessel acid soak.....	8
4.5.4 Leachate sampling and analysis.....	9
4.6 Sequence of test intervals.....	9
5 Presentation and analysis of test data.....	9
5.1 Data recording requirements.....	9
5.2 Presentation of test data.....	10
5.3 Data analysis	11
5.4 Determination of the leachability index.....	13
5.5 Application of results	14
6 References	14

Appendices

Appendix A	Data Forms	15
Appendix B	Example Data and Example Calculations of the leachability index.....	19

Tables

Table A.1	Description of leach specimen	15
Table A.2	Specimen dimensions	15
Table A.3	Analytical techniques	16
Table A.4	Rinse fractions and cumulative fractions for each interval	17
Table A.5	Results for radionuclide <i>i</i> in ANS-16.1 tests with Specimens A and B	17
Table A.6	Values used to calculate regression equation values and uncertainties for test with Specimen A.....	17
Table A.7	Calculated regression equation values and uncertainties	18

Table A.8	Upper and lower bounds for slope, effective diffusion coefficient, and leachability index	18
Table A.9	Upper and lower bounds for y-intercept.....	18
Table B.1	Description of test specimens.....	19
Table B.2	Description of leach test specimen(s).....	19
Table B.3	Analytical techniques	21
Table B.4	Rinse fractions and measured fractions for each interval.....	22
Table B.5	Results for radionuclide <i>i</i> in ANS-16.1 tests with Specimens A and B	22
Table B.6	Values used to calculate regression equation parameter values and uncertainties for test with Specimen A	23
Table B.7	Calculated regression equation values.....	24
Table B.8	Upper and lower bounds for slope, effective diffusion coefficient, and leachability index	25
Table B.9	Upper and lower bounds for y-intercept.....	25

Measurement of the Leachability of Solidified Low-Level Radioactive Wastes by a Short-Term Test Procedure

1 Scope, purpose, and application

1.1 Scope

This standard¹⁾ provides a procedure to measure and index the release rates of non-volatile radionuclides from low-level radioactive waste forms in demineralized water over a test period. It can be applied to any material from which test specimens can be prepared by casting or cutting into a shape for which the surface area and volume can be determined. The results of this procedure do not represent waste form degradation in any specific environmental situation or represent waste form performance. The test method presented in this standard is an adaptation of the method published in the 1986 version of this standard but constrains test parameter values and data analyses to support direct comparisons of test responses of different waste form materials.

1.2 Purpose

Standardized and practical methods are required to measure the leaching characteristics of radionuclides from different solidified wastes and to calculate values suitable for comparisons. The leachability of a waste form is not an intrinsic property of a material but is affected by the disposal environment and test conditions. The purpose of this standard is to provide a method for measuring the leaching response of a material under specified test conditions and to present mathematical procedures for calculating a material-specific "leachability index" value that is appropriate for relative comparisons. This standard is intended to serve as a basis for indexing the relative radionuclide retention in different solidified low-level radioactive waste forms by using a short-term (5-day) test conducted under controlled conditions.

The test responses are not intended to represent the leaching behavior of a waste form in a disposal system because the test does not account for the material degradation mechanism or environmental effects. Under disposal conditions, processes other than leaching (chemical reactions, formation of surface layers and films, cracking, etc.) might be important considerations. Moreover, the interplay of retardation mechanisms (filtration, ion exchange, coprecipitation, etc.) and enhancement mechanisms (chelation, desorption, dissolution, etc.) might be important considerations for radionuclide migration.

1.3 Application

The test set forth in this standard is applicable to all products of low-level radioactive waste solidification processes from which test specimens can be prepared by casting or cutting into a shape for which the surface area and volume can be determined. The test is short-term, simple, and conducted under conditions that can be readily achieved and reproduced. The essential test parameters are fixed in detail to highlight differences in material responses.

¹⁾ The current standard, ANSI/ANS-16.1-2019, is hereinafter referred to as "this standard."