

July 31, 2002

Reaffirmed by ANSI
July 5, 2007

ANSI S2.21-1998

Reaffirmed by ANSI
August 22, 2012

AMERICAN NATIONAL STANDARD

METHOD FOR PREPARATION

OF A STANDARD MATERIAL

FOR DYNAMIC MECHANICAL

MEASUREMENTS


ANSI S2.21-1998

Accredited Standards Committee S2, Mechanical Vibration and Shock

Standards Secretariat
Acoustical Society of America
120 Wall Street, 32nd Floor
New York, New York 10005-3993

The American National Standards Institute, Inc. (ANSI) is the national coordinator of voluntary standards development and the clearinghouse in the U.S. for information on national and international standards.

The Acoustical Society of America (ASA) is an organization of scientists and engineers formed in 1929 to increase and diffuse the knowledge of acoustics and to promote its practical applications.



ANSI S2.21-1998

American National Standard

Method for Preparation of a Standard Material for Dynamic Mechanical Measurements

Secretariat
Acoustical Society of America

Approved 22 June 1998
American National Standards Institute, Inc.

Abstract

This Standard defines a method for preparing a standard viscoelastic material for comparison of different instruments and calibration of the same instrument.

AMERICAN NATIONAL STANDARDS ON ACOUSTICS

The Acoustical Society of America (ASA) provides the Secretariat for Accredited Standards Committees S1 on Acoustics, S2 on Mechanical Vibration and Shock, S3 on Bioacoustics, and S12 on Noise. These committees have wide representation from the technical community (manufacturers, consumers, and general-interest representatives). The standards are published by the Acoustical Society of America through the American Institute of Physics as American National Standards after approval by their respective standards committees and the American National Standards Institute.


These standards are developed and published as a public service to provide standards useful to the public, industry, and consumers, and to Federal, State, and local governments.

Each of the Accredited Standards Committees [operating in accordance with procedures approved by American National Standards Institute (ANSI)] is responsible for developing, voting upon, and maintaining or revising its own standards. The ASA Standards Secretariat administers committee organization and activity and provides liaison between the Accredited Standards Committees and ANSI. After the standards have been produced and adopted by the Accredited Standards Committees, and approved as American National Standards by ANSI, the ASA Standards Secretariat arranges for their publication and distribution.

An American National Standard implies a consensus of those substantially concerned with its scope and provisions. Consensus is established when, in the judgment of the ANSI Board of Standards Review, substantial agreement has been reached by directly and materially affected interests. Substantial agreement means much more than a simple majority, but not necessarily unanimity. Consensus requires that all views and objections be considered and that a concerted effort be made towards their resolution.

The use of American National Standards is completely voluntary. Their existence does not in any respect preclude anyone, whether he or she has approved the standards or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not conforming to the standards.

NOTICE: This American National Standard may be revised or withdrawn at any time. The procedures of the American National Standards Institute require that action be taken periodically to reaffirm, revise, or withdraw this Standard.



Standards Secretariat
Acoustical Society of America
120 Wall Street, 32nd Floor
New York, New York 10005-3993
USA

Telephone: +1 212 248 0373
Telefax: +1 212 248 0146
E-mail: asastds@aip.org
Internet: <http://asa.aip.org>

© 1998 by the Acoustical Society of America. This Standard may not be reproduced in whole or in part in any form for sale, promotion, or any commercial purpose, or any purpose not falling within the provisions of the Copyright Act of 1976, without prior written permission of the publisher. For permission, address a request to the Standards Secretariat of the Acoustical Society of America.

Contents

	Page
Foreword	ii
0 Introduction	1
1 Scope, purpose, and applications	1
1.1 Scope	1
1.2 Purpose	1
1.3 Applications	1
2 Informative references	1
3 Definitions	1
3.1 Polyurethane	1
3.2 Glycol	1
3.3 Diisocyanate	1
3.4 Pre-polymer	1
3.5 Chain extender	1
4 Components	1
4.1 Glycol	1
4.2 Diisocyanate	2
4.3 Chain extender	2
5 Required equipment	2
5.1 Vacuum mixer	2
5.2 Mold	2
5.3 Oven	2
6 Preparation of pre-polymer	2
7 Preparation of chain extender blend	2
8 Preparation of final polymer	2
Figure	
1 Typical dynamic mechanical properties of the standard material at 25 °C	3

Foreword

[This Foreword is for information only, and is not a part of ANSI S2.21-1998 *American National Standard Method for Preparation of a Standard Material for Dynamic Mechanical Measurements.*]

This Standard was developed under the jurisdiction of Accredited Standards Committee S2, Mechanical Vibration and Shock, which has the following scope:

Standards, specifications, methods of measurement and test terminology in the fields of mechanical vibration and shock and condition monitoring and diagnostics of machines, but excluding those aspects which pertain to biological safety, tolerance, and comfort.

At the time this Standard was submitted to Accredited Standards Committee S2, Mechanical Vibration and Shock, for approval, the membership was as follows:

D. J. Evans, *Chair*
R. F. Taddeo, *Vice Chair*
A. Brenig, *Secretary*

Acoustical Society of America	D. J. Evans
	R. F. Taddeo (<i>Alt.</i>)
Boyce Engineering International	M. P. Boyce
	C. Meher-Homji (<i>Alt.</i>)
Brüel & Kjær Instruments	L. J. Pace
	M. Alexander (<i>Alt.</i>)
Endevco Corporation	R. D. Sill
Hewlett Packard Company	N. Olsen
National Electrical Manufacturers Association (NEMA)	D. Rawlings
	E. LaBrush (<i>Alt.</i>)
National Institute of Standards and Technology	D. J. Evans
	B. F. Payne (<i>Alt.</i>)
PCB Piezotronics, Inc.	R. W. Lally
	J. Lin (<i>Alt.</i>)
Sandia Corporation	V. I. Bateman
Schenck Trebel Corporation	B. Dittmar
U.S. Naval Sea Systems Command	R. F. Taddeo
	A. K. Kukk (<i>Alt.</i>)
U.S. Naval Surface Warfare Center	P. C. Shang
	L. D. Cole (<i>Alt.</i>)
Vibration Institute	J. McHugh

Individual Experts of Accredited Standards Committee S2, Mechanical Vibration and Shock, were:

P. K. Baade	L. A. Herstein	D. F. Muster
G. Booth	D. L. Johnson	D. E. Vendittis
K. M. Eldred	A. F. Kilcullen	H. E. von Gierke
S. I. Hayek		

Working Group S2/WG79, Characterization of the Dynamic Properties of Viscoelastic Polymers, which assisted Accredited Standards Committee S2, Mechanical Vibration and Shock, in the development of this Standard, had the following membership:

W. M. Madigosky, *Chair*
B. Hartmann, *Vice-Chair*

B. R. Allen	J. Duncan	S. O. Oyadji
R. Blaine	B. Hosten	J. S. Peraro
D. A. Brown	E. M. Kerwin	D. F. Sauter
R. N. Capps	M. F. Kluesener	J. P. Szabo
R. J. Deigan	G. F. Lee	C. M. Thompson
W. A. Driscoll	J. D. Lee	R. E. Wetton
J. J. Dlubac	A. Nashif	

Suggestions for improvements of this Standard will be welcomed. Send suggestions for improvement to Accredited Standards Committee S2, Mechanical Vibration and Shock, in care of the ASA Standards Secretariat, 120 Wall Street, 32nd Floor, New York, New York 10005-3993, USA. E-mail: asastds@aip.org; Telephone: +1 212 248 0373; Fax +1 212 248 0146.

American National Standard

Method for Preparation of a Standard Material for Dynamic Mechanical Measurements

0 Introduction

0.1 This Standard concerns the preparation of a standard material for use in the calibration of instruments for measuring the dynamic mechanical properties of viscoelastic materials.

0.2 The standard material is chemically classified as a polyurethane.

0.3 The component materials required for the preparation of the standard material are specified in clause 4.

0.4 The laboratory equipment required for the preparation of the standard material is specified in clause 5.

0.5 In the context of this Standard, the phrase "dynamic mechanical properties" means the logarithmic frequency dependence of modulus and loss factor at a given reference temperature.

1 Scope, purpose, and applications

1.1 Scope

This Standard applies to the preparation of a standard material for calibration of instruments for measuring the dynamic mechanical properties of viscoelastic materials.

1.2 Purpose

The purpose of this Standard is to assist users of dynamic mechanical test equipment in preparing the standard material from its basic components.

1.3 Applications

The standard material is used for the calibration of new instruments in comparison with other instruments and in checking the operation of the same instrument at different times.

2 Informative references

[1] ASTM Method D2572-91. *Standard Test Method for Isocyanate Groups in Urethane Materials or Prepolymers*.

[2] W. M. Madigosky and G. F. Lee, "Improved resonance technique for material characterization," *J. Acoust. Soc. Am.* **73**, 1374-1377 (1983).

[3] J. D. Ferry, *Viscoelastic Properties of Polymers*, 3rd ed., Wiley, New York, 1980, pp 264-320.

3 Definitions

For the purposes of this Standard, the following definitions apply:

3.1 polyurethane. A polymer containing the group -NHCOO-.

3.2 glycol. A compound terminated with -OH groups.

3.3 diisocyanate. A compound terminated with -NCO groups.

3.4 pre-polymer. Low molecular weight material formed by the reaction of a glycol with a large excess of diisocyanate.


3.5 chain extender. Compound terminated with -OH groups added to a pre-polymer to complete the reaction of the isocyanate groups and form the final polymer.

4 Components

The material shall be a three component system: a glycol, a diisocyanate, and a chain extender blend of two chemicals.

4.1 Glycol

The glycol shall be polytetramethylene ether glycol of nominal molecular weight 2000. Abbreviation: PTMG2000. The chemical formula for this component is



where the value of n determines the molecular weight. CAS Registry numbers 25190-0601 and 24979-97-3.