



STANDARD

BSR/ASHRAE Standard 86-2013
(Supersedes ANSI/ASHRAE Standard 86-1994)

Methods of Testing the Floc Point of Refrigeration-Grade Oil

Approved by the ASHRAE Standards Committee on January 2, 2013; by the ASHRAE Board of Directors on January 29, 2013; and by the American National Standards Institute on January 30, 2013.

ASHRAE Standards are scheduled to be updated on a five-year cycle; the date following the standard number is the year of ASHRAE Board of Directors approval. The latest edition of an ASHRAE Standard may be purchased on the ASHRAE Web site (www.ashrae.org) or from ASHRAE Customer Service, 1791 Tullie Circle, NE, Atlanta, GA 30329-2305. E-mail: orders@ashrae.org. Fax: 404-321-5478. Telephone: 404-636-8400 (worldwide) or toll free 1-800-527-4723 (for orders in US and Canada). For reprint permission, go to www.ashrae.org/permissions.

© 2013 ASHRAE

ISSN 1041-2336



ASHRAE Standard Project Committee 86
Cognizant TC: 3.4, Lubrication
SPLS Liaison: Boggarm S. Setty

Warren Clough, *Chair**
Corey Anderson*
William Bradford Boggess*
Richard L. Hall*
Ngoc Dung T. Rohatgi*

**Denotes members of voting status when the document was approved for publication*

ASHRAE STANDARDS COMMITTEE 2012–2013

Kenneth W. Cooper, <i>Chair</i>	Julie M. Ferguson	Janice C. Peterson
William F. Walter, <i>Vice-Chair</i>	Krishnan Gowri	Heather L. Platt
Douglass S. Abramson	Cecily M. Grzywacz	Ira G. Poston
Karim Amrane	Richard L. Hall	Douglas T. Reindl
Charles S. Barnaby	Rita M. Harrold	James R. Tauby
Hoy R. Bohanon, Jr.	Adam W. Hinge	James K. Vallort
Steven F. Bruning	Debra H. Kenroy	Craig P. Wray
David R. Conover	Jay A. Kohler	Charles H. Culp, III, <i>BOD ExO</i>
Steven J. Emmerich	Rick A. Larson	Constantinos A. Balaras, <i>CO</i>
	Mark P. Modera	

Stephanie C. Reiniche, *Manager of Standards*

SPECIAL NOTE

This American National Standard (ANS) is a national voluntary consensus standard developed under the auspices of ASHRAE. *Consensus* is defined by the American National Standards Institute (ANSI), of which ASHRAE is a member and which has approved this standard as an ANS, as "substantial agreement reached by directly and materially affected interest categories. This signifies the concurrence of more than a simple majority, but not necessarily unanimity. Consensus requires that all views and objections be considered, and that an effort be made toward their resolution." Compliance with this standard is voluntary until and unless a legal jurisdiction makes compliance mandatory through legislation.

ASHRAE obtains consensus through participation of its national and international members, associated societies, and public review.

ASHRAE Standards are prepared by a Project Committee appointed specifically for the purpose of writing the Standard. The Project Committee Chair and Vice-Chair must be members of ASHRAE; while other committee members may or may not be ASHRAE members, all must be technically qualified in the subject area of the Standard. Every effort is made to balance the concerned interests on all Project Committees.

The Manager of Standards of ASHRAE should be contacted for:

- interpretation of the contents of this Standard,
- participation in the next review of the Standard,
- offering constructive criticism for improving the Standard, or
- permission to reprint portions of the Standard.

DISCLAIMER

ASHRAE uses its best efforts to promulgate Standards and Guidelines for the benefit of the public in light of available information and accepted industry practices. However, ASHRAE does not guarantee, certify, or assure the safety or performance of any products, components, or systems tested, installed, or operated in accordance with ASHRAE's Standards or Guidelines or that any tests conducted under its Standards or Guidelines will be nonhazardous or free from risk.

ASHRAE INDUSTRIAL ADVERTISING POLICY ON STANDARDS

ASHRAE Standards and Guidelines are established to assist industry and the public by offering a uniform method of testing for rating purposes, by suggesting safe practices in designing and installing equipment, by providing proper definitions of this equipment, and by providing other information that may serve to guide the industry. The creation of ASHRAE Standards and Guidelines is determined by the need for them, and conformance to them is completely voluntary.

In referring to this Standard or Guideline and in marking of equipment and in advertising, no claim shall be made, either stated or implied, that the product has been approved by ASHRAE.

CONTENTS

BSR/ASHRAE Standard 86-2013, Methods of Testing the Floc Point of Refrigeration-Grade Oils

SECTION	PAGE
Foreword.....	2
1 Purpose	2
2 Scope	2
3 Definitions.....	2
4 Apparatus	2
5 Test Procedure	3
6 Reproducibility of Results	4
7 Significance of results.....	4
8 References	4
Informative Annex A—Round Robin Test Results.....	4
Informative Annex B—Bibliography.....	4

NOTE

Approved addenda, errata, or interpretations for this standard can be downloaded free of charge from the ASHRAE Web site at www.ashrae.org/technology.

© 2013 ASHRAE

1791 Tullie Circle NE · Atlanta, GA 30329 · www.ashrae.org · All rights reserved.

ASHRAE is a registered trademark of the American Society of Heating, Refrigerating and Air-Conditioning Engineers, Inc.
ANSI is a registered trademark of the American National Standards Institute.

(This foreword is not part of this standard. It is merely informative and does not contain requirements necessary for conformance to the standard. It has not been processed according to the ANSI requirements for a standard and may contain material that has not been subject to public review or a consensus process. Unresolved objectors on informative material are not offered the right to appeal at ASHRAE or ANSI.)

FOREWORD

This standard describes a standard test method for measuring the floc point (waxing tendency) of refrigeration-grade oils. Petroleum-derived oils are mixtures of large numbers of chemically distinct hydrocarbon molecules. At the low temperatures encountered in the low-pressure side of refrigeration units, some of the larger molecules separate from the bulk of the oil in the form of wax-like deposits. Wax deposition of these molecules in refrigeration systems is undesirable, as they are known to clog capillary tubes and to cause expansion valves to stick. The floc point procedure requires, in addition to the oil, a fluid in which the oil is completely miscible to a temperature below that at which floc will form. Refrigerant-12 (R-12) was selected because it fits this requirement. Refrigerant-22 (R-22), for example, cannot be used because phase separation would, generally, result before the floc point was reached. The ensuing hazing, clouding, and separation into two different layers precludes obtaining a floc point. The industry has a great deal of experience in successfully extrapolating floc point data from the test tube to field application.

Development of a floc point using some other fluid besides R-12 is feasible. However, it would require a research project and extrapolation of the data from another fluid without the field correlation, which has been available for R-12 floc point data, could result in major field problems.

This revision includes: (a) a revised title, purpose, and scope, (b) editorial changes to comply with ASHRAE's mandatory language requirements, (c) dual units as needed to comply with ASHRAE's units format policy, and (d) several editorial changes aimed at improving usability.

1. PURPOSE

This standard provides a method for measuring the waxing tendency of refrigeration-grade oils.

2. SCOPE

The floc point measurement indicates the waxing tendency of refrigeration-grade oils at low temperatures. The floc point is defined as the highest temperature at which wax or other solid substances precipitate when a mixture 10% by volume of oil and 90% by volume of R-12 is cooled under specified conditions. The results can be used to compare the waxing tendency of several different oils.

3. DEFINITIONS

floc point: the highest temperature at which solid substances precipitate when a mixture 10% by volume of oil and 90% by volume of R-12 is cooled under specified conditions.

flocculent: containing, or occurring in the form of, loosely aggregated particles or soft flakes.

refrigeration-grade oil: a naphthenic/paraffinic type oil that is stable with system components, will form a friction-reducing film between rubbing surfaces and seal critical clearances, and has low-temperature transport properties suitable for the application for which it is used.

wax: higher molecular weight materials that are not soluble in R-12/mineral oil mixtures at a particular temperature.

4. APPARATUS

4.1 Cooling Bath. A cooling bath is required for obtaining the necessary temperature. It is prepared by using dry ice or a refrigeration system as the cooling source. The cooling bath shall be large enough for testing three sample tubes at one time. A large, wide-mouthed, clear Dewar flask is one cooling bath option. Dry ice in a liquid such as ethanol or acetone is required. The use of liquids such as ethanol is necessary because this liquid has the advantage of reduced frosting when the sample tube is raised from the bath for observation. A mechanical stirrer shall be provided for stirring the bath. Proper stirring is important to eliminate temperature differences. A small piece of aluminum foil in the liquid will indicate the degree of stirring obtained. If an electric motor is used, it is required to be of a type safe for use above the flammable cooling medium. A wire mesh basket with small openings shall be provided in the bath for the introduction of the dry ice so small pieces of dry ice cannot come into contact with the sample tube and cause local cold spots. The wire mesh basket can be raised or lowered to control the bath temperature.

4.2 Temperature-Measuring Devices. The temperature is measured with a precision electrical digital thermometer, a mercury thermometer, or an alcohol thermometer. ASTM standard thermometers 6F or 6C shall be used for this purpose. Thermometers shall be calibrated as prescribed by ASTM E1-07.¹

4.3 Sample Tube. The sample tube consists of a thick walled borosilicate glass tube with a flared end and round bottom, as shown in Figure 1. Tube dimensions are 0.375 in. (9.5 mm) ID × 0.600 in. (15 mm) OD × 9 in. (228 mm) long. The tube shall be permanently graduated at the 0.34 oz (10.0 mL) volume (calibrated at room temperature).

4.4 Metal Connector Fittings. The metal connector fittings shall be as shown in Figure 1.

4.5 Graph Paper. In certain instances, graph paper is used with a glass plate to judge the cloudiness of the test sample. The graph shall have 20 lines per 1.0 in. (25.4 mm).

4.6 Mechanical Vacuum Pump. A mechanical vacuum pump that provides an absolute pressure of 13.3 Pa (0.1 mm Hg) shall be used.