



STANDARD

ANSI/ASHRAE Standard 97-2007 (RA 2017)
(Reaffirmation of ANSI/ASHRAE Standard 97-2007)

Sealed Glass Tube Method to Test the Chemical Stability of Materials for Use within Refrigerant Systems

Approved by ASHRAE on May 31, 2017, and by the American National Standards Institute on June 1, 2017.

ASHRAE Standards are scheduled to be updated on a five-year cycle; the date following the Standard number is the year of ASHRAE approval. The latest edition of an ASHRAE Standard may be purchased on the ASHRAE website (www.ashrae.org) or from ASHRAE Customer Service, 1791 Tullie Circle, NE, Atlanta, GA 30329-2305. E-mail: orders@ashrae.org. Fax: 678-539-2129. Telephone: 404-636-8400 (worldwide) or toll free 1-800-527-4723 (for orders in US and Canada). For reprint permission, go to www.ashrae.org/permissions.

© 2017 ASHRAE

ISSN 1041-2336



ASHRAE Standard Project Committee 97-1999
Cognizant TC: 3.2, Refrigerant System Chemistry
SPLS Liaison: Thomas E. Watson

Robert G. Doerr*, *Chair*
Jay Field, *Secretary*
Warren R. Clough*
Lois L. Lin*

Thomas R. Rajewski*
Shelvin Rosen*
Andrew Swallow*
Henry Balduzzi

Tom Leck
Cheri Wellman
Robert W. Yost

* Denotes members of voting status when the document was previously approved for publication

STANDARDS REAFFIRMATION SUBCOMMITTEE 2006–2007*

James Lutz, *Chair*
Michael Beda

Steven Bushby
R. Michael Martin

Bodh Subherwal
James Woods

* For the 2007 revision in which minor changes were performed (i.e., updating references),
SRS acted as the consensus project committee

ASHRAE STANDARDS COMMITTEE 2016–2017

Rita M. Harrold, *Chair*
Steven J. Emmerich, *Vice-Chair*
James D. Aswegan
Niels Bidstrup
Donald M. Brundage
Drury B. Crawley
John F. Dunlap,
James W. Earley, Jr.
Keith I. Emerson
Julie M. Ferguson

Michael W. Gallagher
Walter T. Grondzik
Vinod P. Gupta
Susanna S. Hanson
Roger L. Hedrick
Rick M. Heiden
Srinivas Katipamula
Cesar L. Lim
Arsen K. Melikov
R. Lee Millies, Jr.

Cyrus H. Nasser
David Robin
Peter Simmonds
Dennis A. Stanke
Wayne H. Stoppelmoor, Jr.
Jack H. Zarour
William F. Walter, *BOD ExO*
Patricia Graef, *CO*

Stephanie C. Reiniche, *Senior Manager of Standards*

SPECIAL NOTE

This American National Standard (ANS) is a national voluntary consensus Standard developed under the auspices of ASHRAE. Consensus is defined by the American National Standards Institute (ANSI), of which ASHRAE is a member and which has approved this Standard as an ANS, as "substantial agreement reached by directly and materially affected interest categories. This signifies the concurrence of more than a simple majority, but not necessarily unanimity. Consensus requires that all views and objections be considered, and that an effort be made toward their resolution." Compliance with this Standard is voluntary until and unless a legal jurisdiction makes compliance mandatory through legislation.

ASHRAE obtains consensus through participation of its national and international members, associated societies, and public review.

ASHRAE Standards are prepared by a Project Committee appointed specifically for the purpose of writing the Standard. The Project Committee Chair and Vice-Chair must be members of ASHRAE; while other committee members may or may not be ASHRAE members, all must be technically qualified in the subject area of the Standard. Every effort is made to balance the concerned interests on all Project Committees.

The Senior Manager of Standards of ASHRAE should be contacted for

- a. interpretation of the contents of this Standard,
- b. participation in the next review of the Standard,
- c. offering constructive criticism for improving the Standard, or
- d. permission to reprint portions of the Standard.

DISCLAIMER

ASHRAE uses its best efforts to promulgate Standards and Guidelines for the benefit of the public in light of available information and accepted industry practices. However, ASHRAE does not guarantee, certify, or assure the safety or performance of any products, components, or systems tested, installed, or operated in accordance with ASHRAE's Standards or Guidelines or that any tests conducted under its Standards or Guidelines will be nonhazardous or free from risk.

ASHRAE INDUSTRIAL ADVERTISING POLICY ON STANDARDS

ASHRAE Standards and Guidelines are established to assist industry and the public by offering a uniform method of testing for rating purposes, by suggesting safe practices in designing and installing equipment, by providing proper definitions of this equipment, and by providing other information that may serve to guide the industry. The creation of ASHRAE Standards and Guidelines is determined by the need for them, and conformance to them is completely voluntary.

In referring to this Standard or Guideline and in marking of equipment and in advertising, no claim shall be made, either stated or implied, that the product has been approved by ASHRAE.

CONTENTS

ANSI/ASHRAE Standard 97-2007 (RA 2017) Sealed Glass Tube Method to Test the Chemical Stability of Materials for Use within Refrigerant Systems

SECTION	PAGE
Foreword	
1 Purpose.....	2
2 Scope.....	2
3 Apparatus.....	2
4 Procedure for Preparing the Sealed Glass Tubes	3
5 Aging the Sealed Glass Tubes.....	6
6 Analysis of the Tubes.....	6
7 Significance of Results.....	6
8 Safety Requirements.....	7
9 References.....	8
Informative Appendix A: Calculation of Refrigerant Pressure in Sealed Tubes Containing 0.7 mL of Refrigerant.....	9
Informative Appendix B: Bibliography	11

NOTE

Approved addenda, errata, or interpretations for this standard can be downloaded free of charge from the ASHRAE website at www.ashrae.org/technology.

© 2017 ASHRAE

1791 Tullie Circle NE · Atlanta, GA 30329 · www.ashrae.org · All rights reserved.

ASHRAE is a registered trademark of the American Society of Heating, Refrigerating and Air-Conditioning Engineers, Inc.
ANSI is a registered trademark of the American National Standards Institute.

(This foreword is not part of this standard. It is merely informative and does not contain requirements necessary for conformance to the standard. It has not been processed according to the ANSI requirements for a standard and may contain material that has not been subject to public review or a consensus process. Unresolved objections on informative material are not offered the right to appeal at ASHRAE or ANSI.)

FOREWORD

ASHRAE Standard 97 describes a uniform means for testing the various materials used within hermetic and nonhermetic refrigerant systems. It is primarily intended as an accelerated screening tool and can provide valuable information on the chemical stability of system materials.

This is a reaffirmation of Standard 97-2007. This standard was prepared under the auspices of ASHRAE. It may be used, in whole or in part, by an association or government agency with due credit to ASHRAE. Adherence is strictly on a voluntary basis and merely in the interests of obtaining uniform guidelines throughout the industry. This version of the reaffirmation has no changes.

1. PURPOSE

The purpose of this standard is to establish a test procedure utilizing sealed glass tubes for the evaluation of materials for use in refrigerant systems.

2. SCOPE

2.1 This standard describes the preparation of sealed glass tubes and the procedure for charging them with refrigerant, lubricant, other materials to be tested, or combinations of these.

2.2 A procedure for aging the tubes, usually at elevated temperatures, is described. The tubes are evaluated by quantitative or qualitative analysis, or both, of the tube contents to yield information for determining the compatibility or chemical stability of materials in refrigerant systems.

2.3 The technique described may be used for evaluating many different types of materials. Therefore, the standard does not describe in detail the preparation of the materials to be tested prior to placing them in the glass tubes, the conditions of exposure, nor the methods of analysis.

2.4 Detailed safety precautions are included in Section 8, "Safety Requirements."

3. APPARATUS

3.1 A *sealed glass tube* generally consists of a borosilicate glass tube 9 mm (0.35 in.) OD × 7 mm (0.27 in.) ID × approximately 180 mm (7.1 in.) long with one end formed into a round bottom. The above are the finished dimensions. The tube is charged with the refrigerant and materials to be tested and then sealed in a rounded tip at the other end.

3.2 The *tube charging apparatus* is illustrated in Figure 1. This apparatus consists of a manifold (metal or glass), vacuum pump, pressure gauge, high vacuum gauge, refrigerant cylinder, valves, and filling ports. The function of this apparatus is




Figure 1 Manifold for filling glass tubes.

to evacuate the tube, add refrigerant, and seal it along with the test materials. It is calibrated so that the refrigerant may be added very accurately by following the change in pressure on the vacuum gauge as refrigerant is added to the tube.

3.3 An *aluminum block* is used for aging the sealed glass tubes at elevated temperatures. The aluminum block has cylindrical holes in it to support the sealed glass tubes being tested. The purpose of the aluminum block is to protect the tubes from each other in the event of breakage. A further function is to maintain temperature uniformity. A typical aluminum block is illustrated in Figure 2. The holes in the block should be drilled completely through, and the block should have a separate removable bottom to simplify cleaning. A vent may be included to release pressure should a tube burst. The overall dimensions shall be sized to accommodate the desired number of sealed glass tubes while maintaining adequate wall thickness. A small wad of glass wool should be placed in the bottom of the drilled hole to cushion and support the tubes during aging.

3.4 *Individual pipe chambers* may be more convenient for testing a small number of samples, instead of the aluminum block described above. These individual chambers may be constructed of metal pipe and closed at both ends with threaded caps.

3.5 The electrically heated *aging oven* shall have mechanical convection capable of maintaining a uniform temperature with $\pm 1.0^{\circ}\text{C}$ (1.8°F) throughout the test chamber. The oven chamber shall be large enough to accommodate the aluminum block and allow for adequate air circulation and venting. The oven shall be equipped with an indicating controller with a control sensitivity of $\pm 0.5^{\circ}\text{C}$ (0.9°F).

3.6 The *tube opening apparatus* is illustrated in Figure 3. This apparatus is suitable for safely and conveniently opening a sealed tube for subsequent analysis of the contents. An alternative apparatus is illustrated in Figure 4.

3.7 *Flexible tubing* (PVC or rubber) is often used in preparation of sealed glass tubes. It is important to clean the tubing prior to use. It must be free of excess plasticizer, lubricants, powders, and other contaminants.