

AASHTO/AWS D1.5M/D1.5:2010  
An American National Standard

# Bridge Welding Code

A Joint Publication of  
American Association of State Highway  
and Transportation Officials



**American Welding Society**

**AASHTO/AWS D1.5M/D1.5:2010  
An American National Standard**

**Approved by the  
American National Standards Institute  
August 18, 2010**

**Bridge Welding Code**

**6th Edition**

**Supersedes AASHTO/AWS D1.5M/D1.5:2008**

Prepared by the  
American Welding Society (AWS) D1 Committee on Structural Welding  
AASHTO Highway Subcommittee on Bridges and Structures

Under the Direction of the  
AWS Technical Activities Committee  
AASHTO Executive Committee

Approved by the  
AWS Board of Directors  
AASHTO Board of Directors/Policy Committee

**Abstract**

This code covers the welding requirements for AASHTO welded highway bridges made from carbon and low-alloy constructional steels. This 2010 edition contains dimensions in metric SI Units and U.S. Customary Units. Clauses 1 through 7 constitute a body of rules for the regulation of welding in steel construction. The provisions for Clause 9 have been distributed throughout the D1.5 code. Clauses 8, 10, and 11 do not contain provisions, as their analogue D1.1 sections are not applicable to the D1.5 code. Clause 12 contains the requirements for fabricating fracture critical members.

A Joint Publication of:

**American Association of State  
Highway and Transportation Officials**  
444 N. Capitol Street, N.W., Suite 225  
Washington, DC 20001

**American Welding Society**  
550 N.W. LeJeune Road  
Miami, FL 33126

International Standard Book Number: 978-0-87171-781-8

American Welding Society

550 N.W. LeJeune Road, Miami, FL 33126

© 2010 by American Welding Society

All rights reserved

Printed in the United States of America

**Photocopy Rights.** No portion of this standard may be reproduced, stored in a retrieval system, or transmitted in any form, including mechanical, photocopying, recording, or otherwise, without the prior written permission of the copyright owner.

Authorization to photocopy items for internal, personal, or educational classroom use only or the internal, personal, or educational classroom use only of specific clients is granted by the American Welding Society provided that the appropriate fee is paid to the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, tel: (978) 750-8400; Internet: <[www.copyright.com](http://www.copyright.com)>.

## Statement on the Use of American Welding Society Standards

All standards (codes, specifications, recommended practices, methods, classifications, and guides) of the American Welding Society (AWS) are voluntary consensus standards that have been developed in accordance with the rules of the American National Standards Institute (ANSI). When AWS American National Standards are either incorporated in, or made part of, documents that are included in federal or state laws and regulations, or the regulations of other governmental bodies, their provisions carry the full legal authority of the statute. In such cases, any changes in those AWS standards must be approved by the governmental body having statutory jurisdiction before they can become a part of those laws and regulations. In all cases, these standards carry the full legal authority of the contract or other document that invokes the AWS standards. Where this contractual relationship exists, changes in or deviations from requirements of an AWS standard must be by agreement between the contracting parties.

AWS American National Standards are developed through a consensus standards development process that brings together volunteers representing varied viewpoints and interests to achieve consensus. While the AWS administers the process and establishes rules to promote fairness in the development of consensus, it does not independently test, evaluate, or verify the accuracy of any information or the soundness of any judgments contained in its standards.

AWS disclaims liability for any injury to persons or to property, or other damages of any nature whatsoever, whether special, indirect, consequential, or compensatory, directly or indirectly resulting from the publication, use of, or reliance on this standard. AWS also makes no guarantee or warranty as to the accuracy or completeness of any information published herein.

In issuing and making this standard available, AWS is neither undertaking to render professional or other services for or on behalf of any person or entity, nor is AWS undertaking to perform any duty owed by any person or entity to someone else. Anyone using these documents should rely on his or her own independent judgment or, as appropriate, seek the advice of a competent professional in determining the exercise of reasonable care in any given circumstances. It is assumed that the use of this standard and its provisions are entrusted to appropriately qualified and competent personnel.

This standard may be superseded by the issuance of new editions. Users should ensure that they have the latest edition.

Publication of this standard does not authorize infringement of any patent or trade name. Users of this standard accept any and all liabilities for infringement of any patent or trade name items. AWS disclaims liability for the infringement of any patent or product trade name resulting from the use of this standard.

Finally, the AWS does not monitor, police, or enforce compliance with this standard, nor does it have the power to do so.

On occasion, text, tables, or figures are printed incorrectly, constituting errata. Such errata, when discovered, are posted on the AWS web page ([www.aws.org](http://www.aws.org)).

Official interpretations of any of the technical requirements of this standard may only be obtained by sending a request, in writing, to the appropriate technical committee. Such requests should be addressed to the American Welding Society, Attention: Managing Director, Technical Services Division, 550 N.W. LeJeune Road, Miami, FL 33126 (see Annex O). With regard to technical inquiries made concerning AWS standards, oral opinions on AWS standards may be rendered. These opinions are offered solely as a convenience to users of this standard, and they do not constitute professional advice. Such opinions represent only the personal opinions of the particular individuals giving them. These individuals do not speak on behalf of AWS, nor do these oral opinions constitute official or unofficial opinions or interpretations of AWS. In addition, oral opinions are informal and should not be used as a substitute for an official interpretation.

This standard is subject to revision at any time by the AWS D1 Committee on Structural Welding and the AASHTO Technical Committee on Welding. It must be reviewed every five years, and if not revised, it must be either reaffirmed or withdrawn. Comments (recommendations, additions, or deletions) and any pertinent data that may be of use in improving this standard are required and should be addressed to AWS Headquarters. Such comments will receive careful consideration by the AWS D1 Committee on Structural Welding and the AASHTO Technical Committee on Welding and the author of the comments will be informed of the Committee's response to the comments. Guests are invited to attend all meetings of the AWS D1 Committee on Structural Welding and the AASHTO Technical Committee on Welding to express their comments verbally. Procedures for appeal of an adverse decision concerning all such comments are provided in the Rules of Operation of the Technical Activities Committee. A copy of these Rules can be obtained from the American Welding Society, 550 N.W. LeJeune Road, Miami, FL 33126.

This page is intentionally blank.

## Personnel

### AWS D1 Committee on Structural Welding

D. K. Miller, Chair	<i>The Lincoln Electric Company</i>
A. W. Sindel, 1st Vice Chair	<i>Alstom Power, Incorporated</i>
T. L. Niemann, 2nd Vice Chair	<i>Minnesota Department of Transportation</i>
S. Morales, Secretary	<i>American Welding Society</i>
N. J. Altebrando	<i>STV, Incorporated</i>
F. G. Armao	<i>The Lincoln Electric Company</i>
E. L. Bickford	<i>Acute Technological Services</i>
B. M. Butler	<i>Walt Disney World Company</i>
R. D. Campbell	<i>Bechtel National, Incorporated</i>
H. H. Campbell III	<i>Pazuzu Engineering</i>
L. E. Collins	<i>Team Industries, Incorporated</i>
R. B. Corbit	<i>Exelon Nuclear Corporation</i>
R. A. Dennis	<i>Consultant</i>
M. A. Grieco	<i>Massachusetts Department of Transportation</i>
C. R. Hess	<i>High Steel Structures, Incorporated (Retired)</i>
C. W. Holmes	<i>Modjeski and Masters, Incorporated</i>
J. J. Kenney	<i>Shell International E &amp; P</i>
J. H. Kiefer	<i>ConocoPhillips Company</i>
V. Kuruvilla	<i>Genesis Quality Systems</i>
J. Lawmon	<i>American Engineering &amp; Manufacturing, Incorporated</i>
N. S. Lindell	<i>Inspectech, Incorporated</i>
D. R. Luciani	<i>Canadian Welding Bureau</i>
S. L. Luckowski	<i>Department of the Army</i>
P. W. Marshall	<i>MHP Systems Engineering</i>
M. J. Mayes	<i>Mayes Testing Engineers, Incorporated</i>
D. L. McQuaid	<i>D. L. McQuaid and Associates, Incorporated</i>
R. D. Medlock	<i>High Steel Structures, Incorporated</i>
J. Merrill	<i>MACTEC, Incorporated</i>
J. B. Pearson, Jr.	<i>LTK Engineering Services</i>
D. C. Phillips	<i>Hobart Brothers Company</i>
D. D. Rager	<i>Rager Consulting, Incorporated</i>
T. J. Schlafly	<i>American Institute of Steel Construction</i>
D. R. Scott	<i>PSI (Retired)</i>
R. E. Shaw, Jr.	<i>Steel Structures Technology Center, Incorporated</i>
R. W. Stieve	<i>Greenman-Pederson, Incorporated</i>
M. M. Tayarani	<i>Massachusetts Department of Transportation</i>
K. K. Verma	<i>Federal Highway Administration</i>
B. D. Wright	<i>Advantage Aviation Technologies</i>

### **Advisors to the D1 Committee on Structural Welding**

W. G. Alexander	<i>WGAPE</i>
E. M. Beck	<i>MACTEC, Incorporated</i>
O. W. Blodgett	<i>The Lincoln Electric Company (Retired)</i>
G. L. Fox	<i>Consultant</i>
G. J. Hill	<i>G. J. Hill and Associates, Incorporated</i>
M. L. Hoitomt	<i>Hoitomt Consulting Services</i>
D. R. Lawrence II	<i>Blue Scope Steel (Retired)</i>
W. A. Milek, Jr.*	<i>Consultant</i>
J. E. Myers	<i>Consultant</i>
J. W. Post	<i>J. W. Post and Associates, Incorporated</i>
P. J. Sullivan	<i>Massachusetts Department of Transportation (Retired)</i>

### **AASHTO Technical Committee for Welding**

A K. Bardow, Chair	<i>Massachusetts Department of Transportation</i>
P. V. Liles, Vice Chair	<i>Georgia Department of Transportation</i>
G. Bailey	<i>West Virginia Department of Transportation</i>
K. B. Carr	<i>Mississippi Department of Transportation</i>
D. L. Dorgan	<i>Minnesota Department of Transportation</i>
B. Newton	<i>California Department of Transportation</i>
W. B. Symonds	<i>Vermont Agency of Transportation</i>
K. K. Verma	<i>Federal Highway Administration</i>

### **Joint AASHTO/AWS Bridge Welding Subcommittee**

T. L. Niemann, Chair	<i>Minnesota Department of Transportation</i>
D. L. McQuaid, Vice Chair	<i>D. L. McQuaid and Associates, Incorporated</i>

### **AASHTO Representatives**

S. Birdsley	<i>Wyoming Department of Transportation</i>
W. Doukas	<i>Maine Department of Transportation</i>
H. E. Gilmer	<i>PDM Bridge, LLC</i>
M. A. Grieco	<i>Massachusetts Department of Transportation</i>
K. Ledford	<i>Georgia Department of Transportation</i>
K. Nelson	<i>Missouri Department of Transportation</i>
S. Walton	<i>North Carolina Department of Transportation</i>

### **AWS Representatives**

C. W. Holmes	<i>Modjeski and Masters, Incorporated</i>
N. S. Lindell	<i>Inspectech, Incorporated</i>
R. D. Medlock	<i>High Steel Structures, Incorporated</i>
D. K. Miller	<i>The Lincoln Electric Company</i>
D. C. Phillips	<i>Hobart Brothers Company</i>
B. Roberds	<i>PDM Bridge, LLC</i>
M. M. Tayarani	<i>Massachusetts Department of Transportation</i>
K. K. Verma	<i>Federal Highway Administration</i>

\*Deceased

**Advisors to the Joint AASHTO/AWS Bridge Welding Subcommittee**

N. J. Altebrando	<i>STV, Incorporated</i>
S. Anderson	<i>Canam Steel Corporation</i>
L. E. Collins	<i>Team Industries, Incorporated</i>
J. J. Edwards	<i>Atema, Incorporated</i>
F. Grasty	<i>KTA-Tator Incorporated</i>
B. Horn	<i>Michelman-Cancelliere Iron Works</i>
D. M. Ison	<i>Tampa Tank Florida Structural Steel</i>
W. M. Kavicky	<i>Trans Bay Steel Corporation</i>
S. W. Kopp	<i>High Steel Structures</i>
J. Mellinger	<i>Pennoni Associates, Incorporated</i>
J. Merrill	<i>Mactec Engineering &amp; Consulting</i>
D. D. Rager	<i>Rager Consulting, Incorporated</i>
R. Rimmer	<i>NYS Department of Transportation</i>
T. J. Schlafly	<i>American Institute of Steel Construction</i>
R. Stieve	<i>Greenman-Pedersen, Incorporated</i>



This page is intentionally blank.

## Foreword

This foreword is not part of AASHTO/AWS D1.5M/D1.5:2010, *Bridge Welding Code*, but is included for informational purposes only.

The preparation of this specification was undertaken in response to a need for a common welding specification for the fabrication of steel highway bridges by welding. The departments of highways and transportation in the 50 states, the District of Columbia, and Puerto Rico that make up the American Association of State Highway and Transportation Officials have routinely used the specifications of the American Welding Society Structural Welding Committee, with appropriate modifications, to produce contract documents suitable for the construction of bridges using Federal Highway funds. The proliferation of requirements by the 50 states, District of Columbia and Puerto Rico that make up AASHTO (American Association of State Highway and Transportation Officials) resulted in the recognition of the need for a single document that could produce greater economies in bridge fabrication, while at the same time addressing the issues of structural integrity and public safety.

The first AWS code for *Fusion Welding and Gas Cutting in Building Construction* was published in 1928. In 1934, a committee was appointed to prepare specifications for the design, construction, alteration, and repair of highway and railway bridges. The first bridge specification was published in 1936. Until 1963, there were separate AWS committees for bridges and buildings. These two committees joined in 1963 to form the Structural Welding Committee of the American Welding Society. The committee has since promulgated standards for the application of welding to the design and construction of structures.

The Federal Highway Administration of the United States Department of Transportation requires states using federal funds for the construction of welded highway bridges to conform to specified standards for design and construction. Conformance to the AWS *Specification for Welded Highway and Railway Bridges* was first specified in the third edition of the AASHTO *Standard Specifications for Highway Bridges* in 1941. In 1962, the Bureau of Public Roads, now the Federal Highway Administration (FHWA), required conformance to a Circular Memorandum, dated November 13, 1962, which transmitted additional provisions for welding A36 steel pending publication of an AWS specification which would contain certain essential provisions not then in the code. Another Circular Memorandum, dated February 11, 1965, specified requirements for CVN testing, and a further Circular Memorandum, dated August 19, 1966, modified provisions of the 1966 Edition of the AWS D2.0-66, *Specification for Welded Highway and Railway Bridges*.

In 1974, AASHTO published the first edition of the *Standard Specification for Welding of Structural Steel Highway Bridges*. The Eleventh Edition of the AASHTO *Standard Specifications for Highway Bridges*, dated 1977, directed "Welding shall conform to the requirements of the AASHTO *Standard Specifications for Welding of Structural Steel Highway Bridges* 1974 and subsequent interim specifications..." AASHTO published the Second and Third editions of the *Standard Specifications for Welding of Structural Steel Highway Bridges* in 1977 and 1981. All of the AASHTO specifications were required to be part of the Contract Documents as modifications or additions to the AWS *Structural Welding Code—Steel*. This was a cumbersome procedure.

In 1982, a subcommittee was formed jointly by AASHTO and AWS, with equal representation from both organizations, to seek accommodation between the separate and distinct requirements of bridge Owners and existing provisions of AWS D1.1. The *Bridge Welding Code* is the result of an agreement between AASHTO and AWS to produce a joint AASHTO/AWS *Structural Welding Code* for steel highway bridges that addresses essential AASHTO needs and makes AASHTO revisions mandatory.

The 1988 version of the *Bridge Welding Code* provided for the qualification of welding procedures by test to assure that weld had the strength, ductility, and toughness necessary for use in redundant structures. Nonredundant fracture critical

bridge members were not provided for in the first edition of the code. While qualification of welding procedures is required, a major effort has been made to specify the minimum number of tests and the simplest tests that give reasonable assurance of required mechanical properties. Efforts are made to discourage individual States from requiring duplication of weld testing unless that testing is specified in the bid documents. Special attention is directed to avoidance of unnecessary hardening of base metal HAZs and the avoidance of hydrogen and other items that can lead to weld or base-metal cracking.

Consequently, while the D1.5-88 document has a superficial resemblance to D1.1 in its general format, there are significant differences that users should be aware of, among them the lack of provisions relating to statically loaded structures, tubular construction or the modification of existing structures. Users are encouraged to develop their own requirements for these applications or use existing documents (e.g., D1.1) with the appropriate modifications.

The publication of AASHTO/AWS D1.5M/D1.5:2010 was justified by the need to monitor, revise, and update code provisions based on the needs of AASHTO member states and industry. The following is a list of the major revisions in the 2010 edition:

- (1) New material 345S [50S] was added to the code.
- (2) ESW requirements were separated from EGW.
- (3) ESW requirements now include ESW-NG (Narrow gap improved Electroslag Welding).
- (4) Tables 4.1 and 4.2 were consolidated into one new Table 4.1. Table 4.2 as it previously existed in older editions of the code has been deleted.
- (5) 5.7 was revised in its entirety to reflect the revisions in the new Table 4.1.
- (6) 5.7.6 was extensively revised for clarification and now includes a subclause covering exceptions for combining FCAW WPSs.
- (7) 5.12 was revised to specify heat input requirements for nonstandard groove weld details.
- (8) Provisions were added to the code to address qualification of hybrid joints (joint involving two base metals of different strength, e.g., 50W to HPS 50W).
- (9) Qualification methods of 5.12 and 5.13 were consolidated under the newly revised 5.12 with modified and improved language.
- (10) Table 5.2 was updated to reflect the newly revised Table 4.1 as well as to clarify which joint details can be used for EGW and ESW.
- (11) Table 5.3 was revised to omit ESW.
- (12) 6.1.3.7 was revised to accept only Jaeger J-2 vision acuity for Inspection Personnel.
- (13) 6.17 was modified to require test equipment qualification every two months instead of every forty hours.
- (14) 6.18.3 was modified to require recalibration after change of operators every two hours instead of every thirty minutes.
- (15) Grades 345S [50S] and HPS 345W [HPS 50W] were added to Table 12.1.
- (16) New normative Annex I was added to address ESW electrode consumable requirements.
- (17) New normative Annex J was added to address guidelines for alternative ESW process.
- (18) New informative Annex Q was introduced to guide users on the use of ESW-NG.
- (19) Commentary for Clause 4 was added to address all the remaining provisions of Clause 4.
- (20) Commentary in C-5.7.4 and C-5.7.4.1 were deleted in their entirety.
- (21) Commentary for new Annex I was added.

**Changes in Code Requirements.** Changes to the text of the 2010 edition are indicated by underlining. Changes to illustrations are highlighted by vertical lines in the margin.

Future revisions to this code will be made based on proposals from the Joint AASHTO/AWS Committee as well as those from document users. It should be re-emphasized here that the Joint Committee is the primary agency for receiving feedback from industry, and requires this input in order to produce a quality document. Other documents that do not receive the ANSI/AASHTO/AWS accreditation should not be relied on as substitutes for the Joint Committee's interpretation of D1.5 provisions.

While the D1.1 and D1.5 codes do share a number of common provisions, it should not be assumed that revisions to one document provision automatically revises its analogous provision in the other; therefore, users are encouraged to treat each code as an independent document.

This code was prepared by the AASHTO/AWS Bridge Welding Committee operating as a Subcommittee of the AWS Structural Welding Committee. The Committee is made up of representatives from the AWS Structural Welding Committee and the AASHTO Technical Committee for Welding. Accommodation was sought on all items where there was disagreement between AASHTO and AWS members. Specific issues considered essential by AASHTO were included in this code to eliminate the need for supplemental exclusions or additions by AASHTO.

The AASHTO/AWS D1.5, *Bridge Welding Code*, will be subject to regular review by the Bridge Welding Committee and will be republished or reaffirmed on an as-needed basis, at intervals not to exceed five years. All proposed changes to this code will be subject to approval by AWS and AASHTO prior to publication.

Comments or inquiries pertaining to this code are welcome (see Annex Q). They should be sent to the Secretary, AWS D1 Committee on Structural Welding, American Welding Society, 550 N.W. LeJeune Road, Miami, FL 33126, or to the Chairman of the AASHTO Technical Committee for Welding, American Association of State Highway and Transportation Officials, 444 N. Capitol Street, N.W., Suite No. 225, Washington, DC 20001.

This page is intentionally blank.

# Table of Contents

	Page No.
<i>Personnel</i> .....	v
<i>Foreword</i> .....	ix
<i>List of Tables</i> .....	xviii
<i>List of Figures</i> .....	xx
<i>List of Forms</i> .....	xxii
<b>1. General Provisions</b> .....	<b>1</b>
1.1 Application.....	1
1.2 Base Metal .....	1
1.3 Welding Processes .....	2
1.4 Fabricator Requirements .....	2
1.5 Definitions.....	2
1.6 Welding Symbols .....	2
1.7 Safety Precautions.....	3
1.8 Standard Units of Measurement .....	3
1.9 Welding Procedure Specifications (WPSs).....	3
1.10 Mechanical Testing .....	3
1.11 Reference Documents .....	3
<b>2. Design of Welded Connections</b> .....	<b>5</b>
Part A—General Requirements .....	5
2.1 Drawings .....	5
2.2 Basic Unit Stresses.....	6
2.3 Effective Weld Areas, Lengths, Throats, and Sizes .....	6
Part B—Structural Details .....	6
2.4 General.....	6
2.5 Welded Filler Plates .....	6
2.6 PJP Groove Welds.....	7
Part C—Details of Welded Joints .....	7
2.7 Joint Qualification.....	7
2.8 Details of Fillet Welds .....	7
2.9 Details of Plug and Slot Welds .....	7
2.10 Lap Joints.....	8
2.11 Corner and T-Joints .....	8
2.12 CJP Groove Welds .....	8
2.13 PJP Groove Welds.....	8
2.14 Prohibited Types of Joints and Welds .....	9
2.15 Combinations of Welds.....	9
2.16 Welds in Combination with Rivets and Bolts .....	9
2.17 Connection Details.....	9
<b>3. Workmanship</b> .....	<b>51</b>
3.1 General Requirements.....	51
3.2 Preparation of Base Metal.....	51
3.3 Assembly .....	54

	Page No.
3.4	Control of Distortion and Shrinkage.....56
3.5	Dimensional Tolerances.....56
3.6	Weld Profiles.....58
3.7	Repairs.....58
3.8	Peening.....59
3.9	Caulking.....60
3.10	Arc Strikes.....60
3.11	Weld Cleaning.....60
3.12	Weld Termination.....60
3.13	Weld Backing.....60
<b>4.</b>	<b>Technique.....65</b>
	Part A—General Requirements.....65
4.1	Filler Metal Requirements.....65
4.2	Preheat and Interpass Temperature Requirements.....66
4.3	Heat Input Control for Grade 690 [100] and 690W [100W].....67
4.4	Stress Relief Heat Treatment.....67
	Part B—Shielded Metal Arc Welding (SMAW).....67
4.5	Electrodes for SMAW.....67
4.6	Procedures for SMAW.....68
	Part C—Submerged Arc Welding (SAW).....69
4.7	General Requirements.....69
4.8	Electrodes and Fluxes for SAW.....69
4.9	Procedures for SAW with a Single Electrode.....70
4.10	Procedures for SAW with Parallel Electrodes.....70
4.11	Procedures for SAW with Multiple Electrodes.....71
	Part D—Gas Metal Arc Welding (GMAW) and Flux Cored Arc Welding (FCAW).....72
4.12	Electrodes.....72
4.13	Shielding Gas.....73
4.14	Procedures for GMAW and FCAW with a Single Electrode.....73
	Part E—Electrodeless Welding (EGW).....73
4.15	Qualification of Process, WPSs, and Joint Details.....73
4.16	Mechanical Properties.....74
4.17	Condition of Electrodes and Guide Tubes.....74
4.18	Shielding Gas.....74
4.19	Procedures for EGW.....74
	Part F—Electroslag Welding (ESW).....74
4.20	Qualification of Process, WPSs, and Joint Details.....74
4.21	Mechanical Properties.....74
4.22	Condition of Electrodes and Consumable Guides.....75
4.23	Condition of Flux.....75
4.24	Consumable Guide Electrical Insulators.....75
4.25	Procedures for ESW.....75
	Part G—Plug and Slot Welds.....76
4.26	Plug Welds.....76
4.27	Slot Welds.....77
4.28	Plug and Slot Welds.....77
	Part H—Control of Production Welding Variables.....77
4.29	Tests.....77
4.30	Control of Variables.....77

	Page No.
4.31 Calibration of Equipment.....	77
4.32 Current Control .....	77
<b>5. Qualification .....</b>	<b>89</b>
5.0 Scope.....	89
Part A—Welding Procedure Specification (WPS) Qualification.....	89
5.1 Approval.....	89
5.2 Qualification Responsibility .....	89
5.3 Duration .....	89
5.4 Base Metal .....	90
5.5 Welding Consumables .....	91
5.6 Test Plate Thickness.....	91
5.7 General Requirements for WPS Qualification.....	91
5.8 Position of Test Welds.....	92
5.9 Options for WPS Qualification or Prequalification .....	93
5.10 Fillet Weld WPS Qualification .....	93
5.11 Prequalified WPS.....	93
5.12 Heat Input <u>Qualifications</u> .....	93
5.13 <u>Electro</u> gas Welding .....	95
5.14 <u>Electro</u> slag Welding .....	95
5.15 Type of Tests and Purpose .....	95
5.16 Weld Specimens—Number, Type, and Preparation.....	95
5.17 Nondestructive Testing (NDT).....	96
5.18 Method of Testing Specimens.....	96
5.19 Test Results Required .....	97
5.20 Retests .....	98
Part B—Welder, Welding Operator, and Tack Welder Qualification.....	98
5.21 General Requirements.....	98
5.22 Production Welding Positions Qualified.....	98
5.23 Qualification Tests Required.....	99
5.24 Limitations of Variables.....	100
5.25 Test Specimens: Number, Type, and Preparation .....	101
5.26 Method of Testing Specimens.....	101
5.27 Test Results Required .....	102
5.28 Retests .....	103
<b>6. Inspection.....</b>	<b>137</b>
Part A—General Requirements .....	137
6.1 General.....	137
6.2 Inspection of Materials .....	138
6.3 Inspection of WPS Qualification and Equipment.....	138
6.4 Inspection of Welder, Welding Operator, and Tack Welder Qualifications .....	138
6.5 Inspection of Work and Records.....	138
6.6 Obligations of the Contractor .....	139
6.7 Nondestructive Testing (NDT).....	139
Part B—Radiographic Testing (RT) of Groove Welds in Butt Joints .....	141
6.8 Extent of Testing .....	141
6.9 General.....	141
6.10 RT Procedure .....	141
6.11 Acceptability of Welds.....	144
6.12 Examination, Report, and Disposition of Radiographs .....	144



	Page No.
Part C—Ultrasonic Testing (UT) of Groove Welds.....	144
6.13 General.....	144
6.14 Extent of Testing.....	144
6.15 UT Equipment.....	144
6.16 Reference Standards.....	145
6.17 Equipment Qualification.....	145
6.18 Calibration for Testing.....	145
6.19 Testing Procedures.....	146
6.20 Preparation and Disposition of Reports.....	147
6.21 Calibration of the UT Unit with IIW or Other Approved Reference Blocks.....	147
6.22 Equipment Qualification Procedures.....	148
6.23 Flaw Size Evaluation Procedures.....	150
6.24 Scanning Patterns.....	150
6.25 Examples of dB Accuracy Certification.....	150
Part D—Weld Acceptance Criteria.....	150
6.26 Quality of Welds.....	150
<b>7. Stud Welding.....</b>	<b>171</b>
7.1 Scope.....	171
7.2 General Requirements.....	171
7.3 Mechanical Requirements.....	171
7.4 Workmanship.....	172
7.5 Technique.....	172
7.6 Stud Application Qualification Requirements.....	173
7.7 Production Control.....	174
7.8 Inspection Requirements.....	175
<b>8. Statically Loaded Structures (No Applications within this code).....</b>	<b>179</b>
<b>9. Welded Steel Bridges (The provisions of this clause in ANSI/AASHTO/AWS D1.5-96 were distributed throughout AASHTO/AWS D1.5M/D1.5:2002 and remain so for this edition).....</b>	<b>181</b>
<b>10. Tubular Structures (No Applications within this code).....</b>	<b>183</b>
<b>11. Strengthening and Repairing Existing Structures (No Applications within this code).....</b>	<b>185</b>
<b>12. AASHTO/AWS Fracture Control Plan (FCP) for Nonredundant Members.....</b>	<b>187</b>
12.1 General Provisions.....	187
12.2 Definitions.....	187
12.3 Contract Documents.....	187
12.4 Base Metal Requirements.....	188
12.5 Welding Processes.....	188
12.6 Consumable Requirements.....	188
12.7 Welding Procedure Specification (WPS).....	192
12.8 Certification and Qualification.....	192
12.9 As-Received Inspection of Base Metal.....	193
12.10 Thermal Cutting.....	193
12.11 Repair of Base Metal.....	193
12.12 Straightening, Curving, and Cambering.....	194
12.13 Tack Welds and Temporary Welds.....	194
12.14 Preheat and Interpass Temperature Control.....	194
12.15 Postweld Thermal Treatments.....	194
12.16 Weld Inspection.....	195
12.17 Repair Welding.....	196

	<b>Page No.</b>
<i>Annexes</i> .....	201
Annex A (Normative)—Effective Throat.....	203
Annex B (Normative)—Effective Throats of Fillet Welds in Skewed T-Joints.....	205
Annex C (Normative)—Flatness of Girder Webs—Bridges.....	207
Annex D (Normative)—Terms and Definitions.....	213
Annex E (Normative)—Manufacturer’s Stud Base Qualification Requirements.....	221
Annex F (Normative)—Part A—Qualification and Calibration of the UT Unit with Other Approved Reference Blocks.....	225
Part B—UT Equipment Qualification Procedures.....	227
Annex G (Normative)—Guidelines on Alternative Methods for Determining Preheat.....	235
Annex H (Normative)—Welding Requirements for Conventional, Nonfracture Critical M 270M/M 270 (A 709/A 709M) HPS 485W [HPS 70W] Components with Reduced Preheat and Interpass Temperature.....	245
<u>Annex I (Normative)—ESW Consumable Requirements.....</u>	<u>247</u>
<u>Annex J (Normative)—Guidelines for the Acceptance of Alternative ESW Processes.....</u>	<u>249</u>
Annex <u>K</u> (Informative)—Weld Quality Requirements for Tension Joints.....	251
Annex <u>L</u> (Informative)—Description of Common Weld and Base Metal Discontinuities.....	253
Annex <u>M</u> (Informative)—Short Circuiting Transfer.....	263
Annex <u>N</u> (Informative)—Suggested Sample Welding Forms.....	267
Annex <u>O</u> (Informative)—Guidelines for Preparation of Technical Inquiries for the Joint AASHTO/AWS Subcommittee on Bridge Welding.....	281
Annex <u>P</u> (Informative)—Reference Documents.....	283
<u>Annex Q (Informative)—Guide for Use of Electroslag Welding—Narrow Gap (ESW-NG).....</u>	<u>285</u>
<i>Commentary on Bridge Welding Code</i> .....	297
Foreword.....	299
Index.....	441
List of AWS Documents on Structural Welding.....	455

## List of Tables

Table	Page No.
2.1	Minimum Fillet Weld Size ..... 11
2.2	Minimum Effective Weld Size for PJP Groove Welds ..... 11
3.1	Limits on Acceptability and Repair of Cut Edge Discontinuities of Material ..... 62
3.2	Camber Tolerance for Typical Girder ..... 62
3.3	Camber Tolerance for Girders without a Designed Concrete Haunch ..... 62
4.1	Matching Filler Metal Requirements for WPSs Qualified in Conformance with 5.12 ..... 78
4.2	Filler Metal Requirements for Exposed Bare Application of M 270M/M 270 (A 709/A 709M) Gr. 345W [50W] and Gr. HPS 345W [HPS 50W] Steels ..... 84
4.3	Minimum Preheat and Interpass Temperature, °C [°F] ..... 85
4.4	Minimum Holding Time ..... 85
4.5	Alternate Stress-Relief Heat Treatment ..... 85
4.6	Allowable Atmospheric Exposure of Low-Hydrogen SMAW Electrodes ..... 86
4.7	Required Voltage for ESW ..... 86
5.1	WPS Qualification Requirements for Consumables ..... 104
5.2	WPS Qualification or Prequalification Options ..... 104
5.3	PQR Essential Variable Changes for WPSs Qualified per 5.12.4 ..... 105
5.4	Additional PQR Essential Variable Changes Requiring WPS Requalification for EGW ..... 108
5.5	PQR Essential Variable Changes Requiring WPS Requalification for ESW ..... 109
5.6	Required Number of Test Specimens—WPS Qualification ..... 109
5.7	Welder Qualification—Type and Position Limitations ..... 109
5.8	Number and Type of Specimens and Range of Thickness Qualified—Welder and Welding Operator Qualification ..... 110
6.1	Hole-Type IQI Requirements ..... 153
6.1A	Wire IQI Requirements ..... 153
6.2	Testing Angle ..... 154
6.3	UT Acceptance-Rejection Criteria—Tensile Stress ..... 156
6.4	UT Acceptance-Rejection Criteria—Compressive Stress ..... 157
7.1	Mechanical Property Requirements for Studs ..... 176
7.2	Minimum Fillet Weld Size for Small Diameter Studs ..... 176
12.1	CVN Test Values of Weld Metal with Matching Strength ..... 198
12.2	Tack Weld Requirements ..... 198
12.3	M 270M/M 270 (A 709/A 709M) Gr. 250 [36], 345 [50], 345S [50S] Minimum Preheat and Interpass Temperatures, °C [°F] ..... 199
12.4	M 270M/M 270 (A 709/A 709M) Gr. 345W [50W], HPS 345W [HPS 50W], HPS 485W [HPS 70W] Minimum Preheat and Interpass Temperatures, °C [°F] ..... 199
12.5	M 270M/M 270 (A 709/A 709M) Gr. 690 [100], 690W [100W] Minimum and Maximum Preheat/Interpass Temperatures, °C [°F] ..... 199
B.1	Equivalent Fillet Weld Leg Size Factors for Skewed T-Joints, R = 0 ..... 206
G.1	Susceptibility Index Grouping as Function of Hydrogen Level “H” and Composition Parameter P <sub>cm</sub> ..... 238
G.2	Minimum Preheat and Interpass Temperatures for Three Levels of Restraint ..... 238
H.1	Minimum Preheat and Interpass Temperature for M 270M/M 270 (A 709/A 709M) HPS 485W [HPS 70W], °C [°F] ..... 246
H.2	Filler Metals for Use with the Reduced Preheat of Table H.1, Diffusible Hydrogen Levels 4 mL/100 g Maximum ..... 246

<b>Table</b>		<b>Page No.</b>
<u>I.1</u>	<u>Required Filler Metal Chemistry for ESW</u> .....	248
<u>I.2</u>	<u>Maximum Alloy Limits for ESW Consumable Guide</u> .....	248
<u>L.1</u>	<u>Common Types of Discontinuities</u> .....	257
<u>M.1</u>	<u>Typical Current Ranges for Short Circuiting Transfer Gas Metal Arc Welding of Steel (GMAW-S)</u> .....	264
<u>Q.1</u>	<u>Example ESW-NG Consumable Guide Configurations</u> .....	293
<u>Q.2</u>	<u>Example Operating Conditions for ESW-NG of ASTM A 709/A 709M Grades 250 [36], 345 [50], 345S [50S], and 345W [50W]</u> .....	293

## List of Figures

Figure		Page No.
2.1	Filler Plates Less Than 6 mm [1/4 in] Thick.....	12
2.2	Filler Plates 6 mm [1/4 in] or Thicker.....	12
2.3	Details for Fillet Welds.....	13
2.4	Details of Welded Joints for CJP Groove Welds.....	15
2.5	Details of Welded Joints for PJP Groove Welds.....	35
2.6	Fillet Welds on Opposite Sides of a Common Plane of Contact.....	47
2.7	Transition of Thickness at Butt Joints of Parts Having Unequal Thickness.....	48
2.8	Transition of Width at Butt Joints of Parts Having Unequal Width.....	49
3.1	Discontinuities in Cut Plate.....	63
3.2	Workmanship Tolerances in Assembly of Groove Welded Joints.....	63
3.3	Acceptable and Unacceptable Weld Profiles.....	64
4.1	Weld Bead in Which Depth and Width Exceed the Width of the Weld Face.....	87
5.1	WPS Qualification or Pretest—Test Plate A.....	111
5.2	WPS Verification—Test Plate B.....	112
5.3	Weld Soundness Test Plate for Details Not Conforming to Figure 2.4 or 2.5—Test Plate C.....	113
5.4	Positions of Fillet Welds.....	114
5.5	Positions of Groove Welds.....	115
5.6	Position of Test Plates for Groove Welds.....	116
5.7	Position of Test Plates for Fillet Welds.....	117
5.8	Fillet Weld Soundness Test (Macroetch) for WPS Qualification—Test Plate D.....	118
5.9	Standard Round All-Weld-Metal Tension Specimen.....	119
5.10	Reduced Section Tension Specimen.....	119
5.11	Side-Bend Specimen.....	120
5.12	Face- and Root-Bend Specimen.....	120
5.13	CVN Test Specimen—Type A.....	121
5.14	Guided Bend Test Jig.....	122
5.15	<u>Alternate</u> Wraparound Guided Bend Test Jig.....	123
5.16	<u>Alternate</u> Roller-Equipped Guided Bend Test Jig for Bottom Ejection of Test Specimen.....	124
5.17	Test Plate for Unlimited Thickness—Welder Qualification.....	125
5.18	Optional Test Plate for Unlimited Thickness—Horizontal Position—Welder Qualification.....	126
5.19	Test Plate for Limited Thickness—All Positions—Welder Qualification.....	127
5.20	Optional Test Plate for Limited Thickness—Horizontal Position—Welder Qualification.....	127
5.21	Fillet-Weld-Break and Macroetch Test Plate—Welder Qualification—Option 1.....	128
5.22	Fillet Weld Root-Bend Test Plate—Welder Qualification—Option 2.....	129
5.23	Plug Weld Macroetch Test Plate—Welder Qualification.....	130
5.24	Test Plate for Unlimited Thickness—Welding Operator Qualification.....	131
5.25	Butt Joint for Welding Operator Qualification—ESW and EGW.....	132
5.26	Fillet-Weld-Break and Macroetch Test Plate—Welding Operator Qualification—Option 1.....	133
5.27	Fillet Weld Root Bend Test Plate—Welding Operator Qualification—Option 2.....	134
5.28	Fillet-Weld-Break Specimen—Tack Welder Qualification.....	135
5.29	Method of Rupturing Specimen—Tack Welder Qualification.....	135
6.1A	Radiographic Identification and Hole-Type or Wire IQI Locations on Approximately Equal Thickness Joints 250 mm [10 in] and Greater in Length.....	158
6.1B	Radiographic Identification and Hole-Type or Wire IQI Locations on Approximately Equal Thickness Joints Less than 250 mm [10 in] in Length.....	158

Figure	Page No.
6.1C	Radiographic Identification and Hole-Type or Wire IQI Locations on Transition Joints 250 mm [10 in] and Greater in Length ..... 159
6.1D	Radiographic Identification and Hole-Type or Wire IQI Locations on Transition Joints Less than 250 mm [10 in] in Length..... 159
6.1E	Hole-Type IQI Design ..... 160
6.1F	Wire-Type IQI ..... 161
6.2	RT Edge Block Placement..... 162
6.3	Transducer Crystal ..... 163
6.4	Qualification Procedure of Search Unit Using IIW Reference Block..... 163
6.5A	International Institute of Welding (IIW) UT Reference Blocks ..... 164
6.5B	Other Approved UT Reference Blocks ..... 165
6.6	Transducer Positions (Typical)..... 167
6.7	Plan View of UT Scanning Patterns ..... 168
6.8	Weld Quality Requirements for Discontinuities Occurring in Tension Welds (Limitations of Porosity and Fusion Discontinuities) ..... 169
6.9	Weld Requirements for Discontinuities Occurring in Compression Welds (Limitations of Porosity or Fusion Type Discontinuities)..... 170
7.1	Dimension and Tolerances of Standard-Type Shear Connectors ..... 177
7.2	Typical Tension Test Fixture ..... 177
7.3	Torque Testing Arrangement and Table of Testing Torques ..... 178
E.1A	Bend Testing Device ..... 223
E.1B	Suggested Type of Device for Qualification Testing of Small Studs ..... 223
F.1	Example of the Use of Form F-1 UT Unit Certification ..... 228
F.2	Example of Form F-2 ..... 229
F.3	Example of the Use of Form F-2..... 230
F.4	Example of Form F-3 ..... 231
F.5	Example of the Use of Form F-3..... 232
F.6	Form F-4—Report of UT of Welds ..... 233
G.1	Zone Classification of Steels ..... 239
G.2	Critical Cooling Rate for 350 HV and 400 HV ..... 240
G.3	Charts to Determine Cooling Rates for Single-Pass Submerged Arc Fillet Welds ..... 241
G.4	Relation Between Fillet Weld Size and Energy Input ..... 244
<u>L.1</u>	Weld in Butt Joint..... 258
<u>L.2</u>	Weld in Corner Joint..... 259
<u>L.3</u>	Weld in T-Joint ..... 260
<u>L.4</u>	Weld in Lap Joint ..... 261
<u>L.5</u>	Single-Pass Fillet Weld in T-Joint ..... 261
<u>L.6</u>	Single-V-Groove Weld in Butt Joint ..... 262
<u>M.1</u>	Oscillograms and Sketches of Short Circuiting Arc Metal Transfer..... 265
<u>Q.1</u>	<u>ESW Single and Multiple Guide Configurations</u> ..... 294
<u>Q.2</u>	<u>ESW Welded and Single Piece Sumps</u> ..... 294
<u>Q.3</u>	<u>ESW Sump and Run-Off Tab Illustration</u> ..... 295
<u>Q.4</u>	<u>Allowable Operating Ranges for ESW-NG</u> ..... 296
<b>Commentary</b>	
C-2.1	Details of Alternative Groove Preparations for Corner Joints ..... 320
C-3.1	Examples of Unacceptable Reentrant Corners..... 343
C-3.2	Examples of Good Practice for Cutting Copers ..... 343
C-3.3	Permissible Offset in Abutting Members ..... 344
C-3.4	Correction of Misaligned Members ..... 344
C-3.5	Illustration of Camber Tolerances for Steel Beams..... 345
C-3.6	Measurement of Flange Warpage and Tilt ..... 346
C-3.7	Tolerances Bearing Points ..... 347

## List of Forms

<b>Form</b>		<b>Page No.</b>
<u>N-1</u>	Certificate of Conformance to Requirements for Welding Electrodes.....	268
<u>N-2</u>	Sample Welding Procedure Specification .....	269
<u>N-3</u>	Procedure Qualification Record (PQR) for Qualification, Pretest, and Verification Results.....	270
<u>N-4</u>	Procedure Qualification Record (PQR) Worksheet.....	271
<u>N-5</u>	Welder and Welding Operator Qualification Record .....	272
<u>N-6</u>	Report of Radiographic Examination of Welds .....	273
<u>N-7</u>	Report of Magnetic Particle Examination of Welds.....	274
<u>N-8</u>	<u>ESW-NG Procedure Qualification Record</u> .....	275
<u>N-9</u>	<u>ESW-NG Welding Procedure Specification</u> .....	279

# Bridge Welding Code

## 1. General Provisions

### 1.1 Application

**1.1.1** This code covers welding fabrication requirements applicable to welded highway bridges. The code is applicable to both shop and field fabrication of steel bridges and bridge components. The code is to be used in conjunction with the *AASHTO Standard Specification for Highway Bridges* or the *AASHTO LRFD Bridge Design Specifications*.

The code is not intended to be used for the following:

- (1) Steels with a minimum specified yield strength greater than 690 MPa [100 ksi]
- (2) Pressure vessels or pressure piping
- (3) Base metals other than carbon or low alloy steels
- (4) Structures composed of structural tubing

Fabrication of structures or components not specifically addressed by this code shall be performed in conformance with the special provisions of the contract or in conformance with the written directives of the Engineer who may choose to reference an alternate applicable welding standard.

**1.1.2** The fundamental premise of the code is to provide general stipulations applicable to any routine bridge situation. Acceptance criteria for production welds different from those described in the code may be used for a particular application, provided they are suitably documented by the proposer and approved by the Engineer.

Such alternate acceptance criteria may be based upon evaluation of suitability for service using past experience, experimental evidence, or engineering analysis considering material type, service load effects, and environmental factors.

**1.1.3** The term *Engineer* as used in this code shall mean the State Bridge Engineer, or the Bridge Engineer's designated representative. The Engineer acts on behalf of the State or Owner and unless otherwise specified, shall

be the Owner's official representative. All references to acceptance or approval shall mean acceptance or approval by the Engineer.

**1.1.4** The term *Contractor* as used in this code indicates the party responsible for performing the work as required by the contract documents. The term Contractor is used collectively to mean contractor, manufacturer, fabricator, erector, or other party performing the work.

### 1.2 Base Metal

**1.2.1 Specified Base Metal.** The contract documents shall designate the specification and classification of base metals to be used.

**1.2.2 Approved Base Metals.** Unless otherwise specified, base metals to be welded under this code shall meet the requirements of the latest edition of AASHTO M 270M/M 270 (ASTM A 709/A 709M) for the grade of steel shown on the plans or described in the specifications. All Grade 345 (50) steel that is to be welded shall be Type 1, 2, or 3. Other steels may be approved by the Engineer. Thickness limitations shall not apply to bearing components.

M 270M/M 270 steels of a designated grade are essentially the same as ASTM A 709/A 709M steels of the same grade. The provisions of this code are not intended for use with steels having a minimum specified yield strength over 690 MPa [100 ksi].

**1.2.3 Thickness Limitations.** The provisions of this code do not apply to welding base metals less than 3 mm [1/8 in] thick. Where base metals thinner than 3 mm [1/8 in] are to be welded, the requirements of AWS D1.3/D1.3M, *Structural Welding Code—Sheet Steel*, should apply. When used in conjunction with AWS D1.3/D1.3M, the applicable provisions of this code shall be observed.