

ANSI/AWS A5.25/A5.25M-97 (R2009)
An American National Standard

Specification for Carbon and Low-Alloy Steel Electrodes and Fluxes for Electroslag Welding



American Welding Society

Key Words—Filler metal specifications, low-alloy steel electrodes, carbon steel electrodes, arc welding electrodes, metal cored electrodes, electroslag welding

ANSI/AWS A5.25/A5.25M-97 (R2009)
An American National Standard

**Approved by the
American National Standards Institute
December 8, 1997**

**Specification for
Carbon and Low-Alloy Steel
Electrodes and Fluxes for
Electroslag Welding**

Supersedes ANSI/AWS A5.25-91

Prepared by the
American Welding Society (AWS) A5 Committee on Filler Metals

Under the Direction of the
AWS Technical Activities Committee

Approved by the
AWS Board of Directors

Abstract

Classification requirements are specified for fluxes and solid and composite metal cored electrodes for electroslag welding. The requirements for electrodes include chemical composition of the electrode for solid electrodes and of weld metal for metal cored electrodes. Requirements for fluxes include the mechanical properties and soundness of weld metal taken from a groove weld made with a particular electrode using a prescribed welding procedure. Standard electrode sizes, marking, and packaging requirements are included.

This specification makes use of both U.S. Customary Units and the International System of Units (SI). Since these are not equivalent, each system must be used independently of the other.



American Welding Society

550 N.W. LeJeune Road, Miami, FL 33126

Foreword

This foreword is not part of ANSI/AWS A5.25/A5.25M-97 (R2009), *Specification for Carbon and Low-Alloy Steel Electrodes and Fluxes for Electroslag Welding*, but is included for informational purposes only.

This document is the first of the A5.25 specifications to use both U.S. Customary Units and the International System of Units (SI). The measurements are not exact equivalents; therefore, each system must be used independently of the other, without combining in any way. In selecting rational metric units, the ANSI/AWS A1.1, *Metric Practice Guide for the Welding Industry*, and ISO 544, *Welding consumables — Technical delivery conditions for welding filler materials — Type of product, dimensions, tolerances and markings*, are used as guides. Tables and figures make use of both U.S. Customary and SI Units, which with the application of the specified tolerances provide for interchangeability of products in both U.S. Customary and SI Units.

Added Annex B (Informative), Guidelines for Preparation of Technical Inquiries.

The current document is the second revision of this specification, as shown below:

Document Development

AWS A5.25-78	<i>Specification for Consumables Used for Electroslag Welding of Carbon and High Strength Low Alloy Steels</i>
ANSI/AWS A5.25-91	<i>Specification for Carbon and Low Alloy Steel Electrodes and Fluxes for Electroslag Welding</i>
ANSI/AWS A5.25-97R	<i>Specification for Carbon and Low-Alloy Steel Electrodes and Fluxes for Electroslag Welding</i>

Comments and suggestions for the improvement of this standard are welcome. They should be sent to the Secretary, AWS A5 Committee on Filler Metals, American Welding Society, 550 N.W. LeJeune Road, Miami, FL 33126.

Table of Contents

	Page No.
<i>Personnel (Reaffirmation)</i>	v
<i>Personnel (Original)</i>	vii
<i>Foreword</i>	ix
<i>List of Tables</i>	xii
<i>List of Figures</i>	xii
1. Scope	1
2. Classification	1
3. Acceptance	1
4. Certification	1
5. Units of Measure and Rounding-Off Procedure	1
6. Summary of Tests	4
7. Retest	4
8. Weld Test Assemblies	5
9. Chemical Analysis	6
10. Radiographic Test	8
11. Tension Test	8
12. Impact Test	8
13. Method of Manufacture	9
14. Electrode Requirements	9
15. Flux Requirements	14
Annex A (Informative)—Guide to AWS Specification for Carbon and Low-Alloy Steel Electrodes and Fluxes for Electroslag Welding	17
Annex B (Informative)—Guidelines for the Preparation of Technical Inquiries	25
AWS Filler Metal Specifications by Material and Welding Process	27
AWS Filler Metal Specifications and Related Documents	29

List of Tables

Table		Page No.
1	Chemical Composition Requirements for Solid Electrodes	2
2	Chemical Composition Requirements for Weld Metal from Composite Metal Cored Electrodes.....	3
3	A5.25 Tension Test Requirements (As Welded).....	3
3M	A5.25M Tension Test Requirements (As Welded)	3
4	A5.25 Impact Test Requirements (As Welded)	4
4M	A5.25M Impact Test Requirements (As Welded).....	4
5	Required Tests.....	5
6	Base Metals for Test Assemblies	8
7	Standard Sizes.....	11
8	Standard Package Dimensions and Weights	12
A.1	Comparison of A5.25/A5.25M Classifications and Classifications in Other AWS Specifications and Proposed ISO Designations	18

List of Figures

Figure		Page No.
1	Weld Ingot.....	6
2	Groove Weld Test Assembly for Mechanical Properties and Soundness	7
3	Tension Test Specimen	9
4	Radiographic Acceptance Standards	10
5	Charpy V-Notch Impact Test Specimen.....	11
6A	Dimensions of 12 and 14 in. [300 and 350 mm] Standard Spools	13
6B	Dimensions of 22, 24, and 30 in. [560, 610, and 760 mm] Standard Spools (Reels).....	14
A.1	Classification System.....	18

Specification for Carbon and Low-Alloy Steel Electrodes and Fluxes for Electroslag Welding

1. Scope

This specification prescribes requirements for the classification of electrodes (both solid and composite metal cored) and fluxes for electroslag welding of carbon and low-alloy steels.

Part A General Requirements

2. Classification

2.1 The solid electrodes covered by this specification are classified according to the chemical composition of the electrode, as specified in Table 1.

2.2 The composite metal cored electrodes covered by this specification are classified according to the chemical composition of the weld metal produced by use with a specific flux of a particular manufacturer and trade designation as specified in Table 2.

2.3 Fluxes covered by this specification are classified according to the mechanical properties of the weld metal as specified in Tables 3 and 4, when using an electrode of a particular classification.

2.4 Electrodes classified under one classification shall not be classified under any other classification in this specification. Fluxes may be classified under any number of classifications using a different electrode for each. Fluxes classified as FESX2-XXX may also be classified as FESX0-XXX and FESXZ-XXX, as specifically permitted by Note (a) to Table 4.

2.5 The electrodes and fluxes classified under this specification are intended for electroslag welding, but that is not to prohibit their use with any other process for which they are found suitable.

3. Acceptance

Acceptance¹ of the electrodes and fluxes shall be in accordance with the provisions of ANSI/AWS A5.01, *Filler Metal Procurement Guidelines*.²

4. Certification

By affixing the AWS Specification and Classification designations to the packaging, or the classification to the product, the manufacturer certifies that the product meets the requirements of this specification.³

5. Units of Measure and Rounding-Off Procedure

5.1 This specification makes use of both U.S. Customary Units and the International System of Units (SI). The measurements are not exact equivalents; therefore, each

¹ See Section A3 (in Annex A), Acceptance, for further information concerning acceptance, testing of the material shipped, and the ANSI/AWS A5.01, *Filler Metal Procurement Guidelines*.

² AWS standards are published by the American Welding Society, 550 N.W. LeJeune Road, Miami, FL 33126.

³ See Section A4 (in Annex A), Certification, for further information concerning certification and the testing called for to meet this requirement.