

**AWS D1.1/D1.1M:2015**  
**An American National Standard**

# **Structural Welding Code— Steel**



*second printing, March 2016*

**AWS D1.1/D1.1M:2015**  
**An American National Standard**

**Approved by the**  
**American National Standards Institute**  
**July 28, 2015**

**Structural Welding Code—**  
**Steel**

**23rd Edition**

**Supersedes AWS D1.1/D1.1M:2010**

Prepared by the  
American Welding Society (AWS) D1 Committee on Structural Welding

Under the Direction of the  
AWS Technical Activities Committee

Approved by the  
AWS Board of Directors

**Abstract**

This code covers the welding requirements for any type of welded structure made from the commonly used carbon and low-alloy constructional steels. Clauses 1 through 9 constitute a body of rules for the regulation of welding in steel construction. There are nine normative and eleven informative annexes in this code. A Commentary of the code is included with the document.



ISBN: 978-0-87171-864-8  
© 2015 by American Welding Society  
All rights reserved  
Printed in the United States of America  
Errata: Second Printing, March 2016

**Photocopy Rights.** No portion of this standard may be reproduced, stored in a retrieval system, or transmitted in any form, including mechanical, photocopying, recording, or otherwise, without the prior written permission of the copyright owner.

Authorization to photocopy items for internal, personal, or educational classroom use only or the internal, personal, or educational classroom use only of specific clients is granted by the American Welding Society provided that the appropriate fee is paid to the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, tel: (978) 750-8400; Internet: <[www.copyright.com](http://www.copyright.com)>.

## Statement on the Use of American Welding Society Standards

All standards (codes, specifications, recommended practices, methods, classifications, and guides) of the American Welding Society (AWS) are voluntary consensus standards that have been developed in accordance with the rules of the American National Standards Institute (ANSI). When AWS American National Standards are either incorporated in, or made part of, documents that are included in federal or state laws and regulations, or the regulations of other governmental bodies, their provisions carry the full legal authority of the statute. In such cases, any changes in those AWS standards must be approved by the governmental body having statutory jurisdiction before they can become a part of those laws and regulations. In all cases, these standards carry the full legal authority of the contract or other document that invokes the AWS standards. Where this contractual relationship exists, changes in or deviations from requirements of an AWS standard must be by agreement between the contracting parties.

AWS American National Standards are developed through a consensus standards development process that brings together volunteers representing varied viewpoints and interests to achieve consensus. While AWS administers the process and establishes rules to promote fairness in the development of consensus, it does not independently test, evaluate, or verify the accuracy of any information or the soundness of any judgments contained in its standards.

AWS disclaims liability for any injury to persons or to property, or other damages of any nature whatsoever, whether special, indirect, consequential, or compensatory, directly or indirectly resulting from the publication, use of, or reliance on this standard. AWS also makes no guarantee or warranty as to the accuracy or completeness of any information published herein.

In issuing and making this standard available, AWS is neither undertaking to render professional or other services for or on behalf of any person or entity, nor is AWS undertaking to perform any duty owed by any person or entity to someone else. Anyone using these documents should rely on his or her own independent judgment or, as appropriate, seek the advice of a competent professional in determining the exercise of reasonable care in any given circumstances. It is assumed that the use of this standard and its provisions is entrusted to appropriately qualified and competent personnel.

This standard may be superseded by the issuance of new editions. This standard may also be corrected through publication of amendments or errata, or supplemented by publication of addenda. Information on the latest editions of AWS standards including amendments, errata, and addenda is posted on the AWS web page ([www.aws.org](http://www.aws.org)). Users should ensure that they have the latest edition, amendments, errata, and addenda.

Publication of this standard does not authorize infringement of any patent or trade name. Users of this standard accept any and all liabilities for infringement of any patent or trade name items. AWS disclaims liability for the infringement of any patent or product trade name resulting from the use of this standard.

AWS does not monitor, police, or enforce compliance with this standard, nor does it have the power to do so.

On occasion, text, tables, or figures are printed incorrectly, constituting errata. Such errata, when discovered, are posted on the AWS Webpage ([www.aws.org](http://www.aws.org)).

Official interpretations of any of the technical requirements of this standard may only be obtained by sending a request, in writing, to the appropriate technical committee. Such requests should be addressed to the American Welding Society, Attention: Managing Director, Technical Services Division, 8669 NW 36 St, # 130, Miami, FL 33166 (see Annex N). With regard to technical inquiries made concerning AWS standards, oral opinions on AWS standards may be rendered. These opinions are offered solely as a convenience to users of this standard, and they do not constitute professional advice. Such opinions represent only the personal opinions of the particular individuals giving them. These individuals do not speak on behalf of AWS, nor do these oral opinions constitute official or unofficial opinions or interpretations of AWS. In addition, oral opinions are informal and should not be used as a substitute for an official interpretation.

This standard is subject to revision at any time by the AWS D1 Committee on Structural Welding. It must be reviewed every five years, and if not revised, it must be either reaffirmed or withdrawn. Comments (recommendations, additions, or deletions) and any pertinent data that may be of use in improving this standard are required and should be addressed to AWS Headquarters. Such comments will receive careful consideration by the AWS D1 Committee on Structural Welding and the author of the comments will be informed of the Committee's response to the comments. Guests are invited to attend all meetings of the AWS D1 Committee on Structural Welding to express their comments verbally. Procedures for appeal of an adverse decision concerning all such comments are provided in the Rules of Operation of the Technical Activities Committee. A copy of these Rules can be obtained from the American Welding Society, 8669 NW 36 St, # 130, Miami, FL 33166.

This page is intentionally blank.

## Foreword

This foreword is not part of AWS D1.1/D1.1M:2015, *Structural Welding Code—Steel*, but is included for informational purposes only.

The first edition of the *Code for Fusion Welding and Gas Cutting in Building Construction* was published by the American Welding Society in 1928 and called Code 1 Part A. It was revised in 1930 and 1937 under the same title. It was revised again in 1941 and given the designation D1.0. D1.0 was revised again in 1946, 1963, 1966, and 1969. The 1963 edition published an amended version in 1965, and the 1966 edition published an amended version in 1967. The code was combined with D2.0, *Specifications for Welding Highway and Railway Bridges*, in 1972, given the designation D1.1, and retitled *AWS Structural Welding Code*. D1.1 was revised again in 1975, 1979, 1980, 1981, 1982, 1983, 1984, 1985, 1986, 1988, 1990, 1992, 1994, 1996, 1998, 2000, 2002, 2004, 2006, 2008 and 2010. A second printing of D1.1:2010 was published in 2011. From 1972 to 1988, the D1.1 code covered the welding of both buildings and bridges. In 1988, AWS published its first edition of AASHTO/AWS D1.5, *Bridge Welding Code*; coincident with this, the D1.1 code changed references of buildings and bridges to statically loaded and dynamically loaded structures, respectively, in order to make the document applicable to a broader range of structural applications. After the publishing of the 2010 edition, it was decided that the *AWS Structural Welding Code—Steel* would be published on a five year revision cycle instead of a two year revision cycle. This was done in order to sync the publication cycle of AWS Structural Welding Code-Steel with the publication cycles of the AISC Steel Building Specification and the International Building Code. This 2015 edition is the 23rd edition of D1.1.

Underlined text in the clauses, subclauses, tables, figures, or forms indicates a change from the 2010 edition. A vertical line in the margin of a table or figure also indicates a change from the 2010 edition.

The following is a summary of the most significant technical changes contained in D1.1/D1.1M:2015:

The 2015 edition of the code has been reorganized. The tubular provisions, tables, and figures previously located throughout the code are now within Clause 9 entitled “Tubular Structures.” The reorganization required numerous reference changes and renumbering of the subclauses, tables, and figures. Many of the tables in Clause 4 contained provisions for Plate as well as Pipe or Tubing. The tables have been divided to only include Plate if contained in Clause 4 and Pipe or Tubing if contained in Clause 9. This separation of the information contained in the tables also resulted in many changes to the footnotes delineated in the tables.

Clauses 1, 7, and 8 have only been slightly impacted by the reorganization. However, Clauses 2, 3, 4, 5, and 6 have been greatly impacted with the reorganization.

## Summary of Changes

Clause/Table/ Figure/Annex	Modification
Clause 2	The most significant change to Clause 2 from the 2010 edition is that Part D entitled “Specific Requirements for Design of Tubular Connections (Statically or Cyclically Loaded)” has been relocated to Clause 9.
2.4.2.7	Additional language was added regarding the calculation of effective throat of a combination PJP flare bevel groove weld and fillet weld.

## Summary of Changes (Continued)

Clause/Table/ Figure/Annex	Modification
2.9.3.5	Added provisions for wrapping welds on opposite sides of a common plane to permit seal welding.
Table 2.5	Fatigue curve cases and figures revised to agree with AISC 360.
3.7.4	Shielding gas provisions revised to permit the use of electrodes classified to AWS A5.36.
3.13.2.1	New subclause that provides conditions under which backing other than steel may be used in prequalified WPSs.
Table 3.1	Reformatted the table moving filler metals in corresponding groups in Table 3.2. Updated the list of base metals permitted in prequalified WPSs and corrected the group of some base metal grades.
Table 3.2	New table for filler metal requirements that contains the information previously contained in Table 3.1 with the addition of a classification for A5.36 for carbon and low-alloy steel electrodes for FCAW and metal cored electrodes for GMAW processes.
Table 3.3	(Previously Table 3.2) Revised the base metals to correspond with those in Table 3.1
Table 3.4	(Previously Table 3.3) Addition of AWS A5.36.
Table 3.7	(Previously Table 3.6) Clarification of a SAW parameter variable.
Notes for Figures 3.2 and 3.3	Addition of note "O" permitting various orientations of connected elements in CJP Groove, T-, and Corner joints.
Figure 3.5	New figure for prequalified fillet weld joint details.
Figure 3.6	New figure for prequalified CJP groove, T-, and corner joints.
4.12.3	Restructured for easier reading.
4.21	(Previously 4.25, 4.26, 4.30) Reorganized "Extent of Qualification."
4.27.7	(Previously 4.36.7) Clarified CVN Test requirements when sub-sized specimens are tested.
Tables 4.1, 4.2, 4.3, 4.4, 4.10, and 4.11	The information found in the tables that referenced pipes and tubing are now contained in the tables found in Clause 9.
Tables 4.5, 4.6, and 4.9	Added provisions for electrodes classified to AWS A5.36.
5.3.2.5	Additional language and clarification regarding baking requirements when welding with low-hydrogen electrodes for ASTM A514 and A517 steels.
5.3.4	Reorganized the list of AWS Filler metal specifications for GMAW and FCAW as well as added AWS A5.36.
5.6	Clarified language regarding preheat and interpass temperatures.
5.7	Moved language regarding oxygen gouging to 5.14.6 and 5.25.
5.8.1	Revised for clarification.
5.8.3	Revised to delete ASTM A709 100 (690) and 100W (690W) and to include ASTM A709 Grade HPS 100W [HPS 690W] per ASTM.
5.9	(Previous 5.9 entitled "Backing, Backing Gas, or Inserts" was deleted) (Previously 5.10) Restructured for clarification.

## Summary of Changes (Continued)

Clause/Table/ Figure/Annex	Modification
5.9.1.3	(Previously 5.10.3) “Backing Thickness” was revised to make a general requirement that steel backing be of sufficient thickness to prevent melt-through. The explicit thicknesses previously required were moved to commentary as recommendations.
5.14.1–5.14.4	(Previously 5.15) Substrate cleanliness requirements were significantly revised.
5.14.6	(Previously 5.15.2) Revised to clarify when oxygen gouging is permitted.
5.17.2	(Previously 5.18.2) Revised for clarity regarding when locations of the depth of the web from tension flanges of beams or girders are considered outside the tension zone.
5.19	(Previously 5.20) Revised provisions regarding the location and sequence of member and element splices.
5.25	(Previously 5.26) Revised to limit oxygen gouging to as-rolled steels.
Table 5.8	(Previously Table 5.9) Note c revised to clarify when welds are exempt from reinforcement and convexity limitations.
Table 5.9	(Previously Table 5.10) Minimum allowable convexity was eliminated from Schedule D for outside corner joints. Table footnote b was rewritten regarding restriction on convexity was replaced with a note regarding concavity and now applies to Schedules B and D.
6.4.2	Revised to clarify as to what a welder, welding operator, or tack welder must demonstrate, when their work appears to be below the requirements of the code.
6.4.3	Revised to include tack welder.
6.10	Revised to replace “applicable requirements” with “acceptance criteria.”
6.11	Revised to remove ASTM A709 Grades 100 and 100W and include ASTM A709 Grade HPS 100W [HPS 690W].
6.21.1	(Previously 6.22.1) Reference added to new Table 6.8 showing qualification and calibration requirements.
6.24.2	Revised to clarify when calibration for sensitivity and horizontal sweep shall be made.
Table 6.1	Revised to remove ASTM A709 Grades 100 and 100W and include ASTM A709 Grade HPS 100W [HPS 690W].
Tables 6.4 and 6.5	Revised to remove the tubular provisions, now contained in Tables found in Clause 9.
Table 6.8	New table added to clarify UT equipment qualification and calibration requirements.
Clause 9	The tubular provisions extracted from the 2010 code were virtually unchanged when relocated to Clause 9.
9.6.1.6	(Previously 2.25.1.6) The definition of $1_2$ was revised to remove the word “chord.”
9.18	(Previously 4.21) Revised to clarify what type of welds do not require tubular qualification.
Table 9.1	New table developed from the tubular provisions contained in Table 2.5 of the previous edition. The content pertinent to nontubular members remained in Table 2.5
Tables 9.9, 9.10, 9.11, 9.12, 9.13, and 9.14	New tables developed from the tubular provisions in the previous edition of Clause 4. The content pertinent to nontubular members remains in Clause 4.



### Summary of Changes (Continued)

Clause/Table/ Figure/Annex	Modification
Tables 9.16, 9.17, 9.18, and 9.19	New tables developed from the tubular provisions in the previous edition of Clause 6. The content pertinent to nontubular members remains in Clause 6.
Table 9.5	(Previously Table 2.9) Addition of footnote “a” for clarification.
Figure 9.6	(Previously Figure 2.18) Dimension labels in the figure were revised for clarification.
Figure 9.29	(Previously Figure 6.4) Footnotes revised to remove the exception for T-, Y-, and K-connections.
Figure 9.30	(Previously Figure 6.5) Note to disregard discontinuities below the scanning level was deleted from the figure and the placement of the Accumulative Discontinuities arrow was revised for clarification.
Annex A	Figures added to clarify effective throat for various joint types and combinations.
Annex I	(Previously Annex J) Definitions for the symbols $l_2$ , $r_m$ , $t_w$ were revised and a new symbol $r_w$ and its definition were added corresponding to changes in Figure 9.6.
Annex J	(Previously Annex K) Terms and definitions are now considered normative, meaning that they include mandatory elements for use with this code. There was also the addition of new terms “fin” and “nondestructive testing (NDT).”
Annex M	(Previously Annex N) Sample welding forms were extensively revised for clarification.
Annex R	Annex R entitled “Safe Practices” was eliminated in this edition. Readers are referred in Clause 1 to other publications for safety provision.
Annex U	New Annex regarding AWS A5.36 filler metal classifications and properties.

### Summary of Clauses in D1.1:2010 Relocated to Clause 9 in D1.1:2015

D1.1:2010 Clause	D1.1:2015 Clause and Title
2.20	9.1 General
2.21	9.2 Allowable Stresses
2.20.1	9.2.1 Eccentricity
2.21.1	9.2.2 Base Metal Stresses
2.21.2	9.2.3 Tubular Section Limitations
2.21.3	9.2.4 Weld Stresses
2.21.4	9.2.5 Fiber Stresses
2.21.5	9.2.6 Load and Resistance Factor Design
2.21.6	9.2.7 Fatigue of Circular Tube Connections
2.21.6.1	9.2.7.1 Stress Range and Member Type
2.21.6.2	9.2.7.2 Fatigue Stress Categories
2.21.6.3	9.2.7.3 Basic Allowable Stress Limitation

**Summary of Clauses in D1.1:2010 Relocated to Clause 9 in D1.1:2015 (Continued)**

<b>D1.1:2010 Clause</b>	<b>D1.1:2015 Clause and Title</b>
2.21.6.4	9.2.7.4 Cumulative Damage
2.21.6.5	9.2.7.5 Critical Members
2.21.6.6	9.2.7.6 Fatigue Behavior Improvement
2.21.6.7	9.2.7.7 Size and Profile Effects
2.22	9.3 Identification
2.23	9.4 Symbols
2.24	9.5 Weld Design
2.24.1	9.5.1 Fillet Welds
2.24.1.1	9.5.1.1 Effective Area
2.24.1.2	9.5.1.2 Beta Limitation for Prequalified Details
2.24.1.3	9.5.1.3 Lap Joints
2.24.2	9.5.2 Groove Welds
2.24.2.1	9.5.2.1 Prequalified PJP Groove Weld Details
2.24.2.2	9.5.2.2 Prequalified CJP Groove Weld Details Welded from One Side without Backing in T-, Y-, and K-Connections
2.24.3	9.5.3 Stresses in Welds
2.24.4	9.5.4 Circular Connections Lengths
2.24.5	9.5.5 Box Connection Lengths
2.24.5.1	9.5.5.1 K- and N-Connections
2.24.5.2	9.5.5.2 T-, Y- and X-Connections
2.25	9.6 Limitations of the Strength of Welded Connections
2.25.1	9.6.1 Circular T-, Y-, and K-Connections
2.25.1.1	9.6.1.1 Local Failure
2.25.1.2	9.6.1.2 General Collapse
2.25.1.3	9.6.1.3 Uneven Distribution of Load (Weld Sizing)
2.25.1.4	9.6.1.4 Transitions
2.25.1.5	9.6.1.5 Other Configurations and Loads
2.25.1.6	9.6.1.6 Overlapping Connections
2.25.2	9.6.2 Box T-, Y-, and K-Connections
2.25.2.1	9.6.2.1 Local Failure
2.25.2.2	9.6.2.2 General Collapse
2.25.2.3	9.6.2.3 Uneven Distribution of Load (Effective Width)
2.25.2.4	9.6.2.4 Overlapping Connections

**Summary of Clauses in D1.1:2010 Relocated to Clause 9 in D1.1:2015 (Continued)**

<b>D1.1:2010 Clause</b>	<b>D1.1:2015 Clause and Title</b>
2.25.2.5	9.6.2.5 Bending
2.25.2.6	9.6.2.6 Other Configurations
2.26	9.7 Thickness Transition
2.27	9.8 Material Limitations
2.27.1	9.8.1 Limitations
2.27.1.1	9.8.1.1 Yield Strength
2.27.1.2	9.8.1.2 Reduced Effective Yield
2.27.1.3	9.8.1.3 Box T-, Y-, and K-Connections
2.27.1.4	9.8.1.4 ASTM A500 Precaution
2.27.2	9.8.2 Tubular Base Metal Notch Toughness
2.27.2.1	9.8.2.1 CVN Test Requirements
2.27.2.2	9.8.2.2 LAST Requirements
2.27.2.3	9.8.2.3 Alternative Notch Toughness
3.9	9.9 Fillet Weld Requirements
3.9.2	9.9.1 Details
3.12	9.10 PJP Requirements
3.12.4	9.10.1 Details
3.12.4.1	9.10.1.1 Matched Box Connections
3.13	9.11 CJP Groove Weld Requirements
3.13.4	9.11.1 Butt Joints
3.13.5	9.11.2 Tubular T-, Y-, and K-Connections
3.13.5.1	9.11.2.1 Joint Details
4.3	9.12 Common Requirements for WPS and Welding Personnel Performance Qualification
4.3.4	9.12.1 Positions of Welds
4.4	9.13 Production Welding Positions Qualified
4.5, 4.9, 4.9.1.1(6)(b), 4.9.2.1	9.14 Type of Qualification Tests, Methods of Testing and Acceptance Criteria for WPS Qualification
4.13	9.15 CJP Groove Welds for Tubular Connections
4.13.1	9.15.1 CJP Butt Joints with Backing or Backgouging
4.13.2	9.15.2 CJP Butt Joints without Backing Welded from One Side Only
4.13.3	9.15.3 T-,Y-, or K-Connections with Backing or Backgouging
4.13.4	9.15.4 T-,Y-, or K-Connections without Backing Welded from One Side Only
4.13.4.1	9.15.4.1 WPSs without Prequalified Status

**Summary of Clauses in D1.1:2010 Relocated to Clause 9 in D1.1:2015 (Continued)**

<b>D1.1:2010 Clause</b>	<b>D1.1:2015 Clause and Title</b>
4.13.4.2	9.15.4.2 CJP Groove Welds in a T-,Y-, or K-Connection with WPS with Dihedral Angles Less than 30°
4.13.4.3	9.15.4.3 CJP Groove Welds in a T-,Y-, or K-Connection WPS Using GMAW-S
4.13.4.4	9.15.4.4 Welding Requiring CVN Toughness
4.14	9.16 PJP and Fillet Welds Tubular T-, Y-, or K-Connections and Butt Joints
4.19.1	9.17 Production Welding Positions, Thicknesses and Diameters Qualified
4.19.1.1, 4.19.2.1	9.17.1 Welders and Welding Operators
4.19.2.2, 4.20.2.1	9.17.2 Tack Welders
4.21	9.18 Weld Types for Welder and Welding Operator Performance Qualification
4.27	9.19 CJP Groove Welds for Tubular Connections
4.27.1	9.19.1 Other Joint Details or WPSs
4.28	9.20 PJP Groove Welds for Tubular Connections
4.29	9.21 Fillet Welds for Tubular Connections
4.31	9.22 Methods of Testing and Acceptance Criteria for Welder and Welding Operator Qualification
4.31.2.2	9.22.1 Macroetch Test for T-, Y-, and K-Connections
4.31.2.3(3)	9.22.1.1 Macroetch Test Acceptance Criteria
4.31.3.1	9.22.2 RT Test Procedure and Technique
5.10	9.23 Backing
5.10.2	9.23.1 Full-Length Backing
5.22	9.24 Tolerance of Joint Dimensions
5.22.3.1	9.24.1 Girth Weld Alignment (Tubular)
5.22.4	9.24.2 Groove Dimensions
5.22.4.2	9.24.2.1 Tubular Cross-Sectional Variations
6.9	9.25 Visual Inspection
6.11	9.26 NDT
6.7	9.26.1 Scope
6.11.1	9.26.2 Tubular Connection Requirements
6.13	9.27 UT
6.13.3	9.27.1 Acceptance Criteria for Tubular Connections
6.13.3.1	9.27.1.1 Class R (Applicable When UT is Used as an Alternate to RT)
6.13.3.2	9.27.1.2 Class X (Experience-Based, Fitness-for Purpose Criteria Applicable to T-,Y- and K-Connections in Structures with Notch-Toughness Weldments)
6.17	9.28 RT Procedures

**Summary of Clauses in D1.1:2010 Relocated to Clause 9 in D1.1:2015 (Continued)**

<b>D1.1:2010 Clause</b>	<b>D1.1:2015 Clause and Title</b>
6.17.1	9.28.1 Procedure
6.17.7	9.28.2 IQI Selection and Placement
6.18	9.29 Supplementary RT Requirements for Tubular Connections
6.18.1	9.29.1 Circumferential Groove Welds in Butt Joints
6.18.1.1	9.29.1.1 Single-Wall Exposure/Single-Wall View
6.18.1.2	9.29.1.2 Double-Wall Exposure/Single-Wall View
6.18.1.3	9.29.1.3 Double-Wall Exposure/Double-Wall View
6.27	9.30 UT of Tubular T-, Y-, and K-Connections
6.27.1	9.30.1 Procedure.
6.27.2	9.30.2 Personnel
6.27.3	9.30.3 Calibration
6.27.3.1	9.30.3.1 Range
6.27.3.2	9.30.3.2 Sensitivity Calibration
6.27.4	9.30.4 Base Metal Examination
6.27.5	9.30.5 Weld Scanning
6.27.6	9.30.6 Optimum Angle
6.27.7	9.30.7 Discontinuity Evaluation
6.27.8	9.30.8 Reports
6.27.8.1	9.30.8.1 Forms
6.27.8.2	9.30.8.2 Reported Discontinuities
6.27.8.3	9.30.8.3 Incomplete Inspection
6.27.8.4	9.30.8.4 Reference Marks

**Summary of Tables in D1.1:2010 Relocated to Clause 9 in D1.1:2015**

<b>D1.1:2010 Table</b>	<b>D1.1:2015 Table and Title</b>
2.5	9.1 Fatigue Stress Design Parameters
2.6	9.2 Allowable Stresses in Tubular Connection Welds
2.7	9.3 Stress Categories for Type and Location of Material for Circular Sections
2.8	9.4 Fatigue Category Limitations on Weld Size or Thickness and Weld Profile (Tubular Connections)
2.9	9.5 Z Loss Dimensions for Calculating Prequalified PJP T-, Y-, and K-Tubular Connection Minimum Weld Sizes

**Summary of Tables in D1.1:2010 Relocated to Clause 9 in D1.1:2015 (Continued)**

<b>D1.1:2010 Table</b>	<b>D1.1:2015 Table and Title</b>
2.10	9.6 Terms for Strength of Connections (Circular Sections)
3.5	9.7 Joint Detail Applications for Prequalified CJP T-, Y-, and K-Tubular Connections
3.6	9.8 Prequalified Joint Dimensions and Groove Angles for CJP Groove Welds in Tubular T-, Y-, and K-Connections Made by SMAW, GMAW-S, and FCAW
4.1	9.9 WPS Qualification—Production Welding Positions Qualified by Pipe and Box Tube Tests
4.2	9.10 WPS Qualification—CJP Groove Welds: Number and Type of Test Specimens and Range of Thickness and Diameter Qualified
4.3	9.11 Number and Type of Test Specimens and Range of Thickness Qualified—WPS Qualification; PJP Groove Welds
4.4	9.12 Number and Type of Test Specimens and Range of Thickness Qualified—WPS Qualification; Fillet Welds
4.10	9.13 Welder and Welding Operator Qualification—Production Welding Positions Qualified by Pipe and Box Tube Tests
4.11	9.14 Welder and Welding Operator Qualification—Number and Type of Specimens and Range of Thickness and Diameter Qualified
5.5	9.15 Tubular Root Opening Tolerances Butt Joints Welded Without Backing
6.1	9.16 Visual Inspection Acceptance Criteria
6.4	9.17 Hole-Type IQI Requirements
6.5	9.18 Wire IQI Requirements
6.6	9.19 IQI Selection and Placement

## Summary of Figures in D1.1:2010 Relocated to Clause 9 in D1.1:2015

<b>D1.1:2010 Figure</b>	<b>D1.1:2015 Figure and Title</b>
2.13	9.1 Allowable Fatigue Stress and Strain Ranges for Stress Categories, Tubular Structures for Atmospheric Service
2.14	9.2 Parts of a Tubular Connection
2.15	9.3 Fillet Welded Lap Joint (Tubular)
2.16	9.4 Tubular T-, Y-, and K-Connection Fillet Weld Footprint Radius
2.17	9.5 Punching Shear Stress
2.18	9.6 Detail of Overlapping Joint
2.19	9.7 Limitations for Box T-, Y-, and K-Connections
2.20	9.8 Overlapping K-Connections
2.21	9.9 Transition of Thickness of Butt Joints in Parts of Unequal Thickness (Tubular)
3.2	9.10 Fillet Welded Prequalified Tubular Joints Made by SMAW, GMAW, and FCAW
3.5	9.11 Prequalified Joint Details for PJP T-, Y-, and K-Tubular Connections
3.6	9.12 Prequalified Joint Details for CJP T-, Y-, and K-Tubular Connections
3.7	9.13 Definitions and Detailed Selections for Prequalified CJP T-, Y-, and K-Tubular Connections
3.8	9.14 Prequalified Joint Details for CJP Groove Welds in Tubular T-, Y-, and K-Connections—Standard Flat Profiles for Limited Thickness
3.9	9.15 Prequalified Joint Details for CJP Groove Welds in Tubular T-, Y-, and K-Connections—Profile with Toe Fillet for Intermediate Thickness
3.10	9.16 Prequalified Joint Details for CJP Groove Welds in Tubular T-, Y-, and K-Connections—Concave Improved Profile for Heavy Sections or Fatigue
4.4	9.17 Positions of Test Pipe or Tubing for Groove Welds
4.6	9.18 Positions of Test Pipes or Tubing for Fillet Welds
4.7	9.19 Location of Test Specimens on Welded Test Pipe—WPS Qualification
4.8	9.20 Location of Test Specimens for Welded Box Tubing—WPS Qualification
4.20	9.21 Pipe Fillet Weld Soundness Test-WPS Qualification
4.24	9.22 Tubular Butt Joint-Welder Qualification with and without Backing
4.25	9.23 Tubular Butt Joint-WPS Qualification with and without Backing
4.26	9.24 Acute Angle Heel Test (Restrains not Shown)
4.27	9.25 Test Joint for T-, Y-, and K-Connections without Backing on Pipe or Box Tubing ( $\geq 6$ in [150 mm] O.D.) -Welder and WPS Qualification
4.28	9.26 Test Joint for T-, Y-, and K-Connections without Backing on Pipe or Box Tubing ( $< 4$ in [100 mm] O.D.)-Welder and WPS Qualification
4.29	9.27 Corner Macroetch Test Joint for T-, Y-, and K-Connections without Backing on Box Tubing for CJP Groove Welds-Welder and WPS Qualification
4.34	9.28 Location of Test Specimens on Welded Test Pipe and Box Tubing-Welder Qualification

### Summary of Figures in D1.1:2010 Relocated to Clause 9 in D1.1:2015 (Continued)

D1.1:2010 Figure	D1.1:2015 Figure and Title
6.4	9.29 Class R Indications
6.5	9.30 Class X Indications
6.13	9.31 Single-Wall Exposure-Single-Wall View
6.14	9.32 Double-Wall Exposure-Single-Wall View
6.15	9.33 Double-Wall Exposure-Double-Wall (Elliptical) View, Minimum Two Exposures
6.16	9.34 Double-Wall Exposure-Double-Wall View, Minimum Three Exposures
6.22	9.35 Scanning Techniques

**AWS B4.0, *Standard Methods for Mechanical Testing of Welds***, provides additional details of test specimen preparation and details of test fixture construction.

**Commentary.** The Commentary is nonmandatory and is intended only to provide insightful information into provision rationale.

**Normative Annexes.** These annexes address specific subjects in the code and their requirements are mandatory requirements that supplement the code provisions.

**Informative Annexes.** These annexes are not code requirements but are provided to clarify code provisions by showing examples, providing information, or suggesting alternative good practices.

**Index.** As in previous codes, the entries in the Index are referred to by subclause number rather than by page number. This should enable the user of the Index to locate a particular item of interest in minimum time.

**Errata.** It is the Structural Welding Committee's Policy that all errata should be made available to users of the code. Therefore, any significant errata will be published in the Society News Section of the *Welding Journal* and posted on the AWS web site at: <http://www.aws.org/technical/d1/>.

**Suggestions.** Your comments for improving AWS D1.1/D1.1M:2015, *Structural Welding Code—Steel* are welcome. Submit comments to the Managing Director, Technical Services Division, American Welding Society, 8669 NW 36 St, # 130, Miami, FL 33166; telephone (305) 443-9353; fax (305) 443-5951; e-mail [info@aws.org](mailto:info@aws.org); or via the AWS web site <<http://www.aws.org>>.



# Table of Contents

	Page No.
<i>Dedication</i> .....	v
<i>Personnel</i> .....	vii
<i>Foreword</i> .....	xv
<i>List of Tables</i> .....	xxxiv
<i>List of Figures</i> .....	xxxvii
<b>1. General Requirements</b> .....	<b>1</b>
1.1 Scope .....	1
1.2 Limitations .....	1
1.3 Definitions .....	1
1.4 Responsibilities .....	2
1.5 Approval .....	3
1.6 Welding Symbols .....	3
1.7 Safety Precautions .....	3
1.8 Standard Units of Measurement .....	3
1.9 Reference Documents .....	3
<b>2. Design of Welded Connections</b> .....	<b>5</b>
2.1 Scope .....	5
<i>Part A—Common Requirements for Design of Welded Connections (Nontubular and Tubular Members)</i> .....	5
2.2 General .....	5
2.3 Contract Plans and Specifications .....	5
2.4 Effective Areas .....	6
<i>Part B—Specific Requirements for Design of Nontubular Connections (Statically or Cyclically Loaded)</i> .....	8
2.5 General .....	8
2.6 Stresses .....	8
2.7 Joint Configuration and Details .....	9
2.8 Joint Configuration and Details—Groove Welds .....	10
2.9 Joint Configuration and Details—Fillet Welded Joints .....	10
2.10 Joint Configuration and Details—Plug and Slot Welds .....	11
2.11 Filler Plates .....	11
2.12 Built-Up Members .....	12
<i>Part C—Specific Requirements for Design of Nontubular Connections (Cyclically Loaded)</i> .....	12
2.13 General .....	12
2.14 Limitations .....	12
2.15 Calculation of Stresses .....	13
2.16 Allowable Stresses and Stress Ranges .....	13
2.17 Detailing, Fabrication, and Erection .....	14
2.18 Prohibited Joints and Welds .....	15
2.19 Inspection .....	15
<b>3. Prequalification of WPSs</b> .....	<b>45</b>
3.1 Scope .....	45
3.2 Welding Processes .....	45
3.3 Base Metal/Filler Metal Combinations .....	45

	Page No.
3.4 Engineer's Approval for Auxiliary Attachments .....	46
3.5 Minimum Preheat and Interpass Temperature Requirements .....	46
3.6 Limitation of WPS Variables .....	46
3.7 General WPS Requirements.....	46
3.8 Common Requirements for Parallel Electrode and Multiple Electrode SAW .....	47
3.9 Fillet Weld Requirements.....	47
3.10 Plug and Slot Weld Requirements.....	47
3.11 Common Requirements of PJP and CJP Groove Welds .....	47
3.12 PJP Requirements .....	48
3.13 CJP Groove Weld Requirements.....	48
3.14 Postweld Heat Treatment .....	48
<b>4. Qualification .....</b>	<b>109</b>
4.1 Scope.....	109
<i>Part A—General Requirements .....</i>	<i>109</i>
4.2 General.....	109
4.3 Common Requirements for WPS and Welding Personnel Performance Qualification .....	110
<i>Part B—Welding Procedure Specification (WPS) Qualification.....</i>	<i>110</i>
4.4 Production Welding Positions Qualified .....	110
4.5 Type of Qualification Tests .....	110
4.6 Weld Types for WPS Qualification.....	110
4.7 Preparation of WPS.....	111
4.8 Essential Variables .....	111
4.9 Methods of Testing and Acceptance Criteria for WPS Qualification .....	111
4.10 CJP Groove Welds .....	113
4.11 PJP Groove Welds .....	113
4.12 Fillet Welds .....	113
4.13 Plug and Slot Welds .....	114
4.14 Welding Processes Requiring Qualification.....	114
<i>Part C—Performance Qualification .....</i>	<i>115</i>
4.15 General.....	115
4.16 Type of Qualification Tests Required.....	115
4.17 Weld Types for Welder and Welding Operator Performance Qualification.....	115
4.18 Preparation of Performance Qualification Forms .....	116
4.19 Essential Variables .....	116
4.20 CJP Groove Welds for Nontubular Connections.....	116
4.21 Extent of Qualification.....	116
4.22 Methods of Testing and Acceptance Criteria for Welder and Welding Operator Qualification .....	116
4.23 Method of Testing and Acceptance Criteria for Tack Welder Qualification.....	117
4.24 Retest.....	117
<i>Part D—Requirements for CVN Testing.....</i>	<i>118</i>
4.25 General .....	118
4.26 Test Locations .....	118
4.27 CVN Tests .....	118
4.28 Test Requirements.....	119
4.29 Retest.....	119
4.30 Reporting.....	119
<b>5. Fabrication.....</b>	<b>165</b>
5.1 Scope.....	165
5.2 Base Metal.....	165
5.3 Welding Consumables and Electrode Requirements .....	165

	Page No.	
5.4	ESW and EGW Processes.....	167
5.5	WPS Variables.....	168
5.6	Preheat and Interpass Temperatures.....	168
5.7	Heat Input Control for Quenched and Tempered Steels.....	168
5.8	Stress-Relief Heat Treatment.....	168
5.9	Backing.....	169
5.10	Welding and Cutting Equipment.....	169
5.11	Welding Environment.....	169
5.12	Conformance with Design.....	170
5.13	Minimum Fillet Weld Sizes.....	170
5.14	Preparation of Base Metal.....	170
5.15	Reentrant Corners.....	172
5.16	Weld Access Holes, Beam Copes, and Connection Material.....	172
5.17	Tack Welds and Construction Aid Welds.....	172
5.18	Camber in Built-Up Members.....	173
5.19	Splices.....	173
5.20	Control of Distortion and Shrinkage.....	173
5.21	Tolerance of Joint Dimensions.....	174
5.22	Dimensional Tolerance of Welded Structural Members.....	174
5.23	Weld Profiles.....	177
5.24	Technique for Plug and Slot Welds.....	177
5.25	Repairs.....	177
5.26	Peening.....	178
5.27	Caulking.....	178
5.28	Arc Strikes.....	179
5.29	Weld Cleaning.....	179
5.30	Weld Tabs.....	179
<b>6.</b>	<b>Inspection.....</b>	<b>191</b>
	<i>Part A—General Requirements.....</i>	<i>191</i>
6.1	Scope.....	191
6.2	Inspection of Materials and Equipment.....	192
6.3	Inspection of WPSs.....	192
6.4	Inspection of Welder, Welding Operator, and Tack Welder Qualifications.....	192
6.5	Inspection of Work and Records.....	192
	<i>Part B—Contractor Responsibilities.....</i>	<i>193</i>
6.6	Obligations of the Contractor.....	193
	<i>Part C—Acceptance Criteria.....</i>	<i>193</i>
6.7	Scope.....	193
6.8	Engineer’s Approval for Alternate Acceptance Criteria.....	193
6.9	Visual Inspection.....	193
6.10	<u>Penetrant Testing (PT) and Magnetic Particle Testing (MT)</u> .....	193
6.11	<u>Nondestructive Testing (NDT)</u> .....	194
6.12	<u>Radiographic Testing (RT)</u> .....	194
6.13	<u>Ultrasonic Testing (UT)</u> .....	195
	<i>Part D—NDT Procedures.....</i>	<i>196</i>
6.14	Procedures.....	196
6.15	Extent of Testing.....	196
	<i>Part E—Radiographic Testing (RT).....</i>	<i>197</i>
6.16	RT of Groove Welds in Butt Joints.....	197
6.17	RT Procedures.....	197
6.18	Examination, Report, and Disposition of Radiographs.....	199

	Page No.
<i>Part F—Ultrasonic Testing (UT) of Groove Welds</i> .....	199
6.19 General .....	199
6.20 Qualification Requirements .....	199
6.21 UT Equipment .....	199
6.22 Reference Standards .....	200
6.23 Equipment Qualification .....	201
6.24 Calibration for Testing .....	201
6.25 Testing Procedures .....	201
6.26 Preparation and Disposition of Reports .....	203
6.27 Calibration of the UT Unit with IIW Type or Other Approved Reference Blocks (Annex G) .....	203
6.28 Equipment Qualification Procedures .....	204
6.29 Discontinuity Size Evaluation Procedures .....	206
6.30 Scanning Patterns .....	206
6.31 Examples of dB Accuracy Certification .....	206
<i>Part G—Other Examination Methods</i> .....	207
6.32 General Requirements .....	207
6.33 Radiation Imaging Systems .....	207
6.34 Advanced Ultrasonic Systems .....	207
6.35 Additional Requirements .....	208
<b>7. Stud Welding</b> .....	<b>245</b>
7.1 Scope .....	245
7.2 General Requirements .....	245
7.3 Mechanical Requirements .....	246
7.4 Workmanship/Fabrication .....	246
7.5 Technique .....	246
7.6 Stud Application Qualification Requirements .....	247
7.7 Production Control .....	248
7.8 Fabrication and Verification Inspection Requirements .....	249
7.9 Manufacturers’ Stud Base Qualification Requirements .....	249
<b>8. Strengthening and Repair of Existing Structures</b> .....	<b>255</b>
8.1 General .....	255
8.2 Base Metal .....	255
8.3 Design for Strengthening and Repair .....	255
8.4 Fatigue Life Enhancement .....	255
8.5 Workmanship and Technique .....	256
8.6 Quality .....	256
<b>9. Tubular Structures</b> .....	<b>257</b>
9.1 General .....	257
<i>Part A—Design of Tubular Connections</i> .....	257
9.2 Allowable Stresses .....	257
9.3 Identification .....	258
9.4 Symbols .....	258
9.5 Weld Design .....	258
9.6 Limitations of the Strength of Welded Connections .....	260
9.7 Thickness Transition .....	264
9.8 Material Limitations .....	264
<i>Part B—Prequalification of Welding Procedure Specifications (WPSs)</i> .....	265
9.9 Fillet Weld Requirements .....	265
9.10 PJP Requirements .....	265
9.11 CJP Groove Weld Requirements .....	265

	Page No.
<i>Part C—Welding Procedure Specification (WPS) Qualification</i> .....	266
<u>9.12</u> Common Requirements for WPS and Welding Personnel Performance Qualification .....	266
<u>9.13</u> Production Welding Positions Qualified .....	266
<u>9.14</u> Type of Qualification Tests, <u>Methods of Testing</u> , and <u>Acceptance Criteria for WPS Qualification</u> .....	266
<u>9.15</u> CJP Groove Welds for Tubular Connections .....	267
<u>9.16</u> PJP and Fillet Welds Tubular T-, Y-, or K-Connections and Butt Joints .....	268
<i>Part D—Performance Qualification</i> .....	268
<u>9.17</u> Production Welding Positions, <u>Thicknesses and Diameters</u> Qualified .....	268
<u>9.18</u> Weld Types for Welder and Welding Operator Performance Qualification .....	268
<u>9.19</u> CJP Groove Welds for Tubular Connections .....	268
<u>9.20</u> PJP Groove Welds for Tubular Connections.....	269
<u>9.21</u> Fillet Welds for Tubular Connections .....	269
<u>9.22</u> Methods of Testing and Acceptance Criteria for Welder and Welding Operator Qualification .....	269
<i>Part E—Fabrication</i> .....	269
<u>9.23</u> Backing .....	269
<u>9.24</u> Tolerance of Joint Dimensions.....	270
<i>Part F—Inspection</i> .....	270
<u>9.25</u> Visual Inspection.....	270
<u>9.26</u> NDT .....	270
<u>9.27</u> UT .....	270
<u>9.28</u> RT Procedures .....	271
<u>9.29</u> Supplementary RT Requirements for Tubular Connections .....	271
<u>9.30</u> UT of Tubular T-, Y-, and K-Connections .....	271
<i>Annexes</i> .....	327
Annex A (Normative)—Effective Throat ( <u>E</u> ) .....	329
Annex B (Normative)—Effective Throats of Fillet Welds in Skewed T-Joints.....	333
Annex D (Normative)—Flatness of Girder Webs—Statically Loaded Structures.....	337
Annex E (Normative)—Flatness of Girder Webs—Cyclically Loaded Structures .....	341
Annex F (Normative)—Temperature-Moisture Content Charts .....	347
Annex <u>G</u> (Normative)—Qualification and Calibration of UT Units with Other Approved Reference Blocks.....	351
Annex <u>H</u> (Normative)—Guideline on Alternative Methods for Determining Preheat.....	355
Annex <u>I</u> (Normative)—Symbols for Tubular Connection Weld Design .....	365
Annex <u>J</u> (Normative)—Terms and Definitions .....	367
Annex <u>K</u> (Informative)—Guide for Specification Writers .....	375
Annex <u>L</u> (Informative)—UT Equipment Qualification and Inspection Forms .....	377
Annex <u>M</u> (Informative)—Sample Welding Forms .....	387
Annex <u>N</u> (Informative)—Guidelines for the Preparation of Technical Inquiries for the Structural Welding Committee .....	409
Annex <u>O</u> (Informative)—Local Dihedral Angle .....	411
Annex <u>P</u> (Informative)—Contents of Prequalified WPS.....	417
Annex <u>Q</u> (Informative)—UT Examination of Welds by Alternative Techniques.....	419
Annex <u>R</u> (Informative)—Ovalizing Parameter Alpha .....	435
Annex <u>S</u> (Informative)—List of Reference Documents .....	437
Annex <u>T</u> (Informative)—Filler Metal Strength Properties .....	439
Annex <u>U</u> (Informative)—AWS A5.36 Filler Metal Classifications and Properties .....	451
<i>Commentary</i> .....	467
Foreword.....	469
Index .....	587
List of AWS Documents on Structural Welding.....	603

## List of Tables

Table	Page No.
2.1	Effective Size of Flare-Groove Welds Filled Flush..... 16
2.2	Z Loss Dimension (Nontubular) ..... 16
2.3	Allowable Stresses ..... 17
2.4	Equivalent Strength Coefficients for Obliquely Loaded Fillet Welds..... 18
2.5	Fatigue Stress Design Parameters ..... 19
3.1	<u>Approved Base Metals for Prequalified WPSs</u> ..... 49
3.2	<u>Filler Metals for Matching Strength for Table 3.1, Groups I, II, III, and IV Materials</u> ..... 53
3.3	<u>Prequalified Minimum Preheat and Interpass Temperature</u> ..... 57
3.4	<u>Filler Metal Requirements for Exposed Bare Applications of Weathering Steels</u> ..... 60
3.5	<u>Minimum Prequalified PJP Weld Size (E)</u> ..... 60
3.6	<u>Prequalified WPS Requirements</u> ..... 61
3.7	<u>Prequalified WPS Variables</u> ..... 62
4.1	WPS Qualification—Production Welding Positions Qualified by Plate, Pipe, and Box Tube Tests ..... 120
4.2	WPS Qualification-CJP Groove Welds: Number and Type of Test Specimens and Range of Thickness Qualified ..... 121
4.3	Number and Type of Test Specimens and Range of Thickness Qualified—WPS Qualification; PJP Groove Welds ..... 123
4.4	Number and Type of Test Specimens and Range of Thickness Qualified—WPS Qualification; Fillet Welds ..... 123
4.5	PQR Essential Variable Changes Requiring WPS Requalification for SMAW, SAW, GMAW, FCAW, and GTAW ..... 124
4.6	PQR Supplementary Essential Variable Changes for CVN Testing Applications Requiring WPS Requalification for SMAW, SAW, GMAW, FCAW, and GTAW ..... 127
4.7	PQR Essential Variable Changes Requiring WPS Requalification for ESW or EGW ..... 128
4.8	Table 3.1, Table 4.9, and Unlisted Steels Qualified by PQR ..... 129
4.9	Code-Approved Base Metals and Filler Metals Requiring Qualification per Clause 4 ..... 130
4.10	Welder and Welding Operator Qualification—Production Welding Positions Qualified by Plate Tests..... 135
4.11	Welder and Welding Operator Qualification—Number and Type of Specimens and Range of Thickness and Diameter Qualified..... 136
4.12	Welding Personnel Performance Essential Variable Changes Requiring Requalification ..... 138
4.13	Electrode Classification Groups..... 138
4.14	CVN Test Requirements ..... 139
4.15	CVN Test Temperature Reduction ..... 139
5.1	Allowable Atmospheric Exposure of Low-Hydrogen Electrodes..... 180
5.2	Minimum Holding Time ..... 180
5.3	Alternate Stress-Relief Heat Treatment ..... 180
5.4	Limits on Acceptability and Repair of Mill Induced Laminar Discontinuities in Cut Surfaces..... 180
5.5	<u>Camber Tolerance for Typical Girder</u> ..... 181
5.6	<u>Camber Tolerance for Girders without a Designed Concrete Haunch</u> ..... 181
5.7	<u>Minimum Fillet Weld Sizes</u> ..... 181
5.8	<u>Weld Profiles</u> ..... 182
5.9	<u>Weld Profile Schedules</u> ..... 182

Table	Page No.
6.1	Visual Inspection Acceptance Criteria.....209
6.2	UT Acceptance-Rejection Criteria (Statically Loaded Nontubular Connections).....210
6.3	UT Acceptance-Rejection Criteria (Cyclically Loaded Nontubular Connections).....211
6.4	Hole-Type IQI Requirements.....212
6.5	Wire IQI Requirements.....212
6.6	IQI Selection and Placement.....213
6.7	Testing Angle.....214
6.8	<u>UT Equipment Qualification and Calibration Requirements</u> .....216
7.1	Mechanical Property Requirements for Studs.....251
7.2	Minimum Fillet Weld Size for Small Diameter Studs.....251
9.1	Fatigue Stress Design Parameters.....274
9.2	Allowable Stresses in Tubular Connection Welds.....275
9.3	Stress Categories for Type and Location of Material for Circular Sections.....277
9.4	Fatigue Category Limitations on Weld Size or Thickness and Weld Profile (Tubular Connections).....279
9.5	Z Loss Dimensions for Calculating Prequalified PJP T-, Y-, and K-Tubular Connection Minimum Weld Sizes.....279
9.6	Terms for Strength of Connections (Circular Sections).....280
9.7	Joint Detail Applications for Prequalified CJP T-, Y-, and K-Tubular Connections.....280
9.8	Prequalified Joint Dimensions and Groove Angles for CJP Groove Welds in Tubular T-, Y, and K-Connections Made by SMAW, GMAW-S, and FCAW.....281
9.9	WPS Qualification—Production Welding Positions Qualified by Plate, Pipe, and Box Tube Tests.....282
9.10	WPS Qualification—CJP Groove Welds: Number and Type of Test Specimens and Range of Thickness and Diameter Qualified.....283
9.11	Number and Type of Test Specimens and Range of Thickness Qualified—WPS Qualification; PJP Groove Welds.....285
9.12	Number and Type of Test Specimens and Range of Thickness Qualified—WPS Qualification; Fillet Welds.....285
9.13	Welder and Welding Operator Qualification—Production Welding Positions Qualified by Plate, Pipe, and Box Tube Tests.....286
9.14	Welder and Welding Operator Qualification—Number and Type of Specimens and Range of Thickness and Diameter Qualified.....287
9.15	Tubular Root Opening Tolerances, <u>Butt Joints Welded Without Backing</u> .....289
9.16	Visual Inspection Acceptance Criteria.....290
9.17	Hole-Type IQI Requirements.....291
9.18	Wire IQI Requirements.....291
9.19	IQI Selection and Placement.....292
B.1	Equivalent Fillet Weld Leg Size Factors for Skewed T-Joints.....334
D.1	Intermediate Stiffeners on Both Sides of Web.....338
D.2	No Intermediate Stiffeners.....338
D.3	Intermediate Stiffeners on One Side Only of Web.....339
E.1	Intermediate Stiffness on Both Sides of Web, Interior Girders.....342
E.2	Intermediate Stiffness on One Side Only of Web, Fascia Girders.....343
E.3	Intermediate Stiffness on One Side Only of Web, Interior Girders.....344
E.4	Intermediate Stiffness on Both Sides of Web, Fascia Girders.....345
E.5	No Intermediate Stiffeners, Interior or Fascia Girders.....345
H.1	Susceptibility Index Grouping as Function of Hydrogen Level “H” and Composition Parameter $P_{cm}$ .....358
H.2	Minimum Preheat and Interpass Temperatures for Three Levels of Restraint.....358
Q.1	Acceptance-Rejection Criteria.....424
U.1	<u>AWS A5.36/A5.36M Carbon Steel Electrode Classifications with Fixed Requirements</u> .....453
U.2	<u>AWS A5.36/A5.36M Tension Test Requirements</u> .....454
U.3	<u>AWS A5.36/A5.36M Charpy Impact Test Requirements</u> .....454

<b>Table</b>	<b>Page No.</b>
<u>U.4</u> Electrode Usability Characteristics .....	455
<u>U.5</u> AWS A5.36/A5.36M Composition Requirements for Shielding Gases .....	457
<u>U.6</u> Weld Metal Chemical Composition Requirements .....	458
<u>U.7</u> AWS A5.20/A5.20M Procedure Requirements for “D” Optional Supplemental Designator .....	460
<u>U.8</u> AWS A5.36/A5.36M Procedure Requirements for “D” Optional Supplemental Designator .....	460
<u>U.9</u> Comparison of Classifications of AWS A5.18, A5.20, A5.28, and A5.29 Specifications to AWS A5.36 Fixed and Open Classifications for Multiple-Pass FCAW and GMAW—Metal Cored Electrodes .....	461
<i>Commentary</i>	
C-3.1 Typical Current Ranges for GMAW-S on Steel .....	498
C-8.1 Guide to Welding Suitability .....	549
C-8.2 Relationship Between Plate Thickness and Burr Radius .....	549
C-9.1 Survey of Diameter/Thickness and Flat Width/Thickness Limits for Tubes .....	572
C-9.2 Suggested Design Factors .....	573
C-9.3 Values of JD .....	573
C-9.4 Structural Steel Plates .....	574
C-9.5 Structural Steel Pipe and Tubular Shapes .....	575
C-9.6 Structural Steel Shapes .....	575
C-9.7 Classification Matrix for Applications .....	576
C-9.8 CVN Testing Conditions .....	576
C-9.9 CVN Test Values .....	577
C-9.10 HAZ CVN Test Values .....	577



## List of Figures

Figure	Page No.
2.1	Maximum Fillet Weld Size Along Edges in Lap Joints ..... 36
2.2	Transition of Butt Joints in Parts of Unequal Thickness (Cyclically Loaded Nontubular) ..... 37
2.3	Transition of Thicknesses (Statically Loaded Nontubular)..... 38
2.4	Transversely Loaded Fillet Welds ..... 38
2.5	Minimum Length of Longitudinal Fillet Welds at End of Plate or Flat Bar Members ..... 39
<u>2.6</u>	<u>Termination of Welds Near Edges Subject to Tension</u> ..... 39
2.7	End Return at Flexible Connections ..... 40
2.8	Fillet Welds on Opposite Sides of a Common Plane ..... 40
2.9	Thin Filler Plates in Splice Joint ..... 41
2.10	Thick Filler Plates in Splice Joint ..... 41
2.11	Allowable Stress Range for Cyclically Applied Load (Fatigue) in Nontubular Connections (Graphical Plot of Table 2.5)..... 42
2.12	Transition of Width (Cyclically Loaded Nontubular)..... 43
3.1	Weld Bead in which Depth and Width Exceed the Width of the Weld Face ..... 64
<u>3.2</u>	<u>Prequalified PJP Groove Welded Joint Details (Dimensions in Inches)</u> ..... 66
<u>3.2</u>	<u>Prequalified PJP Groove Welded Joint Details (Dimensions in Millimeters)</u> ..... 74
<u>3.3</u>	<u>Prequalified CJP Groove Welded Joint Details (Dimensions in Inches)</u> ..... 82
<u>3.3</u>	<u>Prequalified CJP Groove Welded Joint Details (Dimensions in Millimeters)</u> ..... 93
<u>3.4</u>	<u>Prequalified Skewed T-Joint Details (Nontubular)</u> ..... 104
<u>3.5</u>	<u>Prequalified Fillet Weld Joint Details (Dimensions in Inches)</u> ..... 105
<u>3.5</u>	<u>Prequalified Fillet Weld Joint Details (Dimensions in Millimeters)</u> ..... 106
<u>3.6</u>	<u>Prequalified CJP Groove, T-, and Corner Joint</u> ..... 107
4.1	Positions of Groove Welds ..... 140
4.2	Positions of Fillet Welds ..... 141
4.3	Positions of Test Plates for Groove Welds ..... 142
<u>4.4</u>	<u>Positions of Test Plate for Fillet Welds</u> ..... 143
<u>4.5</u>	<u>Location of Test Specimens on Welded Test Plates—ESW and EGW—WPS Qualification</u> ..... 144
<u>4.6</u>	<u>Location of Test Specimens on Welded Test Plate Over 3/8 in [10 mm] Thick—WPS Qualification</u> ..... 145
<u>4.7</u>	<u>Location of Test Specimens on Welded Test Plate 3/8 in [10 mm] Thick and Under— WPS Qualification</u> ..... 146
<u>4.8</u>	<u>Face and Root Bend Specimens</u> ..... 147
<u>4.9</u>	<u>Side Bend Specimens</u> ..... 148
4.10	Reduced-Section Tension Specimens ..... 149
<u>4.11</u>	<u>Guided Bend Test Jig</u> ..... 150
<u>4.12</u>	<u>Alternative Wraparound Guided Bend Test Jig</u> ..... 151
<u>4.13</u>	<u>Alternative Roller-Equipped Guided Bend Test Jig for Bottom Ejection of Test Specimen</u> ..... 151
4.14	All-Weld-Metal Tension Specimen ..... 152
<u>4.15</u>	<u>Fillet Weld Soundness Tests for WPS Qualification</u> ..... 153
<u>4.16</u>	<u>Test Plate for Unlimited Thickness—Welder Qualification and Fillet Weld Consumable Verification Tests</u> ..... 154
<u>4.17</u>	<u>Test Plate for Unlimited Thickness—Welding Operator Qualification and Fillet Weld Consumable Verification Tests</u> ..... 154
<u>4.18</u>	<u>Location of Test Specimen on Welded Test Plate 1 in [25 mm] Thick—Consumables Verification for Fillet Weld WPS Qualification</u> ..... 155

<b>Figure</b>	<b>Page No.</b>
<u>4.19</u> Optional Test Plate for Unlimited Thickness—Horizontal Position—Welder Qualification .....	156
<u>4.20</u> Test Plate for Limited Thickness—All Positions—Welder Qualification .....	157
<u>4.21</u> Optional Test Plate for Limited Thickness—Horizontal Position—Welder Qualification .....	158
<u>4.22</u> Fillet Weld Root Bend Test Plate—Welder or Welding Operator Qualification—Option 2 .....	159
<u>4.23</u> Method of Rupturing Specimen—Tack Welder Qualification .....	160
<u>4.24</u> Butt Joint for Welding Operator Qualification—ESW and EGW .....	160
<u>4.25</u> Fillet Weld Break and Macroetch Test Plate—Welder or Welding Operator Qualification Option 1 .....	161
<u>4.26</u> Plug Weld Macroetch Test Plate—Welder or Welding Operator Qualification and WPS Qualification .....	162
<u>4.27</u> Fillet Weld Break Specimen—Tack Welder Qualification .....	163
<u>4.28</u> CVN Test Specimen Locations .....	164
<u>5.1</u> Edge Discontinuities in Cut Material .....	183
<u>5.2</u> Weld Access Hole Geometry .....	184
<u>5.3</u> Workmanship Tolerances in Assembly of Groove Welded Joints .....	185
<u>5.4</u> Requirements for Weld Profiles .....	186
<u>6.1</u> Discontinuity Acceptance Criteria for Statically Loaded Nontubular and Statically or Cyclically Loaded Tubular Connections .....	218
<u>6.2</u> Discontinuity Acceptance Criteria for Cyclically Loaded Nontubular Connections in Tension (Limitations of Porosity and Fusion Discontinuities) .....	223
<u>6.3</u> Discontinuity Acceptance Criteria for Cyclically Loaded Nontubular Connections in Compression (Limitations of Porosity or Fusion-Type Discontinuities) .....	228
<u>6.4</u> Hole-Type IQI .....	233
<u>6.5</u> Wire IQI .....	234
<u>6.6</u> RT Identification and Hole-Type or Wire IQI Locations on Approximately Equal Thickness Joints 10 in [250 mm] and Greater in Length .....	235
<u>6.7</u> RT Identification and Hole-Type or Wire IQI Locations on Approximately Equal Thickness Joints Less than 10 in [250 mm] in Length .....	236
<u>6.8</u> RT Identification and Hole-Type or Wire IQI Locations on Transition Joints 10 in [250 mm] and Greater in Length .....	237
<u>6.9</u> RT Identification and Hole-Type or Wire IQI Locations on Transition Joints Less than 10 in [250 mm] in Length .....	238
<u>6.10</u> RT Edge Blocks .....	238
<u>6.11</u> Transducer Crystal .....	239
<u>6.12</u> Qualification Procedure of Search Unit Using IIW Reference Block .....	239
<u>6.13</u> Typical IIW Type Block .....	240
<u>6.14</u> Qualification Blocks .....	241
<u>6.15</u> Plan View of UT Scanning Patterns .....	243
<u>6.16</u> Transducer Positions (Typical) .....	244
<u>7.1</u> Dimension and Tolerances of Standard-Type Headed Studs .....	252
<u>7.2</u> Typical Tension Test Fixture .....	252
<u>7.3</u> Torque Testing Arrangement and Table of Testing Torques .....	253
<u>7.4</u> Bend Testing Device .....	254
<u>7.5</u> Suggested Type of Device for Qualification Testing of Small Studs .....	254
<u>9.1</u> Allowable Fatigue Stress and Strain Ranges for Stress Categories, Tubular Structures for Atmospheric Service .....	293
<u>9.2</u> Parts of a Tubular Connection .....	294
<u>9.3</u> Fillet Welded Lap Joint (Tubular) .....	297
<u>9.4</u> Tubular T-, Y-, and K-Connection Fillet Weld Footprint Radius .....	297
<u>9.5</u> Punching Shear Stress .....	298
<u>9.6</u> Detail of Overlapping Joint .....	298
<u>9.7</u> Limitations for Box T-, Y-, and K-Connections .....	299

<b>Figure</b>	<b>Page No.</b>
<u>9.8</u>	Overlapping K-Connections.....299
<u>9.9</u>	Transition of Thickness of Butt Joints in Parts of Unequal Thickness (Tubular) .....300
<u>9.10</u>	Fillet Welded Prequalified Tubular Joints Made by SMAW, GMAW, and FCAW .....301
<u>9.11</u>	Prequalified Joint Details for PJP T-, Y-, and K-Tubular Connections .....302
<u>9.12</u>	Prequalified Joint Details for CJP T-, Y-, and K-Tubular Connections .....305
<u>9.13</u>	Definitions and Detailed Selections for Prequalified CJP T-, Y-, and K-Tubular Connections .....306
<u>9.14</u>	Prequalified Joint Details for CJP Groove Welds in Tubular T-, Y-, and K-Connections— Standard Flat Profiles for Limited Thickness .....307
<u>9.15</u>	Prequalified Joint Details for CJP Groove Welds in Tubular T-, Y-, and K-Connections— Profile with Toe Fillet for Intermediate Thickness .....308
<u>9.16</u>	Prequalified Joint Details for CJP Groove Welds in Tubular T-, Y-, and K-Connections— Concave Improved Profile for Heavy Sections or Fatigue.....309
<u>9.17</u>	Positions of Test Pipe or Tubing for Groove Welds.....310
<u>9.18</u>	Positions of Test Pipes or Tubing for Fillet Welds.....311
<u>9.19</u>	Location of Test Specimens on Welded Test Pipe—WPS Qualification .....312
<u>9.20</u>	Location of Test Specimens for Welded Box Tubing—WPS Qualification .....313
<u>9.21</u>	Pipe Fillet Weld Soundness Test—WPS Qualification.....314
<u>9.22</u>	Tubular Butt Joint—Welder Qualification with and without Backing.....315
<u>9.23</u>	Tubular Butt Joint—WPS Qualification with and without Backing .....315
<u>9.24</u>	Acute Angle Heel Test (Restraints not Shown) .....316
<u>9.25</u>	Test Joint for T-, Y-, and K-Connections without Backing on Pipe or Box Tubing (≥ 6 in [150 mm] O.D.)—Welder and WPS Qualification.....317
<u>9.26</u>	Test Joint for T-, Y-, and K-Connections without Backing on Pipe or Box Tubing (< 4 in [100 mm] O.D.)—Welder and WPS Qualification.....318
<u>9.27</u>	Corner Macroetch Test Joint for T-, Y-, and K-Connections without Backing on Box Tubing for CJP Groove Welds—Welder and WPS Qualification .....319
<u>9.28</u>	Location of Test Specimens on Welded Test Pipe and Box Tubing—Welder Qualification .....320
<u>9.29</u>	Class R Indications.....321
<u>9.30</u>	Class X Indications .....323
<u>9.31</u>	Single-Wall Exposure—Single-Wall View .....324
<u>9.32</u>	Double-Wall Exposure—Single-Wall View.....324
<u>9.33</u>	Double-Wall Exposure—Double-Wall (Elliptical) View, Minimum Two Exposures .....325
<u>9.34</u>	Double-Wall Exposure—Double-Wall View, Minimum Three Exposures .....325
<u>9.35</u>	Scanning Techniques.....326
<u>A.1</u>	Fillet Weld.....329
<u>A.2</u>	Unreinforced Bevel Groove Weld.....330
<u>A.3</u>	Bevel Groove Weld with Reinforcing Fillet Weld .....330
<u>A.4</u>	Bevel Groove Weld with Reinforcing Fillet Weld .....331
<u>A.5</u>	Unreinforced Flare Bevel Groove Weld.....331
<u>A.6</u>	Flare Bevel Groove Weld with Reinforcing Fillet Weld .....332
<u>F.1</u>	Temperature-Moisture Content Chart to be Used in Conjunction with Testing Program to Determine Extended Atmospheric Exposure Time of Low-Hydrogen SMAW Electrodes.....348
<u>F.2</u>	Application of Temperature-Moisture Content Chart in Determining Atmospheric Exposure Time of Low-Hydrogen SMAW Electrodes.....349
<u>G.1</u>	Other Approved Blocks and Typical Transducer Position .....353
<u>H.1</u>	Zone Classification of Steels.....360
<u>H.2</u>	Critical Cooling Rate for 350 HV and 400 HV .....360
<u>H.3</u>	Graphs to Determine Cooling Rates for Single-Pass SAW Fillet Welds .....361
<u>H.4</u>	Relation Between Fillet Weld Size and Energy Input.....364
<u>Q.1</u>	Standard Reference Reflector .....425
<u>Q.2</u>	Recommended Calibration Block .....425
<u>Q.3</u>	Typical Standard Reflector (Located in Weld Mock-Ups and Production Welds) .....426
<u>Q.4</u>	Transfer Correction .....427

<b>Figure</b>	<b>Page No.</b>
Q.5	Compression Wave Depth (Horizontal Sweep Calibration) .....427
Q.6	Compression Wave Sensitivity Calibration.....428
Q.7	Shear Wave Distance and Sensitivity Calibration .....428
Q.8	Scanning Methods.....429
Q.9	Spherical Discontinuity Characteristics .....430
Q.10	Cylindrical Discontinuity Characteristics .....430
Q.11	Planar Discontinuity Characteristics .....431
Q.12	Discontinuity Height Dimension .....431
Q.13	Discontinuity Length Dimension .....432
Q.14	Display Screen Marking.....432
Q.15	Report of UT (Alternative Procedure) .....433
R.1	Definition of Terms for Computed Alpha .....435
U.1	<u>AWS A5.36/A5.36M Open Classification System .....466</u>
 <i>Commentary</i>	
C-2.1	Balancing of Fillet Welds About a Neutral Axis .....485
C-2.2	Shear Planes for Fillet and Groove Welds .....485
C-2.3	Eccentric Loading .....486
C-2.4	Load Deformation Relationship for Welds .....486
C-2.5	Example of an Obliquely Loaded Weld Group.....487
C-2.6	Graphical Solution of the Capacity of an Obliquely Loaded Weld Group .....488
C-2.7	Single Fillet Welded Lap Joints .....489
C-3.1	Oscillograms and Sketches of GMAW-S Metal Transfer .....498
C-3.2	Examples of Centerline Cracking .....499
C-3.3	Details of Alternative Groove Preparations for Prequalified Corner Joints.....499
C-4.1	Type of Welding on Pipe That Does Not Require Pipe Qualification.....504
C-5.1	Examples of Unacceptable Reentrant Corners.....515
C-5.2	Examples of Good Practice for Cutting Copos .....515
C-5.3	Permissible Offset in Abutting Members.....516
C-5.4	Correction of Misaligned Members .....516
C-5.5	Typical Method to Determine Variations in Girder Web Flatness .....517
C-5.6	Illustration Showing Camber Measurement Methods.....518
C-5.7	Measurement of Flange Warpage and Tilt .....519
C-5.8	Tolerances at Bearing Points .....520
C-6.1	90° T- or Corner Joints with Steel Backing .....532
C-6.2	Skewed T- or Corner Joints .....532
C-6.3	Butt Joints with Separation Between Backing and Joint .....533
C-6.4	Effect of Root Opening on Butt Joints with Steel Backing .....533
C-6.5	Resolutions for Scanning with Seal Welded Steel Backing .....534
C-6.6	Scanning with Seal Welded Steel Backing .....534
C-6.7	Illustration of Discontinuity Acceptance Criteria for Statically Loaded Nontubular and Statically or Cyclically Loaded Tubular Connections.....535
C-6.8	Illustration of Discontinuity Acceptance Criteria for Statically Loaded Nontubular and Statically or Cyclically Loaded Tubular Connections 1-1/8 in [30 mm] and Greater, Typical of Random Acceptable Discontinuities .....536
C-6.9	Illustration of Discontinuity Acceptance Criteria for Cyclically Loaded Nontubular Connections in Tension.....537
C-7.1	Allowable Defects in the Heads of Headed Studs.....542
C-8.1	Microscopic Intrusions.....550
C-8.2	Fatigue Life .....550
C-8.3	Toe Dressing with Burr Grinder.....551
C-8.4	Toe Dressing Normal to Stress.....551
C-8.5	Effective Toe Grinding .....552
C-8.6	End Grinding.....552

<b>Figure</b>	<b>Page No.</b>
C-8.7 Hammer Peening .....	553
C-8.8 Toe Remelting .....	554
C-9.1 Illustrations of Branch Member Stresses Corresponding to Mode of Loading .....	577
C-9.2 Improved Weld Profile Requirements .....	578
C-9.3 Simplified Concept of Punching Shear .....	578
C-9.4 Reliability of Punching Shear Criteria Using Computed Alpha .....	579
C-9.5 Transition Between Gap and Overlap Connections .....	580
C-9.6 Upper Bound Theorem.....	580
C-9.7 Yield Line Patterns .....	581

# Structural Welding Code—Steel

## 1. General Requirements

### 1.1 Scope

This code contains the requirements for fabricating and erecting welded steel structures. When this code is stipulated in contract documents, conformance with all provisions of the code shall be required, except for those provisions that the Engineer (see 1.4.1) or contract documents specifically modifies or exempts.

The following is a summary of the code clauses:

**1. General Requirements.** This clause contains basic information on the scope and limitations of the code, key definitions, and the major responsibilities of the parties involved with steel fabrication.

**2. Design of Welded Connections.** This clause contains requirements for the design of welded connections composed of tubular, or nontubular, product form members.

**3. Prequalification of WPSs.** This clause contains the requirements for exempting a Welding Procedure Specification (WPS) from the WPS qualification requirements of this code.

**4. Qualification.** This clause contains the requirements for WPS qualification and the performance qualification tests required to be passed by all welding personnel (welders, welding operators, and tack welders) to perform welding in accordance with this code.

**5. Fabrication.** This clause contains general fabrication and erection requirements applicable to welded steel structures governed by this code, including the requirements for base metals, welding consumables, welding technique, welded details, material preparation and assembly, workmanship, weld repair, and other requirements.

**6. Inspection.** This clause contains criteria for the qualifications and responsibilities of inspectors, acceptance criteria for production welds, and standard procedures for performing visual inspection and nondestructive testing (NDT).

**7. Stud Welding.** This clause contains the requirements for the welding of studs to structural steel.

**8. Strengthening and Repair of Existing Structures.** This clause contains basic information pertinent to the welded modification or repair of existing steel structures.

**9. Tubular Structures.** This clause contains exclusive tubular requirements. Additionally, the requirements of all other clauses apply to tubulars, unless specifically noted otherwise.

### 1.2 Limitations

The code was specifically developed for welded steel structures that utilize carbon or low alloy steels that are 1/8 in [3 mm] or thicker with a minimum specified yield strength of 100 ksi [690 MPa] or less. The code may be suitable to govern structural fabrications outside the scope of the intended purpose. However, the Engineer should evaluate such suitability, and based upon such evaluations, incorporate into contract documents any necessary changes to code requirements to address the specific requirements of the application that is outside the scope of the code. The Structural Welding Committee encourages the Engineer to consider the applicability of other AWS D1 codes for applications involving aluminum (AWS D1.2), sheet steel equal to or less than 3/16 in [5 mm] thick (AWS D1.3), reinforcing steel (AWS D1.4), and stainless steel (AWS D1.6), strengthening and repair of existing structures (AWS D1.7), seismic supplement (AWS D1.8), and titanium (AWS D1.9). The AASHTO/AWS D1.5 *Bridge Welding Code* was specifically developed for welding highway bridge components and is recommended for those applications.

### 1.3 Definitions

The welding terms used in this code shall be interpreted in conformance with the definitions given in the latest edition of AWS A3.0, *Standard Welding Terms and Definitions, Including Terms for Adhesive Bonding, Brazing, Soldering,*