



ANSI/AWS D10.4-86R
An American National Standard



**Recommended
Practices for
Welding Austenitic
Chromium-Nickel
Stainless Steel
Piping and Tubing**



American Welding Society



Key Words — austenitic pipe, chromium-nickel pipe, gas metal arc welding, gas tungsten arc welding, recommended practice, stainless steel pipe, shielded metal arc welding

ANSI/AWS D10.4-86
An American National Standard

Approved by
American National Standards Institute
November 12, 1986

Recommended Practices
for Welding Austenitic
Chromium-Nickel
Stainless Steel
Piping and Tubing

Superseding AWS D10.4-79

Prepared by
AWS Committee on Piping and Tubing

Issued, 1986

Under the Direction of
AWS Technical Activities Committee

Approved by
AWS Board of Directors
April 11, 1986

Abstract

This document presents a detailed discussion of the metallurgical characteristics and weldability of many grades of austenitic stainless steel used in piping and tubing. The delta ferrite content as expressed by ferrite number (FN) is explained, and its importance in minimizing hot cracking is discussed.

A number of Figures and Tables illustrate recommended joint designs and procedures. Appendix A presents information on the welding of high-carbon stainless steel cast pipe fittings.

Table of Contents

	page no.
<i>Personnel</i>	iii
<i>Foreword</i>	iv
<i>List of Tables</i>	vii
<i>List of Figures</i>	viii
<i>Introduction</i>	1
1. Material Compositions and Specifications	1
1.1 Compositions	1
1.2 Specifications	1
2. Base Metals	1
2.1 Primary Types (304, 305, 309, and 310)	1
2.2 Chromium-Nickel-Molybdenum Types (316 and 317)	3
2.3 Stabilized Types (321 and 347)	3
2.4 Low Carbon Types (304L, 309S, 310S, and 316L)	3
2.5 "H" Types (305H, 316H, 321H, 347H, and 348H)	4
2.6 Stainless Steel for Nuclear Service Types (348 and 348H)	4
2.7 High Carbon Cast Types (HF, HH, HK, HE, HT, HI, HU, and HN)	5
2.8 Low Carbon Cast Types (CF3, CF8, CF8C, CF8M, CF3M, CH8, CPK20, and CH20)	6
3. Filler Metal	6
3.1 Selection of Filler Metal	6
3.2 Welding Electrodes	6
4. Ferrite	7
4.1 Weld Metal Structure	7
4.2 Ferrite Phase	7
4.3 Measurement of Ferrite	8
4.4 Importance of Ferrite	8
4.5 Ferrite in Root Passes and Subsequent Passes	9
4.6 Effect of Welding Conditions on Ferrite	9
5. Welding Processes	9
5.1 Shielded Metal Arc Welding (SMAW)	9
5.2 Gas Tungsten Arc Welding (GTAW)	10
5.3 Gas Metal Arc Welding (GMAW)	10
5.4 Submerged Arc Welding (SAW)	11
5.5 Other Welding Processes	11
6. Welding of Dissimilar Stainless Steel Joints	11
7. Welded Joints in Pipe	11
7.1 Joint Design	11
7.2 Consumable Inserts	14
7.3 Insert Application	14
7.4 Inert Gas Purging	16
7.5 Open Butt Welding	18

8. <i>Welding Techniques</i>	18
8.1 Starting the Arc	18
8.2 Welding Position and Electrode Handling	18
8.3 Weld Size and Contour	19
8.4 Travel Speed	19
8.5 Welding Current	19
8.6 Extinguishing the Arc with SMAW	19
8.7 Cleaning and Finishing	20
8.8 Repair	20
9. <i>Problems Related to Welded Joints</i>	21
9.1 Cracking	21
9.2 Corrosion	23
9.3 Sigma Phase Formation—High-Temperature Service	24
10. <i>Inspection Methods</i>	24
10.1 Visual Inspection	25
10.2 Hydrostatic Testing	25
10.3 Liquid Penetrant Methods	25
10.4 Radiography	25
10.5 Ultrasonic Methods	25
10.6 Inspection With Magnetic Instruments	25
10.7 Acoustic Emission Testing Methods (AET)	25
10.8 Chemical Spot Testing	25
10.9 Halogen Leak Testing Methods	25
10.10 Mass Spectrometer Testing Method	25
11. <i>Safety and Health</i>	26
11.1 Fumes and Gases	26
11.2 Radiation	26
11.3 Electric Shock	26
11.4 Fire Prevention	26
11.5 Explosion	26
11.6 Burns	26
11.7 Further Information	26
Appendix A—Welding High-Carbon Stainless Steels	27
A1. Introduction	27
A2. Some Factors Governing Casting Material Use	27
Appendix B—Document List	33
Appendix C—Safety and Health	34

List of Tables

Table	page no.
1 — Types of Chromium-Nickel Stainless Steel Available in Piping and Tubing	2
2 — Types of Chromium-Nickel Stainless Steel Castings	2
3 — ASTM Specifications Applicable to Austenitic Stainless Steel Piping and Tubing	3
4 — Electrodes and Welding Rods used in Welding Cast and Wrought Austenitic Stainless Steels	4
5 — Chemical Composition Requirements for Weld Metal from Corrosion-Resisting Steel Covered Welding Electrodes	5
6 — Chemical Composition Requirements for Corrosion-Resisting Steel Welding Rods and Electrodes	7
7 — General Guide for Selecting Welding Electrodes and Rods for Joints in Dissimilar Austenitic Stainless Steel Pipe and Tube	12
8 — Procedure for Welding Open Root with GTAW Argon Shielding and Purge, Dcen	21
9 — Procedure for Welding Consumable Insert with GTAW Argon Shielding and Purge, Dcen	22
10 — Procedure for Welding Open Root with GMAW Gas Shielding and Purge	22
A1 — Filler Metal Selection Guide	31

List of Figures

Figure	page no.
1 — Typical Joint Designs for Welding Austenitic Stainless Steel Pipe	13
2 — Standard Consumable Inserts	15
3 — Typical Sections showing Two Types of Consumable Inserts	16
4 — Preweld Purging of Oxidizing Atmosphere	17
A1 — Procedure for Removal of “Unsound” Areas during Joint Preparation for New HK-40 Type Cast Component	28
A2 — Purging Baffle Assembly	29
A3 — Contour of Weld Crater Inhibits Crater Cracks	30

Recommended Practices for Welding Austenitic Chromium-Nickel Stainless Steel Piping and Tubing

Introduction

The ideal piping system would be a single piece of pipe, so formed, shaped, sized, and directed as to contain or convey the fluid required by the process in which it is involved. For most systems this cannot be. Changes in size, shape, direction, and operating conditions usually preclude such a fabrication. Joints become necessary. Piping systems usually must be made of many different components, and the joints that connect them must be as strong and serviceable as the components themselves. Therefore, engineers and mechanics should try to apply those joining methods which most nearly meet the conditions of one-piece fabrication and also allow for necessary assembly, erection, maintenance, and operation.

Most of the austenitic stainless steels are readily weldable when the proper procedures and techniques are followed. They can be joined by most of the fusion welding processes, and good pipe welders can adapt very quickly from carbon steel or low alloy steel to stainless steel. Orbiting pipe welding machines are also very adaptable to these materials.

The instructions in these recommended practices can be put to use by any competent pipe welder in any good shop or field site. Reasonable care is required, as in any pipe welding operation; however, careful adherence to the procedure requirements will usually produce excellent welds in stainless steel piping and tubing.

1. Material Compositions and Specifications

1.1 Compositions. Chemical composition ranges and type numbers for those stainless steels generally available in wrought piping and tubing are listed in Table 1. These are American Iron and Steel Institute (AISI) Standard Compositions. Chemical composition ranges and designations for five stainless steels generally available as cast

pipe are shown in Table 2. These are included because cast valves and fittings are considered part of a piping system.

The weldability of castings may be somewhat less than that of a wrought stainless steel of the same type. This is because fully austenitic castings have much larger grains than similar wrought material. Consequently, there is less grain boundary area along which to disperse the impurities. As a result, there may be a tendency toward hot cracking when welding some castings. However, proper control of the composition of the casting, to obtain four to ten percent delta ferrite, can prevent hot cracking.

1.2 Specifications. Typical American Society for Testing and Materials (ASTM) specifications covering piping and tubing in both cast and wrought form (seamless or welded) are listed in Table 3. ASTM employs the AISI type numbers for designating the austenitic types. However, the ASTM chemical composition requirements differ slightly from the AISI requirements and will vary slightly in different ASTM specifications. The composition ranges specified for cast tubular products are identical with those of the American Castings Institute (ACI). Specifications for covered welding electrodes and welding rods and electrodes are provided in Tables 4 and 5.

2. Base Metals

2.1 Primary Types (304, 305, 309, and 310). These materials have many applications and are widely used for their corrosion and oxidation resistance, high-temperature strength, and low-temperature properties. However, there are a number of welding-related characteristics that may affect all of these, as noted below.

Types 304 and 305 may become sensitized by welding, depending on their carbon content and the manner in which they are welded, and as a result may require solution annealing to restore immunity to intergranular