

ANSI/AWS D11.2-89 (R2006)
An American National Standard



Guide for Welding Iron Castings



American Welding Society



**ANSI/AWS D11.2-89 (R2006)
An American National Standard**

**Approved by the
American National Standards Institute
July 14, 1988**

Guide for Welding Iron Castings

Prepared by the
American Welding Society (AWS) D11 Committee on Welding Iron Castings

Under the Direction of the
AWS Technical Activities Committee

Approved by the
AWS Board of Directors, March 3, 1988

Abstract

This standard presents briefly the history and metallurgy of cast iron and the welding processes applicable to it.

A newly developed weldability test is described in detail and instructions given for its application in specific cases.

Provision is made for qualification of welding procedures and welders when necessary; quality control practice is also included.



American Welding Society

550 N.W. LeJeune Road, Miami, FL 33126

Table of Contents

	Page No.
<i>Personnel (Reaffirmation)</i>	v
<i>Personnel (Original)</i>	vii
<i>Foreword</i>	ix
<i>List of Tables</i>	xiii
<i>List of Figures</i>	xiv
1. Scope and History	1
1.1 Scope.....	1
1.2 History	1
2. Cast Iron — Its Metallurgy and Weldability	1
2.1 Metallurgy.....	1
2.2 Difficulties in Welding Iron Castings.....	4
2.3 AWS Weldability Test Program.....	6
2.4 Preweld Testing for Weldability.....	11
3. General Considerations When Welding Iron Castings	14
3.1 Base Metal Preparation.....	14
3.2 Joint Design	15
3.3 Heat Input	17
3.4 Preheat	17
3.5 Electrode Manipulation	20
3.6 Peening	21
3.7 Cooling	21
3.8 Postweld Heat Treatment.....	21
4. Gas Processes	23
4.1 Oxyfuel Welding (OFW).....	23
4.2 Flame Spraying of Gray Iron (FLSP).....	27
4.3 Braze Welding	27
5. Arc Welding Processes	30
5.1 General.....	30
5.2 Shielded Metal Arc Welding (SMAW).....	30
5.3 Gas Metal Arc Welding (GMAW)	35
5.4 Flux Cored Arc Welding (FCAW)	37
5.5 Gas Tungsten Arc Welding (GTAW).....	41
5.6 Submerged Arc Welding (SAW).....	44
6. Surfacing and Overlaying	45
6.1 Processes.....	45
6.2 Thermal Spraying	45
6.3 Other Processes.....	47
6.4 Surfacing Materials.....	48
6.5 Technique	50
7. Applications	50
7.1 Casting Defect Repair.....	50
7.2 Repair of Machining Defects.....	51

	Page No.
7.3 Repair of Castings After Service	51
7.4 Fabrication	51
8. Welding Procedure and Performance Qualification.....	51
8.1 General.....	51
8.2 Welding Procedure Qualification	52
8.3 Welding and Welding Operator Performance Qualification	52
9. Quality Control.....	52
9.1 General.....	52
9.2 Quality Control Practices and Procedures	52
9.3 Acceptance Criteria	54
10. Safety and Health	54
10.1 Fumes and Gases	54
10.2 Radiation.....	55
10.3 Electric Shock.....	55
10.4 Fire Prevention.....	55
10.5 Explosion	55
10.6 Burns.....	55
10.7 Further Information	55
Appendix A — Weldability Test	51
A1. Introduction.....	57
A2. Equipment Required	57
A3. Welding Conditions	58
A4. Test Procedure	59
Appendix B — Applications	63
Appendix C — Welding Procedure and Performance Qualification	83
C1. General.....	83
C2. Welding Procedure Qualification	83
C3. Inspection Results Required	95
C4. Welding and Welding Operator Performance Qualification	97
Appendix D — Recommended System for Classification of Welds in Iron Castings, and Associated Quality Levels	105
D1. Classification of Welds in Iron Castings	105
D2. Test Requirements	105
Appendix E — ASME Code Cases.....	109
E1. Case 1867.....	109
E2. Case 1939.....	109
Appendix F — Safety and Health	111

List of Tables

Table	Page No.
1 — Comparison of No-Crack Temperature to Material Type, Strength, and “M” Number	8
2 — Comparison of No-Crack Temperature to Weld and HAZ Hardness	8
3 — Chemical Composition	9
4 — Chemical Composition of Filler Metals	24
5a — Chemical Composition, Rods and Electrodes for Braze Welding Iron Castings	29
5b — Properties and Applications of Braze Welding Filler Metal	29
6 — Chemical Composition of Filler Metals	32
7 — Typical Mechanical Properties of All-Weld-Metal	34
8 — Hardness of Deposited Weld Metal	34
9 — Chemical Composition and Mechanical Property Requirements for Covered Copper-Alloy Welding Electrodes	35
10 — Gas Metal Arc Welding Variables for Nickel-Base Electrodes	38
11A — Chemical Composition Requirements for Bare Filler Metal	39
11B — Mechanical Properties of Weld Metal	39
11C — GMAW Welding Parameters	39
12 — Typical Welding Conditions, FCAW, Nickel-Iron-Manganese Electrodes	42
13 — Typical Current Ranges (DCEN) for Tungsten Electrodes	44
14 — Submerged Arc Welding Recommendations for Nickel-Base Electrodes	45
15 — Surveillance Recommendations for Weld Repairs	53
A1 — Mechanical Properties	59
A2 — Test Results	60
A3 — Hardness Tests on Specimens Welded at No-Crack Temperature	61
A4 — Hardness Tests on Specimens Welded Below No-Crack Temperature	61
A5 — Hardness Tests on Malleable Iron Specimens	61
C1 — Base Metals for Procedure Qualification	84
C2 — Filler Metal Classification	99
D1 — Weld Quality Control Requirements for Welds in Iron Castings	105
D2 — Acceptance Criteria for Magnetic Particle, Dye Penetrant, and Visual Tests	106

List of Figures

Figure	Page No.
1 — Gray Iron Microstructure Showing Random Flake Graphite Distribution in a Matrix of Ferrite and Pearlite	2
2 — White Iron Microstructure Showing Nearly Complete Carbon Solution in a Matrix of Cementite (Iron Carbide)	3
3 — Malleable Iron Microstructure Showing Temper Carbon Nodule Distribution in Ferrite and Pearlite	3
4 — Ductile Iron Microstructure Showing Nodular Graphite Distribution in a Matrix of Ferrite and Pearlite	5
5 — Compacted Graphite Microstructure Showing Mixture of Flake and Nodular Graphite Distribution in a Matrix of Ferrite and Pearlite	5
6 — Grade 80-60-03 Ductile Iron GTAW Spot Weld Specimen	6
7 — Grade 80-60-03 Ductile Iron GTAW Weld Bead Specimen	7
8 — Relation of No-Crack Temperature to C.E. #2 for Several Grades of Iron Castings	10
9 — Gray Iron ASTM A 48, Grade 35 Typical Microstructure Showing As-quenched Weld Metal, Partially Hardened Heat Affected Zone, and Unaffected Base Metal	11
10 — Malleable Iron ASTM A220, Grade 50005 Typical Microstructure of Temper Carbon Nodules, in Coarse Dendritic Matrix	12
11 — Ductile Iron ASTM A536, Grade 100-70-03 Showing Nearly Uniform Nodular Graphite Distribution, Including Isolated Nodules in Weld Metal	12
12 — Ductile Iron ASTM A536, Grade 120-90-02 Showing Uniform Nodular Graphite Distribution	13
13 — Compacted Graphite Showing a Typical Microstructure of the Weld and HAZ	13
14 — Weld Toe Crack in Specimen of Gray Iron Welding Without Filler Metal Using GTAW	14
15 — Photomicrograph of HAZ Weld Toe Crack Shown in Figure 14	14
16 — Suggested Complete Joint Penetration, Single Grooves	16
17 — Suggested Complete Joint Penetration (CJP) and Partial Joint Penetration (PJP), Grooves	18
18 — Groove Designs	19
19 — Groove Face Grooving	19
20 — Studding to Increase Strength at the Weld Interface	20
21 — Joint Design Improvements	21
22 — Fundamentals Involved in Preheating Castings for Welding	22
23 — Block and Cascade Welding Sequences	26
24 — Elements of a Typical Welding Circuit for Shielded Metal Arc Welding	31
25 — Gas Metal Arc Welding Process	36
26 — Gas Metal Arc Welding Equipment	37
27 — Self Shielded Flux Cored Arc Welding Processes	40
28 — Gas Shielded Flux Cored Arc Welding Processes	41
29 — Flux Cored Arc Welding Equipment	42
30 — Gas Tungsten Arc Welding and Equipment Arrangement	43
31 — Automatic Submerged Arc Welding Process	44
32A — Typical Wire Flame Spraying Installation Adaptable to Rod and Cord	46
32B — Cross Section of Typical Wire Rod or Cord Flame Spray Gun	46
33A — Typical Installation of a Powder Flame Spray Process	47
33B — Cross Section of a Powder Flame Spray Gun	47
34A — Arc Spray Components Combined into a Single Unit	48
34B — Cross Section Schematic of an Arc Spray Gun	48
35A — Complete Installation Plasma Spray System	49
35B — Sectional View of Plasma Spraying Torch	49
A1 — Test Block for Gray and Ductile Iron	57
A2 — Test Blocks for Malleable Iron	58

Figure	Page No.
Application No. 1 Foundry Shakeout Table	64
Application No. 2 Ingot Mold Repair	65
Application No. 3 Crane Hoist Drum Repair	66
Application No. 4 Fabrication of Driveshafts	67
Application No. 5 Salvage of Cast Iron Dam Wheels	68
Application No. 6 Repair of Cast Iron Conveyor Sprockets	69
Application No. 7 Repair of Cast Iron Bathtub Die	70
Application No. 8 Salvage of Cast Iron Columns	71
Application No. 9 Fabrication of a Heat Exchanger Header	72
Application No. 10 Salvage of Steel Mill Rolls	73
Application No. 11 Repair of Coupling Plate	74
Application No. 12 Repair of a Cast Iron Lathe Bed	75
Application No. 13 Fabrication of Air Cylinder	76
Application No. 14 Repair of Cast Iron Water Pump Housing	77
Application No. 15 Surfacing of Axial Compressor Rotor	78
Application No. 16 Repair of Broken Cast Iron Motor Support	79
Application No. 17 Repair of Cast Iron Pump Housing	80
Application No. 18 Repair of Cast Iron Gear Housing	81
Application No. 19 Salvage of VTL Table	82
C1 — Position of Groove Welds	88
C2 — Test Positions of Groove Welds	89
C3 — Positions of Test Pipes for Groove Welds	90
C4 — Position of Fillet Welds	91
C5 — Standard Fillet Weldment Test Positions	92
C6 — Groove Weld Procedure Qualification Tests for Soundness and Tensile Properties	94
C7 — Fillet Weld Soundness Test for Procedure Qualification	95
C8 — Pipe Fillet Weld Soundness Test — Procedure and Performance Qualification	96
C9 — Round Tension Specimens	97
C10 — Reduced Section Tensions Specimens	98
C11 — Fillet Weld Soundness Test for Performance Qualification	100

Guide for Welding Iron Castings

1. Scope and History

1.1 Scope. The term *cast iron* encompasses a family of ferrous alloys with a variety of metallurgical, mechanical, and physical properties. The chemical composition and welding requirements of the metals vary within the family. This document discusses the relative weldability of various types of cast irons and the filler metals and processes used to weld them. It recommends the steps for qualification of welding procedures, welding operators and welders, and requirements for the quality of welds. The terms *welding procedure*, *welding operator*, and *welder*, are used as defined in the latest edition of ANSI/AWS A3.0, *Standard Welding Terms and Definitions*.

1.2 History

1.2.1 Types of Iron. Although iron has been used in various forms for over two thousand years, iron castings in the form used today evolved in Europe in the 15th and 16th centuries. The microstructure of medieval castings basically was gray iron with areas of white iron and nonmetallic inclusions. Refinements in foundry practices and melt control resulted in a more uniform structure.

Malleabilizing, a method of increasing the ductility of white cast iron by heat treatment, was first developed in the early 1700's. About a century later, black heart malleable iron was developed.

In the 1940's, ductile (spheroidal graphite) iron was developed. The ductility is improved by spheroidizing the graphite by the addition of magnesium, rare earth elements, or both.

The most recently developed form of cast iron is compacted graphite, a hybrid material with properties between gray and ductile irons.

1.2.2 Welding. Oxyfuel gas and arc welding of cast iron did not gain wide acceptance until early in the 20th century. The first filler metals were cast along with the iron castings so that the compositions were similar. Later, both ferrous and nonferrous (copper or nickel)

base electrodes and rods were developed and are still in use today.

New, more refined welding processes and procedures were developed to extend greatly the number of applications where welding is used. Shielded metal arc (SMAW), gas metal arc (GMAW), flux cored arc (FCAW) and submerged arc (SAW) welding currently are popular arc welding processes.

Gas tungsten arc (GTAW) and proprietary processes are used in a variety of applications.

2. Cast Iron — Its Metallurgy and Weldability

2.1 Metallurgy

2.1.1 General. Cast iron may be described as an alloy of iron, carbon and silicon. All commercially produced irons also contain manganese. They may be alloyed with nickel, chromium, copper, molybdenum, tin, antimony, vanadium, and other elements. The alloying elements may be present individually or in combination.

The carbon content is in excess of the quantity that can be retained in solid solution by austenite. Thus, during solidification, a portion of the carbon separates from the melt as either iron carbide (Fe_3C) or graphite. If the cooling rate is rapid, the carbon rich phase will be iron carbide. Elemental carbon (graphite) precipitates if the cooling rate is slow enough. The type of carbon constituent and its shape (if graphite), in part, determines the type and properties of cast iron. The phases present in the matrix also affect the properties; therefore, the entire microstructure of the casting must be considered when planning a suitable welding procedure.

2.1.2 Gray Iron. The most commonly used form of cast iron is gray iron. In this material, the excess carbon precipitates as flakes of graphite in a matrix of ferrite, pearlite, or a mixture of the two microconstituents (see Figure 1). The resultant product has moderate strength,