



**American Water Works
Association**

ANSI/AWWA B100-09
(Revision of ANSI/AWWA B100-01)

The Authoritative Resource on Safe Water®

AWWA Standard

Granular Filter Material



Effective date: March 1, 2010.

First edition approved by AWWA Board of Directors Nov. 15, 1948.

This edition approved Jan. 25, 2009.

Approved by American National Standards Institute Jan. 14, 2010.

6666 West Quincy Avenue
Denver, CO 80235-3098
T 800.926.7337
www.awwa.org

Advocacy
Communications
Conferences
Education and Training
Science and Technology
Sections

AWWA Standard

This document is an American Water Works Association (AWWA) standard. It is not a specification. AWWA standards describe minimum requirements and do not contain all of the engineering and administrative information normally contained in specifications. The AWWA standards usually contain options that must be evaluated by the user of the standard. Until each optional feature is specified by the user, the product or service is not fully defined. AWWA publication of a standard does not constitute endorsement of any product or product type, nor does AWWA test, certify, or approve any product. The use of AWWA standards is entirely voluntary. This standard does not supersede or take precedence over or displace any applicable law, regulation, or codes of any governmental authority. AWWA standards are intended to represent a consensus of the water supply industry that the product described will provide satisfactory service. When AWWA revises or withdraws this standard, an official notice of action will be placed on the first page of the classified advertising section of *Journal AWWA*. The action becomes effective on the first day of the month following the month of *Journal AWWA* publication of the official notice.

American National Standard

An American National Standard implies a consensus of those substantially concerned with its scope and provisions. An American National Standard is intended as a guide to aid the manufacturer, the consumer, and the general public. The existence of an American National Standard does not in any respect preclude anyone, whether that person has approved the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not conforming to the standard. American National Standards are subject to periodic review, and users are cautioned to obtain the latest editions. Producers of goods made in conformity with an American National Standard are encouraged to state on their own responsibility in advertising and promotional materials or on tags or labels that the goods are produced in conformity with particular American National Standards.

CAUTION NOTICE: The American National Standards Institute (ANSI) approval date on the front cover of this standard indicates completion of the ANSI approval process. This American National Standard may be revised or withdrawn at any time. ANSI procedures require that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of publication. Purchasers of American National Standards may receive current information on all standards by calling or writing the American National Standards Institute, 25 West 43rd Street, Fourth Floor, New York, NY 10036; (212) 642-4900.

All rights reserved. No part of this publication may be reproduced or transmitted in any form or by any means, electronic or mechanical, including photocopy, recording, or any information or retrieval system, except in the form of brief excerpts or quotations for review purposes, without the written permission of the publisher.

Copyright © 2010 by American Water Works Association
Printed in USA

Committee Personnel

The AWWA Standards Committee on Filtering Materials, which reviewed and approved this standard, had the following personnel at the time of approval:

William W. Allis, Jr., *Chair*

R. Lee Roberts, *Vice-Chair*

General Interest Members

G.S. Ajy, River to Tap, Roswell, Ga.	(AWWA)
W.W. Allis Jr., Black & Veatch Corporation, Philadelphia, Pa.	(AWWA)
S.L. Bishop, Metcalf & Eddy Inc., Reading, Mass.	(NEWWA)
R.C. Cheng,* Standards Council Liaison, Long Beach Water Department, Long Beach, Calif.	(AWWA)
W.J. Conlon, Parsons Brinkerhoff Inc., Tampa, Fla.	(AWWA)
R.E. Hubel, Water Counsel LLC, Richmond Hill, Ga.	(AWWA)
S. Kawamura, KWE Inc., San Gabriel, Calif.	(AWWA)
P.L. Kline,* Standards Engineer Liaison, AWWA, Denver, Colo.	(AWWA)
D.S. Koch, Black & Veatch Corporation, Grand Rapids, Mich.	(AWWA)
R.R. Rogers, CDM, Chicago, Ill.	(AWWA)

Producer Members

S.L. Butterworth, Calgon Carbon Corporation, Pittsburgh, Pa.	(AWWA)
J.J. Durkin Jr., Mountaintop Anthracite, Mountain Top, Pa.	(AWWA)
M.A. Eggleston, Unifilt Corporation, Wilkes-Barre, Pa.	(AWWA)
T.M. Getting, ITT Water & Wastewater, Zelienople, Pa.	(AWWA)
J.L. Meltzer, Northern Filter Media Inc., Muscatine, Iowa	(AWWA)
D.M. Oreskovich, Red Flint Sand & Gravel, Eau Claire, Wisc.	(AWWA)
R.L. Roberts, Roberts Filter Group, Darby, Pa.	(AWWA)

* Liaison, nonvoting

User Members

M.G. Barsotti, Champlain Water District, South Burlington, Vt.	(AWWA)
S.E. Creel, American Water, Voorhees, N.J.	(AWWA)
T. Meckes, City Water Light & Power, Springfield, Ill.	(AWWA)
C.M. Triolo, Fairfax County Water Authority, Fairfax, Va.	(AWWA)
K.T. Walsh, Connecticut Water Company, Clinton, Conn.	(AWWA)
L.K. Willett, Hoover Dam Water Treatment System, Boulder City, Nev.	(AWWA)

Contents

All AWWA standards follow the general format indicated subsequently. Some variations from this format may be found in a particular standard.

SEC.	PAGE	SEC.	PAGE
Foreword		1.3	Application..... 1
I	Introduction..... vii	2	References 2
I.A	Background..... vii	3	Definitions 2
I.B	History..... vii	4	Requirements
I.C	Acceptance..... vii	4.1	Physical Requirements..... 4
II	Special Issues..... viii	4.2	Chemical Requirements 7
II.A	Source of Supply..... viii	4.3	Impurities..... 7
II.B	Filter Media ix	4.4	Placing Filter Material 7
II.C	Particle Size Distribution..... ix	4.5	Preparing Filter for Service 10
II.D	Filter Media Support Gravel ix	4.6	Replenishing Filter Media in Existing Filter Bed..... 12
II.E	Acid Solubility..... x	5	Verification
II.F	Anthracite Quality Test..... x	5.1	Approval Sampling..... 13
II.G	Bulk Shipment x	5.2	Sampling..... 13
II.H	Media Records x	5.3	Test Procedures—General..... 16
II.I	Removal of Filter Material and Reuse..... xi	6	Delivery
II.J	Possible Adverse Effects on Submerged Concrete Walls in Filter Box xi	6.1	Marking..... 22
III	Use of This Standard xii	6.2	Packaging and Shipping 22
III.A	Purchaser Options and Alternatives xii	6.3	Affidavit of Compliance 23
III.B	Modification to Standard xii	Appendixes	
IV	Major Revisions..... xiii	A	Bibliography 25
V	Comments xiii	B	Sieves 29
		C	Particle Sizes..... 33
		D	Filter Media Support Gravel Size and Layer Depth 35
Standard		Figure	
1	General	1	Specific Gravity Test Apparatus..... 18
1.1	Scope 1		
1.2	Purpose 1		

SEC.	PAGE	SEC.	PAGE
Tables			
1	Specific Gravity and Acid Solubility Levels for Filter Media.....	4	
2	Appropriate Fluidization Backwash Rates.....	8	
3	Minimum Size of Composite Sample	14	
4	Sampling of Bagged Filter Material	14	
5	Minimum Sample and Acid Quantities for Acid-Solubility Tests.....	16	
6	Minimum Sample Size for Sieve Analyses	19	
7	Maximum Allowable Quantity of Material Retained on an Individual Sieve.....	20	
B.1	Nominal Dimensions, Permissible Variations for Wire Cloth of Standard Test Sieves (USA) Standard Series.....	30	
D.1	Gravel Layers for Two Sizes of Fine Filter Media and Two Sizes of Underdrain Orifices	36	

Foreword

This foreword is for information only and is not a part of ANSI/AWWA B100.

I. Introduction.

I.A. *Background.* The purpose of ANSI/AWWA B100 is to provide purchasers with a standard for the purchase and installation of granular filter material (filter material).

A wealth of information on innovations in filter design is available from various sources, including *Journal AWWA*, *Water Treatment Plant Design*,[†] and references found in appendix A. These sources include design parameters for filters using single and multiple media. As a result, ANSI/AWWA B100 makes reference to filter design only as the design relates to the filter materials used. ANSI/AWWA B604, Standard for Granular Activated Carbon, should be consulted when using GAC as a filter medium, because GAC is not specifically covered in ANSI/AWWA B100.

I.B. *History.* The AWWA Standard for Filtering Material was approved as tentative by the AWWA Board of Directors on Nov. 15, 1948, and as a standard on Jan. 16, 1950. Revisions were approved on June 2, 1953, Jan. 31, 1972, June 20, 1980, Jan. 29, 1989, Dec. 1, 1996, and June 17, 2001. The original standard was approved and promulgated in the course of activities of the Water Purification Division and under jurisdiction of the Committee on Water Works Practice. This edition was approved on Jan. 25, 2009.

I.C. *Acceptance.* In May 1985, the US Environmental Protection Agency (USEPA) entered into a cooperative agreement with a consortium led by NSF International (NSF) to develop voluntary third-party consensus standards and a certification program for direct and indirect drinking water additives. Other members of the original consortium included the Water Research Foundation and the Conference of State Health and Environmental Managers (COSHEM). The American Water Works Association (AWWA) and the Association of State Drinking Water Administrators (ASDWA) joined later.

In the United States, authority to regulate products for use in, or in contact with, drinking water rests with individual states.[‡] Local agencies may choose to impose requirements more stringent than those required by the state. To evaluate the health

* American National Standards Institute, 25 West 43rd Street, Fourth Floor, New York, NY 10036.

† *Water Treatment Plant Design*, 4th Ed., AWWA, ASCE, and CSSE, Denver, Colo. (2004).

‡ Persons outside the United States should contact the appropriate authority having jurisdiction.

effects of products and drinking water additives from such products, state and local agencies may use various references, including

1. An advisory program formerly administered by USEPA, Office of Drinking Water, discontinued on Apr. 7, 1990.
2. Specific policies of the state or local agency.
3. Two standards developed under the direction of NSF, NSF*/ANSI 60, Drinking Water Treatment Chemicals—Health Effects, and NSF/ANSI 61, Drinking Water System Components—Health Effects.
4. Other references, including AWWA standards, *Food Chemicals Codex*, *Water Chemicals Codex*,[†] and other standards considered appropriate by the state or local agency.

Various certification organizations may be involved in certifying products in accordance with NSF/ANSI 61. Individual states or local agencies have authority to accept or accredit certification organizations within their jurisdiction. Accreditation of certification organizations may vary from jurisdiction to jurisdiction.

Annex A, “Toxicology Review and Evaluation Procedures,” to NSF/ANSI 61 does not stipulate a maximum allowable level (MAL) of a contaminant for substances not regulated by a USEPA final maximum contaminant level (MCL). The MALs of an unspecified list of “unregulated contaminants” are based on toxicity testing guidelines (noncarcinogens) and risk characterization methodology (carcinogens). Use of Annex A procedures may not always be identical, depending on the certifier.

ANSI/AWWA B100 does not address additives requirements. Thus, users of this standard should consult the appropriate state or local agency having jurisdiction in order to

1. Determine additives requirements, including applicable standards.
2. Determine the status of certifications by parties offering to certify products for contact with, or treatment of, drinking water.
3. Determine current information on product certification.

II. Special Issues.

II.A. *Source of Supply.* Filter material, such as silica sand, high-density sand, granular activated carbon, or anthracite, as well as support gravel, should be obtained from sources that can certify the site-specific manufacturing facilities are

* NSF International, 789 N. Dixboro Road, Ann Arbor, MI 48105.

† Both publications available from National Academy of Sciences, 500 Fifth Street N.W., Washington, DC 20001.

expressly qualified to produce and supply these materials for water treatment plants, in compliance with the ANSI/AWWA B100 standard.

II.B. *Filter Media.* Filter media is the component of a filter that removes particulate matter from the water during the filtration process. This standard describes anthracite, silica sand, high-density sand, and filter media support gravel material.

High specific gravity (high-density) filter media consisting of garnet, ilmenite, hematite, magnetite, or associated minerals of those ores are used by some utilities in an attempt to remove more suspended solids at higher filtration rates. This small, high-density media remains as a layer under the silica sand as a result of particle size and specific gravity differences in the same way that silica sand remains separated from overlaid anthracite in a dual-media filter. Some intermixing usually occurs at the interface between the layers.

Garnet refers to several different minerals (mostly almandite and andradite) that are silicates of iron, aluminum, and calcium mixtures. However, garnet could also be grossularite, spessartite, and uvarovite, the latter being a chromium mineral. Ilmenite is an iron titanium mineral, which invariably is associated with hematite and magnetite, both iron oxides.

Properties of granular activated carbon when used as a filter medium are described in ANSI/AWWA B604, Standard for Granular Activated Carbon. Properties of media used in precoat filters (such as diatomaceous earth) can be found in ANSI/AWWA B101, Precoat Filter Media. Synthetic media and membrane filters are not included in this standard.

Sand or anthracite filter media used in a wide range of bed depths and particle sizes have produced satisfactory results. Selection of the bed depth, particle size, and particle density of each media layer to be used in any particular filter is the responsibility of the designer and should be done with careful consideration of raw water conditions, plant pretreatment facilities, and filter backwash system design.

If questions arise regarding the authenticity of the anthracite filter medium relative to the standard, the procedures and calculations for anthracite verification can be found in ASTM D388. The results of the verification shall be reported as anthracite or nonanthracite.

II.C. *Particle Size Distribution.* There are two methods of classifying particle size distribution. The designer and end user are cautioned not to use both methods simultaneously. These methods are described in appendix C of this standard.

II.D. *Filter Media Support Gravel.* If the openings in the underdrain system are larger than the filter media, a system of supporting material is required to prevent the filter media from entering and blocking the underdrain system and to help distribute

backwash water evenly. Traditionally, layers of gravel have been used. The size and depth of the gravel layers must be selected to achieve both objectives and also ensure that the gravel will not be displaced by the rising wash water. Guidelines for support gravel size and layer depths are included in appendix D. It should be noted that underdrains are available which do not require the use of support gravel.

II.E. *Acid Solubility.* An acid-solubility test is included in this standard to provide a means of measuring acid-soluble minerals or other impurities that may be present in the filter material. The limits for acid solubility given in this standard are based on tests of filter material with proven performances in a wide range of water treatment applications. Acid-solubility limits are necessary to ensure against substantial quantities of detrimental minerals or other substances in the filter material and also to ensure against substantial solution of filter material in acidic waters or during an acid cleaning. In many cases, the principal acid-soluble impurity in filter silica sand and gravel is calcium carbonate (limestone).

II.F. *Anthracite Quality Test.* ANSI/AWWA B100 defines anthracite, as used herein, as anthracite coal in accordance with ASTM D388. The intent of this reference and definition is to provide the capability to verify the specified filter media is anthracite coal and not bituminous coal.

II.G. *Bulk Shipment.* The issue of protecting filter material from contamination during shipment is addressed in this standard.

Bulk shipment is not recommended; however, when trucks or railcars are specified for hauling a bulk shipment of filter material, it is recommended that an impermeable plastic liner be used, because the trucks or railcars may be contaminated from hauling previous bulk material.

Vibration during transit will result in segregation of the filter material, with the coarser material migrating toward the top. If one compartment of the bulk shipment is divided between two or more filters or filter halves, the media is likely to have different size gradations and consequently perform differently. Therefore, if bulk shipment is allowed, the container should be required to be compartmentalized so that each compartment fills no more than one filter cell. If it is specified, representative filter media samples for analysis can be obtained at the point of production or loading. If the purchaser requires sampling at the point of installation, this requirement should be stated in the specifications.

II.H. *Media Records.* Users are encouraged to maintain records of the physical characteristics and chemical composition of filter material installed in filters. For limits on undesirable impurities, refer to NSF/ANSI 61 and Sec. I.C in the foreword.

II.I. *Removal of Filter Material and Reuse.* Occasionally, there are circumstances, such as a blown filter, an underdrain problem, or a header-lateral distribution system problem, that will cause the necessity for removal of filter material from the filter cell and replacement or reuse of the material. Unless the filter material is new or found by visual inspection to be in near-original condition, reuse is discouraged because the material will be worn to some degree, may be coated, may be damaged or contaminated during handling, and may create potential filtering problems if not properly combined with new material to obtain a desired gradation. In addition, removed material should not be installed in another filter plant without proper investigation of process and filter gradation requirements.

Removal may be performed hydraulically or by hand. Extreme care must be taken not to damage filter cell components, such as the underdrain or header lateral system. If any component is damaged, it should be replaced immediately. If the filter material is to be replaced, it should be disposed of in accordance with applicable regulations. If the filter material is to be reused, extreme care must be taken not to damage or contaminate it. The filter material should be stored in clean containers or on clean reinforced impervious tarpaulins that have not been used for any other purpose. The containers or tarpaulins shall then be covered with a durable opaque material to protect the filter material from the weather and air pollution. If any filter material becomes contaminated, it shall be replaced or cleaned to the user's satisfaction.

Disturbed gravel should be replaced in its proper gradation prior to reuse, and should be sieved to its original gradations. Filter media components (high-density sand, silica sand, or anthracite) will be intermixed and should be separated through sieving or other methods. A small quantity of the filter media may still remain intermixed but should re-stratify during backwashing. Any additional high-density sand and silica sand required should have the same sizing characteristics as the originally specified sands. Anthracite to be reused should have representative samples taken and tested to determine its uniformity coefficient and effective size so that any additional anthracite required can be properly sized to provide a combined anthracite bed meeting original user specifications.

Placement of the filter material in the filter cell, backwashing, and disinfection should be in accordance with procedures stated in this standard. Reuse of GAC does not apply to this standard. See ANSI/AWWA B604, Granular Activated Carbon, for reuse requirements.

II.J. *Possible Adverse Effects on Submerged Concrete Walls in Filter Box.* Aggressive waters have been identified as being responsible for attacking

submerged surfaces of concrete structures. Filter backwashing, including surface wash, may be responsible for accelerating this action by removing loose or softened materials at the surface of the concrete in filter boxes. The engineer may want to evaluate the need to provide a protective coating on submerged surfaces of concrete based on the quality of the water being filtered.

III. Use of This Standard. It is the responsibility of the user of an AWWA standard to determine that the products described in that standard are suitable for use in the particular application being considered.

III.A. Purchaser Options and Alternatives. The following items should be covered by the purchaser:

1. Standard used—that is, ANSI/AWWA B100, Granular Filter Material, of latest revision.
2. Whether compliance with NSF/ANSI 60, Drinking Water Treatment Chemicals—Health Effects, and NSF/ANSI 61, Drinking Water System Components—Health Effects, is required.
3. Method of measurement and payment, and whether this project covers providing filter material only, or providing and placement of the materials and preparation for service.
4. Whether an affidavit of compliance is required or whether the purchaser will select a representative to inspect supply for compliance with this standard.
5. Sizes, types, and characteristics of filter material required and quantities of each (foreword II.B and II.C, Sec. 4.1.1, and Sec. 4.1.2). If the supplier, manufacturer, or constructor is to be held responsible for meeting particle size for filter media in-place, the supplier, manufacturer, or constructor should supervise the transportation, handling, on-site storage, placement, and field preparation of the filter media for sampling. This includes backwashing of filter media prior to sampling.
6. Method of placing the material, if there is a preference (Sec. 4.4.2).
7. Method of checking elevation of top surface of each layer, if there is a preference (Sec. 4.4.2.5).
8. Whether representative samples are required before shipment (Sec. 5.1) or in-place (Sec. 4.5.2.4).
9. Method of disinfecting (Sec. 4.5.3) and who will perform the disinfection procedure.

III.B. Modification to Standard. Any modification to the provisions, definitions, or terminology in this standard must be provided by the purchaser.

IV. Major Revisions. Major revisions made to the standard in this edition include the following:

1. Added definition of anthracite in accordance with ASTM D388.
2. Added Table 7 to clarify maximum sample sizes allowed on individual sieves during sieve analysis.
3. Added references within appendix A—Bibliography.
4. Added appendix C with language related to particle size distribution classification that was in the foreword of the previous revision to the standard.
5. Added appendix D with language related to Filter Media Support Gravel Size and Layer Depth that was in the foreword of the previous revision.

V. Comments. If you have any comments or questions about this standard, please call the AWWA Volunteer and Technical Support Group, at 303.794.7711, FAX at 303.795.7603, write to the group at 6666 West Quincy Avenue, Denver, CO 80235-3098, or e-mail the group at standards@awwa.org.

This page intentionally blank.



**American Water Works
Association**

AWWA Standard

Granular Filter Material

SECTION 1: GENERAL

Sec. 1.1 Scope

This standard describes gravel, high-density gravel, silica sand, high-density media, anthracite filter materials, and the placement of the materials in filters for water supply service application. ANSI/AWWA B604, Standard for Granular Activated Carbon, addresses use of GAC as a filter medium and as an adsorbent.

Sec. 1.2 Purpose

The purpose of this standard is to provide purchasers with a standard for purchasing and installing granular filter material (filter material) and is not a guide for filter design.

Sec. 1.3 Application

This standard can be referenced in specifications for purchasing and receiving filter material and can be used as a guide for testing the physical and chemical properties of filter material samples. The stipulations of this standard apply when this document has been referenced, and then only to filter materials used in the treatment of drinking water supplies.