



**American Water Works
Association**

ANSI/AWWA B201-08
(Revision of ANSI/AWWA B201-03)

The Authoritative Resource on Safe Water®

AWWA Standard

Soda Ash



Effective date: August 1, 2008.
First edition approved by AWWA Board of Directors July 1, 1949.
This edition approved Jan. 27, 2008.
Approved by American National Standards Institute May 22, 2008.

6666 West Quincy Avenue
Denver, CO 80235-3098
T 800.926.7337
www.awwa.org

Advocacy
Communications
Conferences
Education and Training
Science and Technology
Sections

AWWA Standard

This document is an American Water Works Association (AWWA) standard. It is not a specification. AWWA standards describe minimum requirements and do not contain all of the engineering and administrative information normally contained in specifications. The AWWA standards usually contain options that must be evaluated by the user of the standard. Until each optional feature is specified by the user, the product or service is not fully defined. AWWA publication of a standard does not constitute endorsement of any product or product type, nor does AWWA test, certify, or approve any product. The use of AWWA standards is entirely voluntary. This standard does not supersede or take precedence over or displace any applicable law, regulation, or codes of any governmental authority. AWWA standards are intended to represent a consensus of the water supply industry that the product described will provide satisfactory service. When AWWA revises or withdraws this standard, an official notice of action will be placed on the first page of the classified advertising section of *Journal AWWA*. The action becomes effective on the first day of the month following the month of *Journal AWWA* publication of the official notice.

American National Standard

An American National Standard implies a consensus of those substantially concerned with its scope and provisions. An American National Standard is intended as a guide to aid the manufacturer, the consumer, and the general public. The existence of an American National Standard does not in any respect preclude anyone, whether that person has approved the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not conforming to the standard. American National Standards are subject to periodic review, and users are cautioned to obtain the latest editions. Producers of goods made in conformity with an American National Standard are encouraged to state on their own responsibility in advertising and promotional materials or on tags or labels that the goods are produced in conformity with particular American National Standards.

Caution Notice: The American National Standards Institute (ANSI) approval date on the front cover of this standard indicates completion of the ANSI approval process. This American National Standard may be revised or withdrawn at any time. ANSI procedures require that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of publication. Purchasers of American National Standards may receive current information on all standards by calling or writing the American National Standards Institute, 25 West 43rd Street, Fourth Floor, New York, NY 10036; (212) 642-4900.

All rights reserved. No part of this publication may be reproduced or transmitted in any form or by any means, electronic or mechanical, including photocopy, recording, or any information or retrieval system, except in the form of brief excerpts or quotations for review purposes, without the written permission of the publisher.

Copyright © 2008 by American Water Works Association
Printed in USA

Committee Personnel

The AWWA Standards Committee on Softening and Conditioning Chemicals, which reviewed and approved this standard, had the following personnel at the time of approval:

Clyde R. Dugan, *Chair*

General Interest Members

W.J. Conlon, Doosan Hydro Technology, Tampa, Fla.	(AWWA)
T.O. Crowley, Lee's Summit, Mo.	(AWWA)
R.W. Green,* Standards Council Liaison, Water Trax Inc., Vancouver, B.C.	(AWWA)
S.J. Posavec,* Standards Group Liaison, AWWA, Denver, Colo.	(AWWA)
B.H. Wilder, Daytona Beach, Fla.	(AWWA)
M.H. Winegard, Consoer Townsend Envirodyne, Wheaton, Ill.	(AWWA)

Producer Members

J. Althouse, Dow Chemical Company, Ludington, Mich.	(AWWA)
E.W. Coyner, National Lime Association, Arlington, Va.	(AWWA)
W.B. Huebner, Mine Hill, N.J.	(AWWA)
J.M. Shepard, Middletown, Del.	(AWWA)

User Members

I. Alvarez,† John Preston Water Plant, Hialeah, Fla.	(AWWA)
C.R. Dugan, Bath, Mich.	(AWWA)
P.M. Marchand, Providence Water Supply Board, Providence, R.I.	(NEWWA)
G.C. Rosati, City of Mankato Public Utilities, Mankato, Minn.	(AWWA)
A.T. Segars, Miami–Dade Water & Sewer Department, Hialeah, Fla.	(AWWA)
J.C. Thurrott, City of Daytona Beach, Daytona Beach, Fla.	(AWWA)
D.A. Visintainer, City of St. Louis Water Division, St. Louis, Mo.	(AWWA)

* Liaison, nonvoting

† Alternate

This page intentionally blank.

Contents

All AWWA standards follow the general format indicated subsequently. Some variations from this format may be found in a particular standard.

SEC.	PAGE	SEC.	PAGE
<i>Foreword</i>		3	Definitions..... 2
I	Introduction..... vii	4	Requirements
I.A	Background..... vii	4.1	Materials 3
I.B	History..... vii	4.2	Physical Requirements..... 3
I.C	Acceptance vii	4.3	Chemical Composition 3
II	Special Issues viii	4.4	Impurities..... 3
III	Use of This Standard x	5	Verification
III.A	Purchaser Options and Alternatives. x	5.1	Sampling..... 4
III.B	Modification to Standard x	5.2	Apparent Density 4
IV	Major Revisions..... x	5.3	Insoluble Matter..... 5
V	Comments x	5.4	Total Available Alkali..... 5
<i>Standard</i>		5.5	Notice of Nonconformance..... 6
1	General	6	Delivery
1.1	Scope 1	6.1	Marking 7
1.2	Purpose 1	6.2	Packaging and Shipping 7
1.3	Application..... 1	6.3	Affidavit of Compliance 8
2	References..... 2		

This page intentionally blank.

Foreword

This foreword is for information only and is not a part of ANSI/AWWA B201.

I. Introduction.

I.A. *Background.* Soda ash is the common name for the technical grades of anhydrous sodium carbonate (Na_2CO_3). Light and dense soda ash differ in physical characteristics only, such as density (weight of unit volume), angle of repose, and size and shape of particles. Light soda ash is a powder; dense soda ash is granular.

Soda ash is an anhydrous material having a sodium carbonate content of more than 99 percent and a sodium oxide (Na_2O) equivalent of more than 57.9 percent. Sodium carbonate, although readily soluble in water, has the unusual characteristic of attaining maximum solubility at 95.7°F (35.4°C). At this temperature, 100 parts of water dissolve 49.7 parts of sodium carbonate. The solubility of sodium carbonate decreases at temperatures above and below 95.7°F (35.4°C).

I.B. *History.* The first edition of this standard for soda ash was prepared under the direction of the AWWA Water Purification Division. The standard was approved by the Executive Committee of the Water Purification Division and by the Water Works Practice Committee, and received approval of the AWWA Board of Directors on July 1, 1949. Additional reviews resulted in an edited copy that was reaffirmed and approved as "Tentative" by the AWWA Board of Directors on Oct. 15, 1951. The initial document was made standard on May 15, 1953. This standard was revised by the AWWA Standards Committee on Softening and Conditioning Chemicals. Subsequent editions of AWWA B201 were approved on Jan. 26, 1959; Jan. 28, 1974; Jan. 28, 1980; June 14, 1987; Jan. 26, 1992; Jan. 25, 1998; and Jan. 19, 2003. This edition was approved on January 27, 2008.

I.C. *Acceptance.* In May 1985, the US Environmental Protection Agency (USEPA) entered into a cooperative agreement with a consortium led by NSF International (NSF) to develop voluntary third-party consensus standards and a certification program for direct and indirect drinking water additives. Other members of the original consortium included the American Water Works Association Research Foundation (AwwaRF) and the Conference of State Health and Environmental Managers (COSHEM). The American Water Works Association (AWWA) and the Association of State Drinking Water Administrators (ASDWA) joined later.

In the United States, authority to regulate products for use in, or in contact with, drinking water rests with individual states.* Local agencies may choose to impose requirements more stringent than those required by the state. To evaluate the health effects of products and drinking water additives from such products, state and local agencies may use various references, including a standard developed under the direction of NSF, NSF†/ANSI‡ 60, Drinking Water Treatment Chemicals—Health Effects.

Various certification organizations may be involved in certifying products in accordance with NSF/ANSI 60. Individual states or local agencies have authority to accept or accredit certification organizations within their jurisdiction. Accreditation of certification organizations may vary from jurisdiction to jurisdiction.

Annex A, “Toxicology Review and Evaluation Procedures,” to NSF/ANSI 60 does not stipulate a maximum allowable level (MAL) of a contaminant for substances not regulated by a USEPA final maximum contaminant level (MCL). The MALs of an unspecified list of “unregulated contaminants” are based on toxicity testing guidelines (noncarcinogens) and risk characterization methodology (carcinogens). Use of Annex A procedures may not always be identical, depending on the certifier.

ANSI/AWWA B201 addresses additives requirements in Sec. 4.4 of the standard. The transfer of contaminants from chemicals to processed water or the residual solids is becoming a problem of great concern. The language in Sec. 4.4.2 is a recommendation only for direct additives used in the treatment of potable water to be certified by an accredited certification organization in accordance with NSF/ANSI 60, Drinking Water Treatment Chemicals—Health Effects. However, users of the standard may opt to make this certification a requirement for the product. Users of this standard should also consult the appropriate state or local agency having jurisdiction in order to

1. Determine additives requirements, including applicable standards.
2. Determine the status of certifications by parties offering to certify products for contact with, or treatment of, drinking water.
3. Determine current information on product certification.

II. Special Issues. Soda ash is usually shipped in bulk or in 100-lb (45-kg) multiwall paper bags, although it is also available in drums and barrels. The material can be readily handled mechanically by screw or belt conveyors, bucket elevators, or pneumatic systems. Soda ash should be stored in a dry, cool place with minimal

* Persons outside the United States should contact the appropriate authority having jurisdiction.

† NSF International, 789 N. Dixboro Rd., Ann Arbor, MI 48105.

‡ American National Standards Institute, 25 West 43rd Street, Fourth Floor, New York, NY 10036.

exposure to moisture and air. With prolonged storage, soda ash has a tendency to lump and becomes difficult to handle and dissolve.

Soda ash is normally fed into water being treated using volumetric or gravimetric mechanical feeders equipped with dissolving chambers. Less frequently, solution feeding is used. The solution is prepared in tanks and fed by metering pumps.

Soda ash can also be stored in a tank as a slurry with a concentrated 30 percent solution being withdrawn from the upper portion of the tank for application to the treatment process. This method requires much less storage space, because the dry soda ash has a bulk density of 35 lb/ft³ (560 kg/m³). Monohydrate slurries have bulk densities ranging from 83 lb/ft³ to 117 lb/ft³ (1,328 kg/m³ to 1,872 kg/m³). Dry soda ash bulk densities range from 33 lb/ft³ to 68 lb/ft³ (560 kg/m³ to 1,088 kg/m³).

Soda ash is a relatively harmless chemical and, under normal conditions, has no marked effects on skin, the respiratory system, or clothing. It is neither explosive nor inflammable, and it is not classified as a dangerous substance.

Soda ash may produce a temporary irritation of the respiratory system, but the symptoms will disappear once contact with soda ash is discontinued. Persons handling soda ash should be equipped with goggles and dust respirators when dustiness is prevalent. Eye irritation should be treated by flushing the affected eye with tap water for 15 min or longer. Any condition of prolonged irritation should be referred to a physician for treatment.

Individuals who are particularly sensitive to alkaline materials or who have a pre-existing skin disease may develop dermatitis when working with soda ash. It is advisable to use a protective agent, such as an ointment or cream, to prevent this condition. Normal skin irritations can be relieved by bathing the affected parts in a 5 percent boric acid solution.

Every effort should be made to avoid the simultaneous presence of soda ash and lime dust. The combination of these chemicals in the presence of moisture or perspiration will cause the formation of irritating caustic soda. Where both soda ash and lime are used, workers exposed to one chemical should carefully wash it away and remove its dust from clothing before working in the presence of the other chemical.

Workers entering storage bins or silos containing soda ash should always wear approved safety belts and connecting ropes to facilitate rescue in the event the soda ash shifts or slides. In addition, workers should be in constant communication with someone stationed outside the storage facility.

III. Use of This Standard. It is the responsibility of the user of an AWWA standard to determine that the products described in that standard are suitable for use in the particular application being considered.

III.A. *Purchaser Options and Alternatives.* The following items should be covered by the purchaser:

1. Standard used—that is, ANSI/AWWA B201, Soda Ash, of latest revision.
2. Quantity required.
3. Whether compliance with NSF/ANSI 60, Drinking Water Treatment Chemicals—Health Effects, is required.
4. Details of other federal, state or provincial, and local requirements (Sec. 4.1).
5. Density required (Sec. 4.2).
6. Form of shipment—bulk or package, type, and size (Sec. 6.2.1).
7. Affidavit of compliance, if required (Sec. 6.3).
8. Whether alternative security measures have been adopted to replace or augment the security measures set out in Sec. 6.2.4 and Sec. 6.2.5.
9. Whether the purchaser will reject product from containers or packaging with missing or damaged seals. The purchaser may reject product from bulk containers or packages with missing or damaged seals unless the purchaser's tests of representative samples, conducted in accordance with Sec. 5.2, 5.3, and 5.4, demonstrate that the product meets specifications. Failure to meet specifications or the absence of, or irregularities in, seals may be sufficient cause to reject the shipment.

III.B. *Modification to Standard.* Any modification to the provisions, definitions, or terminology in this standard must be provided by the purchaser.

IV. Major Revisions. Major revisions made to the standard in this edition include the following:

1. Inclusion of a requirement for compliance with the Safe Drinking Water Act and other federal regulations (Sec. 4.1).
2. Inclusion of a requirement for tamper-evident packaging (Sec. 6.2.4 and 6.2.5).

V. Comments. If you have any comments or questions about this standard, please call the AWWA Volunteer and Technical Support Group at 303.794.7711, FAX at 303.795.7603, write to the group at 6666 West Quincy Avenue, Denver, CO 80235-3098, or e-mail at standards@awwa.org.



**American Water Works
Association**

ANSI/AWWA B201-08
(Revision of ANSI/AWWA B201-03)

AWWA Standard

Soda Ash

SECTION 1: GENERAL

Sec. 1.1 Scope

This standard describes soda ash for use in the treatment of municipal and industrial water supplies.

Sec. 1.2 Purpose

The purpose of this standard is to provide the minimum requirements for soda ash, including physical, chemical, sampling, testing, packaging, and shipping requirements.

Sec. 1.3 Application

This standard can be referenced in specifications for purchasing and receiving soda ash and can be used as a guide for testing the physical and chemical properties of soda ash samples. The stipulations of this standard apply when this document has been referenced and then only to soda ash used in water supply service applications.