



**American Water Works  
Association**

The Authoritative Resource on Safe Water®

ANSI/AWWA B506-13  
(Revision of AWWA B506-06)

---

---

***AWWA Standard***

---

---

# Zinc Orthophosphate



Effective date: June 1, 2013.

First edition approved by AWWA Board of Directors Feb. 12, 2006.

This edition approved Jan 10, 2013.

Approved by American National Standards Institute April 3, 2013.

---

---

6666 West Quincy Avenue  
Denver, CO 80235-3098  
T 800.926.7337  
www.awwa.org

*Advocacy  
Communications  
Conferences  
Education and Training  
Science and Technology  
Sections*

## **AWWA Standard**

This document is an American Water Works Association (AWWA) standard. It is not a specification. AWWA standards describe minimum requirements and do not contain all of the engineering and administrative information normally contained in specifications. The AWWA standards usually contain options that must be evaluated by the user of the standard. Until each optional feature is specified by the user, the product or service is not fully defined. AWWA publication of a standard does not constitute endorsement of any product or product type, nor does AWWA test, certify, or approve any product. The use of AWWA standards is entirely voluntary. This standard does not supersede or take precedence over or displace any applicable law, regulation, or codes of any governmental authority. AWWA standards are intended to represent a consensus of the water supply industry that the product described will provide satisfactory service. When AWWA revises or withdraws this standard, an official notice of action will be placed on the first page of the Official Notice section of *Journal - American Water Works Association*. The action becomes effective on the first day of the month following the month of *Journal - American Water Works Association* publication of the official notice.

## **American National Standard**

An American National Standard implies a consensus of those substantially concerned with its scope and provisions. An American National Standard is intended as a guide to aid the manufacturer, the consumer, and the general public. The existence of an American National Standard does not in any respect preclude anyone, whether that person has approved the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not conforming to the standard. American National Standards are subject to periodic review, and users are cautioned to obtain the latest editions. Producers of goods made in conformity with an American National Standard are encouraged to state on their own responsibility in advertising and promotional materials or on tags or labels that the goods are produced in conformity with particular American National Standards.

CAUTION NOTICE: The American National Standards Institute (ANSI) approval date on the front cover of this standard indicates completion of the ANSI approval process. This American National Standard may be revised or withdrawn at any time. ANSI procedures require that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of ANSI approval. Purchasers of American National Standards may receive current information on all standards by calling or writing the American National Standards Institute, 25 West 43rd Street, Fourth Floor, New York, NY 10036; (212) 642-4900, or emailing [info@ansi.org](mailto:info@ansi.org).

ISBN-13, print: 978-1-58321-933-1  
ISBN-10, print: 1-58321-933-1

eISBN-13, electronic: 978-1-61300-226-1  
eISBN-10, electronic: 1-61300-226-2

---

All rights reserved. No part of this publication may be reproduced or transmitted in any form or by any means, electronic or mechanical, including photocopy, recording, or any information or retrieval system, except in the form of brief excerpts or quotations for review purposes, without the written permission of the publisher.

Copyright © 2013 by American Water Works Association  
Printed in USA

## Committee Personnel

The AWWA Standards Committee on Scale and Corrosion Control Chemicals, which reviewed and approved this standard, had the following personnel at the time of approval:

Robert A. Ryder, *Chair*

### *General Interest Members*

J.H. Bambei Jr.,* Denver Water, Denver, Colo.	(AWWA)
M.S. McFadden, HDR Engineering Inc., Bellevue, Wash.	(AWWA)
D. Orozco, Robert Cole & Associates, Engineers, Safety Harbor, Fla.	(AWWA)
S.J. Posavec,* Standards Group Liaison, AWWA, Denver, Colo.	(AWWA)
R.A. Ryder, Kennedy Jenks Consultants, San Francisco, Calif.	(AWWA)
R. Vaidya, CDM Smith, Atlanta, Ga.	(AWWA)

### *Producer Members*

H.T. Belcher Jr., Corrtac Systems Corporation, Currituck, N.C.	(AWWA)
C.P. Principi, Carus Corporation, Belmont, N.C.	(AWWA)
V.J. Verdone, Pristine Water Solutions Inc., Waukegan, Ill.	(AWWA)

### *User Members*

E.J. Kiefer, North Shore Water Commission, Milwaukee, Wisc.	(AWWA)
R.M. Powell, Pinellas County Utilities Laboratory, Largo, Fla.	(AWWA)
J.C. Thurrott, City of Daytona Beach, Daytona Beach, Fla.	(AWWA)
Y. Zhang, Long Beach Water Department, Long Beach, Calif.	(AWWA)

---

\* Liaison, nonvoting

This page intentionally blank.

## Contents

*All AWWA standards follow the general format indicated subsequently. Some variations from this format may be found in a particular standard.*

SEC.	PAGE	SEC.	PAGE
<b><i>Foreword</i></b>		<b>2</b>	<b>References</b> ..... 2
I	Introduction..... vii	<b>3</b>	<b>Definitions</b> ..... 2
I.A	Background..... vii	<b>4</b>	<b>Requirements</b>
I.B	History..... x	4.1	Physical Requirements..... 3
I.C	Acceptance..... x	4.2	Chemical Requirements ..... 3
II	Special Issues..... xi	4.3	Impurities..... 4
II.A	Storage and Handling	<b>5</b>	<b>Verification</b>
	Precautions..... xi	5.1	Sampling..... 4
III	Use of This Standard..... xi	5.2	Test Procedures ..... 5
III.A	Purchaser Options and	5.3	Notice of Nonconformance..... 7
	Alternatives ..... xi	<b>6</b>	<b>Delivery</b>
III.B	Modification to Standard ..... xii	6.1	Marking..... 8
IV	Major Revisions..... xii	6.2	Packaging and Shipping ..... 8
V	Comments ..... xii	6.3	Affidavit of Compliance or
			Certified Analysis..... 9
<b><i>Standard</i></b>		<b><i>Table</i></b>	
<b>1</b>	<b>General</b>	Table 1	Sample Size Determination for
1.1	Scope ..... 1		Orthophosphate Analysis ..... 6
1.2	Purpose ..... 1		
1.3	Application..... 1		

This page intentionally blank.

## Foreword

*This foreword is for information only and is not a part of ANSI\* / AWWA B506.*

### I. Introduction.

I.A. *Background.* Phosphate chemicals are among the few substances that can be safely and effectively used in potable water for corrosion inhibition. There are several types of phosphate inhibitors available, including zinc orthophosphate (ZOP), which was originally found to suppress iron corrosion by the Long Beach, Calif., Water Department in the 1940s.<sup>†</sup> Since that time, various formulations of ZOP have been used as corrosion inhibitors in potable water supplies, particularly in the western United States.

ZOP can be an effective chemical inhibitor of electrolytic corrosion, in iron, steel, copper, and lead, which occurs in aggressive (low- to moderate-hardness and alkalinity) water. ZOP was originally used to suppress colored water caused by leaching tuberculation of iron pipe.<sup>†</sup> This treatment technology can be effective in waters without elevated concentrations of iron and manganese to sequester and where calcium precipitation and scaling are of minimal concern.

ZOP can also reduce asbestos fiber counts and provide protection for asbestos-cement and concrete pipe. It prevents concrete pipe deterioration in aggressive waters because the zinc interacts with cement and forms a protective zinc carbonate barrier on the surface at zinc concentrations as low as 0.2 mg/L.<sup>‡</sup>

ZOP formulations consist of zinc salts (sulfate and chloride) combined with orthophosphate formulated in a wide variety of phosphate-to-zinc ratios, ranging from 16:1 to 15:1.

Typically, as the zinc-to-phosphate ratio and dosage is decreased, it is necessary to increase the phosphate portion and dosage. The reverse also often occurs. The zinc proportion is provided by dissolving zinc in sulfonic, sulfuric, or hydrochloric acid and mixing that solution with sodium orthophosphate or phosphoric acid. Until the mid-1980s, the zinc proportion was more economical than the phosphate, and higher

---

\* American National Standards Institute, 25 West 43rd Street, Fourth Floor, New York, NY 10036.

† Murray, W.B. 1970. A Corrosion Inhibitor Process for Domestic Water. *Journal – AWWA* 62(10): 659–662.

‡ Leroy, P., et al., Cement-Based Materials (354); and Vik, E.A., et al., Mitigation of Corrosion Effects (426). 1996. In *Internal Corrosion of Water Distribution Systems*, 2nd ed. Denver, Colo.: American Water Works Association Research Foundation and DVGW-Technologieszentrum Wasser.

zinc-to-orthophosphate ratios were used. Chemical costs change relatively rapidly, and the cost value of the ratio may change.

ZOP solutions are usually acidic, have a pH of less than 2, and are a hazardous chemical. Double containment of large storage vessels, piping, and other chemical handling safety measures are appropriate and required.

ZOP in metal-corrosion suppression is believed to function by two direct mechanisms: film formation and electrochemical passivation. In metal-corrosion protection, the orthophosphate provides an anodic inhibitor, and zinc films form at the cathode and provide a cathodic inhibitor. The blockage of both anodic and cathodic corrosion sites provides a double interruption of the electrochemical-corrosion reaction, which can be more effective than a single-acting inhibitor, which is typical for other phosphate or silicate chemicals.

Asbestos–cement pipe, concrete pipe, or cement linings can be protected by zinc carbonate film, which minimizes aggressive (less than zero Langelier Index) water from leaching calcium and deteriorating the cement surface. There is no apparent benefit of the orthophosphate in cement protection, and other zinc formulations, including zinc chloride, can be used. However, ZOP can be a wide-ranging corrosion inhibitor for multiple pipe and reservoir materials of water distribution and consumer plumbing systems.

Typically, maximum ZOP dosages are limited to between 5 mg/L and 30 mg/L, depending on supplier qualifications of NSF\*/ANSI 60, Drinking Water Chemicals—Health Effects, testing in the United States. The supplier can provide operators with appropriate information on certification and dosage limit of the product for use in potable water. German and other European potable water standards do not allow the use of zinc in chemicals added to potable water, and the possible use of ZOP as a corrosion inhibitor must be evaluated in each country for its intended use.

The zinc concentration is frequently limited to between 0.2 and 2 mg/L to avoid water system secondary-contaminant limits and wastewater and effluent-discharge toxicity limits. However, as is typical for most corrosion inhibitors, it is necessary to use a passivating dose of three to five times the maintenance inhibitor dose for a month or more to reach all portions of the distribution system and initially passivate the metal to provide the protective films.

Phosphate concentrations should typically be in the range of 0.5 to 2 mg/L as P. Sometimes, phosphate may stimulate bacteria and bioslime growths, particularly in

---

\* NSF International, 789 N. Dixboro Road, Ann Arbor, MI 48105.



warmer water and where chloramination disinfection is practiced. There have been instances in warmer waters in Hawaii and the southeastern United States where elevated heterotrophic bacteria counts and other microbiological organisms have caused skin rashes in people bathing.\* This possibility should always be considered when evaluating a phosphate corrosion inhibitor.

It is highly desirable to test and evaluate the effectiveness of various combinations of zinc-to-phosphorus ratios and at various dosages by both instrumentation and pipe-coupon pilot plant tests.† Control tests of no inhibitor, orthophosphate without zinc, and at various pH and alkalinity values should be evaluated in order to select the optimum corrosion-inhibitor concentration for iron, steel, copper, lead, and cement protection. It is also quite likely that type, strategy, and temperature effects will result in use of a larger inhibitor dose in summer warm-water temperature conditions than in winter. Either in situ metal coupon, real-time linear polarization, or electrochemical noise measurements may optimize inhibitor dosage for changing water conditions. Inhibitor dosage control may be automated, such as by linear polarization or electrochemical noise sensors using programmable logic controllers (PLCs).

The water characteristics that are most important when applying ZOP in corrosion protection are pH, alkalinity, hardness, and temperature. The optimum pH for use of ZOP is 7.2–7.8, and ZOP optimum dosage rates are typically lower in elevated pH and colder waters. ZOP should not be fed to water exhibiting a pH above 8.1 to avoid premature precipitation of the zinc and undesirable turbidity or particulates in the distributed water. Much of the success with ZOP as a corrosion inhibitor has been obtained in waters exhibiting low-to-moderate hardness and alkalinity.

A recognized limitation of using a ZOP corrosion inhibitor is contribution of the zinc loading at the wastewater treatment plant and in the effluent discharged to surface waters. This is sometimes regulated to be as low as 0.5 mg/L or lower, and effluent toxicity limits may be lower than 0.1 mg/L. Another recognized effect of using ZOP corrosion inhibitor is consumption of alkalinity and possible reduction in water pH, typically by 0.1 to 0.2 units. Formulations with low zinc content may provide effective corrosion suppression while meeting wastewater regulations. Many different ratios are available from suppliers.

---

\* Edwards, M., B. Marshall, Y. Zhang, & Y.-J., Lee. 2005. Unintended Consequences of Chloramination Hit Home. In *Proc. Disinfection 2005*, Feb. 6–9, 2005, Mesa, Ariz. Water Environment Federation, Alexandria, Va.

† *Internal Corrosion of Water Distribution Systems*. 2nd Edition. 1996. Ch. 9, Corrosion Assessment Technologies. Water Research Foundation, Denver, Colo.

Typically, zinc is measured in the water at the end of distribution systems to provide an indication that the inhibitor dosage is sufficient to reach all portions of the piping system. Because of the corrosion inhibitor's filming effect, it is possible to have the dosage interrupted for several days to perhaps a week and not seriously compromise corrosion protection, if the maintenance dose is resumed.

I.B. *History.* The first edition of ANSI/AWWA B506, Standard for Zinc Orthophosphate, was approved by the AWWA Board of Directors on Feb. 12, 2006. This edition was approved on Jan. 20, 2013.

I.C. *Acceptance.* In May 1985, the US Environmental Protection Agency (USEPA) entered into a cooperative agreement with a consortium led by NSF International (NSF) to develop voluntary third-party consensus standards and a certification program for direct and indirect drinking water additives. Other members of the original consortium included the American Water Works Association Research Foundation (AwwaRF, now Water Research Foundation\*) and the Conference of State Health and Environmental Managers (COSHEM). The American Water Works Association (AWWA) and the Association of State Drinking Water Administrators (ASDWA) joined later.

In the United States, authority to regulate products for use in, or in contact with, drinking water rests with individual states.† Local agencies may choose to impose requirements more stringent than those required by the state. To evaluate the health effects of products and drinking water additives from such products, state and local agencies may use various references, including two standards developed under the direction of NSF, NSF/ANSI 60, Drinking Water Treatment Chemicals—Health Effects, and NSF/ANSI 61, Drinking Water System Components—Health Effects.

Various certification organizations may be involved in certifying products in accordance with NSF/ANSI 60. Individual states or local agencies have authority to accept or accredit certification organizations within their jurisdiction. Accreditation of certification organizations may vary from jurisdiction to jurisdiction.

Annex A, "Toxicology Review and Evaluation Procedures," to NSF/ANSI 60 does not stipulate a maximum allowable level (MAL) of a contaminant for substances not regulated by a USEPA final maximum contaminant level (MCL). The MALs of an unspecified list of "unregulated contaminants" are based on toxicity testing guidelines

---

\* Water Research Foundation, 6666 W. Quincy Ave., Denver, CO 80235.

† Persons outside the United States should contact the appropriate authority having jurisdiction.

(noncarcinogens) and risk characterization methodology (carcinogens). Use of Annex A procedures may not always be identical, depending on the certifier.

ANSI/AWWA B506 addresses additives requirements in Sec. 4.3.2 of the standard. The transfer of contaminants from chemicals to processed water or to residual solids is becoming a problem of greater concern. The language in Sec. 4.3.2 is a recommendation only for direct additives used in the treatment of potable water to be certified by an accredited certification organization in accordance with NSF/ANSI 60, Drinking Water Treatment Chemicals—Health Effects. However, users of the standard may opt to make this certification a requirement for the product. Users of this standard should consult the appropriate state, provincial, or local agency having jurisdiction in order to

1. Determine additives requirements, including applicable standards.
2. Determine the status of certifications by parties offering to certify products for contact with, or treatment of, drinking water.
3. Determine current information on product certification.

## **II. Special Issues.**

II.A. *Storage and Handling Precautions.* ZOP that is a dry solid should be stored in closed containers in a cool, dry area on concrete floors and should be protected from physical damage. Dry ZOP has an affinity for water and can easily absorb moisture, which can result in severe caking and lumping.

Liquid ZOP is generally manufactured with phosphoric acid and zinc salts. Therefore, ZOP products should be stored and handled as any typical acid and should be considered hazardous.

**III. Use of This Standard.** It is the responsibility of the user of an AWWA standard to determine that the products described in that standard are suitable for use in the particular application being considered.

III.A. *Purchaser Options and Alternatives.* The following information should be provided by the purchaser.

1. Standard used—that is, ANSI/AWWA B506, Standard for Zinc Orthophosphate, of latest revision.
2. Quantity required.
3. Whether compliance with NSF/ANSI 60, Drinking Water Treatment Chemicals—Health Effects, is required.
4. Zn:PO<sub>4</sub><sup>3-</sup> ratio desired.
5. Details of other federal, state or provincial, and local requirements (Section 4).
6. Type of material—dry or liquid (Sec. 4.2).

7. Whether the purchaser will reject product from containers or packaging with missing or damaged seals. The purchaser may reject product from bulk containers or packages with missing or damaged seals unless the purchaser's tests of representative samples, conducted in accordance with Sec. 5.2, demonstrate that the product meets the standard. Failure to meet the standard or the absence of, or irregularities in, seals may be sufficient cause to reject a shipment.

8. Whether alternative security measures have been adopted to replace or augment the security measures set out in Sec. 6.2.3 and 6.2.4.

9. Form of shipment—bulk or package, and the type and size of container (Sec. 6.2).

10. Affidavit of compliance, or certified analysis, if required (Sec. 6.3).

III.B. *Modification to Standard.* Any modification of the provisions, definitions, or terminology in this standard must be provided by the purchaser.

**IV. Major Revisions.** Major changes made to the standard in this revision include the following:

1. Inclusion of a requirement for compliance with the Safe Drinking Water Act and other federal regulations.

2. Inclusion of a requirement for tamper-evident packaging (Sec. 6.2.3 and 6.2.4).

**V. Comments.** If you have any comments or questions about this standard, please call the AWWA Engineering and Technical Services Department at 303.794.7711, FAX at 303.795.7603, write to the department at 6666 West Quincy Avenue, Denver, CO 80235-3098, or email at [standards@awwa.org](mailto:standards@awwa.org).



**American Water Works  
Association**

The Authoritative Resource on Safe Water®

---

---

## *AWWA Standard*

---

---

# Zinc Orthophosphate

---

## SECTION 1: GENERAL

---

### **Sec. 1.1 Scope**

This standard describes zinc orthophosphate (ZOP) corrosion inhibitor in dry and liquid forms for use in the treatment of potable water, wastewater, or reclaimed water.

### **Sec. 1.2 Purpose**

The purpose of this standard is to provide minimum requirements for ZOP, including physical, chemical, sampling, packaging, shipping, and testing requirements.

### **Sec. 1.3 Application**

This standard can be referenced in documents for purchasing and receiving ZOP and can be used as a guide for testing the physical and chemical properties of ZOP samples. The stipulations of this standard apply when this document has been referenced and then only to ZOP used in the treatment of potable water, wastewater, or reclaimed water.