



**American Water Works  
Association**

The Authoritative Resource on Safe Water®

ANSI/AWWA B604-12  
(Revision of ANSI/AWWA B604-05)

---

---

*AWWA Standard*

---

---

# Granular Activated Carbon



Effective date: June 1, 2012.

First edition approved by AWWA Board of Directors Jan. 28, 1974.

This edition approved Jan. 22, 2012.

Approved by American National Standards Institute March 27, 2012.

---

---

6666 West Quincy Avenue  
Denver, CO 80235-3098  
T 800.926.7337  
www.awwa.org

Advocacy  
Communications  
Conferences  
Education and Training  
Science and Technology  
Sections

## **AWWA Standard**

This document is an American Water Works Association (AWWA) standard. It is not a specification. AWWA standards describe minimum requirements and do not contain all of the engineering and administrative information normally contained in specifications. The AWWA standards usually contain options that must be evaluated by the user of the standard. Until each optional feature is specified by the user, the product or service is not fully defined. AWWA publication of a standard does not constitute endorsement of any product or product type, nor does AWWA test, certify, or approve any product. The use of AWWA standards is entirely voluntary. This standard does not supersede or take precedence over or displace any applicable law, regulation, or codes of any governmental authority. AWWA standards are intended to represent a consensus of the water supply industry that the product described will provide satisfactory service. When AWWA revises or withdraws this standard, an official notice of action will be placed on the first page of the Official Notice section of *Journal - American Water Works Association*. The action becomes effective on the first day of the month following the month of *Journal - American Water Works Association* publication of the official notice.

## **American National Standard**

An American National Standard implies a consensus of those substantially concerned with its scope and provisions. An American National Standard is intended as a guide to aid the manufacturer, the consumer, and the general public. The existence of an American National Standard does not in any respect preclude anyone, whether that person has approved the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not conforming to the standard. American National Standards are subject to periodic review, and users are cautioned to obtain the latest editions. Producers of goods made in conformity with an American National Standard are encouraged to state on their own responsibility in advertising and promotional materials or on tags or labels that the goods are produced in conformity with particular American National Standards.

CAUTION NOTICE: The American National Standards Institute (ANSI) approval date on the front cover of this standard indicates completion of the ANSI approval process. This American National Standard may be revised or withdrawn at any time. ANSI procedures require that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of publication. Purchasers of American National Standards may receive current information on all standards by calling or writing the American National Standards Institute, 25 West 43rd Street, Fourth Floor, New York, NY 10036; (212) 642-4900, or e-mailing [info@ansi.org](mailto:info@ansi.org).

ISBN-13, print: 978-1-58321-885-3  
ISBN-10, print: 1-58321-885-8

eISBN-13, electronic: 978-1-61300-143-1  
eISBN-10, electronic: 1-61300-143-6

---

All rights reserved. No part of this publication may be reproduced or transmitted in any form or by any means, electronic or mechanical, including photocopy, recording, or any information or retrieval system, except in the form of brief excerpts or quotations for review purposes, without the written permission of the publisher.

Copyright © 2012 by American Water Works Association  
Printed in USA

## Committee Personnel

The AWWA Standards Committee on Activated Carbon, which reviewed and approved this standard, had the following personnel at the time of approval:

David W. Mazyck, Chair

### *General Interest Members*

R.G. Bond, Black & Veatch Corporation, Kansas City, Mo.	(AWWA)
W.B. Dowbiggin, CDM, Raleigh, N.C.	(AWWA)
D.J. Hartman, CH2M HILL, Blue Ash, Ohio	(AWWA)
D.R.U. Knappe, North Carolina State University, Raleigh, N.C.	(AWWA)
D.W. Mazyck, University of Florida, Gainesville, Fla.	(AWWA)
T.J. McCandless,* Standards Engineer Liaison, AWWA, Denver, Colo.	(AWWA)
T.F. Speth, USEPA, Cincinnati, Ohio	(AWWA)
I.H. Suffet, UCLA School of Public Health, Los Angeles, Calif.	(AWWA)
R.S. Summers, University of Colorado at Boulder, Boulder, Colo.	(AWWA)
M.A. Waer, Hatch Mott Macdonald, Lakewood, Colo.	(AWWA)

### *Producer Members*

S.L. Butterworth, Calgon Carbon Corporation, Pittsburgh, Pa.	(AWWA)
H.E. Brown,† Prescott, Ariz.	(AWWA)
J.L. Fisher, Fish Associates, Glenshaw, Pa.	(AWWA)
J.N. Gibson, Mead Westvaco, Covington, Va.	(AWWA)
D.M. Jordan, Siemens, San Francisco, Calif.	(AWWA)
W.F. Naylor, NORIT Americas Inc., Marshall, Texas	(AWWA)
R. Potwora, Carbon Resources LLC, Oceanside, Calif.	(AWWA)
J. Sharpe, Standard Purification, Palm Beach Gardens, Fla.	(AWWA)

### *User Members*


J.A. Bella, Passaic Valley Water Commission, Clifton, N.J.	(AWWA)
T. Hayes, City of Phoenix, Phoenix, Ariz.	(AWWA)
C.E. Stringer, Dallas Water Utilities, Dallas, Texas	(AWWA)
W.A. Vernon, Phoenix, Ariz.	(AWWA)
W.M. Wulfeck, Northern Kentucky Water District, Fort Thomas, Ky.	(AWWA)

---

\* Liaison, nonvoting

† Alternate

This page intentionally blank.




# Contents

*All AWWA standards follow the general format indicated subsequently. Some variations from this format may be found in a particular standard.*

SEC.	PAGE	SEC.	PAGE
<b>Foreword</b>		<b>2</b>	<b>References</b> ..... 2
I. Introduction.....	vii	<b>3</b>	<b>Definitions</b> ..... 2
I.A. Background.....	vii	<b>4</b>	<b>Requirements</b>
I.B. History.....	vii	4.1	Materials ..... 3
I.C. Acceptance.....	viii	4.2	Characteristics..... 4
II. Special Issues.....	ix	4.3	Impurities..... 5
II.A. Storage and Handling Precautions....	ix	<b>5</b>	<b>Verification</b>
II.B. Activated Carbon Dust .....	ix	5.1	Sampling..... 5
II.C. Adsorptive Performance .....	x	5.2	Test Procedures .....
II.D. Filter Media. ....	x	5.3	Notice of Nonconformance .....
II.E. GAC Size Distribution. ....	xi	<b>6</b>	<b>Delivery</b>
II.F. Abrasion Resistance.....	xii	6.1	Marking..... 19
II.G. Non-wettable.....	xii	6.2	Packaging and Shipping .....
II.H. Reactivation .....	xiv	6.3	Affidavit of Compliance .....
III. Use of This Standard .....	xiv		<b>Figures</b>
III.A. Purchaser Options and Alternatives .....	xiv	1	Apparent density apparatus .....
III.B. Modification to Standard .....	xv	2	Stirring abrasion unit .....
IV. Major Revisions.....	xvi	3	Testing pan assembly for Ro-Tap abrasion test (not to scale).....
V. Comments .....	xvi	4	Abrasion testing pan for Ro-Tao abrasion test (not to scale).....
<b>Standard</b>		B.1	Sample determination of tannin extract by carbon adsorption .....
<b>General</b>			
1.1 Scope .....	1		
1.2 Purpose .....	1		
1.3 Application.....	1		

<b>Tables</b>		3	Sieving apparatus required for	
F.1	Typical characteristics for a		stirring abrasion test .....	11
	range of GAC Products .....	xiii		
1	Sampling of bagged media* .....	6	4 Recommended particle sieve sizes....	15
2	US standard sieves and		5 $D_i$ values for Ro-Tap	
	opening sizes .....	10	abrasion test .....	17
		6	6 Example Ro-Tap abrasion test.....	17

---



## Foreword

*This foreword is for information only and is not a part of ANSI/AWWA B604-12.*

### **I. Introduction.**

I.A. *Background.* Activated carbon is a crude form of graphite that is produced by a carefully controlled oxidation process to develop a porous carbon structure with a large internal surface area greater than 500 m<sup>2</sup>/g. This surface area gives the activated carbon the capacity to adsorb dissolved organic materials from water.

The major raw materials used in the manufacture of granular activated carbons (GAC) include, but are not limited to, peat, bituminous coal, coconut shells, wood, and lignite. During activation, the raw materials are either reacted at high temperatures in the presence of steam, or at more moderate temperatures in the presence of activation chemicals. The activation process first drives off volatile components from the raw material, creating a fine porous structure, and then enlarges the pores, which creates the extensive internal pore structure required to obtain appreciable adsorption of organic chemicals.

Water treatment with GAC is accomplished by percolating the water to be treated through fixed-bed adsorbers containing GAC. The GAC may be crushed and screened to any particle size, but typical sizes used for water treatment range from No. 8 to No. 50 US standard sieve sizes.

I.B. *History.* The first edition of ANSI/AWWA B604, Granular Activated Carbon, was approved by the AWWA Board of Directors on Jan. 28, 1974. Subsequent revisions to ANSI/AWWA B604 were prepared by the AWWA Standards Committee and approved on June 17, 1990, and June 23, 1996. The fourth edition of B604 was approved on Jan. 16, 2005. This edition was approved by the AWWA Board of Directors on Jan. 22, 2012.

ANSI/AWWA B604 provides information on preparing documents for the purchase of virgin GAC to be used as an adsorption medium and filtration/adsorption medium for the treatment of municipal and industrial water supplies. Powdered activated carbon is covered in ANSI/AWWA B600, reactivated carbon is covered in ANSI/AWWA B605, and other filtering materials including anthracite coal are covered in ANSI/AWWA B100.

---

\* American National Standards Institute, 25 West 43rd Street, Fourth Floor, New York, NY 10036.

This standard does not cover the design of activated carbon handling facilities or adsorption processes. Design information may be found in *Journal - American Water Works Association* and in other publications, some of which are listed in the bibliography (appendix A) to this standard.

I.C. *Acceptance.* In May 1985, the US Environmental Protection Agency (USEPA) entered into a cooperative agreement with a consortium led by NSF International (NSF) to develop voluntary third-party consensus standards and a certification program for direct and indirect drinking water additives. Other members of the original consortium included the American Water Works Association Research Foundation (AwwaRF, now Water Research Foundation) and the Conference of State Health and Environmental Managers (COSHEM). The American Water Works Association and the Association of State Drinking Water Administrators (ASDWA) joined later.

In the United States, authority to regulate products for use in, or in contact with, drinking water rests with individual states.\* Local agencies may choose to impose requirements more stringent than those required by the state. To evaluate the health effects of products and drinking water additives from such products, state and local agencies may use various references, including

1. An advisory program formerly administered by USEPA, Office of Drinking Water, discontinued on Apr. 7, 1990.
2. Specific policies of the state or local agency.
3. Two standards developed under the direction of NSF, NSF<sup>†</sup>/ANSI 60, Drinking Water Treatment Chemicals—Health Effects, and NSF/ANSI 61, Drinking Water System Components—Health Effects.
4. Other references, including AWWA standards, *Food Chemicals Codex*, *Water Chemicals Codex*,<sup>‡</sup> and other standards considered appropriate by the state or local agency.

Various certification organizations may be involved in certifying products in accordance with NSF/ANSI 61. Individual states or local agencies have authority to accept or accredit certification organizations within their jurisdiction. Accreditation of certification organizations may vary from jurisdiction to jurisdiction.

Annex A, "Toxicology Review and Evaluation Procedures," to NSF/ANSI 61 does not stipulate a maximum allowable level (MAL) of a contaminant for substances not

---

\* Persons outside the United States should contact the appropriate authority having jurisdiction.

† NSF International, 789 North Dixboro Road, Ann Arbor, MI 48113.

‡ Both publications available from National Academy of Sciences, 500 Fifth Street N.W., Washington, DC 20418.



regulated by a USEPA final maximum contaminant level (MCL). The MALs of an unspecified list of “unregulated contaminants” are based on toxicity testing guidelines (noncarcinogens) and risk characterization methodology (carcinogens). Use of annex A procedures may not always be identical, depending on the certifier.

ANSI/AWWA B604 does not address additives requirements. Users of this standard should consult the appropriate state or local agency having jurisdiction in order to

1. Determine additives requirements, including applicable standards.
2. Determine the status of certifications by parties offering to certify products for contact with, or treatment of, drinking water.
3. Determine current information on product certification.

## **II. Special Issues.**

**II.A. Storage and Handling Precautions.** The following safety precautions should be exercised to minimize or eliminate hazards when handling and storing GAC. Wet activated carbon will readily adsorb oxygen from the air, creating an acute oxygen depletion hazard in confined areas. Appropriate safety measures for oxygen-deficient atmospheres should be strictly adhered to when entering enclosed or partially enclosed areas containing activated carbon.

GAC should be stored in a building or compartment that is as fire resistant as possible. Packaged GAC should be stacked in rows with aisles between them so that each package may be easily removed in case of fire. Nothing else should be stored in the same building or compartment with activated carbon. Strict precautions must be taken to avoid GAC contacting strong oxidizing agents such as chlorine, hypochlorites, potassium permanganate, ozone, and peroxide. Mixing activated carbon with hydrocarbons (such as oils, gasoline, diesel fuel, grease, paint thinners, and so forth) may cause spontaneous combustion. Therefore, activated carbon must be kept separate from hydrocarbon storage or spills.

In case of an activated carbon fire, the safest procedure, if possible, is to place the smoldering material in a metal container and remove it from the building. An activated carbon fire may also be smothered by means of a very fine spray or mist of water from a hose or by a foam-type chemical extinguisher. A direct stream of water should not be used, as it will cause the smoldering particles to fly into the air and spread the fire.

**II.B. Activated Carbon Dust.** Respiratory protection should be worn when bags of activated carbon or dry bulk material are unloaded or otherwise handled. Excessive dusting and inhalation of activated carbon dust should be avoided. Activated carbon dusts are classified as “nuisance particulates” and the applicable Threshold Limit Values should be followed.

Activated carbon is an electrical conductor and should not be allowed to accumulate as dust near or on open electrical circuits. Electrical outlets, lights, and motors in dry-activated-carbon feed and storage rooms should be watertight to preclude the entrance of activated carbon dust.

II.C. *Adsorptive Performance.* To accurately assess the effectiveness of a GAC treatment, testwork should be completed using water from the particular plant in question for tests. Test methods may include testing for removal of a specific challenge compound, such as for taste and odors caused by geosmin or 2-methylisoborneol (MIB) present in the water to be treated. It is strongly recommended that activated carbon users follow this approach, as tests will reflect the actual conditions under which the activated carbon will be used.

Various surrogate tests have been developed that give an indication of a GAC's performance under specific conditions. The tests use a specific adsorbate at a high concentration to reduce the amount of time required to run the test. These tests are of limited versatility and are not necessarily indicative of an activated carbon's performance for a given application. Examples of these tests are the iodine number, tannin value, and acetoxime adsorption tests. Iodine number is indicative of the total surface area of a carbon. Acetoxime number is used as an index of activated carbon's ability to remove some low-molecular-weight organic compounds, such as volatile organic chemicals from groundwater. The Acetoxime Test's applicability for evaluating activated carbon for use in surface water applications has not been demonstrated. Tannin value is used as an index of a carbon's ability to remove high molecular weight impurities, such as natural organic matter. The test method for iodine number can be found in ASTM\* D4607. Information on tannin value and acetoxime adsorption tests may be found in appendix B to ANSI/AWWA B604 for those purchasers who want to include these requirements in their documents. Please note that the use of these surrogates may not appropriately model adsorption of actual water contaminants. The Water Research Foundation's† *Standardized Protocol for the Evaluation of GAC* has been developed for the evaluation of GACs.

II.D. *Filter Media.* Filter media are those portions of the filter bed that remove particulate matter from the water during the filtration process. This standard covers GAC, which serves as both an adsorbent and filter medium. Properties of other filter media, such as sand, anthracite coal, and filter media support, such as gravel are

---

\* ASTM International, 100 Barr Harbor Drive, West Conshohocken, PA 19428.

† Water Research Foundation, 6666 West Quincy Avenue, Denver, CO 80235.

contained in ANSI/AWWA B100. Information pertaining to the placement of GAC filter material can be located in appendix C.

II.E. *GAC Size Distribution.* The selection of the type, size, and bed depth of GAC in any particular application is site specific and depends on the raw water quality, pretreatment provided, and water quality objectives. These are site-specific design criteria and must be determined by the design engineer.

In general, for a given pretreatment of raw water and a given filtration rate, coarse media will permit longer filtration runs, but the rate of adsorption is slower. The organic removal and filtration efficiency will normally decrease as the particle size is increased. However, the head loss will also increase with decreasing particle size, and, as a result, the filter runs may be shorter. The uniformity coefficient (UC) of GAC used as a filter medium may be less than the UC of GAC used as an adsorbent. Experience indicates that a more uniform filter medium results in greater filtration efficiency. With GAC, the UC is typically larger than for conventional filter media to promote re-stratification of the filter after backwash and to minimize disruption of the adsorption wave front (mass transfer zone).

GAC is normally used as a filter medium because of its adsorption characteristics. Efficient adsorption requires that the adsorption wave front be maintained during the backwash–filtration cycle. Excessive intermixing of the GAC during the backwash cycle will reduce the adsorption capacity of the filter bed material and increase the cost of operation. Maintaining a stratified bed is more important with GAC than with other media, such as sand or anthracite. As the activated carbon granules in the upper portion of the bed adsorb organic materials, their density increases and the particles settle to a lower portion of the bed. To assist in the maintenance of bed stratification, and the adsorption wave front, and to achieve efficient adsorption, GAC is typically produced as nonuniform in particle size distribution as possible. Of the GAC used, the smallest particles should not reach transport velocity before expansion of the largest fraction is achieved. This normally occurs at a uniformity coefficient of approximately 2.1. Where filtration is the primary function of the GAC, more uniform carbons may be warranted. The design engineer must balance the adsorption performance with the filtration requirements.

In specifying the size of GAC, it is normal to express the effective size of the particle and maximum allowable uniformity coefficient, or the average particle size and maximum uniformity coefficient. An oversize and undersize allowance may also be specified on the mesh sizes that incorporate the desired carbon gradation. For example, when specifying an 8 × 30 mesh size, the maximum amount that is retained on the 8 mesh (oversize) and the maximum percent that passes the 30-mesh screen (undersize)

may also be specified. Commonly manufactured size ranges for GAC are expressed in US standard sieve sizes that include, but are not limited to, 8 × 16, 8 × 20, 8 × 25, 8 × 30, 10 × 30, 12 × 40, 14 × 40, 20 × 40, and 20 × 50, with effective size ranges from 0.35 mm to 2.0 mm. Extruded carbons are also produced in various size ranges. The typical properties of the more standard GAC products are shown in Table F.1.

Dual- or multimedia GAC filters have been used in lieu of a single medium in standard filter-adsorbers for water treatment. In such filters, media are selected to provide a coarse layer of GAC above the smaller and denser sand layer. This coarse-to-fine grading combines longer filter runs with the superior filtration characteristics of finer media. The larger media must be lighter than the smaller media to provide the desired gradation, and the relative sizes of the various media should be selected on the basis of the desired backwash properties. The relative size depends on the density and shape of the media, as well as particle size. It should be noted that intermixing sand with GAC may introduce reactivation problems, in addition to reducing filtration efficiency.

II.F. *Abrasion Resistance.* GACs used for municipal water treatment are exposed to a variety of external forces during shipping, loading into adsorption beds, backwashing, and reactivation. These forces can cause activated carbon granule crushing on impact, granule-to-granule abrasion, and the generation of undesirable fines. Because of the difficulty in devising a test that simulates the various handling conditions that may be encountered, the industry has not yet agreed on any one standard test for predicting activated carbon durability.

Two tests, the stirring abrasion test and the Ro-Tap abrasion test, have been included in this standard for measuring GAC durability. It is recognized that differences in bulk density and other physical properties of the various manufactured activated carbons, which might not be related to durability, influence the results obtained in using these tests. For this reason, it is current practice to use the stirring abrasion test for lignite- and wood-based GAC and the Ro-Tap abrasion test for bituminous- and coconut-based GACs.

II.G. *Non-wettable.* For GAC to be effective as a filtration medium, the carbon particles must wet and settle into a filter bed. Because of some manufacturing processes, some fraction of the activated carbon may not entirely wet and submerge. This can result in loss of activated carbon following initial placement in a filter. If losses are sufficient, there can be a change in the particle size distribution that may lead to poor filtration performance. A test method to measure how much material will wet and sink is included in this standard.

**Table F.1 Typical characteristics for a range of GAC products\***

Standard US Mesh Size	Uniformity Coefficient	Effective Size ( <i>mm</i> )	Apparent Density	
			( <i>lb/ft<sup>3</sup></i> )	( <i>g/cc</i> )
Bituminous Coal-Based GAC				
12 × 40	≤1.9	0.55–0.75	27–41	0.43–0.66
10 × 20	≤1.6	0.80–1.10	28–39	0.45–0.62
8 × 30	≤2.1	0.70–1.00	28–41	0.45–0.66
8 × 20	≤1.5	1.00–1.20	29–39	0.46–0.62
8 × 16	≤1.5	1.20–1.50	29–39	0.46–0.62
6 × 14	≤1.5	1.70–1.90	31–39	0.50–0.62
Lignite Coal-Based GAC				
20 × 50	≤2.1	0.30–0.50	22–26	0.35–0.42
20 × 40	≤1.5	0.45–0.65	22–26	0.35–0.42
12 × 40	≤2.1	0.55–0.80	22–26	0.35–0.42
10 × 30	≤1.6	0.70–0.90	22–26	0.35–0.42
12 × 20	≤1.7	0.70–1.00	22–26	0.35–0.42
8 × 30	≤1.8	0.70–1.00	22–26	0.35–0.42
8 × 16	≤1.5	1.20–1.50	22–26	0.35–0.42
8 × 20	<1.5	1.00–1.20	22–26	0.35–0.42
Wood-Based GAC				
6 × 18	≤2.0	1.30–1.60	13–18	0.21–0.29
8 × 25	≤2.0	0.90–1.10	13–18	0.21–0.29
8 × 30	≤2.1	0.60–0.80	18–22	0.29–0.35
12 × 40	≤2.1	0.60–0.80	18–22	0.29–0.35
Coconut-Based GAC				
8 × 20	≤1.5	1.00–1.20	29–35	0.46–0.56
8 × 30	<2.1	0.80–1.10	28–33	0.45–0.53
12 × 30	<2.0	0.60–0.90	28–33	0.45–0.53

\*The characteristics shown represent a range of GAC products and not a specific grade and mesh size. The manufacturer's product data bulletins should be consulted for information of specific grades and particle sizes.

II.H. *Reactivation.* The reactivation of GAC for municipal drinking water is covered in separate standards, ANSI/AWWA B605 and ASTM D6781.

**III. Use of This Standard.** It is the responsibility of the user of an AWWA standard to determine that the products described in that standard are suitable for use in the particular application being considered.

III.A. *Purchaser Options and Alternatives.* The following items should be provided by the purchaser.

1. Standard used—that is, ANSI/AWWA B604, Granular Activated Carbon, of latest revision.

2. Whether compliance with NSF/ANSI 61 Drinking Water System Components—Health Effects, is required, in addition to the requirements of the Safe Drinking Water Act.

3. Quantity of GAC to be purchased. Activated carbon intended for immediate placement in an adsorption bed is typically purchased by volume and is back-washed and drained in place. Makeup activated carbon or activated carbon intended for subsequent placement is purchased on a volume or weight basis.

4. When requested, a representative sample of the GAC shall be submitted to the purchaser for acceptance before shipment. The sample must be submitted in clean, vapor-proof containers, clearly marked with the address of the supplier, and identified with the lot number of the contents. A duplicate sample shall be tested by the supplier and a certified test report shall be submitted to the purchaser with the purchaser's sample, showing compliance with the requirements of the purchaser, along with a statement certifying that the material for shipment is equal in quality to the sample submitted.

5. Name of the manufacturer whose product will be furnished by the supplier.

6. The purchaser may authorize shipment on the basis of the supplier's certification of quality or may test the reference sample submitted by the supplier to confirm compliance before shipment is authorized.

7. Details of other federal, state, local, and provincial requirements (Sec. 4.1).

8. The particle-size range, effective size, and uniformity coefficient requirements (Sec. 4.2.3, 4.2.4, 4.2.5).

9. The uniformity coefficient requirement (Sec. 4.2.5)

10. The Iodine Number requirement (Sec. 4.2.9)

11. Additional adsorptive capacity test requirements (Sec. 4.2.10).

12. The purchaser may elect to accept the GAC on the basis of (1) the supplier's certified test report and an accompanying affidavit of compliance indicating the



product proposed for use complies with this standard and with the purchasers with no exceptions; (2) the supplier's certified test report completed by a qualified third-party testing laboratory approved by the purchaser and an accompanying affidavit of compliance; (3) the purchaser's own testing of the reference sample submitted by the supplier and the required affidavit of compliance; or (4) the purchaser's own testing of the representative sample, collected according to Sec. 5.1 after receipt of shipment, showing compliance with this standard and the purchase documents.

13. Provisions for reaching agreement on sampling technique (Sec. 5.1.2).

14. Required sample technique (Sec. 5.1.2). The purchaser may elect to collect a representative sample of the material after delivery. The procedure used shall be in accordance with Sec. 5.1. One of the three sample portions taken may be tested to determine compliance with the purchase documents.

15. If remainder of the gross composite sample should be retained or returned to the package (Sec. 5.1.6, item 2).

16. Additional marking requirements (Sec. 6.1).

17. Method of packaging and shipping. Individual bags, boxes, or fiber drums may contain from 35 lb (16 kg) to 200 lb (91 kg) each and semibulk containers may contain 500 lb (363 kg) to 2,000 lb (908 kg) or other quantity as agreed on by the purchaser and supplier.

18. If shipment is to be in bulk: list type of railcar or hopper truck and adequately describe the GAC receiving structures (pressure vessels, gravity contactors, etc.) and conveyance (Sec. 6.2.4); and whether bulk shipments are to be accompanied by weight certificates of certified weighers (Sec. 6.2.5).

19. Whether alternative security measures have been adopted to replace or augment the security measures set out in Sec. 6.2.6.

20. Whether the purchaser will reject product from containers or packaging with missing or damaged seals. The purchaser may reject product from bulk containers or packages with missing or damaged seals unless the purchaser's tests of representative samples, conducted in accordance with Sec. 5.1 and 5.2 demonstrate that the product meets specifications. Failure to meet specifications or the absence of, or irregularities in, seals may be sufficient cause to reject the shipment.

21. Whether an affidavit of compliance is required (Sec. 6.3).

22. Whether this is a supply contract or a supply and installation contract.

III.B. *Modification to Standard.* Any modification of the provisions, definitions, or terminology in this standard must be provided by the purchaser.

**IV. Major Revisions.** Major revisions made to the standard include the following:

1. Added an alternative procedure for determination of percent moisture (Sec. 5.2.3.3)
2. Added security requirements for bulk shipments (Sec. 6.2.6)
3. Added a mandatory requirement for delivery of Affidavit of Compliance (Sec. 6.3)
4. Filter Material and Placing and Preparation was moved to appendix C.

**V. Comments.** If you have any comments or questions about this standard, please call AWWA Engineering and Technical Services at 303.794.7711, FAX at 303.795.7603, write to the department at 6666 West Quincy Avenue, Denver, CO 80235-3098, or e-mail at [standards@awwa.org](mailto:standards@awwa.org).







**American Water Works  
Association**

---

---

*AWWA Standard*

---

---

# Granular Activated Carbon

---

## SECTION 1: GENERAL

---

### Sec. 1.1 Scope

This standard describes virgin granular and extruded activated carbons for use as a filter medium and adsorbent in water treatment. It involves the selection, placement, and use of granular activated carbon (GAC) in filter adsorbers where the GAC must function as filter medium and adsorbent, as well as in those systems where the primary function is adsorption.

### Sec. 1.2 Purpose

The purpose of this standard is to provide the minimum requirements for GAC, including physical, testing, packing, and shipping requirements.

### Sec. 1.3 Application

This standard can be referenced in documents for purchasing and receiving GAC and can be used as a guide for testing the physical properties of GAC samples. The stipulations of this standard apply when this document has been referenced and then only to GAC used in water supply service applications.