



**American Water Works
Association**

ANSI/AWWA C205-07
(Revision of ANSI/AWWA C205-00)

The Authoritative Resource on Safe Water®

AWWA Standard

Cement–Mortar Protective Lining and Coating for Steel Water Pipe—4 In. (100 mm) and Larger—Shop Applied



Effective date: March 1, 2008.

First edition approved by AWWA Board of Directors June 26, 1941.

This edition approved Jan. 21, 2007.

Approved by American National Standards Institute Aug. 2, 2007.

6666 West Quincy Avenue
Denver, CO 80235-3098
T 800.926.7337
www.awwa.org

Advocacy
Communications
Conferences
Education and Training
Science and Technology
Sections

AWWA Standard

This document is an American Water Works Association (AWWA) standard. It is not a specification. AWWA standards describe minimum requirements and do not contain all of the engineering and administrative information normally contained in specifications. The AWWA standards usually contain options that must be evaluated by the user of the standard. Until each optional feature is specified by the user, the product or service is not fully defined. AWWA publication of a standard does not constitute endorsement of any product or product type, nor does AWWA test, certify, or approve any product. The use of AWWA standards is entirely voluntary. AWWA standards are intended to represent a consensus of the water supply industry that the product described will provide satisfactory service. When AWWA revises or withdraws this standard, an official notice of action will be placed on the first page of the classified advertising section of *Journal AWWA*. The action becomes effective on the first day of the month following the month of *Journal AWWA* publication of the official notice.

American National Standard

An American National Standard implies a consensus of those substantially concerned with its scope and provisions. An American National Standard is intended as a guide to aid the manufacturer, the consumer, and the general public. The existence of an American National Standard does not in any respect preclude anyone, whether that person has approved the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not conforming to the standard. American National Standards are subject to periodic review, and users are cautioned to obtain the latest editions. Producers of goods made in conformity with an American National Standard are encouraged to state on their own responsibility in advertising and promotional materials or on tags or labels that the goods are produced in conformity with particular American National Standards.

CAUTION NOTICE: The American National Standards Institute (ANSI) approval date on the front cover of this standard indicates completion of the ANSI approval process. This American National Standard may be revised or withdrawn at any time. ANSI procedures require that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of publication. Purchasers of American National Standards may receive current information on all standards by calling or writing the American National Standards Institute, 25 West 43rd Street, Fourth Floor, New York, NY 10036; (212) 642-4900.

All rights reserved. No part of this publication may be reproduced or transmitted in any form or by any means, electronic or mechanical, including photocopy, recording, or any information or retrieval system, except in the form of brief excerpts or quotations for review purposes, without the written permission of the publisher.

Copyright © 2008 by American Water Works Association
Printed in USA

Committee Personnel

The Steel Water Pipe-Manufacturer's Technical Advisory Committee (SWPMTAC) Task Group on updating ANSI/AWWA C205, which developed this standard, had the following personnel at the time:

Henry H. Bardakjian, *Chair*

H.H. Bardakjian, Ameron International, Rancho Cucamonga, Calif.	(AWWA)
B.J. Britton, W. Walsh Company, Attleboro, Md.	(AWWA)
R.J. Card, Brico Industries Inc., Atlanta, Ga.	(AWWA)
J.E. Hohider, Heitkamp Inc., Watertown, Conn.	(AWWA)
B.D. Keil, Continental Pipe Manufacturing Company, Pleasant Grove, Utah	(AWWA)
L. McKinney, Womble Company, Houston, Texas	(AWWA)
G.F. Ruchti, American SpiralWeld Pipe Company, Punta Gorda, Fla.	(AWWA)
J.C. Taylor, Piping Systems Inc., Fort Worth, Texas	(AWWA)
B. Vanderploeg, Northwest Pipe Company, Portland, Ore.	(AWWA)
D.R. Wagner, Consultant, St. Louis, Mo.	(AWWA)

The AWWA Standards Committee on Steel Pipe, which reviewed and approved this standard, had the following personnel at the time of approval:

John H. Bambei Jr., *Chair*

George J. Tupac, *Vice-Chair*

Dennis A. Dechant, *Secretary*

General Interest Members

J.B. Allen, * Standards Engineer Liaison, AWWA, Denver, Colo.	(AWWA)
W.R. Brunzell, Brunzell Associates Ltd., Skokie, Ill.	(AWWA)
R.L. Coffey, HDR Engineering Inc., Omaha, Neb.	(AWWA)
H.E. Dunham, MWH Americas Inc., Bellevue, Wash.	(AWWA)
S.N. Foellmi, Black & Veatch Corporation, Irvine, Calif.	(AWWA)

*Liaison, nonvoting

J.W. Green, McDonough Associates Inc., Chicago, Ill.	(AWWA)
M.B. Horsley,* Black & Veatch Corporation, Kansas City, Mo.	(AWWA)
J.K. Jeyapalan, Engineering Consultant, New Milford, Conn.	(AWWA)
J.L. Mattson, Corrosion Control Technologies, Sandy, Utah	(AWWA)
W.J. Moncrief,* HDR Engineering Inc., San Diego, Calif.	(AWWA)
R. Ortega, Lockwood Andrews & Newman, Houston, Texas	(AWWA)
A.E. Romer, Boyle Engineering Corporation, Newport Beach, Calif.	(AWWA)
H.R. Stoner, Consultant, North Plainfield, N.J.	(AWWA)
C.C. Sundberg, CH2M Hill, Issaquah, Wash.	(AWWA)
G.J. Tupac, G.J. Tupac & Associates Inc., Pittsburgh, Pa.	(AWWA)
W.R. Whidden, Post Buckley Schuh & Jernigan, Orlando, Fla.	(AWWA)
M.C. Young,† Bucher Willis & Ratcliff Corporation, Kansas City, Mo.	(AWWA)

Producer Members

S.A. Arnaout, Hanson Pipe & Products Inc., Dallas, Texas	(AWWA)
H.H. Bardakjian, Ameron International, Rancho Cucamonga, Calif.	(AWWA)
M. Bauer, Tnemec Company Inc., North Kansas City, Mo.	(AWWA)
R.J. Card, Victaulic Depend-O-Lok Inc., Atlanta, Ga.	(AWWA)
R.R. Carpenter, American Cast Iron Pipe Company, Birmingham, Ala.	(MSS)
D. Dechant, Northwest Pipe Company, Denver, Colo.	(AWWA)
B.D. Keil, Continental Pipe Manufacturing Company, Pleasant Grove, Utah	(SPFA)
J.L. Luka,* American SpiralWeld Pipe Company, Columbia, S.C.	(AWWA)
B. Vanderploeg,* Northwest Pipe Company, Portland, Ore.	(AWWA)
J.A. Wise, Canus International Sales Inc., Surrey, B.C.	(AWWA)

User Members

G.A. Andersen, New York City Bureau of Water Supply, Little Neck, N.Y.	(AWWA)
J.H. Bambei Jr., Denver Water Department, Denver, Colo.	(AWWA)
D.W. Coppes, Massachusetts Water Resources Authority, Southborough, Mass.	(NEWWA)

*Alternate

† Liaison, nonvoting

R.V. Frisz, US Bureau of Reclamation, Denver, Colo.	(USBR)
G. George, Tacoma Water, Tacoma, Wash.	(AWWA)
T.J. Jordan, Metropolitan Water District of Southern California, La Verne, Calif.	(AWWA)
M. McReynolds,* Metropolitan Water District of Southern California, La Mirada, Calif.	(AWWA)
G. Oljaca, Greater Vancouver Regional District, Burnaby, B.C.	(AWWA)
V.B. Soto, Los Angeles Water and Power, Los Angeles, Calif.	(AWWA)
G.P. Stine, San Diego County Water Authority, Escondido, Calif.	(AWWA)
J.V. Young, City of Richmond, Richmond, B.C.	(AWWA)

*Alternate

This page intentionally blank.

Contents

All AWWA standards follow the general format indicated subsequently. Some variations from this format may be found in a particular standard.

SEC.		PAGE	SEC.		PAGE
	<i>Foreword</i>		3	Definitions	3
I	Introduction.....	ix	4	Requirements	
I.A	Background.....	ix	4.1	General	4
I.B	History.....	ix	4.2	Material	5
I.C	Acceptance	x	4.3	Surface Preparation	6
II	Special Issues.....	xi	4.4	Cement–Mortar Lining	7
II.A	Soft, Aggressive Waters	xi	4.5	Cement–Mortar Coating	10
II.B	Intermittent Operations.....	xi	4.6	Cement–Mortar Overcoat.....	15
II.C	Flow Velocity.....	xi	4.7	Field Joints	17
II.D	Strain Limitations	xi	5	Verification	
II.E	Weld-After-Backfill	xi	5.1	Sampling and Testing Cement Mortar for Linings	19
III	Use of This Standard	xii	5.2	Testing Cement Mortar for Coatings	20
III.A	Purchaser Options and Alternatives	xii	5.3	Inspection and Testing by Purchaser	20
III.B	Modification to Standard.....	xiii	6	Delivery	
IV	Major Revisions	xiii	6.1	General	21
V	Comments	xiii	6.2	Plastic End Caps.....	21
	<i>Standard</i>		6.3	Affidavit of Compliance.....	21
1	General			Tables	
1.1	Scope	1	1	Cement–Mortar-Lining Thickness.....	8
1.2	Purpose	2			
1.3	Application	2			
2	References	2			

This page intentionally blank.

Foreword

This foreword is for information only and is not a part of ANSI/AWWA C205.

I. Introduction.

I.A. *Background.* Cement–mortar-lined-and-coated steel pipe was first used in the United States in the late 1800s. Some of the first pipelines were in service for almost a century by the time the first national standard was written. However, it was not until the 1920s that a practical method of plant-applied cement–mortar lining was developed. The first plant-applied linings were installed by standing the pipe on end, placing a tapered plug with a rope attached to the leading end inside the pipe, placing enough cement mortar on top of the plug to coat the pipe, and then pulling the plug up through the pipe. Improvements in the lining process were developed, and the centrifugal process for plant-applied cement–mortar lining emerged.

Cement–mortar-lined and cement–mortar-coated steel pipe combines the physical strength of steel with the protective qualities of cement mortar. The lining, applied centrifugally, creates a smooth, dense finish that protects the pipe from tuberculation and provides a measure of corrosion protection. The smooth interior surface provides a high flow coefficient for the design life of the pipeline under normal operating conditions. In addition, the cement–mortar coating results in a tough, durable, and rugged coating that forms an alkaline environment where oxidation or corrosion of the steel is inhibited.

I.B. *History.* The first edition of this standard, designated 7A.7-41, Standard Specifications for Cement–Mortar Protective Coating for Steel Water Pipe of Sizes 30 Inches and Over, was approved by the AWWA Board of Directors on June 26, 1941. Before that, a tentative draft had been published in the January 1940 *Journal AWWA* for review and comment.

The first edition provided a section for the field application of cement–mortar lining, which was deleted by action of the Board of Directors effective June 30, 1951. Pending the promulgation of AWWA C602, Cement–Mortar Lining of Water Pipelines—4 In. (100 mm) and Larger—In Place, the ninth, tenth, and eleventh printing of 7A.7 (AWWA C205) continued to carry the withdrawn section.

The next edition, published in 1962, was a major revision and provided for pipe sizes of 4 in. (100 mm) and larger. The standard was subsequently revised in 1971, 1980, 1985, 1989, 1995, and 2000. This edition was approved on Jan. 21, 2007.

I.C. *Acceptance.* In May 1985, the US Environmental Protection Agency (USEPA) entered into a cooperative agreement with a consortium led by NSF International (NSF) to develop voluntary third-party consensus standards and a certification program for direct and indirect drinking water additives. Other members of the original consortium included the American Water Works Association Research Foundation (AwwaRF) and the Conference of State Health and Environmental Managers (COSHEM). The American Water Works Association (AWWA) and the Association of State Drinking Water Administrators (ASDWA) joined later.

In the United States, authority to regulate products for use in or in contact with drinking water rests with individual states.* Local agencies may choose to impose requirements more stringent than those required by the state. To evaluate the health effects of products and drinking water additives from such products, state and local agencies may use various references, including

1. An advisory program formerly administered by USEPA, Office of Drinking Water, discontinued on April 7, 1990.
2. Specific policies of the state or local agency.
3. Two standards developed under the direction of NSF, NSF[†]/ANSI[‡] 60, Drinking Water Treatment Chemicals—Health Effects, and NSF/ANSI 61, Drinking Water System Components—Health Effects.
4. Other references, including AWWA standards, *Food Chemicals Codex*,[§] *Water Chemicals Codex*[§] and other standards considered appropriate by the state or local agency.

Various certification organizations may be involved in certifying products in accordance with NSF/ANSI 61. Individual states or local agencies have authority to accept or accredit certification organizations within their jurisdiction. Accreditation of certification organizations may vary from jurisdiction to jurisdiction.

Annex A, “Toxicology Review and Evaluation Procedures,” to NSF/ANSI 61 does not stipulate a maximum allowable level (MAL) of a contaminant for substances not regulated by a USEPA final maximum contaminant level (MCL). The MALs of

*Persons outside the United States should contact the appropriate authority having jurisdiction.

†NSF International, 789 N. Dixboro Road, Ann Arbor, MI 48105.

‡American National Standards Institute, 25 West 43rd Street, Fourth Floor, New York, NY 10036.

§Both publications available from National Academy of Sciences, 500 Fifth Street, N.W., Washington, DC 20001.

an unspecified list of “unregulated contaminants” are based on toxicity testing guidelines (noncarcinogens) and risk characterization methodology (carcinogens). Use of Annex A procedures may not always be identical, depending on the certifier.

ANSI/AWWA C205 does not address additives requirements. Thus, users of this standard should consult the appropriate state or local agency having jurisdiction in order to

1. Determine additives requirements, including applicable standards.
2. Determine the status of certifications by parties offering to certify products for contact with or treatment of drinking water.
3. Determine current information on product certification.

II. Special Issues. The purchaser of cement–mortar linings or coatings is cautioned about the following concerns:

II.A. *Soft, aggressive waters.* Soft, aggressive waters, as well as prolonged contact with heavily chlorinated water, may be injurious to cement–mortar linings. When this environment is anticipated, further studies may be necessary to determine the suitability of this type of lining.

II.B. *Intermittent operations.* Cement–mortar linings are best suited for pipelines that are continuously filled with water. When cement–mortar-lined pipelines are operated under prolonged empty conditions, special precautions may have to be taken to prevent excessive drying out of the cement–mortar lining.

II.C. *Flow velocity.* Cement–mortar linings perform best when flow velocities are in normal ranges. When the flow velocity exceeds approximately 20 ft/sec (6.1 m/sec), special studies may be required to determine the suitability of this type of lining material.

II.D. *Strain limitations.* Consideration should be given to limiting the maximum strains (or stresses) developed in the steel cylinder of cement–mortar-lined or coated steel water pipe from internal pressure to ensure the long-term design life of the system.

II.E. *Weld-after-backfill.* Weld-after-backfill is the sequence of assembling a lap welded joint, welding the outside (if required), applying the exterior coating, backfilling the pipe, and then welding the inside joint at a later time (where inside welding is safe and practical). Welding inside field joints after backfill may damage or compromise the performance of shop and field-applied dielectric coatings. Prior to specifying or approving weld-after-backfill, consult with the manufacturers regarding recommended products, installation, and backfill procedures required for the weld-

after-backfill sequence. At the request of the purchaser, the manufacturer shall provide testing or historical information to verify that the exterior coating complies with this standard after completion of welding.

III. Use of This Standard. It is the responsibility of the user of an AWWA standard to determine that the products described in that standard are suitable for use in the particular application being considered.

III.A. Purchaser Options and Alternatives. When purchasing protective cement–mortar lining or coating for steel water pipe under the provisions of this standard, the following items (including specific details where applicable) should be specified by the purchaser:

1. Standard used—that is, ANSI/AWWA C205, Cement–Mortar Protective Lining and Coating for Steel Water Pipe—4 In. (100 mm) and Larger—Shop Applied, of latest revision.

2. Whether compliance with NSF/ANSI 61, Drinking Water System Components—Health Effects, is required, in addition to the requirements of the Safe Drinking Water Act.

3. If interior lining only, exterior coating only, or both lining and coating are required.

4. Footage, inside diameter after lining, lengths of pipe sections, steel-wall thickness, type of joint, and information regarding fittings.

5. Details of other federal, state or provincial, and local requirements (Sec. 4.1.3)

6. Whether reinforcing wire should be galvanized (Sec. 4.2.1.1).

7. Type of wire-fabric reinforcement required, if limited to a single type (Sec. 4.2.1.2).

8. Type of cement required, if other than Type I, Type II, or Type V (Sec. 4.2.2.1).

9. Lining options or restrictions, if any, such as thickness of lining (Sec. 4.4.2), thickness tolerances (Sec. 4.4.2), and length of lining holdback (Sec. 4.4.2).

10. Coating options or restrictions, if any, such as type of undercoat, if any (Sec. 4.5.1); length of coating holdback (Sec. 4.5.3); thickness of mortar coating (Sec. 4.5.3); minimum thickness (Sec. 4.5.3); type of reinforcement (Sec. 4.5.5); and method of curing (Sec. 4.5.9).

11. Whether cement–mortar overcoat is required (Sec. 4.6), and whether cement–mortar overcoat in a single application is allowed (Sec. 4.6.5.1, 4.6.5.2, and 4.6.6.1).

12. If cement–mortar overcoat cracks between $\frac{1}{16}$ in. (1.6 mm) and $\frac{1}{8}$ in. (3.2 mm) in width require repair (Sec. 4.6.8.2).

13. If additional testing of cement mortar for linings is required (Sec. 5.1.1).

14. The basis of payment for additional testing specified or ordered by the purchaser (Sec. 5.1.1).

15. If an affidavit of compliance is required (Sec. 6.3).

III.B. *Modification to Standard.* Any modification to the provisions, definitions, or terminology in this standard must be provided by the purchaser.

IV. **Major Revisions.** The major revisions to this edition of the standard are summarized as follows:

1. Added weld-after-backfill discussion in foreword Sec. II.E.

2. Added Standards Council materials language as new Sec. 4.1.3.

3. Added alternative reinforcement placement for cement–mortar overcoats (Sec. 4.6.5.1).

4. Added alternative spiral wire reinforcement for cement–mortar overcoats (Sec. 6.5.2).

5. Added language for single application of a cement–mortar overcoat (Sec. 4.6.6.1).

6. Revised language for overcoat cracking (Sec. 4.6.8.2).

V. **Comments.** If you have any comments or questions about this standard, please call the AWWA Volunteer & Technical Support group at 303.794.7711, FAX at 303.795.7603, write to the group at 6666 West Quincy Avenue, Denver, CO 80235-3098, e-mail at standards@awwa.org.

This page intentionally blank.



American Water Works
Association

ANSI/AWWA C205-07
(Revision of ANSI/AWWA C205-00)

AWWA Standard

Cement–Mortar Protective Lining and Coating for Steel Water Pipe—4 In. (100 mm) and Larger—Shop Applied

SECTION 1: GENERAL

Sec. 1.1 Scope

This standard describes the material, application, and curing of shop-applied cement–mortar protective linings and coatings for steel water pipe and fittings and field jointing of cement–mortar-lined-and-coated steel water pipe and fittings.

1.1.1 *Pipe-lining application methods.* The inside of pipe shall receive a cement–mortar lining applied by centrifugally spinning or by a method known to provide equivalent results.

1.1.2 *Fitting lining application methods.* The application of cement–mortar linings to miters, angles, bends, reducers, and other special sections, the shape of which precludes application by the spinning process, shall be accomplished by mechanical placement, pneumatic placement, or hand application and finished to produce a smooth, dense surface.