



**American Water Works
Association**

Dedicated to the World's Most Important Resource®

ANSI/AWWA C231-17
(First Edition)

AWWA Standard



Field Welding of Stainless-Steel Water Pipe

Effective date: Dec. 1, 2017.

First edition approved by AWWA Board of Directors June 11, 2017.

Approved by American National Standards Institute June 29, 2017.




AWWA Standard

This document is an American Water Works Association (AWWA) standard. It is not a specification. AWWA standards describe minimum requirements and do not contain all of the engineering and administrative information normally contained in specifications. The AWWA standards usually contain options that must be evaluated by the user of the standard. Until each optional feature is specified by the user, the product or service is not fully defined. AWWA publication of a standard does not constitute endorsement of any product or product type, nor does AWWA test, certify, or approve any product. The use of AWWA standards is entirely voluntary. This standard does not supersede or take precedence over or displace any applicable law, regulation, or code of any governmental authority. AWWA standards are intended to represent a consensus of the water industry that the product described will provide satisfactory service. When AWWA revises or withdraws this standard, an official notice of action will be placed on the first page of the Official Notice section of *Journal—American Water Works Association*. The action becomes effective on the first day of the month following the month of *Journal—American Water Works Association* publication of the official notice.

American National Standard

An American National Standard implies a consensus of those substantially concerned with its scope and provisions. An American National Standard is intended as a guide to aid the manufacturer, the consumer, and the general public. The existence of an American National Standard does not in any respect preclude anyone, whether that person has approved the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not conforming to the standard. American National Standards are subject to periodic review, and users are cautioned to obtain the latest editions. Producers of goods made in conformity with an American National Standard are encouraged to state on their own responsibility in advertising and promotional materials or on tags or labels that the goods are produced in conformity with particular American National Standards.

CAUTION NOTICE: The American National Standards Institute (ANSI) approval date on the front cover of this standard indicates completion of the ANSI approval process. This American National Standard may be revised or withdrawn at any time. ANSI procedures require that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of publication. Purchasers of American National Standards may receive current information on all standards by calling or writing the American National Standards Institute, 25 West 43rd Street, Fourth Floor, New York, NY 10036; 212.642.4900; or emailing info@ansi.org.



ISBN-13, print: 978-1-62576-272-6

eISBN-13, electronic: 978-1-61300-456-2

DOI:<http://dx.doi.org/10.12999/AWWA.C231.17>

All rights reserved. No part of this publication may be reproduced or transmitted in any form or by any means, electronic or mechanical, including photocopy, recording, or any information or retrieval system, except in the form of brief excerpts or quotations for review purposes, without the written permission of the publisher.

Copyright © 2017 by American Water Works Association
Printed in USA

Committee Personnel

The Steel Water Pipe Manufacturers Technical Advisory Committee (SWPMTAC) Task Group on C231, which developed this standard, had the following personnel at the time:

E. Sinjon Bradberry, *Chair*

E. Bird, Smith-Blair, Texarkana, Texas	(AWWA)
S. Bradberry, Ford Meter Box, Pell City, Ala.	(AWWA)
A. Collins, JCM Industries, Nash, Texas	(AWWA)
B. Dix, Felker Brothers, Marshfield, Wis.	(AWWA)
J. Grocki, Nickel Institute, Enfield, Conn.	(AWWA)
G. Hines, Mueller Company, Cleveland, Tenn.	(AWWA)
T. Keffaber, The Ford Meter Box Company, Wabash, Ind.	(AWWA)
M. Langenhan, Total Piping Solutions Inc., Olean, N.Y.	(AWWA)
G. Larsen, Smith-Blair, Texarkana, Texas	(AWWA)
A. Lemke, Romac Industries, Bothell, Wash.	(AWWA)
M. Levine, Straub Coupling, National City, Calif.	(AWWA)
D. Piontek, Total Piping Solutions Inc., Olean, N.Y.	(AWWA)
P. Ray, JCM Industries, Nash, Texas	(AWWA)
J. Reinheimer, Robar Industries Ltd., Surrey, B.C., Canada	(AWWA)
D. Seals, JCM Industries, Nash, Texas	(AWWA)
A. Thoemke, Victaulic, Atlanta, Ga.	(AWWA)
N. Thogersen, Romac Industries Inc., Bothell, Wash.	(AWWA)

The AWWA Standards Committee on Steel Pipe, which reviewed and approved this standard, had the following personnel at the time of approval:

J. Warren Green, *Chair*

Mike Quinnell, *Secretary*

General Interest Members

R.J. Card,* Lockwood, Andrews & Newman, Sugar Hill, Ga.	(AWWA)
J.W. Green, Lockwood, Andrews & Newman, Oakbrook Terrace, Ill.	(AWWA)
J.E. Koch, HDR Engineering Inc., La Conner, Wash.	(AWWA)

* Alternate

D. Mason,* Standards Council Liaison, O & M Enterprises Inc., Holden, Mo.	(AWWA)
C.A. Prein, Prein & Newhof, Grand Rapids, Mich.	(AWWA)
E.S. Ralph,* Standards Engineer Liaison, AWWA, Denver, Colo.	(AWWA)
R.M. Schwecke,† HDR Engineering Inc., Phoenix, Ariz.	(AWWA)
T.A. Tovey, CH2M, Portland, Ore.	(AWWA)

Producer Members

A. Collins, JCM Industries, Nash, Texas	(AWWA)
D. Dechant, Dechant Infrastructure Service, Aurora, Colo.	(AWWA)
B.D. Keil, Northwest Pipe Company, Draper, Utah	(AWWA)
A. Lemke, Romac Industries Inc., Bothell, Wash.	(AWWA)
R.D. Mielke,† Northwest Pipe Company, Raleigh, N.C.	(AWWA)
J. Reinheimer, Robar Industries Ltd., Surry, B.C., Canada	(AWWA)
C.P. Shelley, Victaulic Company, Doraville, Ga.	(AWWA)
C.C. Sundberg,† Victaulic Company, Issaquah, Wash.	(AWWA)

User Members

M. Garcia, Denver Water, Denver, Colo.	(AWWA)
J.E. Holzapfel, City of Naperville, Naperville, Ill.	(AWWA)
D.J. Martin, Ashwaubenon Water and Sewer Utility, Green Bay, Wis.	(AWWA)
J.F. O'Brien, Genesee County Water and Waste Service, Flint, Mich.	(AWWA)
B.R. Osborne, Clark County Water Reclamation District, Las Vegas, Nev.	(AWWA)
B. Powell, Green Bay Water Utility, Green Bay, Wis.	(AWWA)
M. Quinnell, Saginaw-Midland Water Supply, Bay City, Mich.	(AWWA)
R. Wagner, Dallas Water Utilities, Dallas, Texas	(AWWA)

* Liaison, nonvoting

† Alternate

Contents

All AWWA standards follow the general format indicated subsequently. Some variations from this format may be found in a particular standard.

SEC.	PAGE	SEC.	PAGE
<i>Foreword</i>		4.3	Qualification of Welding Procedures, Welders, and Welding Operators 5
I	Introduction..... vii	4.4	Stainless-Steel Filler Material..... 6
I.A	Background..... vii	4.5	Welding Procedure Details..... 6
I.B	History..... vii	4.6	Repair of Welds..... 8
I.C	Acceptance..... vii	5	Verification
II	Special Issues..... viii	5.1	Inspection 8
III	Use of This Standard viii	5.2	Testing..... 9
III.A	Purchaser Options and Alternatives viii	5.3	Rejection 9
III.B	Modification to Standard ix	6	Delivery
IV	Major Revisions..... ix	6.1	Marking..... 9
V	Comments ix	6.2	Affidavit of Compliance 9
<i>Standard</i>		<i>Appendixes</i>	
1	General	A	Stainless-Steel Filler Material 11
1.1	Scope 1	B	Postfabrication Cleaning of Stainless Steels..... 13
1.2	Purpose 1	<i>Tables</i>	
1.3	Application..... 2	A.1	Recommended Filler Materials..... 11
2	References 2	A.2	Recommended Filler Material for Joining Dissimilar Metals..... 12
3	Definitions 2		
4	Requirements		
4.1	General Requirements 4		
4.2	Joint Types 4		

This page intentionally blank.

Foreword

This foreword is for information only and is not a part of ANSI/AWWA C231.*

I. Introduction.

I.A. *Background.* The provisions of this standard describe the requirements for welding stainless-steel water pipe joints in water transmission and distribution lines. The purchaser for each project is responsible for determining if any unusual circumstances related to the project require additional provisions that are not included in the standard.

The design of field-welded joints is not discussed in this standard. Useful information on this subject may be found in AWWA Manual M11, *Steel Pipe: A Guide for Design and Installation*,[†] and in *Useful Information on the Design of Plate Structures*.[‡]

I.B. *History.* This is the first edition of this standard. This edition was approved by the AWWA Board of Directors on June 11, 2017.

I.C. *Acceptance.* In May 1985, the US Environmental Protection Agency (USEPA) entered into a cooperative agreement with a consortium led by NSF International (NSF[§]) to develop voluntary third-party consensus standards and a certification program for direct and indirect drinking water additives. Other members of the original consortium included the Water Research Foundation (formerly AwwaRF) and the Conference of State Health and Environmental Managers (COSHEM). The American Water Works Association (AWWA) and the Association of State Drinking Water Administrators (ASDWA) joined later.

In the United States, authority to regulate products for use in, or in contact with, drinking water rests with individual states.[¶] Local agencies may choose to impose requirements more stringent than those required by the state. To evaluate the health effects of products and drinking water additives from such products, state and local agencies may use various references, including

Specific policies of the state or local agency.

* American National Standards Institute, 25 West 43rd Street, Fourth Floor, New York, NY 10036.

† AWWA Manual M11. *Steel Pipe—A Guide for Design and Installation*. Denver, CO: AWWA.

‡ American Iron and Steel Institute. *Useful Information on the Design of Plate Structures, Steel Plate Engineering Data*, Vol. 2. Washington, D.C.: American Iron and Steel Institute (1101 17th Street, NW, Suite 1300, Washington, DC 20036).

§ NSF International, 789 North Dixboro Road, Ann Arbor, MI 48105.

¶ Persons outside the United States should contact the appropriate authority having jurisdiction.

1. Two standards developed under the direction of NSF: NSF/ANSI 60, Drinking Water Treatment Chemicals—Health Effects, and NSF/ANSI 61, Drinking Water System Components—Health Effects.

2. Other references, including AWWA standards, *Food Chemicals Codex*, *Water Chemicals Codex*,* and other standards considered appropriate by the state or local agency.

Various certification organizations may be involved in certifying products in accordance with NSF/ANSI 61. Individual states or local agencies have authority to accept or accredit certification organizations within their jurisdictions. Accreditation of certification organizations may vary from jurisdiction to jurisdiction.

Annex A, “Toxicology Review and Evaluation Procedures,” to NSF/ANSI 61 does not stipulate a maximum allowable level (MAL) of a contaminant for substances not regulated by a USEPA final maximum contaminant level (MCL). The MALs of an unspecified list of “unregulated contaminants” are based on toxicity testing guidelines (noncarcinogens) and risk characterization methodology (carcinogens). Use of Annex A procedures may not always be identical, depending on the certifier.

ANSI/AWWA C231 does not address additives requirements. Thus, users of this standard should consult the appropriate state or local agency having jurisdiction in order to

1. Determine additives requirements, including applicable standards.
2. Determine the status of certifications by parties offering to certify products for contact with, or treatment of, drinking water.
3. Determine current information on product certification.

II. Special Issues. This standard has no applicable information for this section.

III. Use of This Standard. It is the responsibility of the user of an AWWA standard to determine that the products described in that standard are suitable for use in the particular application being considered.

III.A. *Purchaser Options and Alternatives.* The following information should be provided by the purchaser:

1. Standard used—that is, ANSI/AWWA C231, Field Welding of Stainless-Steel Water Pipe, of latest revision.

* Both publications available from National Academy of Sciences, 500 Fifth Street, NW, Washington, DC 20418.

2. Whether compliance with NSF/ANSI 61, Drinking Water System Components—Health Effects, is required.
3. Details of other federal, state or provincial, and local requirements (Sec. 4.1.1).
4. Type of joint (Sec. 4.2).
5. Option regarding backing rings (Sec. 4.2.3).
6. Weld inspection, if required (Section 5.1.3).
7. Testing methods, if required (Section 5.2).
8. Nondestructive testing of welded joints if substituted for hydrostatic tests (Sec. 5.2).
9. Affidavit of compliance (Sec. 6.2).

III.B. *Modification to Standard.* Any modification of the provisions, definitions, or terminology in this standard must be provided by the purchaser.

IV. Major Revisions. This is the first edition of the standard.

V. Comments. If you have any comments or questions about this standard, please call the AWWA Engineering and Technical Services at 303.794.7711, FAX at 303.795.7603; write to the department at 6666 West Quincy Avenue, Denver, CO 80235-3098; or email at standards@awwa.org.

This page intentionally blank.



**American Water Works
Association**

Dedicated to the World's Most Important Resource®

ANSI/AWWA C231-17
(First Edition)

AWWA Standard

Field Welding of Stainless-Steel Water Pipe

SECTION 1: GENERAL

Sec. 1.1 Scope

This standard describes manual, semiautomatic, and automatic field welding by the metal arc-welding processes for stainless-steel potable water, wastewater, and reclaimed water pipe manufactured in accordance with ANSI/AWWA C220. This standard describes field welding of two types of circumferential pipe joints: lap joints and butt joints. This standard also applies to other welding required in field fabrication and installation of specials and appurtenances. When possible, fabrications should be performed by the manufacturer at a manufacturing facility. The design of field-welded joints is not within the scope of this standard.

This standard recognizes AWS* D1.6/D1.6M as the supporting document that provides more specific information except as noted in this standard.

Sec. 1.2 Purpose

The purpose of this standard is to provide minimum requirements for field welding and inspection of field welds on stainless-steel potable water, wastewater, and reclaimed water pipe.

* American Welding Society, 550 Northwest LeJuene Road, Miami, FL 33126.