

This is a preview of "AWWA C900-2016". [Click here to purchase the full version from the ANSI store.](#)



**American Water Works
Association**

Dedicated to the World's Most Important Resource®

ANSI/AWWA C900-16
(Revision of ANSI/AWWA C900-07 and C905-10)

AWWA Standard



Polyvinyl Chloride (PVC) Pressure Pipe and Fabricated Fittings, 4 In. Through 60 In. (100 mm Through 1,500 mm)

Effective date: Aug. 1, 2016.

First edition approved by AWWA Board of Directors June 8, 1975.

This edition approved Jan. 16, 2015.

Approved by American National Standards Institute April 7, 2016

Incorporates Errata dated August 2018.



This is a preview of "AWWA C900-2016". [Click here to purchase the full version from the ANSI store.](#)


AWWA Standard

This document is an American Water Works Association (AWWA) standard. It is not a specification. AWWA standards describe minimum requirements and do not contain all of the engineering and administrative information normally contained in specifications. The AWWA standards usually contain options that must be evaluated by the user of the standard. Until each optional feature is specified by the user, the product or service is not fully defined. AWWA publication of a standard does not constitute endorsement of any product or product type, nor does AWWA test, certify, or approve any product. The use of AWWA standards is entirely voluntary. This standard does not supersede or take precedence over or displace any applicable law, regulation, or code of any governmental authority. AWWA standards are intended to represent a consensus of the water industry that the product described will provide satisfactory service. When AWWA revises or withdraws this standard, an official notice of action will be placed on the first page of the Official Notice section of *Journal – American Water Works Association*. The action becomes effective on the first day of the month following the month of *Journal – American Water Works Association* publication of the official notice.

American National Standard

An American National Standard implies a consensus of those substantially concerned with its scope and provisions. An American National Standard is intended as a guide to aid the manufacturer, the consumer, and the general public. The existence of an American National Standard does not in any respect preclude anyone, whether that person has approved the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not conforming to the standard. American National Standards are subject to periodic review, and users are cautioned to obtain the latest editions. Producers of goods made in conformity with an American National Standard are encouraged to state on their own responsibility in advertising and promotional materials or on tags or labels that the goods are produced in conformity with particular American National Standards.

CAUTION NOTICE: The American National Standards Institute (ANSI) approval date on the front cover of this standard indicates completion of the ANSI approval process. This American National Standard may be revised or withdrawn at any time. ANSI procedures require that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of publication. Purchasers of American National Standards may receive current information on all standards by calling or writing the American National Standards Institute, 25 West 43rd Street, Fourth Floor, New York, NY 10036; 212.642.4900; or emailing info@ansi.org.



ISBN-13, print: 978-1-62576-175-0

eISBN-13, electronic: 978-1-61300-386-2

DOI: <http://dx.doi.org/10.12999/AWWA.C900.16>

All rights reserved. No part of this publication may be reproduced or transmitted in any form or by any means, electronic or mechanical, including photocopy, recording, or any information or retrieval system, except in the form of brief excerpts or quotations for review purposes, without the written permission of the publisher.

Copyright © 2016 by American Water Works Association
Printed in USA

Committee Personnel

The Standard C900 Subcommittee that developed this standard had the following personnel at the time:

Robert Walker, *Chair*

L.M. Bowles, Bureau of Reclamation, Denver, Colo.	(AWWA)
B. Clark, JM Manufacturing Co. Inc., DBA JM Eagle, Los Angeles, Calif.	(AWWA)
D.L. Eckstein, EBAA Iron Sales Inc., Williamston, S.C.	(AWWA)
W. Fassler, Uni-Bell PVC Pipe Association, Ripon, Calif.	(AWWA)
C.A. Fisher, Star Pipe Products, North Richland Hills, Texas	(AWWA)
M. Glasgow, North American Pipe Corporation, Ashland City, Tenn.	(AWWA)
J.F. Houle, IPEX Inc., Mississauga, Ont., Canada	(AWWA)
M. Huynh, JM Manufacturing Co. Inc., DBA JM Eagle, Los Angeles, Calif.	(AWWA)
K.S. Jeng-Bullock, City of Houston, Houston, Texas	(AWWA)
T.E. Layton, Orange County Utilities, Orlando, Fla.	(AWWA)
T. Marti, Underground Solutions Inc., Warrendale, Pa.	(AWWA)
S.K. Rajah, Bellevue, Wash.	(AWWA)
E.E. Schmidt, Diamond Plastics Corporation, Grand Island, Neb.	(AWWA)
G. Scoby, Palo Alto Utilities Department, Palo Alto, Calif.	(AWWA)
B. Sukolsky, Specified Fittings, Bellingham, Wash.	(AWWA)
R.P. Walker, Underground Solutions Inc., Southlake, Texas	(AWWA)
W.R. Whidden, Woolpert, Orlando, Fla.	(AWWA)

The AWWA Standards Committee on Polyvinyl Chloride Pressure Pipe and Fittings, which reviewed and approved this standard, had the following personnel at the time of approval:

Bill Whidden, *Chair*

Robert P. Walker, *Vice-Chair*

General Interest Members

J.P. Castronovo, Blue Ridge, Ga.	(AWWA)
A. Chastain-Howley,* Black & Veatch, Frisco, Texas	(AWWA)
A.J. Ciechanowski, NSF International, Ann Arbor, Mich.	(AWWA)

* Liaison, nonvoting

S.J. Cook, Black & Veatch, Virginia Beach, Va.	(AWWA)
S. Ferry, Microbac Laboratories Inc., Boulder, Colo.	(AWWA)
J. Hebenstreit, UL LLC, Northbrook, Ill.	(UL)
S.C. Macleod,* Melville, N.Y.	(AWWA)
M.T. Marino, Nussbaumer & Clarke Inc., Buffalo, N.Y.	(AWWA)
T.J. McCandless,† Standards Engineer Liaison, AWWA, Denver, Colo.	(AWWA)
S.A. McKelvie,* HDR Engineering Inc., Boston, Mass.	(AWWA)
J.R. Paschal, Paschal Engineering LLC, Howell, Mich.	(AWWA)
J.K. Snyder, Snyder Environmental Engineering Associates, Audubon, Pa.	(AWWA)
W.R. Whidden, Woolpert, Winter Park, Fla.	(AWWA)

Producer Members

R.R. Bishop, Diamond Plastics Corporation, Grand Island, Neb.	(AWWA)
L.J. Gill, IPEX Management Inc., Oakville, Ont., Canada	(AWWA)
S.B. Gross, North American Pipe Corporation, Wayne, Pa.	(AWWA)
G. Gundel,* Specified Fittings Inc., Bellingham, Wash.	(AWWA)
J.F. Houle, Uni-Bell PVC Pipe Association, Silverton, Ore.	(AWWA)
M. Huynh, JM Manufacturing Co. Inc., DBA JM Eagle, Los Angeles, Calif.	(AWWA)
R. Magargal,* CertainTeed Corporation, Valley Forge, Pa.	(AWWA)
T. Marti,* Underground Solutions Inc., Warrendale, Pa.	(AWWA)
J. Riordan, HARCO Fittings, Lynchburg, Va.	(AWWA)
L.D. Schmidt,* Diamond Plastics Corporation, Grand Island, Neb.	(AWWA)
B. Sukolsky, Specified Fittings, Bellingham, Wash.	(AWWA)
R.P. Walker, Underground Solutions Inc., Southlake, Texas	(AWWA)

User Members

D.R. Andrews, Marion County Utilities, Belleview, Fla.	(AWWA)
J.R. Barbier, Denver Water, Denver, Colo.	(AWWA)
L.M. Bowles, Bureau of Reclamation, Denver, Colo.	(AWWA)
K.S. Jeng-Bullock, City of Houston, Houston, Texas	(AWWA)
A. Korell, City of North Bay, North Bay, Ont., Canada	(AWWA)
T.E. Layton, Orange County Utilities, Orlando, Fla.	(AWWA)

* Alternate

† Liaison, nonvoting

Contents

All AWWA standards follow the general format indicated subsequently. Some variations from this format may be found in a particular standard.

SEC.	PAGE	SEC.	PAGE
Foreword			
I	Introduction.....	vii	
I.A	Background.....	vii	
I.B	History.....	vii	
I.C	Acceptance.....	viii	
II	Special Issues.....	ix	
II.A	Selection of Pressure Class.....	ix	
II.B	Concern Regarding UV Light Effects	ix	
III	Use of This Standard	ix	
III.A	Purchaser Options and Alternatives	ix	
III.B	Modification to Standard	x	
IV	Major Revisions.....	x	
V	Comments	xi	
Standard			
1	General		
1.1	Scope	1	
1.2	Purpose	1	
1.3	Application.....	2	
2	References	2	
3	Definitions	3	
4	Requirements		
4.1	Permeation	7	
4.2	Materials	8	
4.3	Pipe Requirements	9	
4.4	Machined Coupling Requirements..	20	
4.5	Fabricated Fitting Requirements.....	20	
4.6	Joint Design Performance Qualification Requirements.....	22	
4.7	Pressure-Class Designation Requirements and Pressure Design Recommendations.....	23	
5	Verification		
5.1	Quality Control and Qualification Test Requirements.....	25	
5.2	Quality-Control Records.....	29	
5.3	Plant Inspection	29	
5.4	Basis for Rejection	29	
6	Marking and Delivery		
6.1	Marking Requirements.....	29	
6.2	Shipping.....	31	
6.3	Affidavit of Compliance	31	
Appendixes			
A	Bibliography	33	
B	Recurring (Cyclic) Surge		
B.1	Discussion	35	
B.2	Design Example	35	
Figures			
1	Lap Shear Test.....	22	
B.1	Illustration of Stress Terms	36	
B.2	Cyclic Design Curves	36	

This is a preview of "AWWA C900-2016". [Click here to purchase the full version from the ANSI store.](#)

SEC.	PAGE	SEC.	PAGE
Tables		2	Pressure-Test Requirements 18
1A	Pipe Barrel Dimensions, Pressure Classes, and Dimension Ratios for PVC Pipe With Cast Iron Outside Diameter (CIOD) 10	3	Temperature Coefficients, F_T 19
1B	Pipe Barrel Dimensions, Pressure Classes, and Dimension Ratios for PVC Pipe With IPS Outside Diameter 16	4	Allowable Maximum Occasional Surge Pressure Capacity and Allowable Sudden Changes in Water Velocity for Pipe Operating at 73°F at Working Pressures Expressed as Percent of Nominal Pressure Class (PC) 25

Foreword

This foreword is for information only and is not a part of ANSI/AWWA C900.

I. Introduction.

I.A. *Background.* This standard pertains to 4-in. through 60-in. (100-mm through 1,500-mm) polyvinyl chloride (PVC) pressure pipe and fabricated fittings with outside diameter (OD) dimensions that conform with either those of ductile and cast iron pipe (CIOD) or steel pipe (IPS). Outside-diameter to wall-thickness (OD/*t*) dimension ratios (DRs) of 14, 17, 18, 21, 25, 26, 27.5, 32.5, 41, and 51 are included and correspond with pressure classes (PCs) of 305, 250, 235, 200, 165, 160, 150, 125, 100, and 80 psi. Design considerations are provided in AWWA Manual M23, *PVC Pipe—Design and Installation*. The manual includes chapters on general properties of PVC pipe; manufacturing, testing, and inspection; pressure capacity; design factors for external forces; hydraulics; receiving, storage, and handling; testing and maintenance; and service connections (tapping). Recommended installation guidance is provided in ANSI/AWWA C605, *Underground Installation of Polyvinyl Chloride (PVC) and Molecularly Oriented Polyvinyl Chloride (PVCO) Pressure Pipe and Fittings*.

I.B. *History.* In 1966, the American Water Works Association (AWWA) appointed Committee 8350-D to study and report on the adaptability of plastic pipe for use within the water industry. The committee presented its report on June 6, 1967, at AWWA's annual conference. The report included a recommendation that a task group be appointed to prepare standards for the use of plastic materials. The AWWA Standards Committee on Thermoplastic Pressure Pipe Standards Committee was established in 1968.

In June 1988, the Thermoplastic Pressure Pipe Committee was divided into two separate committees: the Polyvinyl Chloride Pressure Pipe and Fittings Standards Committee and the Polyolefin Pressure Pipe and Fittings Standards Committee.

ANSI/AWWA C900 was the first thermoplastic pipe standard approved by the AWWA Board of Directors in June of 1975. This is the sixth edition of ANSI/AWWA C900. Previous revisions to ANSI/AWWA C900 were prepared by the AWWA Standards Committee and approved in Jan. 1981, Jan. 1989, June 1997, and June 2007. This edition of ANSI/AWWA C900 was approved on Jan. 16, 2016.

* American National Standards Institute, 25 West 43rd Street, Fourth Floor, New York, NY 10036.

I.C. *Acceptance.* In May 1985, the US Environmental Protection Agency (USEPA) entered into a cooperative agreement with a consortium led by NSF International (NSF) to develop voluntary third-party consensus standards and a certification program for direct and indirect drinking water additives. Other members of the original consortium included the Water Research Foundation (formerly AwwaRF) and the Conference of State Health and Environmental Managers (COSHEM). The American Water Works Association (AWWA) and the Association of State Drinking Water Administrators (ASDWA) joined later.

In the United States, authority to regulate products for use in, or in contact with, drinking water rests with individual states.* Local agencies may choose to impose requirements more stringent than those required by the state. To evaluate the health effects of products and drinking water additives from such products, state and local agencies may use various references, including

1. An advisory program formerly administered by USEPA, Office of Drinking Water, discontinued on Apr. 7, 1990.
2. Specific policies of the state or local agency.
3. Two standards developed under the direction of NSF†: NSF/ANSI‡ 60, Drinking Water Treatment Chemicals—Health Effects, and NSF/ANSI 61, Drinking Water System Components—Health Effects.
4. Other references, including AWWA standards, *Food Chemicals Codex*, *Water Chemicals Codex*,§ and other standards considered appropriate by the state or local agency.

Various certification organizations may be involved in certifying products in accordance with NSF/ANSI 61. Individual states or local agencies have authority to accept or accredit certification organizations within their jurisdictions. Accreditation of certification organizations may vary from jurisdiction to jurisdiction.

Annex A, “Toxicology Review and Evaluation Procedures,” to NSF/ANSI 61 does not stipulate a maximum allowable level (MAL) of a contaminant for substances not regulated by a USEPA final maximum contaminant level (MCL). The MALs of an unspecified list of “unregulated contaminants” are based on toxicity testing guidelines

* Persons outside the United States should contact the appropriate authority having jurisdiction.

† NSF International, 789 North Dixboro Road, Ann Arbor, MI 48105.

‡ American National Standards Institute, 25 West 43rd Street, Fourth Floor, New York, NY 10036.

§ Both publications available from National Academy of Sciences, 500 Fifth Street, NW, Washington, DC 20001.

(noncarcinogens) and risk characterization methodology (carcinogens). Use of Annex A procedures may not always be identical, depending on the certifier.

ANSI/AWWA C900 does not address additives requirements. Thus, users of this standard should consult the appropriate state or local agency having jurisdiction in order to

1. Determine additives requirements including applicable standards.
2. Determine the status of certifications by parties offering to certify products for contact with, or treatment of, drinking water.
3. Determine current information on product certification.

II. Special Issues. The pressure-class designation requirements and pressure design recommendations presented in this standard are different from those in AWWA Manual M23, PVC Pipe—Design and Installation, second edition (2002). The requirements of this standard take precedence over the design recommendations in AWWA Manual M23, second edition. Inconsistencies with AWWA M23 and this standard should be discussed with the manufacturer. The committee intends to revise the third edition of M23 to align with this standard.

II.A. Selection of Pressure Class. The minimum pressure class of the pipe selected should be equal to or greater than the system working pressure. The sum of the system working pressure and occasional surge pressure should not exceed 1.60 times the pressure class of the pipe. The system working pressure and recurring surge pressure should be analyzed using the method in Sec. 4.7. If surge pressures govern the selection of the pressure class, consideration should be given to removal of the cause of surge pressures or to the incorporation of surge suppressors in the system.

II.B. Concern Regarding UV Light Effects. The effect of ultraviolet (UV) light on PVC pipe should be insignificant. User concerns such as outdoor storage should be discussed with the manufacturer.

III. Use of This Standard. It is the responsibility of the user of an AWWA standard to determine that the products described in that standard are suitable for use in the particular application being considered.

III.A. Purchaser Options and Alternatives. The following items should be provided by the purchaser:

1. Standard to be used—that is, ANSI/AWWA C900, Polyvinyl Chloride (PVC) Pressure Pipe and Fabricated Fittings, 4 In. Through 60 In. (100 mm Through 1,500 mm), of latest revision.
2. Whether compliance with NSF/ANSI 61, Drinking Water System Components—Health Effects, is required.

3. Details of other federal, state or provincial, and local requirements (Sec. 4.2.1).

4. Pipe and fabricated fittings.*

a. Nominal size [for example, 14 in. (350 mm)].

b. Working, occasional, and recurring surge pressures (Section 3).

c. Pressure class or dimension ratio (DR) (see Tables 1A and 1B).

d. Linear feet of each pressure class or DR for each nominal pipe size to be furnished.

e. Number, nominal size, pressure class, or DR and configuration for fittings and couplings (for example, 17, nominal 24-in. DR 25, 45° bends, IPS).*

5. When desired, requirements such as the following should be specified in the purchase contract:

a. Standard lengths (Sec. 4.3.2.4).

b. Shipping (Sec. 6.2).

c. Affidavit of compliance (Sec. 6.3).

6. Plant inspection. If plant inspections are desired, provisions must be specified in the purchase contract (Sec. 5.3).

a. Production notice. The manufacturer should be required to give adequate advance notice of when and where production of ordered materials will start.

b. Inspection aids. The manufacturer should be required to make available, without charge, to the purchaser's inspector such tools and assistance as are necessary for inspection and handling of materials.

c. Inspection limitations. To exclude inspection of proprietary manufacturing processes, the manufacturer should be required to give adequate advance notice to the purchaser.

III.B. *Modification to Standard.* Any modifications to the provisions, definitions, or terminology in this standard must be provided by the purchaser.

IV. Major Revisions. Major changes made to the standard in this edition include the following:

1. Pipe size range expanded to include nominal 54 and 60 in. (1,350 and 1,500 mm) along with all of the sizes covered in ANSI/AWWA C905. This expansion eliminates the need for a separate standard (i.e., ANSI/AWWA C905) for nominal sizes above 12 in. (300 mm).

* Purchase documents may allow or require the use of fittings other than those described in ANSI/AWWA C900. Some examples of compatible fittings include those covered in ANSI/AWWA standards C208, C153, and C110.

2. Expansion of the scope to include nonpotable water applications.
3. The addition of a ring-tensile (apparent tensile strength at yield) test.
4. The addition of integrity verification test requirements for nonstandard pipe lengths.
5. The addition of qualification test requirements for fusion joints.
6. The addition of pressure classes 150, 200, and 250 psi for pipe with cast iron outside diameters (CIODs).
7. Contract language has been removed from Sec. 5.4.

V. Comments. If you have any comments or questions about this standard, please call AWWA Engineering and Technical Services at 303.794.7711, FAX at 303.795.7603; write to the department at 6666 West Quincy Avenue, Denver, CO 80235-3098; or email at standards@awwa.org.

This is a preview of "AWWA C900-2016". [Click here to purchase the full version from the ANSI store.](#)

This page intentionally blank.



**American Water Works
Association**

Dedicated to the World's Most Important Resource®

ANSI/AWWA C900-16
(Revision of ANSI/AWWA C900-07 and C905-10)

AWWA Standard

Polyvinyl Chloride (PVC) Pressure Pipe and Fabricated Fittings, 4 In. Through 60 In. (100 mm Through 1,500 mm)

SECTION 1: GENERAL

Sec. 1.1 Scope

This standard covers polyvinyl chloride (PVC) pipe and fabricated fittings manufactured for conveying potable water, reclaimed water, irrigation water, wastewater, or any fluid compatible with nonplasticized PVC. The standard includes eight dimension ratios (DRs) and nominal sizes ranging from 4 in. through 60 in. (100 mm through 1,500 mm). Standard pipe outside diameters (ODs) conform to the ductile iron and cast iron sizing system, referred to as *cast iron* or *CIOD*, and steel pipe, referred to as *IPS* (iron pipe size). Pressure classes range from 80 psi (550 kPa) to 305 psi (2,100 kPa).

This standard does not include injection-molded PVC fittings. Injection-molded PVC fittings are covered in ANSI/AWWA C907.

Sec. 1.2 Purpose

The purpose of this standard is to provide minimum manufacturing, verification, and marking requirements for PVC pressure pipe and fabricated fittings, 4 in. (100 mm) through 60 in. (1,500 mm).