



**American Water Works
Association**

ANSI/AWWA C906-07
(Revision of ANSI/AWWA C906-99)

The Authoritative Resource on Safe Water®

AWWA Standard

Polyethylene (PE) Pressure Pipe and Fittings, 4 In. (100 mm) Through 63 In. (1,600 mm), for Water Distribution and Transmission



Effective date: June 1, 2007.

First edition approved by AWWA Board of Directors June 21, 1990.

This edition approved Jan. 21, 2007.

Approved by American National Standards Institute Feb. 15, 2007.

6666 West Quincy Avenue
Denver, CO 80235-3098
T 800.926.7337
www.awwa.org

Advocacy
Communications
Conferences
Education and Training
► **Science and Technology**
Sections

AWWA Standard

This document is an American Water Works Association (AWWA) standard. It is not a specification. AWWA standards describe minimum requirements and do not contain all of the engineering and administrative information normally contained in specifications. The AWWA standards usually contain options that must be evaluated by the user of the standard. Until each optional feature is specified by the user, the product or service is not fully defined. AWWA publication of a standard does not constitute endorsement of any product or product type, nor does AWWA test, certify, or approve any product. The use of AWWA standards is entirely voluntary. AWWA standards are intended to represent a consensus of the water supply industry that the product described will provide satisfactory service. When AWWA revises or withdraws this standard, an official notice of action will be placed on the first page of the classified advertising section of *Journal AWWA*. The action becomes effective on the first day of the month following the month of *Journal AWWA* publication of the official notice.

American National Standard

An American National Standard implies a consensus of those substantially concerned with its scope and provisions. An American National Standard is intended as a guide to aid the manufacturer, the consumer, and the general public. The existence of an American National Standard does not in any respect preclude anyone, whether that person has approved the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not conforming to the standard. American National Standards are subject to periodic review, and users are cautioned to obtain the latest editions. Producers of goods made in conformity with an American National Standard are encouraged to state on their own responsibility in advertising and promotional materials or on tags or labels that the goods are produced in conformity with particular American National Standards.

CAUTION NOTICE: The American National Standards Institute (ANSI) approval date on the front cover of this standard indicates completion of the ANSI approval process. This American National Standard may be revised or withdrawn at any time. ANSI procedures require that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of publication. Purchasers of American National Standards may receive current information on all standards by calling or writing the American National Standards Institute, 25 West 43rd Street, Fourth Floor, New York, NY 10036; (212) 642-4900.

Science and Technology

AWWA unites the entire water community by developing and distributing authoritative scientific and technological knowledge. Through its members, AWWA develops industry standards for products and processes that advance public health and safety. AWWA also provides quality improvement programs for water and wastewater utilities.

All rights reserved. No part of this publication may be reproduced or transmitted in any form or by any means, electronic or mechanical, including photocopy, recording, or any information or retrieval system, except in the form of brief excerpts or quotations for review purposes, without the written permission of the publisher.

Copyright © 2007 by American Water Works Association
Printed in USA

Committee Personnel

The Standards Committee on Polyolefin Pressure Pipe and Fittings, which developed and approved this standard, had the following personnel at the time of approval:

Michael G. Boyle, *Chair*

General Interest Members

J.B. Allen, * Standards Group Liaison, AWWA, Denver, Colo.	(AWWA)
J.P. Castronovo, CH2M Hill, Knoxville, Tenn.	(AWWA)
K.C. Choquette, Iowa Department of Public Health, Des Moines, Iowa	(CSSE)
W.J. Dixon, * SC Liaison, Dixon Engineering Inc., Lake Odessa, Mich.	(AWWA)
D.E. Duvall, Engineering Systems Inc., Aurora, Ill.	(AWWA)
M.L. Magnant, Iowa Department of Public Health, Des Moines, Iowa	(AWWA)
D.L. McPherson, MWH Americas Inc., Cleveland, Ohio	(AWWA)
S.A. Mruk, New Providence, N.J.	(AWWA)
J.R. Paschal, Bodycote-Broutman, Ypsilanti, Mich.	(NSF)
J.R. Peters, M.D. Wessler & Associates Inc., Indianapolis, Ind.	(AWWA)
S. Ziobro, FM Approvals, West Glocester, R.I.	(AWWA)

Producer Members

W.I. Adams, W.L. Plastics, Cedar City, Utah	(AWWA)
J.M. Craig, McElroy Manufacturing Inc., Tulsa, Okla.	(AWWA)
L.J. Gill, Ipex Inc., Mississauga, Ont.	(AWWA)
S.C. Rademacher, Uponor North America, Saint Paul, Minn.	(AWWA)
C.G. Rubeiz, Plastics Pipe Institute, Washington, D.C.	(AWWA)
H. Svetlik, Independent Pipe Products Inc., Dallas, Texas	(AWWA)

User Members

M.G. Boyle, City of Austin, Pflugerville, Texas	(AWWA)
---	--------

* Liaison, nonvoting

J.D. Cox, City of Stockton Municipal Utilities Department, Stockton, Calif.	(AWWA)
M.R. Falarski, East Bay Municipal Utility District, Oakland, Calif.	(AWWA)
R.P. Fuerst, Bureau of Reclamation, Denver, Colo.	(AWWA)
W.F. Guillaume, Orlando, Fla.	(NEWWA)

Contents

All AWWA standards follow the general format indicated subsequently. Some variations from this format may be found in a particular standard.

SEC.	PAGE	SEC.	PAGE
Foreword		4.6	Pipe Classification and Working Pressure Rating 19
I	Introduction..... vii	5	Verification
I.A	Background..... vii	5.1	General 23
I.B	History..... vii	5.2	Material Testing Requirements 23
I.C	Acceptance viii	5.3	Manufacturer Qualification 23
II	Special Issues..... ix	5.4	Pipe Testing Requirements 24
II.A	Advisory Information on Production Application..... ix	5.5	Fitting Testing Requirements 25
III	Use of This Standard x	5.6	Provision for Test Sample Failure.... 25
III.A	Purchaser Options and Alternatives ... x	5.7	Bend-Back Test..... 25
III.B	Modification of Standard..... xi	5.8	Plant Inspection by Purchaser..... 26
IV	Major Revisions xi	6	Delivery
V	Comments xi	6.1	Marking..... 27
Standard		6.2	Shipping 28
1	General	6.3	Affidavit of Compliance..... 28
1.1	Scope 1	Appendixes	
1.2	Purpose 2	A	Bibliography 29
1.3	Application 2	B	Pipe Classification and Working Pressure Rating 31
2	References 2	C	Working Pressure Rating and Pressure Class..... 33
3	Definitions..... 4	Figures	
4	Requirements	1	Cross Section of Polyethylene Flange Assembly 18
4.1	Permeation..... 6	2	Mechanical Joint Adapter 19
4.2	Materials 6		
4.3	Pipe Requirements 8		
4.4	Fusion Fittings Requirements 17		
4.5	Joining Methods 18		

SEC.	PAGE	SEC.	PAGE
Tables			
1	PE Pipe and Fittings Materials 7		Pressure Class/Maximum Working Pressure Rating 21
2	Elevated-Temperature [176±3.6°F (80±2°C)] Sustained-Pressure Test .. 8	10	Temperature Compensation Multipliers (F _T) 22
3	Outside Diameters (ODs) and Tolerances, IPS Sizing System (ANSI B36.10) 9	B.1	Allowable Maximum Surge Pressure Surges Above Working Pressure (WP) and Corresponding Estimated Maximum Allowable Sudden Change in Water Velocity for Pipe Operating at 80°F (27°C) and at a Maximum Working Pressure (WP) Equal to the Pipe's Nominal Pressure Class (PC) 31
4	Minimum Wall Thicknesses (in.), IPS Sizing System 10		
5	DI: Outside Diameters (ODs) and Tolerances for Ductile-Iron Sizing System (DIOD) 12	C.1	Pressure Surge per Foot of Extinguished Velocity by Pipe DR for PE 3408 Materials..... 33
6	DI: Minimum Wall Thicknesses (in.) for Ductile-Iron Sizing System (DIOD) 13	C.2	Working Pressure Rating by DR for Velocity Changes for PE 3408 Materials 35
7	Outside Diameters and Tolerances, Metric Sizing System (ISO 161/1) 14		
8	Minimum Wall Thicknesses (mm), Metric Sizing System 1459		

Foreword

This foreword is for information only and is not a part of ANSI/AWWA C906.

I. Introduction.

I.A. *Background.* This standard describes polyethylene (PE) pressure pipe and fittings in diameters ranging from 4 through 63 in. (100 through 1,600 mm) for use primarily in the construction and rehabilitation of underground water distribution systems.

This document describes pipes and fittings made from PE materials with standard PE code designations PE 2406, PE 3406, and PE 3408. Pipes are classified in accordance with standard pipe dimension ratios (DRs) (i.e., the ratio of pipe outside diameter to pipe minimum wall thickness) that range from 7.3 to 32.5. The resultant combinations of PE material designations and DRs yield pipe with pressure classes (PC) ranging from 40 to 254 psig (276 to 1,750 kPa).

Three standard pipe diameter systems are described, as follows:

- Outside diameters in accordance with the iron pipe size (IPS) system (ANSI B36.10).
- Outside diameters in accordance with the ductile iron sizing system (DIOD) (ANSI/AWWA C110/A21.10).
- Outside diameters in accordance with the International Standards Organization (ISO) sizing system (ISO 161/1).

However, this standard also includes provision for specifying pipe with custom diameters and diameter ratios.

I.B. *History.* In 1984, the Standards Committee on Thermoplastic Pressure Pipe appointed a subcommittee to prepare a standard covering 4 in. (100 mm) and larger diameter polyethylene (PE) pressure pipe and fittings. The first proposed draft was submitted to the Thermoplastic Pressure Pipe Committee by letter ballot in May 1986.

The Thermoplastic Pressure Pipe Committee was subsequently dissolved, and its standards responsibilities were divided between two new AWWA standards committees—the PVC Pressure Pipe and Fittings Committee and the Polyolefin Pressure Pipe and Fittings Committee. The Polyolefin Pressure Pipe and Fittings Committee assumed the responsibility for developing this standard in the fall of 1988. The first edition of C906 was approved by the AWWA Board of Directors on June 21, 1990,

and the second edition was approved on June 20, 1999. This edition was approved Jan. 21, 2007.

I.C. *Acceptance.* In May 1985, the US Environmental Protection Agency (USEPA) entered into a cooperative agreement with a consortium led by NSF International (NSF) to develop voluntary third-party consensus standards and a certification program for direct and indirect drinking water additives. Other members of the original consortium included the American Water Works Association Research Foundation (AwwaRF) and the Conference of State Health and Environmental Managers (COSHEM). The American Water Works Association (AWWA) and the Association of State Drinking Water Administrators (ASDWA) joined later.

In the United States, authority to regulate products for use in, or in contact with, drinking water rests with individual states.* Local agencies may choose to impose requirements more stringent than those required by the state. To evaluate the health effects of products and drinking water additives from such products, state and local agencies may use various references, including

1. An advisory program formerly administered by USEPA, Office of Drinking Water, discontinued on Apr. 7, 1990.
2. Specific policies of the state or local agency.
3. Two standards developed under the direction of NSF: NSF[†]/ANSI[‡] 60, Drinking Water Treatment Chemicals—Health Effects, and NSF/ANSI 61, Drinking Water System Components—Health Effects.
4. Other references, including AWWA standards, *Food Chemicals Codex*, *Water Chemicals Codex*,[§] and other standards considered appropriate by the state or local agency.

Various certification organizations may be involved in certifying products in accordance with NSF/ANSI 61. Individual states or local agencies have authority to accept or accredit certification organizations within their jurisdiction. Accreditation of certification organizations may vary from jurisdiction to jurisdiction.

*Persons outside the US should contact the appropriate authority having jurisdiction.

†NSF International, 789 N. Dixboro Road, Ann Arbor, MI 48113.

‡American National Standards Institute, 25 West 43rd Street, Fourth Floor, New York, NY 10036.

§Both publications available from National Academy of Sciences, 500 Fifth Street, N.W., Washington, DC 20418.

Annex A, "Toxicology Review and Evaluation Procedures," to NSF/ANSI 61 does not stipulate a maximum allowable level (MAL) of a contaminant for substances not regulated by a USEPA final maximum contaminant level (MCL). The MALs of an unspecified list of "unregulated contaminants" are based on toxicity testing guidelines (noncarcinogens) and risk characterization methodology (carcinogens). Use of Annex A procedures may not always be identical, depending on the certifier.

ANSI/AWWA C906 does not address additives requirements (i.e., substances that can be extracted from the pipe by flowing potable water). Users of this standard should consult the appropriate state or local agency having jurisdiction in order to

1. Determine additives requirements, including applicable standards.
2. Determine the status of certifications by parties offering to certify products for contact with, or treatment of, drinking water.
3. Determine current information on product certification.

II. Special Issues.

II.A. *Advisory Information on Product Application.* This standard presents criteria related to the manufacture and purchase of polyethylene pressure pipe to be used in the transmission of potable water in either buried or aboveground applications. Pipe provided according to the provisions of this standard may also be suitable for insertion into existing pipelines for rehabilitation and for the transmission of other liquids.

This standard restricts the materials used for the manufacture of polyethylene pipe to three standard PE code designations: PE 2406, PE 3406, and PE 3408. These three materials provide two series of pressure class ratings, one for PE 2406 or PE 3406 material and one for PE 3408 material. This standard describes 10 dimension ratios for nominal pipe sizes ranging from 4 in. (100 mm) through 63 in. (1,600 mm). Actual outside pipe diameters conform to the outside diameter dimensions of iron pipe sizes (IPS), ductile-iron pipe sizes (DIOD), or to those outside diameters established by the International Organization for Standardization (ISO).

Although this standard generally presents adequate information for ordering pipe that meets project working pressure requirements, it does not include information to guide the designer in the determination of wall thicknesses, pipe flexibility requirements, and installation conditions to meet external loading conditions. The AWWA manual M55: *PE Pipe Design and Installation* provides this information. In addition, consultation with PE pipe manufacturers is recommended.

III. Use of This Standard. It is the responsibility of the user of an AWWA standard to determine that the products described in that standard are suitable for use in the particular application being considered.

III.A. Purchaser Options and Alternatives. Some items in this standard are optional requiring identification of the selected option(s) such as material type, color, and size. When specifying products described in this standard, the purchaser should provide specific information regarding the following:

1. Standard used—that is, ANSI/AWWA C906, Standard for Polyethylene (PE) Pressure Pipe and Fittings, 4 In. (100 mm) Through 63 In. (1,600 mm), for Water Distribution and Transmission, of latest edition.

2. Whether compliance with NSF/ANSI 61 Drinking Water System Components—Health Effects, is required, in addition to the requirements of the Safe Drinking Water Act.

3. Details of other federal, state, local, and provincial requirements (Sec. 4.2.1).

4. Pipe.

- a. Standard code designation of the PE material (Sec. 4.2.1 and Table 1).

- b. Color or color coding.

- c. Nominal size, outside diameter base (IPS, DIOD, or ISO), dimension ratio (DR), and pressure class (PC); length of individual pieces, and total linear feet for each different item to be provided. For special sizes, the purchaser should establish, in consultation with the pipe manufacturer, the actual outside diameter, the actual dimension ratio, and the actual wall thickness.

5. Fittings.

- a. Standard code designation of the PE material (Sec. 4.2.1 and Table 1).

- b. Description of fitting (e.g., tee, elbow, and so forth), nominal size(s) at point of fusion, whether molded or fabricated, and pressure class (PC).

6. Fusion conditions. To ensure optimum efficiency of fusion when joining the product(s) being purchased, the purchaser should request from the manufacturer a list of the recommended fusion parameters, and documentation that these parameters have been validated by appropriate testing. If the purchased piping is to be fused with existing PE piping, the purchaser should inform the manufacturer of the cell classifi-

cation of the existing PE pipe (see Table 1 and ASTM* D3350), and obtain from the manufacturer a list of the validated fusion parameters that may be used to join the purchased piping to the existing piping.

7. Additional requirements. The following requirements may also be specified in the purchase contract:

- a. Special quality-assurance testing (Sec. 5).
- b. Plant inspection by purchaser (Sec. 5).
- c. Special markings (Sec. 6.1).
- d. Shipping (Sec. 6.2).
- e. Affidavit of compliance (Sec. 6.3).

III.B. *Modification of Standard.* Any modification of the provisions, definitions, or terminology in this standard must be provided by the purchaser.

IV. **Major Revisions.** Major changes made to the standard in this revision include the following:

1. Materials language has been added (Sec. III.A.2 and Sec. 4.2.1).
2. Design and installation materials have been deleted from the standard as they are now covered in AWWA M55 (Sec. 2, 4.5.2, 4.5.3, 4.5.4, and 4.5.5).
3. Design information not yet incorporated in AWWA M55 has been moved from Sec. 4.6.2 to appendix B.

V. **Comments.** If you have any comments or questions about this standard, please call the AWWA Volunteer and Technical Support Group at 303.794.7711, FAX 303.795.7603, write to the group at 6666 West Quincy Avenue, Denver, CO 80235-3098, or e-mail standards@awwa.org.

*ASTM International, 100 Barr Harbor Drive, West Conshohocken, PA 19428.

This page intentionally blank.



American Water Works
Association

ANSI/AWWA C906-07
(Revision of ANSI/AWWA C906-99)

AWWA Standard

Polyethylene (PE) Pressure Pipe and Fittings, 4 In. (100 mm) Through 63 In. (1,600 mm), for Water Distribution and Transmission

SECTION 1: GENERAL

Sec. 1.1 Scope

This standard describes polyethylene (PE) pressure pipe made from materials conforming to standard PE code designations PE 2406, PE 3406, and PE 3408. The pipe is primarily intended for use in transporting potable water in either buried or aboveground installations. The standard describes 10 dimension ratios (DRs) for nominal pipe sizes ranging from 4 in. (100 mm) through 63 in. (1,600 mm). Pipe outside diameters (ODs) conform to the outside diameter dimensions of iron pipe (OD-based, IPS), to those established by the International Organization for Standardization (ISO), or to those established for DI equivalent ODs (DIOD).

Pressure classes range from 40 psi (276 kPa) to 198 psi (1,365 kPa) for both PE 2406 and PE 3406 materials, and from 51 psi (352 kPa) to 254 psi (1,751 kPa) for PE 3408 material.