



**American Water Works
Association**

The Authoritative Resource on Safe Water®

ANSI/AWWA D104-11
(Revision of ANSI/AWWA D104-04)

AWWA Standard

Automatically Controlled, Impressed-Current Cathodic Protection for the Interior Submerged Surfaces of Steel Water Storage Tanks



Effective date: March 1, 2011.

First edition approved by AWWA Board of Directors Jan. 27, 1991.

This edition approved Jan. 23, 2011.

Approved by American National Standards Institute Dec. 16, 2010.

6666 West Quincy Avenue
Denver, CO 80235-3098
T 800.926.7337
www.awwa.org

Advocacy
Communications
Conferences
Education and Training
Science and Technology
Sections

AWWA Standard

This document is an American Water Works Association (AWWA) standard. It is not a specification. AWWA standards describe minimum requirements and do not contain all of the engineering and administrative information normally contained in specifications. The AWWA standards usually contain options that must be evaluated by the user of the standard. Until each optional feature is specified by the user, the product or service is not fully defined. AWWA publication of a standard does not constitute endorsement of any product or product type, nor does AWWA test, certify, or approve any product. The use of AWWA standards is entirely voluntary. This standard does not supersede or take precedence over or displace any applicable law, regulation, or codes of any governmental authority. AWWA standards are intended to represent a consensus of the water supply industry that the product described will provide satisfactory service. When AWWA revises or withdraws this standard, an official notice of action will be placed on the first page of the classified advertising section of *Journal AWWA*. The action becomes effective on the first day of the month following the month of *Journal AWWA* publication of the official notice.

American National Standard

An American National Standard implies a consensus of those substantially concerned with its scope and provisions. An American National Standard is intended as a guide to aid the manufacturer, the consumer, and the general public. The existence of an American National Standard does not in any respect preclude anyone, whether that person has approved the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not conforming to the standard. American National Standards are subject to periodic review, and users are cautioned to obtain the latest editions. Producers of goods made in conformity with an American National Standard are encouraged to state on their own responsibility in advertising and promotional materials or on tags or labels that the goods are produced in conformity with particular American National Standards.

CAUTION NOTICE: The American National Standards Institute (ANSI) approval date on the front cover of this standard indicates completion of the ANSI approval process. This American National Standard may be revised or withdrawn at any time. ANSI procedures require that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of publication. Purchasers of American National Standards may receive current information on all standards by calling or writing the American National Standards Institute, 25 West 43rd Street, Fourth Floor, New York, NY 10036; (212) 642-4900, or e-mailing info@ansi.org.

All rights reserved. No part of this publication may be reproduced or transmitted in any form or by any means, electronic or mechanical, including photocopy, recording, or any information or retrieval system, except in the form of brief excerpts or quotations for review purposes, without the written permission of the publisher.

Copyright © 2011 by American Water Works Association
Printed in USA

Committee Personnel

The AWWA Cathodic Protection Task Force, which developed this standard, had the following personnel at the time:

David H. Kroon, *Chair*

| | |
|---|--------|
| R.A. Aboyure, Engineered Storage Products Company, Dekalb, Ill. | (AWWA) |
| L. Barrett, Gibsonia, Pa. | (AWWA) |
| J.R. Conrady, Conrady Consultant Services, Wilsonville, Ala. | (AWWA) |
| C.W. Dessens, City of Houston, Houston, Texas | (AWWA) |
| R.V.D. Field, Engineered Storage Products Company, DeKalb, Ill. | (AWWA) |
| M. Fogata, California Corrosion Specialists, San Diego, Calif. | (AWWA) |
| R.A. Gummow, Correng Consulting Services, Downsview, Ont. | (AWWA) |
| R.J. Kochilla, City of Cleveland, Parma, Ohio | (AWWA) |
| D.H. Kroon, Corrpro Companies Inc., Houston, Texas | (AWWA) |
| J. Rog, Corrpro Waterworks, Medina, Ohio | (AWWA) |
| L.D. Scott, CB&I Inc., San Luis Obispo, Calif. | (AWWA) |

The Standards Committee on Steel Elevated Tanks, Standpipes, and Reservoirs, which reviewed and approved this standard, had the following personnel at the time of approval:

Stephen W. Meier, *Chair*

User Members

| | |
|--|--------|
| J. Camarena, East Bay Municipal Utility District, Oakland, Calif. | (AWWA) |
| T. M. Dawson, Emerald Coast Utilities Authority, Pensacola, Fla. | (AWWA) |
| M.W. Griffin,* Missouri–American Water Company, St. Louis, Mo. | (AWWA) |
| C.P. Harder, City of Fort Worth, Fort Worth, Texas | (AWWA) |
| E.J. King, Connecticut Water Company, Clinton, Conn. | (AWWA) |
| J.L. Ortiz, San Francisco Public Utilities Commission, San Francisco, Calif. | (AWWA) |
| J.P. Scott, New Jersey–American Water Company, Delran, N.J. | (AWWA) |

* Alternate

General Interest Members

| | |
|---|--------|
| D.M. Algranti, Albert A. Webb Associates, Riverside, Calif. | (AWWA) |
| E. Darrimon, Bay Area Coating Consultant Service Inc., Denair, Calif. | (AWWA) |
| W.J. Dixon, Dixon Engineering Inc., Lake Odessa, Mich. | (AWWA) |
| F.S. Kurtz,* Standards Engineer Liaison, AWWA, Denver, Colo. | (AWWA) |
| S.W. Meier, Tank Industry Consultants, Indianapolis, Ind. | (AWWA) |
| J.W. Nollenberger, Centennial, Colo. | (AWWA) |
| B.M. Shepherd,* Standards Council Liaison, Claremont, Calif. | (AWWA) |
| J.I. Strand, Short Elliott Hendrickson Inc., Chippewa Falls, Wis. | (AWWA) |
| C.C. Sundberg, CH2M HILL, Issaquah, Wash. | (AWWA) |
| R.S. Wozniak, Bow Tech Ltd., Batavia, Ill. | (AWWA) |

Producer Members

| | |
|--|--------|
| J.W. Davis, Tnemec Company, Kansas City, Mo. | (AWWA) |
| B.E. Kromer, Tank Builders Inc., Euless, Texas | (AWWA) |
| S. Lamb, Nickel Institute, Huntington, W.V. | (AWWA) |
| G.A. Larson, CB&I Inc., Clive, Iowa | (AWWA) |
| K. McGuire, Columbian TecTank Inc., Parsons, Kan. | (AWWA) |
| L.D. Scott,† CB&I Inc., San Luis Obispo, Calif. | (AWWA) |
| D.L. Stilger, Caldwell Tanks Inc., Louisville, Ky. | (AWWA) |

* Liaison, nonvoting

† Alternate

Contents

All AWWA standards follow the general format indicated subsequently. Some variations from this format may be found in a particular standard.

| SEC. | PAGE | SEC. | PAGE |
|------------------------|--|--------------------------|--|
| <i>Foreword</i> | | 2 | References 2 |
| I | Introduction vii | 3 | Definitions 2 |
| I.A | Background vii | 4 | Requirements |
| I.B | History vii | 4.1 | Design 5 |
| I.C | Acceptance vii | 4.2 | System Components 7 |
| II | Special Issues viii | 4.3 | Installation 8 |
| II.A | Protective Coatings viii | 5 | Verification |
| II.B | Cathodic Protection ix | 5.1 | Inspection and Handling 10 |
| III | Use of This Standard xi | 5.2 | Testing 10 |
| III.A | Purchaser Options and Alternatives xi | 5.3 | Operation and Maintenance Manual 10 |
| III.B | Modification to Standard xiv | <i>Appendixes</i> | |
| IV | Major Revisions xiv | A | Commentary and Additional Information 11 |
| V | Comments xiv | B | Operation Guidelines for Cathodic Protection Systems 15 |
| <i>Standard</i> | | C | Recommended Maintenance and Service 17 |
| 1 | General | | |
| 1.1 | Scope 1 | | |
| 1.2 | Purpose 1 | | |
| 1.3 | Application 2 | | |

This page intentionally blank.

Foreword

This foreword is for information only and is not a part of ANSI/AWWA D104.*

I. Introduction.

I.A. *Background.* This standard describes automatically controlled, impressed-current cathodic protection systems for the interior submerged surfaces of steel water storage tanks. This standard does not cover sacrificial (galvanic) anode-type cathodic protection systems (see ANSI/AWWA D106) or manually controlled rectifiers.

I.B. *History.* Before the development of AWWA D104, cathodic protection equipment was covered in AWWA D102, Painting and Repainting Steel Tanks, Standpipes, Reservoirs, and Elevated Tanks for Water Storage. AWWA D102-64 addressed cathodic protection equipment in Section 4. In the 1978 edition of that standard, however, the provisions for cathodic protection equipment were removed, and the development of a new AWWA standard on cathodic protection was needed. This standard became ANSI/AWWA D104, Automatically Controlled, Impressed Current Cathodic Protection for the Interior of Steel Water Tanks. The first edition of ANSI/AWWA D104 was approved by the AWWA Board of Directors on Jan. 27, 1991. The second edition was approved on Feb. 2, 1997. The third edition was approved on June 17, 2001. The fourth edition was approved on June 13, 2004. This edition was approved on Jan. 23, 2011.

I.C. *Acceptance.* In May 1985, the US Environmental Protection Agency (USEPA) entered into a cooperative agreement with a consortium led by NSF International (NSF) to develop voluntary third-party consensus standards and a certification program for direct and indirect drinking water additives. Other members of the original consortium included the American Water Works Association Research Foundation (AwwaRF, now the Water Research Foundation[†]) and the Conference of State Health and Environmental Managers (COSHEM). The American Water Works Association (AWWA) and the Association of State Drinking Water Administrators (ASDWA) joined later.

In the United States, authority to regulate products for use in, or in contact with, drinking water rests with individual states.[‡] Local agencies may choose to impose requirements more stringent than those required by the state. To evaluate the health

* American National Standards Institute, 25 West 43rd Street, Fourth Floor, New York, NY 10036.

† Water Research Foundation, 6666 W. Quincy Avenue, Denver, CO 80235.

‡ Persons outside the United States should contact the appropriate authority having jurisdiction.

effects of products and drinking water additives from such products, state and local agencies may use various references, including

1. An advisory program formerly administered by USEPA, Office of Drinking Water, discontinued on Apr. 7, 1990.
2. Specific policies of the state or local agency.
3. Two standards developed under the direction of NSF, NSF*/ANSI 60, Drinking Water Treatment Chemicals—Health Effects, and NSF/ANSI 61, Drinking Water System Components—Health Effects.
4. Other references, including AWWA standards, *Food Chemicals Codex*, *Water Chemicals Codex*,[†] and other standards considered appropriate by the state or local agency.

Various certification organizations may be involved in certifying products in accordance with NSF/ANSI 61. Individual states or local agencies have authority to accept or accredit certification organizations within their jurisdiction. Accreditation of certification organizations may vary from jurisdiction to jurisdiction.

Annex A, "Toxicology Review and Evaluation Procedures," to NSF/ANSI 61 does not stipulate a maximum allowable level (MAL) of a contaminant for substances not regulated by a USEPA final maximum contaminant level (MCL). The MALs of an unspecified list of "unregulated contaminants" are based on toxicity testing guidelines (noncarcinogens) and risk characterization methodology (carcinogens). Use of Annex A procedures may not always be identical, depending on the certifier.

ANSI/AWWA D104 does not address additives requirements. Thus, users of this standard should consult the appropriate state or local agency having jurisdiction in order to

1. Determine additives requirements, including applicable standards.
2. Determine the status of certifications by parties offering to certify products for contact with, or treatment of, drinking water.
3. Determine current information on product certification.

II. Special Issues.

II.A. *Protective Coatings.* Protective coatings are commonly used in steel water storage tanks. They are an effective method of corrosion control except where flaws exist in the coating caused by poor surface preparation, improper application, defective materials, unanticipated conditions, deterioration over time, or damage. When

* NSF International, 789 N. Dixboro Road, Ann Arbor, MI 48105.

† Both publications available from the National Academy of Sciences, 500 Fifth Street, NW, Washington, DC 20001.

properly designed and maintained, cathodic protection systems will arrest corrosion at flaws in the submerged coated surface. Properly applied coatings reduce the bare surface area requiring protection and reduce the amount of current required to protect the surface. Use and maintenance of protective coatings extends the life of the cathodic protection system and reduces operating costs. For submerged areas of a tank, cathodic protection can also reduce the frequency of coating maintenance. Cathodic protection or coatings alone can reduce corrosion on the interior submerged surfaces; however, the combination of coatings and cathodic protection may be more economical and effective than using coatings or cathodic protection alone.

II.B. *Cathodic Protection.* The two major components of an automatically controlled, impressed-current cathodic protection system are the direct current (DC) power supply controller (rectifier) and the anode system. The range of output current capacity required for an automatically controlled rectifier in a specific application is determined by assuming the area of submerged, bare steel to be protected when the interior tank coating is new and when the interior coating has deteriorated to the point where recoating is necessary. In potable water, current density requirements can range from 0.5 to 5.0 mA/ft² (5.4 to 53.8 mA/m²) of bare steel surface. Applications involving turbulence, high temperature, or both may require higher current densities. For newly coated tanks, the total current requirement may be as little as 1 percent of the current required to protect an uncoated surface. As a rule, rectifiers for newly coated tanks should have sufficient current capacity to protect the anticipated bare submerged surface area before coating repair or replacement. The required operating voltage of a rectifier for a specific tank depends on the current required to provide adequate protection and the total circuit resistance of the system.

Automatically controlled rectifier systems should be used for cathodic protection of water storage tanks. Automatically controlled systems use one or more long-life reference electrodes to monitor the protection levels maintained on the submerged surfaces. The reference electrode continuously monitors the tank-to-water potential, free of IR (voltage) drop error. IR drop must be eliminated or minimized to accurately determine the voltage between the tank and the reference electrode submerged in the tank. The controller instantaneously interrupts the flow of cathodic protection current, providing an IR drop-free measurement, which closely approximates the polarized potential. The controller compares the measured tank-to-water potential to a preset value and automatically adjusts the current output of the rectifier. Automatic units include a tank-to-water potential monitoring meter, which can be easily checked by the purchaser.

NOTE: Manually controlled rectifiers are not recommended for use in water storage tanks and are not covered by this standard because they require frequent monitoring, testing, and manual adjustment of the rectifier current output whenever the current requirements change because of changes in water level, coating condition, temperature, water chemistry, water turbulence, or accumulation of polarization films. Failure to adjust rectifier current output can result in corrosion caused by underprotection or coating damage caused by overprotection.

The second major component of an automatically controlled system is the anode system. The anode system includes the anode material and the method of suspending the anode within the tank. The type of anode material and suspension system used is typically based on the tank's susceptibility to icing conditions.

For tanks subject to icing conditions, a seasonal or a long-life anode system may be used. A seasonal (or temporary) arrangement consists of vertically suspended anodes. This type of suspension system is susceptible to ice damage. Ice will adhere to some portion of the anode string and tear the anodes loose, causing the system to fail. Because it is anticipated that the anodes will be damaged annually, low-cost aluminum rod anodes are used. While the anode system is intact, the system will operate properly during the more corrosive summer season. In locations subject to freezing temperatures, there is usually a two- to five-month period during the winter when the system may not operate properly because of ice damage. This type of anode system will usually require annual replacement of the anodes and vertical anode suspension system. Anode remnants should be removed from the tank whenever the interior is accessible.

A long-life anode system includes suspension systems that are designed to be more resistant to ice damage and permit the use of long-life anode materials that have a design life of at least 10 years. The potential for ice damage is reduced by attaching the anode material to a buoyant or horizontally submerged radial-type rope system, which is attached to the walls of the tank and prevents the anode system from coming in contact with ice formations. Another type of system compensates for ice damage by attaching the anode material to an extendable element suspended from the tank roof. The extendable element stretches with the movement of ice and allows the anode to eventually return to its original position.

For tanks not subject to icing conditions, anodes may be suspended from the tank roof without an extendable element or may be horizontally supported from a buoyant, submerged, radial-type rope system.

III. Use of This Standard. It is the responsibility of the user of an AWWA standard to determine that the products described in that standard are suitable for use in the particular application being considered.

Contractual responsibilities for items such as design, material, fabrication, construction, inspection, testing, and operation have been removed from the standard and must be addressed in the contract documents.

Many tanks using automatically controlled, impressed-current cathodic protection systems for interior submerged surfaces* have been in service for more than 30 years. Proper design and maintenance of impressed-current cathodic protection systems can help steel water storage tanks achieve an almost unlimited service life.

This standard does not cover systems where the purchaser specifies criteria for protection other than those listed in this standard. This standard does not cover systems to be installed in areas subject to regulations or requirements that are more stringent than the requirements contained herein. Where local, municipal, county, or state government requirements apply to the installation of the impressed-current cathodic protection system, such requirements govern, and this standard should be interpreted to supplement them. It is the purchaser's responsibility to supplement or modify this standard for compliance with these local requirements.

At a minimum, it is important that all of the requirements in this standard be met. An impressed-current cathodic protection system cannot be represented as an ANSI/AWWA D104-compliant system if it does not meet the minimum requirements of this standard.

Annual inspection and maintenance of the system is important to ensuring maximum tank life.

AWWA Manual M42, *Steel Water-Storage Tanks*, provides guidance on inspection and maintenance of welded steel tanks for water storage.

This standard does not cover tank disinfection procedures or cleaning and painting. ANSI/AWWA C652, *Standard for Disinfection of Water Storage Facilities*, should be consulted for recommended procedures for disinfection of water storage facilities.

III.A. Purchaser Options and Alternatives. Proper use of this standard requires that the purchaser specify certain requirements. The purchaser may desire to modify, delete, or amplify sections of this standard to suit special conditions. It is strongly

* The word "system" and the phrase "cathodic protection system" are used herein broadly in place of the lengthy phrase "automatically controlled, impressed-current cathodic protection system for interior submerged surfaces of steel water storage tanks."

recommended that such modifications, deletions, or amplifications be made by supplementing this standard.

III.A.1 *Options and Alternatives.* The following list identifies aspects of the system that have more than one acceptable style, configuration, or value. The purchaser must specify the desired option for each of these items or specify that the system designer may select any appropriate option.

1. Whether compliance with NSF/ANSI 61, Drinking Water System Components—Health Effects, is required, in addition to the requirements of the Safe Drinking Water Act.
2. The type of anode.
3. The type of anode suspension system.
4. Required design life of the anode system.

III.A.2 *Items to Be Provided by Purchaser or Installer.* The following recommendations represent good practice about what each party should provide, but they are not requirements of ANSI/AWWA D104. The contract documents should specify which party is to provide each of the following items.

1. When an impressed-current cathodic protection system is to be purchased under this standard, the purchaser should provide the following:
 - a. Access to the site on which the tank is to be built, including sufficient space to permit access to install, inspect, and test the system by customary methods.
 - b. Location from which alternating current (AC) power is to be provided to the rectifier unit.
 - c. A sufficient volume of water in the tank at the time of system installation to allow full system testing.
 - d. Safe access to the tank roof for installation and inspection of system components.
 - e. Certification that the tank roof is safe to access.
 - f. Any materials to be furnished by the purchaser for installation in the system by the system installer.
2. The system designer should submit design calculations, specifications and construction drawings.
3. The system installer should furnish the following items:
 - a. All labor and materials, except materials provided by the purchaser, necessary to complete the installation of the system, including inspection and testing required by this standard.
 - b. Any additional work specified separately by the purchaser in the contract documents, such as disinfection of the tank.
 - c. Operation and maintenance manual.

III.A.3 *Information to Be Specified by Purchaser.* This standard provides minimum requirements for the design, construction, inspection, and testing of tanks without any designation of which party must perform these tasks or select the options. For this reason, the following information should be specified by the purchaser when taking bids for an impressed-current cathodic protection system for interior submerged surfaces of a steel water storage tank:

1. Standard used, that is, ANSI/AWWA D104, Standard for Automatically Controlled, Impressed-Current Cathodic Protection for the Interior Submerged Surfaces of Steel Water Storage Tanks, of latest revision.
2. Compliance requirement for NSF/ANSI 61, Drinking Water System Components—Health Effects (see Sec. 4.1.2[1]).
3. Gross capacity of the tank, the tank diameter, and the type of roof.
4. For elevated tanks, the style or shape of tank, the bottom capacity level (BCL), the head range, and the diameter and type of riser.
5. For ground-supported flat-bottom tanks, the top capacity level (TCL).
6. Chemical analysis of the water to be stored.
7. Water resistivity (for all sources of supply).
8. Water turbulence.
9. Operating temperature and flow rate.
10. Type and age of protective coatings.
11. Maximum anticipated coating deterioration expressed as a percentage of the submerged coating surface area that is allowed to become bare before the coating is repaired or replaced (for design purposes).
12. Cathodic polarization characteristics.
13. Which type of anode system required (see Sec. 4.2.3).
14. Which type of anode suspension system to be installed (see Sec. 4.2.4).
15. Source of AC power.
16. Required design life of the anode system.
17. Location of the site.
18. Desired time for completion.

III.A.4 *Information to Be Provided by the Bidder for an Impressed-Current Cathodic Protection System for Interior Submerged Surfaces of a Steel Water Storage Tank:*

1. A description of the anode material, size, configuration, and suspension system.
2. A description of the quantity and location of the anodes.
3. A statement of the design basis of the system, including tank size and configuration, all water properties, type of coatings, design percentage of bare steel surface protected, and design life of the anodes.

4. Outline of the recommended service and maintenance plan.

III.B. *Modification to Standard.* Any modification to the provisions, definitions, or terminology in this standard must be provided by the purchaser.

IV. Major Revisions. The revisions to ANSI/AWWA D104 in this edition are editorial with the primary intent to improve clarity.

V. Comments. If you have any comments or questions about this standard, please call AWWA Engineering and Technical Services at 303.794.7711, FAX at 303.795.7603, write to the group at 6666 West Quincy Avenue, Denver, CO 80235-3098, or e-mail the group at standards@awwa.org.



**American Water Works
Association**

AWWA Standard

Automatically Controlled, Impressed-Current Cathodic Protection for the Interior Submerged Surfaces of Steel Water Storage Tanks

SECTION 1: GENERAL

Sec. 1.1 Scope

This standard describes automatically controlled, impressed-current cathodic protection systems intended to minimize corrosion of interior submerged surfaces of steel water storage tanks and 30-in. (750-mm) diameter and larger wet risers of elevated tanks.

This standard does not describe sacrificial (galvanic) anode-type cathodic protection systems or manually controlled, impressed-current systems.

Sec. 1.2 Purpose

The purpose of this standard is to provide the minimum requirements for automatically controlled, impressed-current cathodic protection for the interior submerged surfaces of steel water storage tanks, including design, system components, quality of work, installation, operation, and maintenance.