



**American Water Works
Association**

The Authoritative Resource on Safe Water®

ANSI/AWWA D120-09
(Revision of ANSI/AWWA D120-02)

AWWA Standard

Thermosetting Fiberglass-Reinforced Plastic Tanks



Effective date: Oct. 1, 2009.

First edition approved by AWWA Board of Directors Jan. 30, 1984.

This edition approved Jan. 25, 2009.

Approved by American National Standards Institute Aug. 13, 2009.

6666 West Quincy Avenue
Denver, CO 80235-3098
T 800.926.7337
www.awwa.org

Advocacy
Communications
Conferences
Education and Training
Science and Technology
Sections

AWWA Standard

This document is an American Water Works Association (AWWA) standard. It is not a specification. AWWA standards describe minimum requirements and do not contain all of the engineering and administrative information normally contained in specifications. The AWWA standards usually contain options that must be evaluated by the user of the standard. Until each optional feature is specified by the user, the product or service is not fully defined. AWWA publication of a standard does not constitute endorsement of any product or product type, nor does AWWA test, certify, or approve any product. The use of AWWA standards is entirely voluntary. This standard does not supersede or take precedence over or displace any applicable law, regulation, or codes of any governmental authority. AWWA standards are intended to represent a consensus of the water supply industry that the product described will provide satisfactory service. When AWWA revises or withdraws this standard, an official notice of action will be placed on the first page of the classified advertising section of *Journal AWWA*. The action becomes effective on the first day of the month following the month of *Journal AWWA* publication of the official notice.

American National Standard

An American National Standard implies a consensus of those substantially concerned with its scope and provisions. An American National Standard is intended as a guide to aid the manufacturer, the consumer, and the general public. The existence of an American National Standard does not in any respect preclude anyone, whether that person has approved the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not conforming to the standard. American National Standards are subject to periodic review, and users are cautioned to obtain the latest editions. Producers of goods made in conformity with an American National Standard are encouraged to state on their own responsibility in advertising and promotional materials or on tags or labels that the goods are produced in conformity with particular American National Standards.

CAUTION NOTICE: The American National Standards Institute (ANSI) approval date on the front cover of this standard indicates completion of the ANSI approval process. This American National Standard may be revised or withdrawn at any time. ANSI procedures require that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of publication. Purchasers of American National Standards may receive current information on all standards by calling or writing the American National Standards Institute, 25 West 43rd Street, Fourth Floor, New York, NY 10036; (212) 642-4900.

All rights reserved. No part of this publication may be reproduced or transmitted in any form or by any means, electronic or mechanical, including photocopy, recording, or any information or retrieval system, except in the form of brief excerpts or quotations for review purposes, without the written permission of the publisher.

Copyright © 2009 by American Water Works Association
Printed in USA

Committee Personnel

The AWWA Standards Committee on Thermosetting Fiberglass-Reinforced Plastic Tanks, which developed and approved this standard, had the following personnel at the time of approval:

Phillip A. Sharff, *Chair*

General Interest Members

J.J. Cusack Jr., Bryant Associates, Boston, Mass. (AWWA)

M.W. Grimm,* Standards Council Liaison, Sunrise Water Authority,
Happy Valley, Ore. (AWWA)

R. Lewandowski, Corrosion Resistant Composites, Timonium, Md. (AWWA)

S.M. Passarelli,* Standards Engineer Liaison, AWWA, Denver, Colo. (AWWA)

P.A. Sharff, Simpson Gumpertz & Heger Inc., Waltham, Mass. (AWWA)

Producer Members

S.D. Curran, Fiberglass Tank & Pipe Institute, Houston, Texas (AWWA)

J. Small, Darco Incorporated, Denver, Colo. (AWWA)

User Members

C.J. Patla, Connecticut Water Service Inc., Clinton, Conn. (NEWWA)

C.N. Strother, Denver Water, Denver, Colo. (AWWA)

*Liaison, nonvoting

This page intentionally blank.

Contents

All AWWA standards follow the general format indicated subsequently. Some variations from this format may be found in a particular standard.

SEC.	PAGE	SEC.	PAGE
Foreword		4.6	Physical and Mechanical Properties of Tank Shell 8
I	vii	4.7	Environmental Resistance of Tank Shell9
I.A	vii	4.8	Leakage Under Internal Pressure 9
I.B	vii	4.9	Additional Requirements for Underground Tanks 9
I.C	viii	4.10	Construction 9
II	x	5	Verification
III	x	5.1	General 17
III.A	x	5.2	Production Tests..... 18
III.A	x	5.3	Physical and Mechanical Properties of Tank Shell 19
III.B	xi	5.4	Environmental Resistance 20
III.C	xi	5.5	Additional Tests for Underground Tanks 21
IV	xi	5.6	Aboveground-Tank Surface Burning Characteristics 23
V	xi	5.7	Retest 23
		5.8	Inspection and Testing by Purchaser..... 23
Standard		6	Delivery
1	General	6.1	Marking..... 24
1.1	1	6.2	Packaging and Shipping 24
1.2	2	6.3	Handling 25
1.3	2	6.4	Installation..... 25
2	References 2	6.5	Affidavit of Compliance 26
3	Definitions 4		
4	Requirements		
4.1	5		
4.2	5		
4.3	5		
4.4	6		
4.5	7		

Appendixes		3	Pipe for Nozzle Assembly	14	
A	Explanatory Notes to D120	27	4	Minimum Flange Thickness for FRP Nozzles	14
B	Preinstallation Site Analysis for Underground Tanks	29	5	Shear-Bond Area—Nozzles	16
C	Accessories for Underground Tanks	31	6	Torques on Pipe Fittings.....	22
D	Flanged-Joint Bolts, Gaskets, and Installation	33	Figures		
Tables		3	1	Flanged Nozzle.....	15
1	Design Loads	7	2	Reinforcement of Cut Tank Wall for Nozzle Attachment	16
2	Minimum Widths of Overlaid Joints (Exclusive of Taper)	11	3	Installed Nozzle (With Pipe Penetration).....	17
			4	Installed Nozzle (Without Pipe Penetration).....	17

Foreword

This foreword is for information only and is not a part of ANSI/AWWA D120.

I. Introduction.

I.A. *Background.* The purpose of this standard is to establish the significant quality requirements for commercially available thermosetting fiberglass-reinforced plastic (FRP) tanks for use in the water utility industry. This standard is based on the technology for the fabrication of the tanks by either the contact-molded or filament-wound process. It is intended that the tanks are to be used for the storage of water and other liquids. Both aboveground and underground tanks are covered. The specific application must consider the limitations as specified according to Sec. 1.1, and information must be provided by the user to completely describe the tank requirements.

I.B. *History.* In June 1971, the Engineering and Construction Committee, appointed by the AWWA Technical and Professional Council, evaluated the use of reinforced plastics in the water utility industry and found sufficient use of products made from this material to recommend the development of an AWWA standard. One of the most extensive uses of reinforced plastics was for the construction of tanks. At the 1974 fall meeting, the AWWA Standards Council approved the formation of a committee for the preparation of an AWWA standard for reinforced plastic tanks for the water utility industry.

The standards committee began the preparation of the new standard early in 1975. The responses to a questionnaire sent out by the Engineering and Construction Committee indicated that the methods being followed for specifying and purchasing reinforced plastic products varied within the water utility industry. Frequently, it was the practice for the water utilities that were planning on using reinforced plastic products to state the actual or anticipated service conditions, and the manufacturer then warranted the product for that service. In other instances, the manufacturer presented a product for a particular type and condition of service, and the water utility then made the selection based on this presentation. Because of these practices, functional and product-design requirements used by both water utilities and tank fabricators evolved, and many of these were available to the committee.

In addition, applicable standards, specifications, and test methods published by ASTM International* (ASTM) and the US Department of Commerce were reviewed

* ASTM International, 100 Barr Harbor Drive, West Conshohocken, PA 19428.

by the committee. There were two documents the committee used as the basis for the AWWA standard: (1) ASTM D3299, Specification for Filament-Wound Glass-Fiber-Reinforced Thermoset Resin Chemical-Resistant Tanks, and (2) National Bureau of Standards Voluntary Product Standard PS-15, Custom Contact-Molded Reinforced Polyester Chemical-Resistant Process Equipment.

The initial draft of the first edition of the standard was prepared and circulated to the committee members in 1976. The final draft was submitted to the committee for letter ballot voting on Apr. 15, 1983, and a consensus for acceptance was received. The standard was reaffirmed without revision on June 18, 1989.

In June 1997, the AWWA Standards Committee on Thermosetting Fiberglass-Reinforced Plastic Tanks began preparation of the revised standard. Inquiries into the water storage industry indicated the need for standards governing underground fiberglass-reinforced plastic tanks. The committee decided to incorporate in the revised standard current relevant standards for underground tanks used for storage of products other than water. For this purpose, the committee referred to UL* 1316, Glass-Fiber-Reinforced Plastic Underground Storage Tanks. Further, the committee recognized the need to update the standard to incorporate current standards for aboveground tank design and production. Standards referred to for this purpose included (1) ASTM D3299, Specification for Filament-Wound Glass-Fiber-Reinforced Thermoset Resin Corrosion-Resistant Tanks and (2) ASTM D4097, Specification for Contact-Molded Glass-Fiber-Reinforced Thermoset Resin Corrosion-Resistant Tanks.

The initial draft of the second edition of the standard was prepared and circulated to the committee members in 1998. The final draft was submitted to the committee for letter ballot voting in December 2001, and a consensus for acceptance was received. The second edition was approved by the AWWA Board of Directors on June 16, 2002.

This edition was approved on Jan. 25, 2009.

I.C. *Acceptance.* In May 1985, the US Environmental Protection Agency (USEPA) entered into a cooperative agreement with a consortium led by NSF International (NSF) to develop voluntary third-party consensus standards and a certification program for direct and indirect drinking water additives. Other members of the consortium included the American Water Works Association Research Foundation (AwwaRF), the Conference of State Health and Environmental Managers (COSHEM), the American Water Works Association (AWWA), and the Association of State Drinking Water Administrators (ASDWA). The consortium is responsible for

* Underwriters Laboratories Inc., 333 Pfingsten Rd., Northbrook, IL 60062.

the cooperative effort of manufacturers, regulators, product users, and other interested parties that develop and maintain the NSF standards.

In the United States, authority to regulate products for use in, or in contact with, drinking water rests with individual states. Local agencies may choose to impose requirements more stringent than those required by the state. To evaluate the health effects of products and drinking water additives from such products, state and local agencies may use various references, including

1. An advisory program formerly administered by USEPA, Office of Drinking Water, discontinued on Apr. 7, 1990.
2. Specific policies of the state or local agency.
3. Two standards developed under the direction of NSF, NSF*/ANSI†60, Drinking Water Treatment Chemicals—Health Effects, and NSF/ANSI 61, Drinking Water System Components—Health Effects.
4. Other references, including AWWA standards, *Food Chemicals Codex*, *Water Chemicals Codex*,‡ and other standards considered appropriate by the state or local agency.

Various certification organizations may be involved in certifying products in accordance with NSF/ANSI 61. Individual states or local agencies have authority to accept or accredit certification organizations within their jurisdiction. Accreditation of certification organizations may vary from jurisdiction to jurisdiction.

Annex A to NSF/ANSI 61, “Toxicology Review and Evaluation Procedures,” does not stipulate a maximum allowable level (MAL) of a contaminant for substances not regulated by a USEPA final maximum contaminant level (MCL). The MALs of an unspecified list of “unregulated contaminants” are based on toxicity-testing guidelines (noncarcinogens) and risk characterization methodology (carcinogens). Use of Annex A procedures may not always be identical, depending on the certifier.

This standard does not address additives requirements. Thus, users of ANSI/AWWA D120 should consult the appropriate state or local agency having jurisdiction in order to

1. Determine additives requirements, including applicable standards.
2. Determine the status of certifications by parties offering to certify products for contact with, or treatment of, drinking water.
3. Determine current information on product certification.

* NSF International, 789 N. Dixboro Road, Ann Arbor, MI 48105.

† American National Standards Institute, 25 West 43rd Street, Fourth Floor, New York, NY 10036.

‡ Both publications available from National Academy of Sciences, 500 Fifth Street, N.W., Washington, DC 20001.

II. Special Issues. This standard has no applicable information for this section.

III. Use of This Standard. It is the responsibility of the user of an AWWA standard to determine that the products described in that standard are suitable for use in the particular application being considered. Section III.A summarizes supplemental information that should be considered. The purchaser should review this information and other appropriate data and make provisions in the supplemental conditions to describe the specific service requirements.

III.A. Purchaser Options and Alternatives. Purchasers are advised that, while this standard presents information on materials and procedures for manufacture of the tank, it does not contain complete engineering information needed to prepare complete requirements for a particular tank installation. A specific installation may require provisions more restrictive than those in the standard and most certainly will require additional design and installation features. In placing orders for thermosetting fiberglass-reinforced plastic tanks to be manufactured in accordance with this standard, the purchaser, in its requirements, should include the following information:

1. Standard used—that is, ANSI/AWWA D120, Thermosetting Fiberglass-Reinforced Plastic Tanks, of latest revision.
2. Whether compliance with NSF/ANSI 61, Drinking Water System Components—Health Effects, is required, in addition to the requirements of the Safe Drinking Water Act.
3. Type of tank—aboveground or underground.
4. Capacity.
5. Material to be stored in the tank.
6. Height, width, and weight limitations.
7. Temperature conditions.
8. Fittings and attachments to be provided and their description.
9. Installation conditions.
10. Operating conditions.
11. Whether certified drawings are to be provided (Sec. III.C, Foreword).
12. Details of other federal, state or provincial, and local requirements (Sec. 4.2.1 and Sec. 4.3).
13. Whether ultraviolet absorbers are to be added (Sec. 4.3.1.2).
14. Whether fire-retardant agents are to be added (Sec. 4.3.1.4).
15. Loading conditions and design criteria (Sec. 4.5).

16. Whether the outside surface is to be pigmented, painted, or dyed (Sec. 4.10.2.4).
17. Type of flange gaskets (Sec. 4.10.5).
18. Location of hold-down or lift lugs (Sec. 4.10.7 and 4.10.8).
19. Test samples to be provided by the manufacturer (Sec. 5.1.3).
20. Test media for immersion tests (Sec. 5.4.2.2).
21. Test temperature for immersion tests (Sec. 5.4.2.4).
22. Retest agreement (Sec. 5.7).
23. Whether plant inspection is required (Sec. 5.8.1).
24. Tests to be performed by the manufacturer (Sec. 5.8.4).
25. Whether an affidavit of compliance is to be provided (Sec. 6.5).

III.B. *Modification to Standard.* Any modification to the provisions, definitions, or terminology in this standard must be provided by the purchaser.

III.C. *Information to Be Supplied by Manufacturer.* When required, the manufacturer or its representative shall submit, for acceptance by the purchaser, certified drawings showing the principal dimensions, construction details, and materials used for the fabrication. Work shall be done in accordance with these certified drawings after they have been accepted by the purchaser.

IV. Major Revisions. Major revisions made to the standard in this edition include the following:

1. Acceptable types of fittings for tanks have been expanded and clarified.
2. The internal pressure test for aboveground tanks was limited to hydrostatic testing; and the standard was updated to allow either hydrostatic or aerostatic testing for underground tanks subject to manufacturer's input.
3. Nonmandatory guidance on manways, manway extensions, anchor straps, and connection hardware for underground tanks has been expanded.
4. A new nonmandatory appendix on flanged-joint bolts, gaskets, and installation has been added.

V. Comments. If you have any comments or questions about this standard, please call the AWWA Volunteer and Technical Support Group at 303.794.7711, FAX at 303.795.7603, write to the group at 6666 West Quincy Avenue, Denver, CO 80235-3098, or e-mail at standards@awwa.org.

This page intentionally blank.



**American Water Works
Association**

AWWA Standard

Thermosetting Fiberglass-Reinforced Plastic Tanks

SECTION 1: GENERAL

Sec. 1.1 Scope

This standard describes the composition, performance requirements, construction practices and workmanship, design, and methods of testing thermosetting fiberglass-reinforced plastic (FRP) tanks for the storage of water or other liquids used in water supply service.

1.1.1 *Limit of standard.* This standard is limited to atmospheric pressure, vented, cylindrical, and spherical tanks, installed either aboveground or underground.

1.1.2 *Temperature limits.* This standard is limited to tanks whose service temperature does not exceed 180°F (82°C) for aboveground tanks and 150°F (66°C) for underground tanks. Consult the tank manufacturer for recommended temperature limits (both minimum and maximum) for specific equipment and service requirements.

1.1.3 *Service limits.* The service limits for environmental exposure and structural loads shall be determined based on tests of laminates that are determined by the engineer to be representative of the materials and methods of fabrication used in the tank.