BS ISO 12492:2012



### **BSI Standards Publication**

Rubber, raw —
Determination of
water content by
Karl Fischer method

NO COPYING WITHOUT BSI PERMISSION EXCEPT AS PERMITTED BY COPYRIGHT LAW



BS ISO 12492:2012 BRITISH STANDARD

This is a preview of "BS ISO 12492:2012". Click here to purchase the full version from the ANSI store.

This British Standard is the UK implementation of ISO 12492:2012.

The UK participation in its preparation was entrusted to Technical Committee PRI/23, Test methods for rubber and non-black compounding ingredients.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2012. Published by BSI Standards Limited 2012.

ISBN 978 0 580 66143 3

ICS 83.040.10

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 October 2012.

Amendments issued since publication

Date Text affected

#### INTERNATIONAL

ISO

This is a preview of "BS ISO 12492:2012". Click here to purchase the full version from the ANSI store.

First edition 2012-10-01

# Rubber, raw — Determination of water content by Karl Fischer method

Caoutchouc brut — Détermination de la teneur en eau par la méthode de Karl Fischer



BS ISO 12492:2012 **ISO 12492:2012(E)** 

This is a preview of "BS ISO 12492:2012". Click here to purchase the full version from the ANSI store.



#### **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2012

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office Case postale 56 • CH-1211 Geneva 20 Tel. + 41 22 749 01 11 Fax + 41 22 749 09 47 E-mail copyright@iso.org Web www.iso.org

Published in Switzerland

Con	itent	ts	Page
Fore	word		iv
Introduction			v
1	Scop	pe	1
2	Normative references		1
3	Principle		1
4	Reagents		2
5	Apparatus		
6	Calibration		3
7	Sam	ipling and preparation of test piece	3
8	Procedure		3
	8.1	Power on	
	8.2	Selection of the generator electrode	
	8.3	Filling the electrolysis cell	
	8.4	Equipment check	4
	8.5	Analysis	5
9	Precision		6
10	Test report		6
Anne	<b>x A</b> (n	ormative) Calibration schedule	7

#### **Foreword**

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 12492 was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 2, *Testing and analysis*.

#### Introduction

The water content of raw rubber is one of the important characteristics to be determined as a quality control test. Different synthetic rubbers contain varying amounts of water. Water can affect product quality, texture, shelf life, chemical stability and reactivity. A high amount of water can cause processing difficulties.

Water contamination is a cause for major concern in a large number of applications. In the rubber industry, water is one of the major damaging contaminants and is often overlooked as a primary cause of component failure. For certain applications in the rubber industry, even a small amount of water may have damaging effects on production.

Several methods are available for the determination of water content. A Karl Fischer (KF) coulometric titrator is one of the most accurate methods. Unlike other techniques, it can trace low levels of free, emulsified and dissolved water (which cannot be detected with normal gravimetric methods). The test is capable of measuring water levels as low as 0,01 %.

Unlike gravimetric measurements, which are indirect methods that assume, all volatiles removed are water, Karl Fischer titration is a direct method that is almost specific for water. The method is especially useful for low moisture levels (<1%).

The new test method will help to determine the water content of the raw rubber and rubber compounds in shortest possible time and will be helpful for quality control at the laboratories. Coulometric determination of water is an absolute method.

## Rubber, raw — Determination of water content by Karl Fischer method

WARNING — Persons using this International Standard should be familiar with normal laboratory practice. This International Standard does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any national regulatory conditions.

CAUTION — Certain procedures specified in this International Standard may involve the use or generation of substances, or the generation of waste, that could constitute a local environmental hazard. Reference should be made to appropriate documentation on safe handling and disposal after use.

#### 1 Scope

This International Standard specifies a test method for the determination of water content of raw rubber and compounded rubber using a coulometric Karl Fischer titration method. It applies to the water content range between 0,01 % and 1 %. As this is a very sensitive method, contact of sample with any moisture, even from the surrounding environment, must be eliminated as much as possible.

#### 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 760, Determination of water — Karl Fischer method (General method)

ISO 1795, Rubber, raw natural and raw synthetic — Sampling and further preparative procedure

ISO 18899:2004, Rubber – Guide to the calibration of test equipment

#### 3 Principle

The water determination test (Karl Fischer method) is designed to determine the water content in substances, utilizing the quantitative reaction of water with iodine and sulfur dioxide in the presence of a lower alcohol such as methanol and an organic base, as shown in the following formulae:

$$H_2O + I_2 + SO_2 + 3 RN \rightarrow 2(RN+H)I^- + RN \cdot SO_3$$

$$RN \cdot SO_3 + CH_3OH \rightarrow (RN+H)O \cdot SO_2 \cdot OCH_3$$
.

There are two determination methods which differ in the way the iodine is provided: the volumetric titration method and the coulometric titration method.

In the volumetric titration method, iodine required for reaction with water is previously dissolved and the water content is determined by measuring the amount of iodine consumed as a result of reaction with water present in a sample.

In the coulometric titration method, first, iodine is produced by electrolysis of the reagent containing iodide ion, then the water content in a sample is determined by measuring the quantity of electricity which is required for the electrolysis, i.e. for the production of iodine, based on the quantitative reaction of the generated iodine with water.