

This is a preview of "BS EN ISO 1974:2012". [Click here to purchase the full version from the ANSI store.](#)

BS EN ISO 1974:2012



BSI Standards Publication

Paper — Determination of tearing resistance — Elmendorf method

NO COPYING WITHOUT BSI PERMISSION EXCEPT AS PERMITTED BY COPYRIGHT LAW

raising standards worldwide™



This is a preview of "BS EN ISO 1974:2012". [Click here to purchase the full version from the ANSI store.](#)

This British Standard is the UK implementation of EN ISO 1974:2012. It supersedes BS EN 21974:1994 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PAI/11, Methods of test for paper, board and pulps.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2012. Published by BSI Standards Limited 2012

ISBN 978 0 580 70486 4

ICS 85.060

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 May 2012.

Amendments issued since publication

Date	Text affected
------	---------------

This is a preview of "BS EN ISO 1974:2012". [Click here to purchase the full version from the ANSI store.](#)

EUROPÄISCHE NORM

May 2012

ICS 85.060

Supersedes EN 21974:1994

English Version

Paper - Determination of tearing resistance - Elmendorf method (ISO 1974:2012)

Papier - Détermination de la résistance au déchirement -
Méthode Elmendorf (ISO 1974:2012)

Papier - Bestimmung des Durchreißwiderstandes -
Elmendorf Methode (ISO 1974:2012)

This European Standard was approved by CEN on 10 May 2012.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

This is a preview of "BS EN ISO 1974:2012". [Click here to purchase the full version from the ANSI store.](#)

Foreword

This document (EN ISO 1974:2012) has been prepared by Technical Committee ISO/TC 6 "Paper, board and pulps" in collaboration with Technical Committee CEN/TC 172 "Pulp, paper and board" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 2012, and conflicting national standards shall be withdrawn at the latest by November 2012.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 21974:1994.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 1974:2012 has been approved by CEN as a EN ISO 1974:2012 without any modification.

This is a preview of "BS EN ISO 1974:2012". [Click here to purchase the full version from the ANSI store.](#)

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Apparatus	2
6 Sampling	4
7 Conditioning	4
8 Preparation of test pieces	4
9 Adjustment and calibration of apparatus	5
10 Procedure	5
11 Calculation and expression of results	6
11.1 Tearing resistance	6
11.2 Tear index	6
11.3 Coefficient of variation	7
12 Test report	7
Annex A (normative) Adjustment and maintenance of Elmendorf-type tear testers	8
Annex B (normative) Calibration of Elmendorf-type tear testers	10
Annex C (informative) Precision	12
Bibliography	14

This is a preview of "BS EN ISO 1974:2012". [Click here to purchase the full version from the ANSI store.](#)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 1974 was prepared by Technical Committee ISO/TC 6, *Paper, board and pulps*, Subcommittee SC 2, *Test methods and quality specifications for paper and board*.

This fourth edition cancels and replaces the third edition (ISO 1974:1990), which has been technically revised. The specification for the tester has been moved from Annex A to Clause 5 and is given in more general terms so that this International Standard is applicable to a wider range of designs. In addition, new precision data have been inserted in Annex C.

This is a preview of "BS EN ISO 1974:2012". [Click here to purchase the full version from the ANSI store.](#)

Paper — Determination of tearing resistance — Elmendorf method

1 Scope

This International Standard specifies a method for determining the (out-of-plane) tearing resistance of paper. It can also be used for boards having a low grammage if the tearing resistance is within the range of the instrument.

This International Standard does not apply to corrugated fibreboard, but it may be applied to the components of such boards. It is not suitable for determining the cross-direction tearing resistance of highly directional paper (or board).

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 186, *Paper and board — Sampling to determine average quality*

ISO 187, *Paper, board and pulps — Standard atmosphere for conditioning and testing and procedure for monitoring the atmosphere and conditioning of samples*

ISO 536, *Paper and board — Determination of grammage*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

tearing resistance

mean force per sheet required to continue the tearing started by an initial cut in the test piece

NOTE 1 If the initial cut is in the machine direction, the result is given as the machine-direction tearing resistance; similarly, if the initial cut is in the cross-direction, the result is given as the cross-direction tearing resistance.

NOTE 2 The tearing resistance is expressed in millinewtons (mN).

3.2

tear index

tearing resistance of the paper (or board) divided by its grammage

NOTE The tear index is expressed in millinewton square metres per gram ($\text{mN}\cdot\text{m}^2/\text{g}$).

3.3

test piece

pack of four rectangular sheets of the same size

NOTE The dimensions depend on the design of the apparatus clamp used (see Clause 8).

4 Principle

An initial cut is made in a test piece (of four superimposed sheets), which is then torn out-of-plane through a given distance along one single tear line using a pendulum. The work done in tearing the test piece is measured as the loss in energy of the pendulum.

The mean tearing force of a single sheet is calculated by dividing the work done by the distance torn and the number of sheets in a test piece.