

This is a preview of "BS EN 10025-5:2019". [Click here to purchase the full version from the ANSI store.](#)



BSI Standards Publication

## Hot rolled products of structural steels

---

Part 5: Technical delivery conditions for structural steels  
with improved atmospheric corrosion resistance

This is a preview of "BS EN 10025-5:2019". [Click here to purchase the full version from the ANSI store.](#)

## National foreword

This British Standard is the UK implementation of EN 10025-5:2019. It supersedes BS EN 10025-5:2004, which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee ISE/103, Structural Steels Other Than Reinforcements.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2019  
Published by BSI Standards Limited 2019

ISBN 978 0 580 73969 9

ICS 77.140.50; 91.100.99; 77.140.10

**Compliance with a British Standard cannot confer immunity from legal obligations.**

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 August 2019.

### Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

---

This is a preview of "BS EN 10025-5:2019". [Click here to purchase the full version from the ANSI store.](#)

EUROPÄISCHE NORM

August 2019

ICS 77.140.10; 77.140.50

Supersedes EN 10025-5:2004

English Version

## Hot rolled products of structural steels - Part 5: Technical delivery conditions for structural steels with improved atmospheric corrosion resistance

Produits laminés à chaud en aciers de construction -  
Partie 5 : Conditions techniques de livraison pour les  
aciers de construction à résistance améliorée à la  
corrosion atmosphérique

Warmgewalzte Erzeugnisse aus Baustählen - Teil 5:  
Technische Lieferbedingungen für wetterfeste  
Baustähle

This European Standard was approved by CEN on 16 June 2019.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels**

This is a preview of "BS EN 10025-5:2019". [Click here to purchase the full version from the ANSI store.](#)

<b>Contents</b>		<b>Page</b>
European foreword.....		4
1	Scope .....	6
2	Normative references.....	7
3	Terms and definitions .....	9
4	Classification and designation.....	10
4.1	Classification.....	10
4.1.1	Main quality classes .....	10
4.1.2	Grades and qualities .....	10
4.2	Designation.....	10
5	Information to be supplied by the purchaser .....	11
5.1	Mandatory information .....	11
5.2	Options.....	11
6	Manufacturing process.....	11
6.1	Steel making process .....	11
6.2	Deoxidation .....	11
6.3	Delivery conditions .....	11
7	Requirements .....	12
7.1	General.....	12
7.2	Chemical composition .....	12
7.3	Mechanical properties.....	12
7.3.1	General.....	12
7.3.2	Impact properties .....	13
7.3.3	Improved deformation properties perpendicular to the surface .....	13
7.4	Technological properties .....	13
7.4.1	Weldability .....	13
7.4.2	Formability and flame straightening.....	13
7.5	Surface properties .....	14
7.5.1	Strip.....	14
7.5.2	Plates and wide flats .....	14
7.5.3	Sections.....	14
7.5.4	Bars and rods.....	14
7.6	Internal soundness.....	14
7.7	Dimensions, tolerances on dimensions and shape, mass.....	15
8	Inspection .....	15
8.1	Type of inspection and inspection document.....	15
8.2	Content of inspection document.....	15
8.3	Tests to be carried out for specific inspection.....	16
9	Frequency of testing and preparation of samples and test pieces .....	16
9.1	Frequency of testing.....	16
9.1.1	Chemical analysis.....	16
9.1.2	Mechanical tests .....	16
9.2	Preparation of samples and test pieces .....	16
9.2.1	Selection and preparation of samples for chemical analysis .....	16
9.2.2	Location of samples and orientation and test pieces for mechanical tests.....	17

This is a preview of "BS EN 10025-5:2019". [Click here to purchase the full version from the ANSI store.](#)

<b>9.2.3</b>	<b>Preparation of test pieces for mechanical tests</b> .....	<b>17</b>
<b>9.3</b>	<b>Identification of samples and test pieces</b> .....	<b>18</b>
<b>10</b>	<b>Test methods</b> .....	<b>18</b>
<b>10.1</b>	<b>Chemical analysis</b> .....	<b>18</b>
<b>10.2</b>	<b>Mechanical tests</b> .....	<b>18</b>
<b>10.2.1</b>	<b>Tensile test</b> .....	<b>18</b>
<b>10.2.2</b>	<b>Impact test</b> .....	<b>18</b>
<b>10.3</b>	<b>Ultrasonic testing</b> .....	<b>19</b>
<b>10.4</b>	<b>Retests</b> .....	<b>19</b>
<b>11</b>	<b>Marking, labelling, packaging</b> .....	<b>19</b>
<b>12</b>	<b>Complaints</b> .....	<b>19</b>
<b>13</b>	<b>Options</b> .....	<b>20</b>
<b>Annex A</b>	<b>(normative) Location of samples and test pieces</b> .....	<b>29</b>
<b>Annex B</b>	<b>(informative) Additional information for the use of steel with improved atmospheric corrosion resistance</b> .....	<b>32</b>
<b>Annex C</b>	<b>(informative) Notes on fabrication</b> .....	<b>33</b>
<b>C.1</b>	<b>Weldability</b> .....	<b>33</b>
<b>C.2</b>	<b>Riveting and bolting</b> .....	<b>33</b>
<b>Annex D</b>	<b>(informative) List of Options of EN 10025-2 to -6</b> .....	<b>34</b>
<b>Bibliography</b>	.....	<b>36</b>

## European foreword

This document (EN 10025-5:2019) has been prepared by Technical Committee CEN/TC 459/SC 3 "Structural steels other than reinforcements", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by February 2020 and conflicting national standards shall be withdrawn at the latest by February 2020.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 10025-5:2004.

This document consists of the following parts, under the general title *Hot rolled products of structural steels*:

- *Part 1: General technical delivery conditions*
- *Part 2: Technical delivery conditions for non-alloy structural steels*
- *Part 3: Technical delivery conditions for normalized/normalized rolled weldable fine grain structural steels*
- *Part 4: Technical delivery conditions for thermomechanical rolled weldable fine grain structural steels*
- *Part 5: Technical delivery conditions for structural steels with improved atmospheric corrosion resistance*
- *Part 6: Technical delivery conditions for flat products of high yield strength structural steels in the quenched and tempered condition*

For a short transition period there will be a coexistence of EN 10025-1:2004 with EN 10025-2:2019 to - EN 10025-6:2019, since the new EN 10025-1 has to fulfil the requirements of the CPR and will therefore be published later. For this short transition period up-to-the publication of the next edition of part 1 the following is to be taken into account for EN 10025-1:2004:

- a) all dated and undated references to EN 10025-1:2004 to EN 10025-6:2004 are unchanged to this version with following exception: In 9.2.2.1 the references are 8.3.1 and 8.3.2 instead of 8.4.1 and 8.4.2;
- b) Clauses 5, 12 and 13 of EN 10025-1:2004 are no longer relevant.

The main changes with respect to the previous edition are listed below:

- a) part 5 is now a stand-alone standard for technical delivery conditions including the preparation of samples and test pieces, the test methods, the marking, labelling and packaging and the drawings;
- b) for applications under the CPR this document and part 1 are to be used together;
- c) requirements for elements not defined were added to 7.2.1 and 7.2.2;
- d) Option 33 were added, Options 9 and 21 were deleted;
- e) key to Figure A.1 was updated;

This is a preview of "BS EN 10025-5:2019". [Click here to purchase the full version from the ANSI store.](#)

- f) steel grades S355J4, S420J0W, S420J2W, S420J4W, S460J0W, S460J2W and S460J4W were added to Tables 1 to 5;
- g) Annex B concerning the corresponding EURONORMS deleted;
- h) references were updated and document editorial revised.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Republic of North Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

This is a preview of "BS EN 10025-5:2019". [Click here to purchase the full version from the ANSI store.](#)

## 1 Scope

This document specifies technical delivery conditions for flat and long products of hot rolled steels with improved atmospheric corrosion resistance in the grades and qualities given in Tables 2 and 3 (chemical composition) and Tables 4 and 5 (mechanical properties) in the usual delivery conditions as given in 6.3.

The thicknesses in which products of the steel grades and qualities specified in this document can be supplied are given in Table 1.

**Table 1 — Product forms for the different steel grades with improved atmospheric corrosion resistance depending on their thickness**

Designation		Flat products		Long products		
				Sections	Bars	Rods
Steel name	Steel number	Nominal thickness		Nominal thickness or diameter		
		mm		mm		
		≤ 12	≤ 150	≤ 63	≤ 150	≤ 60
S235J0W	1.8958		x	x	x	x
S235J2W	1.8961		x	x	x	x
S355J0WP	1.8945	x				
S355J2WP	1.8946	x				
S355J0W	1.8959		x	x	x	x
S355J2W	1.8965		x	x	x	x
S355K2W	1.8967		x	x	x	x
S355J4W	1.8787		x	x	x	x
S355J5W	1.8991		x			
S420J0W	1.8943		x	x		
S420J2W	1.8949		x	x		
S420K2W	1.8997		x	x		
S420J4W	1.8954		x			
S420J5W	1.8992		x			
S460J0W	1.8966		x	x		
S460J2W	1.8980		x	x		
S460K2W	1.8990		x	x		
S460J4W	1.8981		x			
S460J5W	1.8993		x			

The steels specified in this document are not intended to be heat treated except products delivered in the delivery condition +N. Stress relieving is accepted. Products delivered in +N condition can be hot formed and/or normalized after delivery (see Clause 3).