

This is a preview of "BS EN 826:2013". [Click here to purchase the full version from the ANSI store.](#)

**BS EN 826:2013**



BSI Standards Publication

# Thermal insulating products for building applications — Determination of compression behaviour

NO COPYING WITHOUT BSI PERMISSION EXCEPT AS PERMITTED BY COPYRIGHT LAW

*raising standards worldwide™*



This is a preview of "BS EN 826:2013". [Click here to purchase the full version from the ANSI store.](#)

This British Standard is the UK implementation of EN 826:2013. It supersedes BS EN 826:1996, which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee B/540, Energy performance of materials components and buildings.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2013.  
Published by BSI Standards Limited 2013.

ISBN 978 0 580 78039 4

ICS 91.100.60

**Compliance with a British Standard cannot confer immunity from legal obligations.**

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 March 2013.

#### **Amendments issued since publication**

| Date | Text affected |
|------|---------------|
|------|---------------|

---

This is a preview of "BS EN 826:2013". [Click here to purchase the full version from the ANSI store.](#)

## EUROPÄISCHE NORM

March 2013

ICS 91.100.60

Supersedes EN 826:1996

English Version

## Thermal insulating products for building applications - Determination of compression behaviour

Produits isolants thermiques destinés aux applications du  
bâtiment - Détermination du comportement en compression

Wärmedämmstoffe für das Bauwesen - Bestimmung des  
Verhaltens bei Druckbeanspruchung

This European Standard was approved by CEN on 15 December 2012.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

This is a preview of "BS EN 826:2013". [Click here to purchase the full version from the ANSI store.](#)

| <b>Contents</b>   |  | Page      |
|---|--|-----------|
| Foreword.....   |  | 3         |
| <b>1</b> <b>Scope.....</b>  |  | <b>5</b>  |
| <b>2</b> <b>Normative references.....</b>   |  | <b>5</b>  |
| <b>3</b> <b>Terms and definitions .....</b>   |  | <b>5</b>  |
| <b>4</b> <b>Principle.....</b>  |  | <b>6</b>  |
| <b>5</b> <b>Apparatus .....</b>   |  | <b>6</b>  |
| <b>6</b> <b>Test specimens .....</b>  |  | <b>6</b>  |
| <b>7</b> <b>Procedure .....</b>   |  | <b>7</b>  |
| <b>8</b> <b>Calculation and expression of results .....</b>   |  | <b>9</b>  |
| <b>9</b> <b>Accuracy of measurement.....</b>  |  | <b>10</b> |
| <b>10</b> <b>Test report .....</b>  |  | <b>11</b> |
| <b>Annex A (normative) Modifications to the general test method for cellular glass products .....</b> |  | <b>12</b> |

This is a preview of "BS EN 826:2013". [Click here to purchase the full version from the ANSI store.](#)

## Foreword

This document (EN 826:2013) has been prepared by Technical Committee CEN/TC 88 "Thermal insulating materials and products", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2013, and conflicting national standards shall be withdrawn at the latest by September 2013.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 826:1996.

The revision of this standard contains no major changes, only minor corrections and clarifications of an editorial nature.

This European standard has been prepared for building applications, but it may also be used in other areas where it is relevant.

This European test standard is one of the following group of related standards on test methods for determining dimensions and properties of thermal insulation materials and products, all of which fall within the scope of CEN/TC 88:

- EN 822, *Thermal insulating products for building applications — Determination of length and width*
- EN 823, *Thermal insulating products for building applications — Determination of thickness*
- EN 824, *Thermal insulating products for building applications — Determination of squareness*
- EN 825, *Thermal insulating products for building applications — Determination of flatness*
- EN 826, *Thermal insulating products for building applications — Determination of compression behaviour*
- EN 1602, *Thermal insulating products for building applications — Determination of the apparent density*
- EN 1603, *Thermal insulating products for building applications — Determination of dimensional stability under constant normal laboratory conditions (23 °C/50 % relative humidity)*
- EN 1604, *Thermal insulating products for building applications — Determination of dimensional stability under specified temperature and humidity conditions*
- EN 1605, *Thermal insulating products for building applications — Determination of deformation under specified compressive load and temperature conditions*
- EN 1606, *Thermal insulating products for building applications — Determination of compressive creep*
- EN 1607, *Thermal insulating products for building applications — Determination of tensile strength perpendicular to faces*
- EN 1608, *Thermal insulating products for building applications — Determination of tensile strength parallel to faces*

This is a preview of "BS EN 826:2013". [Click here to purchase the full version from the ANSI store.](#)

- EN 1609, *Thermal insulating products for building applications — Determination of short-term water absorption by partial immersion*
- EN 12085, *Thermal insulating products for building applications — Determination of linear dimensions of test specimens*
- EN 12086, *Thermal insulating products for building applications — Determination of water vapour transmission properties*
- EN 12087, *Thermal insulating products for building applications — Determination of long-term water absorption by immersion*
- EN 12088, *Thermal insulating products for building applications — Determination of long-term water absorption by diffusion*
- EN 12089, *Thermal insulating products for building applications — Determination of bending behaviour*
- EN 12090, *Thermal insulating products for building applications — Determination of shear behaviour*
- EN 12091, *Thermal insulating products for building applications — Determination of freeze-thaw resistance*
- EN 12429, *Thermal insulating products for building applications — Conditioning to moisture equilibrium under specified temperature and humidity conditions*
- EN 12430, *Thermal insulating products for building applications — Determination of behaviour under point load*
- EN 12431, *Thermal insulating products for building applications — Determination of thickness for floating floor insulating products*
- EN 13793, *Thermal insulating products for building applications — Determination of behaviour under cyclic loading*
- EN 13820, *Thermal insulating materials for building applications — Determination of organic content*

According to the CEN/CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

This is a preview of "BS EN 826:2013". [Click here to purchase the full version from the ANSI store.](#)

## 1 Scope

This European Standard specifies the equipment and procedures to be used when determining the compression behaviour of test specimens. It is applicable to thermal insulating products and can be used to determine the compressive stress in compressive creep tests and for applications in which insulation products are only exposed to short-term loads.

The method can be used for quality control purposes. It may also be employed to obtain reference values from which design values can be calculated using safety factors.

## 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 12085, *Thermal insulating products for building applications — Determination of linear dimensions of test specimens*

ISO 5725-1, *Accuracy (trueness and precision) of measurement methods and results — Part 1: General principles and definitions*

ISO 5725-2, *Accuracy (trueness and precision) of measurement methods and results — Part 2: Basic method for the determination of repeatability and reproducibility of a standard measurement method*

## 3 Terms and definitions

For the purposes of this standard, the following terms and definitions apply.

### 3.1

#### relative deformation

$\varepsilon$

ratio of the reduction in thickness of the test specimen to its initial thickness,  $d_0$ , measured in the direction of loading

### 3.2

#### compressive strength

$\sigma_m$

ratio of the maximum compressive force,  $F_m$ , reached when the strain,  $\varepsilon$ , at yield (see Figure 1b)) or rupture (see Figure 1a)) is less than 10 %, to the initial cross-sectional area of the test specimen

### 3.3

#### compressive stress at 10 % strain

$\sigma_{10}$

ratio of the compressive force,  $F_{10}$ , at 10 % strain,  $\varepsilon_{10}$ , to the initial cross section of the test specimen (see Figures 1c) and 1d)) for products presenting 10 % strain before possible yield or rupture

### 3.4

#### compression modulus of elasticity

$E$

compressive stress divided by the corresponding strain below the proportional limit, when the relationship is linear

Note 1 to entry: See Figure 1.