BS EN 12431:2013



BSI Standards Publication

Thermal insulating products for building applications — Determination of thickness for floating floor insulating products

NO COPYING WITHOUT BSI PERMISSION EXCEPT AS PERMITTED BY COPYRIGHT LAW



raising standards worldwide[™]

This British Standard is the UK implementation of EN 12431:2013. It supersedes BS EN 12431:1998 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee B/540, Energy performance of materials components and buildings.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2013.

Published by BSI Standards Limited 2013

ISBN 978 0 580 78053 0 ICS 91.100.60

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 April 2013.

Amendments issued since publication

Date Text affected

EN 40404

This is a preview of "BS EN 12431:2013". Click here to purchase the full version from the ANSI store.

EUROPÄISCHE NORM

March 2013

ICS 91.100.60

Supersedes EN 12431:1998

English Version

Thermal insulating products for building applications -Determination of thickness for floating floor insulating products

Produits isolants thermiques destinés aux applications du bâtiment - Détermination de l'épaisseur des produits d'isolation pour sol flottant Wärmedämmstoffe für das Bauwesen - Bestimmung der Dicke von Dämmstoffen unter schwimmendem Estrich

This European Standard was approved by CEN on 15 December 2012.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

BS EN 12431:2013 EN 12431:2013 (E)

This is a preview of "BS EN 12431:2013". Click here to purchase the full version from the ANSI store.

Contents

Foreword3		.3
1	Scope	.5
2	Normative references	.5
3	Terms and definitions	.5
4	Principle	.5
5	Apparatus	.5
6	Test specimens	.6
7	Procedure	.7
8	Calculation and expression of results	.8
9	Accuracy of measurement	.8
10	Test report	.8

Foreword

This document (EN 12431:2013) has been prepared by Technical Committee CEN/TC 88 "Thermal insulating materials and products", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2013, and conflicting national standards shall be withdrawn at the latest by September 2013.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 12431:1998.

The revision of this standard contains no major changes, only minor corrections and clarifications of an editorial nature.

This European Standard is one of a series of standards which specify test methods for determining dimensions and properties of thermal insulating materials and products. It supports a series of product standards for thermal insulating materials and products which derive from the Council Directive of 21 December 1988 on the approximation of laws, regulations and administrative provisions of the Member States relating to construction products (Directive 89/106/EEC) through the consideration of the essential requirements.

This European Standard has been drafted for applications in buildings but it may also be used in other areas where it is relevant.

This European test standard is one of the following group of interrelated standards on test methods for determining dimensions and properties of thermal insulation materials and products, all of which fall within the scope of CEN/TC 88:

- EN 822, Thermal insulating products for building applications Determination of length and width
- EN 823, Thermal insulating products for building applications Determination of thickness
- EN 824, Thermal insulating products for building applications Determination of squareness
- EN 825, Thermal insulating products for building applications Determination of flatness
- EN 826, Thermal insulating products for building applications Determination of compression behaviour
- EN 1602, Thermal insulating products for building applications Determination of the apparent density
- EN 1603, Thermal insulating products for building applications Determination of dimensional stability under constant normal laboratory conditions (23 °C/50 % relative humidity)
- EN 1604, Thermal insulating products for building applications Determination of dimensional stability under specified temperature and humidity conditions
- EN 1605, Thermal insulating products for building applications Determination of deformation under specified compressive load and temperature conditions
- EN 1606, Thermal insulating products for building applications Determination of compressive creep

BS EN 12431:2013 EN 12431:2013 (E)

- This is a preview of "BS EN 12431:2013". Click here to purchase the full version from the ANSI store.
- EN 1607, Thermal insulating products for building applications Determination of tensile strength perpendicular to faces
- EN 1608, Thermal insulating products for building applications Determination of tensile strength parallel to faces
- EN 1609, Thermal insulating products for building applications Determination of short-term water absorption by partial immersion
- EN 12085, Thermal insulating products for building applications Determination of linear dimensions of test specimens
- EN 12086, Thermal insulating products for building applications Determination of water vapour transmission properties
- EN 12087, Thermal insulating products for building applications Determination of long-term water absorption by immersion
- EN 12088, Thermal insulating products for building applications Determination of long-term water absorption by diffusion
- EN 12089, Thermal insulating products for building applications Determination of bending behaviour
- EN 12090, Thermal insulating products for building applications Determination of shear behaviour
- EN 12091, Thermal insulating products for building applications Determination of freeze-thaw resistance
- EN 12429, Thermal insulating products for building applications Conditioning to moisture equilibrium under specified temperature and humidity conditions
- EN 12430, Thermal insulating products for building applications Determination of behaviour under point load
- EN 12431, Thermal insulating products for building applications Determination of thickness for floating floor insulating products
- EN 13793, Thermal insulating products for building applications Determination of behaviour under cyclic loading
- EN 13820, Thermal insulating materials for building applications Determination of organic content

According to the CEN/CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

1 Scope

This European Standard specifies the equipment and procedures for determining the thickness of thermal insulating products for impact sound insulation in floating floor applications.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 12085, Thermal insulating products for building applications — Determination of linear dimensions of test specimens

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1 thickness $d_{\rm L}$ thickness of the product under a load of 250 Pa

3.2 thickness *d*_F thickness of the product under a load of 2 kPa

3.3

thickness

 d_{B}

thickness of the product under a load of 2 kPa after application of a short time additional load (48 kPa)

4 Principle

The thickness is determined as the distance measured between a rigid flat base plate on which the test specimen rests and a rigid flat pressure plate exerting different specified pressures on the top surface of the test specimen.

5 Apparatus

5.1 Dial gauge, which permits reading to 0,1 mm, mounted on a rigid frame fastened to a rigid flat base plate.

5.2 Device, with the same accuracy with two readings of the thickness/deformation placed symmetrically on a diagonal on the upper square plate of the device. The mean of these two readings is the thickness/deformation.

5.3 Base plate and pressure plate, which shall be at least as large as the test specimen.

5.4 Device, which exerts a total pressure on the test specimen of (250 ± 5) Pa (including the force exerted by the dial gauge).