

This is a preview of "BS EN ISO 17830:2016". [Click here to purchase the full version from the ANSI store.](#)

BS EN ISO 17830:2016



BSI Standards Publication

Solid biofuels — Particle size distribution of disintegrated pellets

This is a preview of "BS EN ISO 17830:2016". [Click here to purchase the full version from the ANSI store.](#)

This British Standard is the UK implementation of EN ISO 17830:2016. It supersedes BS EN 16126:2012 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PTI/17, Solid biofuels.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2016.
Published by BSI Standards Limited 2016

ISBN 978 0 580 81423 5

ICS 27.190; 75.160.10

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 April 2016.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

This is a preview of "BS EN ISO 17830:2016". [Click here to purchase the full version from the ANSI store.](#)

EUROPÄISCHE NORM

April 2016

ICS 75.160.10; 27.190

Supersedes EN 16126:2012

English Version

Solid biofuels - Particle size distribution of disintegrated pellets (ISO 17830:2016)

Biocombustibles solides - Détermination de la distribution granulométrique des granulés désintégrés (ISO 17830:2016)

Biogene Festbrennstoffe - Bestimmung der Partikelgrößenverteilung von Pellet-Ausgangsmaterial (ISO 17830:2016)

This European Standard was approved by CEN on 20 February 2016.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

European foreword

This document (EN ISO 17830:2016) has been prepared by Technical Committee ISO/TC 238 "Solid biofuels" in collaboration with Technical Committee CEN/TC 335 "Solid biofuels" the secretariat of which is held by SIS.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2016, and conflicting national standards shall be withdrawn at the latest by October 2016.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 16126:2012.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 17830:2016 has been approved by CEN as EN ISO 17830:2016 without any modification.

This is a preview of "BS EN ISO 17830:2016". [Click here to purchase the full version from the ANSI store.](#)

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Reagents	1
6 Apparatus	2
7 Sample preparation	3
8 Procedure	3
8.1 Disintegration	3
8.2 Drying	3
8.3 Moisture conditioning	3
8.4 Sieving	4
9 Calculation	4
10 Performance characteristics	6
11 Test report	6
Annex A (informative) Characteristics on determination of particle size distribution of material within pellets in accordance with the 2007 inter-comparison study	7
Bibliography	8

This is a preview of "BS EN ISO 17830:2016". Click here to purchase the full version from the ANSI store.

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#).

The committee responsible for this document is ISO/TC 238, *Solid biofuels*.

This is a preview of "BS EN ISO 17830:2016". [Click here to purchase the full version from the ANSI store.](#)

Introduction

In power plants with powder fuel burners for energy production, the operators need information about the particle size distribution of the fuel for optimising particle burnout during combustion. Fuel preparation equipment, such as pulverizers, are used for crushing pellets into the original particle sizes before the material was pressed into pellets. The method described in this International Standard is intended to characterize particle size distribution of the material contained within fuel pellets and also allows for a relative comparison of pellets of different manufacturing.

This method is based on experience with pellets made from sawdust, wood shavings and milled wood, as well as straw. The method may also be applicable for pellets produced from other solid biofuel materials provided that they can be dissolved into its constituents in water.

Pellets that are engineered to resist water, e.g. pellets from materials which have undergone some thermal treatments, cannot be characterised by this method.

This is a preview of "BS EN ISO 17830:2016". [Click here to purchase the full version from the ANSI store.](#)

This is a preview of "BS EN ISO 17830:2016". [Click here to purchase the full version from the ANSI store.](#)

Solid biofuels — Particle size distribution of disintegrated pellets

1 Scope

This International Standard aims to define the requirements and method used to determine particle size distribution of disintegrated pellets. It is applicable for pellets that fully disintegrate in hot water.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 16559, *Solid biofuels — Terminology, definitions and descriptions*

ISO 17827-2¹⁾, *Solid biofuels — Determination of particle size distribution for uncompressed fuels — Part 2: Vibrating screen using sieves for classification of samples with apertures of 3,15 mm and below*

ISO 18134-1, *Solid biofuels — Determination of moisture content — Oven dry method — Part 1: Total moisture — Reference method*

EN 14778, *Solid biofuels — Sampling*

EN 14780, *Solid biofuels — Sample preparation*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 16559 and the following apply.

3.1

sieve fraction

material collected on a sieve

4 Principle

The particle size distribution is determined after the sample pellets have been disintegrated in hot deionised water and dried in a drying cabinet or oven. The determination is performed by sieving the dried material in accordance with ISO 17827-2.

5 Reagents

Deionised water.

1) To be published.