

This is a preview of "BS EN 755-2:2013". [Click here to purchase the full version from the ANSI store.](#)

**BS EN 755-2:2013**



**BSI Standards Publication**

# **Aluminium and aluminium alloys — Extruded rod/bar, tube and profiles**

Part 2: Mechanical properties

**bsi.**

...making excellence a habit.™

This is a preview of "BS EN 755-2:2013". [Click here to purchase the full version from the ANSI store.](#)

This British Standard is the UK implementation of EN 755-2:2013. It supersedes BS EN 755-2:2008 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee NFE/35, Light metals and their alloys.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2013. Published by BSI Standards Limited 2013

ISBN 978 0 580 82480 7

ICS 77.150.10

**Compliance with a British Standard cannot confer immunity from legal obligations.**

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 October 2013.

#### **Amendments issued since publication**

Date	Text affected
------	---------------

---

This is a preview of "BS EN 755-2:2013". [Click here to purchase the full version from the ANSI store.](#)

## EUROPÄISCHE NORM

October 2013

ICS 77.150.10

Supersedes EN 755-2:2008

English Version

## Aluminium and aluminium alloys - Extruded rod/bar, tube and profiles - Part 2: Mechanical properties

Aluminium et alliages d'aluminium - Barres, tubes et profilés filés - Partie 2: Caractéristiques mécaniques

Aluminium und Aluminiumlegierungen - Stranggepresste Stangen, Rohre und Profile - Teil 2: Mechanische Eigenschaften

This European Standard was approved by CEN on 22 August 2013.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels**

This is a preview of "BS EN 755-2:2013". [Click here to purchase the full version from the ANSI store.](#)

<b>Contents</b>		Page
Foreword.....		3
<b>1</b>	<b>Scope .....</b>	<b>4</b>
<b>2</b>	<b>Normative references .....</b>	<b>4</b>
<b>3</b>	<b>Mechanical property limits .....</b>	<b>4</b>
<b>3.1</b>	<b>General.....</b>	<b>4</b>
<b>3.2</b>	<b>Elongation .....</b>	<b>4</b>
<b>3.3</b>	<b>Reference list of the tables of mechanical properties of the relevant aluminium and aluminium alloys.....</b>	<b>5</b>
<b>3.4</b>	<b>Tables of mechanical properties.....</b>	<b>7</b>
<b>Annex A (informative) List of tempers used in Tables 1 to 59 (extract of EN 515).....</b>		<b>65</b>
<b>Bibliography .....</b>		<b>66</b>

This is a preview of "BS EN 755-2:2013". [Click here to purchase the full version from the ANSI store.](#)

## Foreword

This document (EN 755-2:2013) has been prepared by Technical Committee CEN/TC 132 "Aluminium and aluminium alloys", the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2014, and conflicting national standards shall be withdrawn at the latest by April 2014.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

CEN/TC 132 affirms its policy that if a patentee refuses to grant licences on standardized products under reasonable and not discriminatory conditions, this product will be removed from the corresponding document.

This document supersedes EN 755-2:2008.

CEN/TC 132 decided to revise EN 755-2:2008 as follows:

- addition of the alloys EN AW-6026 and EN AW-6064A in new Tables 25 and 26;
- EN 10002-1 was replaced by EN ISO 6892-1;
- editorial corrections in Tables 7, 22, 47, 49, 54 and 59.

EN 755 comprises the following parts under the general title "*Aluminium and aluminium alloys — Extruded rod/bar, tube and profiles*":

- *Part 1: Technical conditions for inspection and delivery*
- *Part 2: Mechanical properties*
- *Part 3: Round bars, tolerances on dimensions and form*
- *Part 4: Square bars, tolerances on dimensions and form*
- *Part 5: Rectangular bars, tolerances on dimensions and form*
- *Part 6: Hexagonal bars, tolerances on dimensions and form*
- *Part 7: Seamless tubes, tolerances on dimensions and form*
- *Part 8: Porthole tubes, tolerances on dimensions and form*
- *Part 9: Profiles, tolerances on dimensions and form*

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

This is a preview of "BS EN 755-2:2013". [Click here to purchase the full version from the ANSI store.](#)

## 1 Scope

This European Standard specifies the mechanical property limits resulting from tensile testing applicable to aluminium and aluminium alloy extruded rod/bar, tube and profile.

Technical conditions for inspection and delivery, including product and testing requirements, are specified in EN 755-1. Temper designations are defined in EN 515. The chemical composition limits for these materials are given in EN 573-3.

## 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 755-1, *Aluminium and aluminium alloys — Extruded rod/bar, tube and profiles — Part 1: Technical conditions for inspection and delivery*

EN ISO 6892-1, *Metallic materials — Tensile testing — Part 1: Method of test at room temperature (ISO 6892-1)*

## 3 Mechanical property limits

### 3.1 General

The mechanical properties shall be in conformity with those specified in Table 1 to Table 59 or those agreed upon between supplier and purchaser and stated in the order document.

Table 1 to Table 59 contain limits of mechanical property values obtained by tensile testing according to EN ISO 6892-1 after sampling and test piece preparation according to EN 755-1.

NOTE The mechanical properties refer to test pieces taken in the longitudinal direction. Mechanical properties of test pieces taken in other directions can differ from those for the longitudinal direction quoted in this standard.

Brinell hardness values given in Table 1 to Table 59 expressed as *HBW* values are for information only.

### 3.2 Elongation

If not otherwise agreed, the *A* value shall be used.

The *A* value for elongation is the % elongation measured over a gauge length of  $5,65\sqrt{S_0}$  (where  $S_0$  is the initial cross-sectional area of the test-piece), and expressed in percent.

For certain products the supplier may choose (if not otherwise specified in the order documents) to use the elongation based on  $A_{50\text{mm}}$ . Consequently, values for the  $A_{50\text{mm}}$  are included in the following tables.

The  $A_{50\text{mm}}$  value is the elongation measured over a gauge length of 50 mm and expressed in percent.

Test pieces and their location in the specimen are given in EN 755-1.