

This is a preview of "BS ISO 18852:2015". [Click here to purchase the full version from the ANSI store.](#)

BS ISO 18852:2015



BSI Standards Publication

Rubber compounding ingredients — Determination of multipoint nitrogen surface area (NSA) and statistical thickness surface area (STSA)

bsi.

...making excellence a habit.™

This is a preview of "BS ISO 18852:2015". [Click here to purchase the full version from the ANSI store.](#)

This British Standard is the UK implementation of ISO 18852:2015. It supersedes BS ISO 18852:2012 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PRI/50, Rubber - Raw, natural and synthetic, including latex and carbon black.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2015. Published by BSI Standards Limited 2015

ISBN 978 0 580 86472 8

ICS 83.040.20

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 June 2015.

Amendments issued since publication

Date	Text affected
------	---------------

This is a preview of "BS ISO 18852:2015". [Click here to purchase the full version from the ANSI store.](#)

Third edition
2015-06-01

Rubber compounding ingredients — Determination of multipoint nitrogen surface area (NSA) and statistical thickness surface area (STSA)

*Ingrédients de mélange du caoutchouc — Détermination de la
surface par adsorption d'azote (NSA) et de la surface par épaisseur
statistique (STSA) par méthode multipoints*



Reference number
ISO 18852:2015(E)

© ISO 2015

This is a preview of "BS ISO 18852:2015". [Click here to purchase the full version from the ANSI store.](#)



COPYRIGHT PROTECTED DOCUMENT

© ISO 2015

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

This is a preview of "BS ISO 18852:2015". [Click here to purchase the full version from the ANSI store.](#)

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Principle	1
4 Apparatus	1
5 Reagents	3
6 Preparation of automatic volumetric adsorption measurement apparatus	3
7 Sample preparation	3
7.1 General.....	3
7.2 Vacuum suction method.....	3
7.3 Purge gas flow method.....	4
8 Measurement procedure	5
8.1 Measurement.....	5
8.2 Selection of data points and determination of nitrogen surface area (NSA).....	5
8.2.1 General.....	5
8.2.2 Procedure A.....	5
8.2.3 Procedure B.....	6
8.3 Verification of measured values.....	6
9 Determination of statistical thickness surface area (STSA)	6
9.1 General.....	6
9.2 Procedure.....	7
9.3 Calculation of STSA.....	7
9.4 Verification of measured values.....	7
10 Precision	7
11 Test report	7
Annex A (informative) Precision	8
Bibliography	10

This is a preview of "BS ISO 18852:2015". [Click here to purchase the full version from the ANSI store.](#)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 3, *Raw materials (including latex) for use in the rubber industry*.

This third edition cancels and replaces the second edition (ISO 18852:2012), which has been technically revised with the following changes:

- [Clause 6](#): deletion of the description of what operators do not have to do; specification of what operators have to do. The verification of measured values was moved to [Clause 8](#) for measurement procedure;
- [Clauses 7](#) and [10](#): addition of explanations for operators to carry out the procedure easily;
- [Clause 8](#): the description for selecting data points has been modified;
- the specification of sample mass has been moved to [Clause 7](#) for sample preparation, and the previous [Clause 9](#) was deleted.

This is a preview of "BS ISO 18852:2015". [Click here to purchase the full version from the ANSI store.](#)

Rubber compounding ingredients — Determination of multipoint nitrogen surface area (NSA) and statistical thickness surface area (STSA)

WARNING — Persons using this International Standard should be familiar with normal laboratory practice. This International Standard does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any national regulatory conditions.

1 Scope

This International Standard specifies a method for the determination of the nitrogen surface area (NSA) of carbon blacks and other rubber compounding ingredients, like silicas and zinc oxides, based on the Brunauer, Emmett and Teller (BET) theory of gas adsorption using a multipoint determination as well as the determination of the statistical thickness surface area (STSA), otherwise known as the external surface area. STSA, however, is not applicable to silica and zinc oxide.

The method can also be used for verifying “single-point” procedures described in ISO 4652 and other standards.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4652:2012, *Rubber compounding ingredients — Carbon black — Determination of specific surface area by nitrogen adsorption methods — Single-point procedures*

ISO 5794-1:2010, *Rubber compounding ingredients — Silica, precipitated, hydrated — Part 1: Non-rubber tests*

3 Principle

A sample of carbon black, silica, zinc oxide, etc., is placed in a cell of known volume and degassed. Known volume of nitrogen gas is dosed into the cell that is kept at the temperature of liquid nitrogen. The pressure in the cell decreases to the equilibrium due to the adsorption by the sample. The adsorbed amount at the equilibrium is derived from the difference between the amount of the dosed gas and that of remainder in the cell. The pressure is measured together with the temperature in the system, and the volume of the system is measured with a gas that does not adsorb such as helium before the test. NSA is determined by the BET analysis on the adsorption amount obtained, and STSA is determined by t-plot analysis.

4 Apparatus

4.1 Automatic volumetric adsorption measurement apparatus, consisting of a pressure gauge or transducer, a calibration volume, a Dewar flask and all other accessories required for the analysis.

The pressure gauge or transducer shall have the $\pm 0,25$ % accuracy of full scale at the range from 0 kPa to 133 kPa.

Calibration volume is where the volume of the nitrogen to be adsorbed is measured and shall have a known internal volume with a valve or stopcock. It shall have been calibrated by its manufacturer prior to testing.