

This is a preview of "BS EN 438-4:2016". [Click here to purchase the full version from the ANSI store.](#)

BS EN 438-4:2016



BSI Standards Publication

High-pressure decorative laminates (HPL) — Sheets based on thermosetting resins (usually called laminates)

Part 4: Classification and specifications for compact laminates of thickness 2 mm and greater

bsi.

...making excellence a habit.™

This is a preview of "BS EN 438-4:2016". [Click here to purchase the full version from the ANSI store.](#)

This British Standard is the UK implementation of EN 438-4:2016. It supersedes BS EN 438-4:2005 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PRI/76, Laminated sheet for decorative purposes.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2016.
Published by BSI Standards Limited 2016

ISBN 978 0 580 87152 8

ICS 83.140.20

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 29 February 2016.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

This is a preview of "BS EN 438-4:2016". [Click here to purchase the full version from the ANSI store.](#)

EUROPÄISCHE NORM

February 2016

ICS 83.140.20

Supersedes EN 438-4:2005

English Version

High-pressure decorative laminates (HPL) - Sheets based on thermosetting resins (usually called laminates) - Part 4: Classification and specifications for compact laminates of thickness 2 mm and greater

Stratifiés décoratifs haute pression (HPL) - Plaques à base de résines thermodurcissables (communément appelées stratifiés) - Partie 4: Classification et spécifications des stratifiés compacts d'épaisseur égale ou supérieure à 2 mm

Dekorative Hochdruck-Schichtpressstoffplatten (HPL) - Platten auf Basis härthbarer Harze (Schichtpressstoffe) - Teil 4: Klassifizierung und Spezifikationen für Kompakt-Schichtpressstoffe mit einer Dicke von 2 mm und größer

This European Standard was approved by CEN on 13 December 2015.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

This is a preview of "BS EN 438-4:2016". [Click here to purchase the full version from the ANSI store.](#)

Contents	Page
European foreword	3
1 Scope	4
2 Normative references	4
3 Terms, definitions, symbols and abbreviations	4
3.1 Terms and definitions.....	4
3.2 Symbols.....	5
4 Material types and classification system	5
5 Characteristics and applications	5
6 Requirements	6
6.1 Compliance.....	6
6.2 Inspection requirements	6
6.2.1 General	6
6.2.2 Colour and pattern	6
6.2.3 Surface finish	6
6.2.4 Visual inspection	7
6.3 Dimensional tolerance requirements.....	7
6.4 Test requirements	8
6.4.1 General requirements	8
6.4.2 Notes on requirements for reaction to fire	10
6.5 Supplemental properties	10
Annex A (informative) Addendum to sub-clause 6.4.2, relating to fire performance	11
Bibliography	12

This is a preview of "BS EN 438-4:2016". [Click here to purchase the full version from the ANSI store.](#)

European foreword

This document (EN 438-4:2016) has been prepared by Technical Committee CEN/TC 249 "Plastics", the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2016, and conflicting national standards shall be withdrawn at the latest by August 2016.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 438-4:2005.

EN 438, *High-pressure decorative laminates (HPL) — Sheets based on thermosetting resins (usually called laminates)*, consists of the following parts:

- *Part 1: Introduction and general information*
- *Part 2: Determination of properties*
- *Part 3: Classification and specifications for laminates less than 2 mm thick intended for bonding to supporting substrates*
- *Part 4: Classification and specifications for Compact laminates of thickness 2 mm and greater*
- *Part 5: Classification and specifications for flooring grade laminates less than 2 mm thick intended for bonding to supporting substrates*
- *Part 6: Classification and specifications for Exterior-grade Compact laminates of thickness 2 mm and greater*
- *Part 7: Compact laminate and HPL composite panels for internal and external wall and ceiling finishes*
- *Part 8: Classification and specifications for design laminates*
- *Part 9: Classification and specifications for alternative core laminates*

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

This is a preview of "BS EN 438-4:2016". [Click here to purchase the full version from the ANSI store.](#)

1 Scope

This European Standard specifies performance requirements for two types of compact laminate of thickness 2 mm or greater produced by using a high pressure process intended for interior use .

High-pressure decorative Compact laminates are characterised by their aesthetic qualities, strength, durability and functional performance. Compact HPL sheets are available in a wide variety of colours, patterns and surface finishes; they are extremely strong, and resistant to wear, impact, scratching, moisture, heat and staining; and possess good hygienic and anti-static properties, being easy to clean and maintain.

EN 438-2 specifies the methods of test relevant to this European Standard.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 438-2:2016, *High-pressure decorative laminates (HPL) — Sheets based on thermosetting resins (usually called laminates) — Part 2: Determination of properties*

EN 13501-1, *Fire classification of construction products and building elements — Part 1: Classification using data from reaction to fire tests*

EN 13722, *Furniture — Assessment of the surface gloss*

EN 61340-4-1, *Electrostatics — Part 4-1: Standard test methods for specific applications — Electrical resistance of floor coverings and installed floors (IEC 61340-4-1)*

EN ISO 178, *Plastics — Determination of flexural properties (ISO 178)*

EN ISO 1183-1, *Plastics — Methods for determining the density of non-cellular plastics — Part 1: Immersion method, liquid pycnometer method and titration method (ISO 1183-1)*

EN ISO 11664-2, *Colorimetry — Part 2: CIE standard illuminants (ISO 11664-2)*

3 Terms, definitions, symbols and abbreviations

3.1 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1.1

high-pressure decorative laminate(s)

HPL

sheet(s) consisting of decorative surface layer(s) and core layers bonded together by an high pressure process

Note 1 to entry: Typical values for the high pressure process are a temperature of ≥ 120 °C and a pressure of ≥ 5 MPa.

3.1.2

surface layer

upper decorative layer consisting in one or more sheets of fibrous material (usually paper) impregnated with aminoplastic thermosetting resins (usually melamine based resins)