

This is a preview of "BS ISO 20163:2019". [Click here to purchase the full version from the ANSI store.](#)



BSI Standards Publication

Vulcanized rubber — Determination of free sulfur by gas chromatography (GC) and high performance liquid chromatography (HPLC)

This is a preview of "BS ISO 20163:2019". [Click here to purchase the full version from the ANSI store.](#)

National foreword

This British Standard is the UK implementation of ISO 20163:2019.

The UK participation in its preparation was entrusted to Technical Committee PRI/22, Testing and analysis of rubber.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2019
Published by BSI Standards Limited 2019

ISBN 978 0 580 89152 6

ICS 83.060

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 July 2019.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

This is a preview of "BS ISO 20163:2019". [Click here to purchase the full version from the ANSI store.](#)

First edition
2019-07

Vulcanized rubber — Determination of free sulfur by gas chromatography (GC) and high performance liquid chromatography (HPLC)

Caoutchoucs vulcanisés — Dosage du soufre libre par chromatographie en phase gazeuse (CG) et chromatographie en phase liquide haute performance (HPLC)



Reference number
ISO 20163:2019(E)

© ISO 2019

This is a preview of "BS ISO 20163:2019". [Click here to purchase the full version from the ANSI store.](#)



COPYRIGHT PROTECTED DOCUMENT

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

This is a preview of "BS ISO 20163:2019". [Click here to purchase the full version from the ANSI store.](#)

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Apparatus	2
6 Reagents and materials	3
6.1 Standard solutions.....	3
6.2 Materials for preparation of samples.....	3
6.3 Reagents used in GC.....	3
6.4 Elution solvents used in HPLC.....	4
7 Preparation of standard solutions and calibration curves	4
7.1 Standard addition method.....	4
7.2 External calibration method.....	4
8 Preparation of samples	5
9 Chromatographic procedure	5
9.1 Method A by GC procedure.....	5
9.2 Method B by HPLC procedure.....	5
9.2.1 General.....	5
9.2.2 Standard addition method.....	6
9.2.3 External calibration method.....	6
10 Sample analysis and calculation	6
10.1 General.....	6
10.2 Calculation using standard addition method.....	7
10.3 Sample analysis and calculation using external calibration method.....	7
11 Precision	8
12 Test report	8
Annex A (normative) Calibration using standard addition method	9
Annex B (normative) Calibration using external standard solutions	10
Annex C (informative) Examples of chromatogram	11
Annex D (informative) Precision	12
Bibliography	17

This is a preview of "BS ISO 20163:2019". [Click here to purchase the full version from the ANSI store.](#)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 2, *Testing and analysis*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

This is a preview of "BS ISO 20163:2019". Click here to purchase the full version from the ANSI store.

Vulcanized rubber — Determination of free sulfur by gas chromatography (GC) and high performance liquid chromatography (HPLC)

WARNING 1 — Persons using this document should be familiar with normal laboratory practice. This document does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to determine the applicability of any other restrictions.

WARNING 2 — Certain procedures specified in this document might involve the use or generation of substances, or the generation of waste, that could constitute a local environmental hazard. Reference should be made to appropriate documentation on safe handling and disposal after use.

1 Scope

This document specifies chromatographic methods for the determination of the inorganic free sulfur (S_x) not consumed during the vulcanization of the rubber. This method is used primarily to compare the free sulfur content in different samples.

NOTE 1 In this document, “free sulfur” is used instead of “inorganic free sulfur”.

NOTE 2 The residual curing agent containing sulfur is not concerned by this measure.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1407:2011, *Rubber — Determination of solvent extract*

3 Terms and definitions

There are no term and definition in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 Principle

The free sulfur is quantified following two techniques: gas chromatography/mass spectrometric detector (GC-MS) or gas chromatography/flame ionization detector (GC/FID) (method A) and high performance liquid chromatography/ultraviolet detector (HPLC/UV) (method B).

A sample of vulcanized rubber is first extracted using an appropriate solvent according to ISO 1407:2011 (Method B). A known quantity of triphenylphosphine (TPP) is added to the obtained solution. TPP reacts with free sulfur to form a stable compound, triphenylphosphine sulfide (TPPS). See [Figure 1](#).