

This is a preview of "BS EN ISO 7668:2018". [Click here to purchase the full version from the ANSI store.](#)



BSI Standards Publication

Anodizing of aluminium and its alloys - Measurement of specular reflectance and specular gloss of anodic oxidation coatings at angles of 20 degrees, 45 degrees, 60 degrees or 85 degrees (ISO 7668:2018)

This is a preview of "BS EN ISO 7668:2018". [Click here to purchase the full version from the ANSI store.](#)

National foreword

This British Standard is the UK implementation of EN ISO 7668:2018. It is identical to ISO 7668:2018. It supersedes BS EN ISO 7668:2010, which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee STI/33, Electrodeposited and related coatings.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2018
Published by BSI Standards Limited 2018

ISBN 978 0 580 97200 3

ICS 25.220.20

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 April 2018.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

EUROPÄISCHE NORM

March 2018

ICS 25.220.20

Supersedes EN ISO 7668:2010

English Version

Anodizing of aluminium and its alloys - Measurement of specular reflectance and specular gloss of anodic oxidation coatings at angles of 20 degrees, 45 degrees, 60 degrees or 85 degrees (ISO 7668:2018)

Anodisation de l'aluminium et de ses alliages - Mesurage des caractéristiques de réflectivité et de brillant spéculaires des couches anodiques à angle fixe de 20 degrés, 45 degrés, 60 degrés ou 85 degrés (ISO 7668:2018)

Anodisieren von Aluminium und Aluminiumlegierungen - Messung des gerichteten Reflexionsgrades und des Spiegelglanzes von anodisch erzeugten Oxidschichten bei Winkeln von 20°, 45°, 60° oder 85° (ISO 7668:2018)

This European Standard was approved by CEN on 14 March 2018.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

This is a preview of "BS EN ISO 7668:2018". [Click here to purchase the full version from the ANSI store.](#)

European foreword

This document (EN ISO 7668:2018) has been prepared by Technical Committee ISO/TC 79 "Light metals and their alloys" in collaboration with Technical Committee CEN/TC 132 "Aluminium and aluminium alloys", the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2018, and conflicting national standards shall be withdrawn at the latest by September 2018.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 7668:2010.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 7668:2018 has been approved by CEN as EN ISO 7668:2018 without any modification.

This is a preview of "BS EN ISO 7668:2018". [Click here to purchase the full version from the ANSI store.](#)

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	2
5 Apparatus and geometric conditions	2
5.7 Geometric conditions.....	2
6 Optical standards	6
6.1 Reference standards.....	6
6.1.1 Black glass.....	6
6.1.2 Glass prism (for Method E only).....	6
6.2 Working standards.....	7
6.2.1 Description.....	7
6.2.2 Zero point check.....	7
7 Preparation and calibration of apparatus	7
8 Measurement of specular reflectance and specular gloss	8
8.1 General.....	8
8.2 Measurement of specular reflectance.....	8
8.3 Measurement of specular gloss.....	8
9 Expression of results	11
9.1 General.....	11
9.2 Specular reflectance.....	11
9.3 Specular gloss.....	11
10 Test report	11
Annex A (normative) Specular reflectance and specular gloss of black glass	12

This is a preview of "BS EN ISO 7668:2018". Click here to purchase the full version from the ANSI store.

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 79, *Light metals and their alloys*, Subcommittee SC 2, *Organic and anodic oxidation coatings on aluminium*.

This third edition cancels and replaces the second edition (ISO 7668:2010), which has been technically revised. The main technical changes are as follows:

- the normative references have been added;
- the definition of specular gloss has been revised;
- the references to CIE spectral luminous efficiency and CIE standard illuminants C and D65 have been added.

This is a preview of "BS EN ISO 7668:2018". [Click here to purchase the full version from the ANSI store.](#)

Introduction

Specular reflectance and specular gloss are not unique physical properties of a surface. They vary with the angle of measurement, and with the aperture dimensions that define the incident and the reflected beams, such that measurements of these properties are not independent of the apparatus being used.

The specular reflectance of most surfaces increases with the angle of measurement and accounts for the use of reflectometers with various angles as, for example, for painted surfaces. The specular reflectance characteristics of anodized aluminium, however, do not always behave in the normal manner and, because of its property of double reflection, reflected light comes partly from the film surface and partly from the underlying metal. It is advisable to measure the specular reflectance characteristics at 20°, 45°, 60° and 85° to obtain a complete understanding of the specular reflectance properties of the anodized surface, and careful thought should be given to which method or methods are most relevant in any particular situation. The specular reflectance of bright-anodized aluminium with a mirror finish is best measured using 45° or 20° geometry.

This is a preview of "BS EN ISO 7668:2018". [Click here to purchase the full version from the ANSI store.](#)

This is a preview of "BS EN ISO 7668:2018". Click here to purchase the full version from the ANSI store.

Anodizing of aluminium and its alloys - Measurement of specular reflectance and specular gloss of anodic oxidation coatings at angles of 20 degrees, 45 degrees, 60 degrees or 85 degrees (ISO 7668:2018)

1 Scope

This document specifies methods for the measurement of specular reflectance and specular gloss of flat samples of anodized aluminium using geometries of 20° (Method A), 45° (Method B), 60° (Method C) and 85° (Method D); and of specular reflectance by an additional 45° method (Method E) employing a narrow acceptance angle.

The methods described are intended mainly for use with clear anodized surfaces. They can be used with colour-anodized aluminium, but only with similar colours.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 7583, *Anodizing of aluminium and its alloys — Terms and definitions*

ISO 11664-1, *Colorimetry — Part 1: CIE standard colorimetric observers*

ISO 11664-2, *Colorimetry — Part 2: CIE standard illuminants*

CIE Publication No. 15, *Colorimetry*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 7583 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1

specular reflectance

ratio of the luminous flux, reflected in the specular direction for a specified source and receptor angle, to the luminous flux of the incident light

Note 1 to entry: Normally expressed as a percentage.