



BSI Standards Publication

Glass in building - Thermally toughened soda lime silicate safety glass

Part 1: Definition and description

This is a preview of "BS EN 12150-1:2015+A...". [Click here to purchase the full version from the ANSI store.](#)

National foreword

This British Standard is the UK implementation of EN 12150-1:2015+A1:2019. It supersedes BS EN 12150-1:2015, which is withdrawn.

The start and finish of text introduced or altered by amendment is indicated in the text by tags. Tags indicating changes to CEN text carry the number of the CEN amendment. For example, text altered by CEN amendment A1 is indicated by A1 A1.

The UK participation in its preparation was entrusted to Technical Committee B/520, Glass and glazing in building.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2019
Published by BSI Standards Limited 2019

ISBN 978 0 580 97699 5

ICS 81.040.20

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 September 2015.

Amendments/corrigenda issued since publication

Date	Text affected
31 May 2019	Implementation of CEN amendment A1:2019

EUROPÄISCHE NORM

May 2019

ICS 81.040.20

English Version

Glass in building - Thermally toughened soda lime silicate safety glass - Part 1: Definition and description

Verre dans la construction - Verre de silicate
sodo-calcique de sécurité trempé thermiquement
- Partie 1: Définition et description

Glas im Bauwesen - Thermisch vorgespanntes
Kalknatron-Einscheiben-Sicherheitsglas
- Teil 1: Definition und Beschreibung

This European Standard was approved by CEN on 8 August 2015 and includes Amendment 1 approved by CEN on 6 January 2019.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

This is a preview of "BS EN 12150-1:2015+A...". [Click here to purchase the full version from the ANSI store.](#)

Contents

Page

European foreword	4
Introduction	5
1 Scope	6
2 Normative references	6
3 Terms and definitions	6
4 Glass products	8
5 Fracture characteristics	8
6 Dimensions and tolerances	8
6.1 Nominal thickness and thickness tolerances.....	8
6.2 Width and length (sizes).....	9
6.2.1 General.....	9
6.2.2 Maximum and minimum sizes.....	9
6.2.3 Tolerances and squareness.....	9
6.2.4 Edge deformation produced by the vertical process.....	10
6.3 Flatness.....	11
6.3.1 General.....	11
6.3.2 Measurement of overall bow.....	13
6.3.3 Measurement of $\overline{A_1}$ wave distortion and roller wave distortion $\overline{A_1}$	14
6.3.4 Measurement of edge lift (for horizontally toughened glass only).....	15
6.3.5 Measurement of perimeter deformation of glass produced by air cushion toughening process.....	16
6.3.6 Measurement of local distortion (for vertically toughened glass only).....	16
6.3.7 Limitation on overall bow, roller waves and edge lift for horizontally toughened glass.....	17
6.3.8 Limitation on overall bow, wave and perimeter deformation for toughened glass manufactured by air cushion process.....	18
6.3.9 Limitation on overall bow and local distortion for vertically toughened glass.....	18
6.3.10 Other distortions.....	19
7 Edge and/or surface work, holes, notches and cut-outs	19
7.1 Warning.....	19
7.2 Edge working of glass for toughening.....	19
7.3 Profiled edges.....	20
7.4 Round holes.....	20
7.4.1 General.....	20
7.4.2 Diameter of holes.....	20
7.4.3 Limitations on position of holes.....	20
7.4.4 Tolerances on hole diameters.....	21
7.4.5 Tolerances on position of holes.....	22
7.5 Holes/others.....	22
7.6 Notches and cut-outs.....	23
7.7 Shaped panes.....	23
8 Fragmentation test	23
8.1 General.....	23
8.2 Dimensions and number of test specimens.....	23
8.3 Test procedure.....	23
8.4 Assessment of fragmentation.....	24
8.5 Minimum values from the particle count.....	25
8.6 Selection of the longest particle.....	26
8.7 Maximum length of longest particle.....	26
9 Other physical characteristics	26
9.1 Optical distortion.....	26

This is a preview of "BS EN 12150-1:2015+A...". [Click here to purchase the full version from the ANSI store.](#)

9.1.1	Thermally toughened soda lime silicate safety glass produced by vertical toughening	26
9.1.2	Thermally toughened soda lime silicate safety glass produced by horizontal toughening.....	26
9.2	Anisotropy (iridescence).....	26
9.3	Thermal durability.....	26
9.4	Mechanical strength.....	26
9.5	Classification of performance under accidental human impact.....	27
10	Marking	27
Annex A	(informative) Curved thermally toughened soda lime silicate safety glass	28
Annex B	(informative) Alternative method for the measurement of roller wave distortion	29
Annex C	(informative) Examples of particle count	31
Annex D	(informative) Risk of spontaneous breakage of toughened glass due to nickel sulfide inclusion	34
Bibliography	35

This is a preview of "BS EN 12150-1:2015+A...". [Click here to purchase the full version from the ANSI store.](#)

European foreword

This document (EN 12150-1:2015+A1:2019) has been prepared by Technical Committee CEN/TC 129 "Glass in building", the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 2019, and conflicting national standards shall be withdrawn at the latest by November 2019.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document includes Amendment 1 approved by CEN on 2019-01-06.

This document supersedes A1 EN 12150-1:2015 A1.

The start and finish of text introduced or altered by amendment is indicated in the text by tags A1 A1.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association.

EN 12150, *Glass in building — Thermally toughened soda lime silicate safety glass*, consists of the following parts:

- *Part 1: Definitions and description;*
- *Part 2: Evaluation of conformity/Product standard.*

A1 Deleted text A1

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

This is a preview of "BS EN 12150-1:2015+A...". [Click here to purchase the full version from the ANSI store.](#)

Introduction

Thermally toughened soda lime silicate safety glass has a safer breakage behaviour when compared with annealed glass. When it should be used to offer protection under accidental human impact, thermally toughened soda lime silicate safety glass also should be classified according to EN 12600.

NOTE CEN/TC 129/WG 8 is producing standards for the determination of the design strength of glass and is preparing a design method.

This is a preview of "BS EN 12150-1:2015+A...". [Click here to purchase the full version from the ANSI store.](#)

1 Scope

This European Standard specifies tolerances, flatness, edgework, fragmentation and physical and mechanical characteristics of monolithic flat thermally toughened soda lime silicate safety glass for use in buildings.

Information on curved thermally toughened soda lime silicate safety glass is given in [Annex A](#), but this product does not form part of this European Standard.

Other requirements, not specified in this European Standard, can apply to thermally toughened soda lime silicate safety glass which is incorporated into assemblies, e.g. laminated glass or insulating glass units, or undergo an additional treatment, e.g. coating. The additional requirements are specified in the appropriate glass product standard. Thermally toughened soda lime silicate safety glass, in this case, does not lose its bending strength characteristics and its resistance to temperature differentials.

Surface finished glasses (e.g. sandblasted, acid etched) after toughening are not covered by this European Standard.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 572-1, *Glass in building — Basic soda lime silicate glass products — Part 1: Definitions and general physical and mechanical properties*

EN 572-2, *Glass in building — Basic soda lime silicate glass products — Part 2: Float glass*

EN 572-4, *Glass in building — Basic soda lime silicate glass products — Part 4: Drawn sheet glass*

EN 572-5, *Glass in building — Basic soda lime silicate glass products — Part 5: Patterned glass*

EN 572-8, *Glass in building — Basic soda lime silicate glass products — Part 8: Supplied and final cut sizes*

EN 1096-1, *Glass in building — Coated glass — Part 1: Definitions and classification*

EN 1288-3, *Glass in building — Determination of the bending strength of glass — Part 3: Test with specimen supported at two points (four point bending)*

EN 14428, *Shower enclosures — Functional requirements and test methods*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

thermally toughened soda lime silicate safety glass

thermally toughened safety glass

glass within which a permanent surface compressive stress, additionally to the basic mechanical strength, has been induced by a controlled heating and cooling process in order to give it greatly increased resistance to mechanical and thermal stress and prescribed fragmentation characteristics

NOTE The mechanical properties, i.e. thermal durability and mechanical strength, and safety properties, i.e. fragmentation characteristics, are generated by the level of surface compression. These properties are not size dependent.