BS 8571:2018



**BSI Standards Publication** 

Method of test for determination of fracture toughness in metallic materials using single edge notched tension (SENT) specimens

#### Publishing and copyright information

The BSI copyright notice displayed in this document indicates when the document was last issued.

© The British Standards Institution 2018

Published by BSI Standards Limited 2018

ISBN 978 0 580 51316 9

ICS 25.160.40

The following BSI references relate to the work on this document: Committee reference ISE/101 Draft for comment 18/30366164 DC

### Amendments/corrigenda issued since publication

Date Text affected

CUIICI	115	Page
	Foreword	;;
1	Scone	1
2	Normative references	1
3	Terms definitions and symbols	1
4	Principle	2
5	Test sample and test specimen preparation	3
5.1	Test sample	3
5.2	Test specimen	3
	Figure 1 — Flowchart showing how to use the standard	4
	Figure 2 — SENT test specimen configuration	5
	Figure 3 — W/B ratios in SENT test specimens	7
	Figure 4 — Machining tolerances and surface finish for a SENT specimen	8
5.3	Notching	8
	Figure 5 — Crack plane orientation code for fracture toughness specimens of parent metal and	
	weld metal	9
5.4	Fatigue pre-cracking	10
6	Test procedure	10
6.1	Measurements during testing	10
	Figure 6 — Example knife edges and notch geometries	11
6.2	Test specimen temperature	11
6.3	Testing rate	12
6.4	Post-test measurements	12
7	Determination of resistance curves $\delta - \Delta a$ and $J - \Delta a$	12
7.1	General	12
7.2	Multiple specimen method	12
7.3	Single specimen methods	13
7.4	Calculating J	13
	Figure 7 — Determination of $U_{p'} V_p$ and $V_e$	14
7.5	Calculating CTOD	16
	Figure 8 — Determination of CTOD (δ) from the double clip gauge arrangement	17
7.6	Definition of the R-curve	17
	Figure 9 — Fitting the R-curve to the SENT crack extension data	18
7.7	Assessment of pop-ins	18
8	Determination of single point fracture toughness	18
9	Test data qualification	19
9.1	Checklist for qualification	19
9.2	Test report	19
Annex A	(informative) Guidance for stable crack path deviation during ductile crack extension	20
Annex B	(informative) Guidance for using non-fatigue pre-cracked specimens	21
Annex C	(informative) Example calculation of J and CTOD for SENTs	21
	Bibliography	23

# Summary of pages

This document comprises a front cover, and inside front cover, pages i to iv, pages 1 to 23, an inside back cover and a back cover.

# Foreword

### **Publishing information**

This British Standard is published by BSI Standards Limited, under licence from The British Standards Institution, and came into effect on 30 November 2018. It was prepared by Subcommittee ISE/101/4, *Toughness testing*, under the authority of Technical Committee ISE/101, *Test methods for metals*. A list of organizations represented on these committees can be obtained on request to their secretary.

### **Supersession**

This British Standard supersedes BS 8571:2014, which is withdrawn.

# Information about this document

This standard has been developed primarily to meet the needs of the steel pipeline industry where this method has been used to determine the fracture toughness of girth welds experiencing plastic straining during installation.

This is a full revision of the standard and introduces the following principal changes:

- consolidation of the clamped load *J* equations to give a single formula for all specimen dimensions;
- error in crack shape validity has been corrected;
- annexes have been added giving guidance on crack path deviation, and for testing of specimens with non-sharp notches;
- the example calculation has been revised and now covers calculation of CTOD and J; and
- the permitted range of  $a_0/W$  has been narrowed.

### **Hazard warnings**

**WARNING.** This British Standard calls for the use of substances and/or procedures that can be injurious to health if adequate precautions are not taken. It refers only to technical suitability and does not absolve the user from legal obligations relating to health and safety at any stage.

#### Use of this document

It has been assumed in the preparation of this British Standard that the execution of its provisions will be entrusted to appropriately qualified and experienced people, for whose use it has been produced.

# **Presentational conventions**

The provisions of this standard are presented in roman (i.e. upright) type. Its requirements are expressed in sentences in which the principal auxiliary verb is "shall".

*Commentary, explanation and general informative material is presented in smaller italic type, and does not constitute a normative element.* 

Where words have alternative spellings, the preferred spelling of the Shorter Oxford English Dictionary is used (e.g. "organization" rather than "organisation").

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard cannot confer immunity from legal obligations.

### 1 Scope

This British Standard gives methods for determining fracture toughness in metallic materials in terms of  $\delta$  (crack tip opening displacement, CTOD) and *J* (experimental equivalent of the *J*-integral) using single edge notched tension (SENT) specimens.

This British Standard also gives a method for determining fracture toughness as a resistance to ductile crack extension (R-curve), or single point determination of fracture toughness at onset of unstable crack extension, or pop-in. The method uses specimens which have been notched and fatigue pre-cracked into parent metal, weld metal or heat affected zone (HAZ). The specimens are loaded in tension, and the force and crack mouth opening displacement are recorded.

NOTE Methods to evaluate the suitability of a weld for notch placement within the target area and, where appropriate, to evaluate the effectiveness of the fatigue crack in sampling these areas are given in BS EN ISO 15653.

# 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes provisions of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

BS EN ISO 15653:2018, Metallic materials — Method of test for the determination of quasistatic fracture toughness of welds

ISO 12135:2016, Metallic materials — Unified method of test for the determination of quasistatic fracture toughness

# 3 Terms, definitions and symbols

For the purposes of this British Standard, the following terms, definitions and symbols, and those given in BS EN ISO 15653 and ISO 12135, apply.

# 3.1 Terms and definitions

### 3.1.1 blunting

increase in crack length not associated with the creation of new fracture surface prior to the onset of unstable crack extension, pop-in or slow stable crack extension, and occurring within the same plane as the fatigue pre-crack

### 3.1.2 pop-in

abrupt discontinuity in the force versus displacement record, indicated by a sudden increase in displacement and, generally, a sudden decrease in force, subsequent to which displacement and force increase to above their previous values

### 3.1.3 sample

un-notched blank cut from the source material

### 3.1.4 specimen

machined and notched sample ready for testing