

This is a preview of "BS ISO 4660:2020". [Click here to purchase the full version from the ANSI store.](#)



BSI Standards Publication

Rubber, raw natural — Colour index test

This is a preview of "BS ISO 4660:2020". [Click here to purchase the full version from the ANSI store.](#)

National foreword

This British Standard is the UK implementation of ISO 4660:2020. It supersedes BS ISO 4660:2011, which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PRI/50, Raw materials (including latex) for use in the rubber industry.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2020
Published by BSI Standards Limited 2020

ISBN 978 0 539 01133 3

ICS 83.040.10

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 May 2020.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

This is a preview of "BS ISO 4660:2020". [Click here to purchase the full version from the ANSI store.](#)

Fifth edition
2020-05-07

Rubber, raw natural — Colour index test

Caoutchouc naturel brut — Essai d'indice de couleur



Reference number
ISO 4660:2020(E)

© ISO 2020

This is a preview of "BS ISO 4660:2020". [Click here to purchase the full version from the ANSI store.](#)



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

This is a preview of "BS ISO 4660:2020". [Click here to purchase the full version from the ANSI store.](#)

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Apparatus	1
6 Procedure	5
6.1 Test piece preparation.....	5
6.2 Calibration.....	5
6.3 Colour determination.....	5
6.3.1 Method A — Colour matching against standard coloured glasses.....	5
6.3.2 Method B — Colour spectrophotometer.....	6
7 Expression of results	6
8 Precision and bias	6
9 Test report	6
Annex A (informative) Comparison study for colour determination method	7
Bibliography	9

This is a preview of "BS ISO 4660:2020". [Click here to purchase the full version from the ANSI store.](#)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 3, *Raw materials (including latex) for use in the rubber industry*.

This fifth edition cancels and replaces the fourth edition (ISO 4660:2011), which has been technically revised. The main changes compared to the previous edition are as follows:

- a colour spectrophotometer has been added as an alternative method to determine colour index in [Clauses 1, 4](#) and in [5.8](#);
- the thickness of the material from the punch, in [5.4](#), has been specified to be 3,4 mm ± 0,2 mm;
- the weight of the test portion, in [6.1](#), has been specified to be 20 g ± 5 g;
- the number of pass for test piece preparation, in [6.1](#), has been specified to be two passes;
- the thickness of the final sheet from the mill, in [6.1](#), has been specified to be 1,7 mm ± 0,1 mm;
- the calibration for colour spectrophotometer has been added in [6.2](#);
- the procedure for colour determination using colour spectrophotometer has been added in [6.3.2](#);
- Method B using the colour spectrophotometer has been stated in [Clause 1](#) as the preferred method.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

This is a preview of "BS ISO 4660:2020". [Click here to purchase the full version from the ANSI store.](#)

Rubber, raw natural — Colour index test

WARNING — Persons using this document should be familiar with normal laboratory practice. This document does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices.

1 Scope

This document specifies two methods to determine the colour of raw natural rubber according to a standard colour scale:

- Method A: colour matching against standard coloured glasses;
- Method B: colour determination using colour spectrophotometer.

In case of dispute, the preferred method is Method B.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2393, *Rubber test mixes — Preparation, mixing and vulcanization — Equipment and procedures*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 Principle

The raw rubber is prepared in the form of a moulded disc of specified thickness.

For Method A, the colour of this disc is compared and matched as closely as possible with that of standard glasses. Colour matching is carried out under diffuse daylight illumination against a matt white background, preferably by use of a comparator which suitably locates and shrouds the test piece and standard glass.

For Method B, the colour of the test piece is compared and matched automatically using a colour spectrophotometer.

[Annex A](#) gives additional information on comparison study between Method A and Method B.

5 Apparatus

The usual laboratory apparatus and, in particular, the following.

5.1 Laboratory mill, conforming to the requirements of ISO 2393.