

This is a preview of "PD IEC TS 62607-4-8:...". [Click here to purchase the full version from the ANSI store.](#)



BSI Standards Publication

Nanomanufacturing — Key control characteristics

Part 4-8: Nano-enabled electrical energy storage — Determination of water content in electrode nanomaterials, Karl Fischer method

This is a preview of "PD IEC TS 62607-4-8:...". [Click here to purchase the full version from the ANSI store.](#)

National foreword

This Published Document is the UK implementation of IEC TS 62607-4-8:2020.

The UK participation in its preparation was entrusted to Technical Committee NTI/1, Nanotechnologies.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2020
Published by BSI Standards Limited 2020

ISBN 978 0 539 02443 2

ICS 07.030; 07.120

Compliance with a British Standard cannot confer immunity from legal obligations.

This Published Document was published under the authority of the Standards Policy and Strategy Committee on 29 February 2020.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

This is a preview of "PD IEC TS 62607-4-8:...". [Click here to purchase the full version from the ANSI store.](#)



Edition 1.0 2020-02

TECHNICAL SPECIFICATION



**Nanomanufacturing – Key control characteristics –
Part 4-8: Nano-enabled electrical energy storage – Determination of water
content in electrode nanomaterials, Karl Fischer method**

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

ICS 07.030; 07.120

ISBN 978-2-8322-7813-0

Warning! Make sure that you obtained this publication from an authorized distributor.

This is a preview of "PD IEC TS 62607-4-8:...". [Click here to purchase the full version from the ANSI store.](#)

CONTENTS

FOREWORD.....	4
INTRODUCTION.....	6
1 Scope.....	7
2 Normative references	7
3 Terms and definitions	7
4 Principle	8
5 Reagents.....	9
5.1 Coulometric Karl Fischer reagent.....	9
5.2 Methanol (anhydrous)	9
5.3 Carrier gas.....	9
5.4 Water standard for Karl Fischer coulometric titration	9
6 Apparatus.....	9
6.1 Karl Fischer coulometric titration apparatus	9
6.2 Evaporator	9
6.3 Analytical balance.....	10
6.4 Sample container	10
6.5 Micro-syringe	10
6.6 Dew-point hygrometer.....	10
7 Sample handling and sampling	10
7.1 Sample handling	10
7.2 Sampling.....	11
8 Procedure.....	11
8.1 Maintenance	11
8.1.1 Reagent change	11
8.1.2 Cleaning	11
8.1.3 Calibration	11
8.2 Measurement steps.....	11
8.3 Water content of the sample	12
9 Precision	13
9.1 General.....	13
9.2 Repeatability.....	13
9.3 Reproducibility	13
10 Test report.....	13
Annex A (informative) Case study	14
A.1 General.....	14
A.2 Reagents	14
A.2.1 Coulometric Karl Fischer reagent.....	14
A.2.2 Methanol (anhydrous).....	14
A.2.3 Carrier gas	14
A.2.4 Water standard for Karl Fischer coulometric titration.....	14
A.3 Apparatus	14
A.3.1 Karl Fischer coulometric titration apparatus	14
A.3.2 Evaporator.....	14
A.3.3 Analytical balance	14
A.3.4 Sample container.....	14
A.3.5 Micro-syringe.....	14

This is a preview of "PD IEC TS 62607-4-8:....". [Click here to purchase the full version from the ANSI store.](#)

A.3.6	Dew-point hygrometer.....	15
A.4	Sampling.....	15
A.5	Measurement steps.....	15
A.6	Test results.....	15
	Bibliography.....	17
	Figure 1 – Example of Karl Fischer coulometric titration apparatus and evaporator.....	10
	Figure A.1 – Sample container.....	15
	Table 1 – Sample mass against water to be determined.....	11
	Table A.1 – Test data of water content in sample A	16

This is a preview of "PD IEC TS 62607-4-8:...". [Click here to purchase the full version from the ANSI store.](#)

INTERNATIONAL ELECTROTECHNICAL COMMISSION

NANOMANUFACTURING – KEY CONTROL CHARACTERISTICS –

Part 4-8: Nano-enabled electrical energy storage – Determination of water content in electrode nanomaterials, Karl Fischer method

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

The main task of IEC technical committees is to prepare International Standards. In exceptional circumstances, a technical committee may propose the publication of a Technical Specification when

- the required support cannot be obtained for the publication of an International Standard, despite repeated efforts, or
- the subject is still under technical development or where, for any other reason, there is the future but no immediate possibility of an agreement on an International Standard.

Technical Specifications are subject to review within three years of publication to decide whether they can be transformed into International Standards.

IEC TS 62607-4-8, which is a Technical Specification, has been prepared by IEC technical committee 113: Nanotechnology for electrotechnical products and systems.

This is a preview of "PD IEC TS 62607-4-8:...". [Click here to purchase the full version from the ANSI store.](#)

The text of this Technical Specification is based on the following documents:

DTS	Report on voting
113/491/DTS	113/515/RVDTS

Full information on the voting for the approval of this Technical Specification can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 62607 series, published under the general title *Nanomanufacturing – Key control characteristics*, can be found on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC website under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

IMPORTANT – The 'colour inside' logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

This is a preview of "PD IEC TS 62607-4-8:...". [Click here to purchase the full version from the ANSI store.](#)

INTRODUCTION

Nano-enabled electrical energy storage has been applied in many fields such as portable electronics, electric vehicles and energy storage systems. With continuous rapid development in these applications, nano-enabled electrical energy storage with high performance is in demand. The main properties of the electrical energy storage device are determined by its electrode nanomaterials.

The water content for electrode nanomaterials is one of the important characteristics to be determined as a quality control test. Water can affect electrical performance, cycling performance and safety performance of nano-enabled electrical energy storage devices [1]¹, [2]. A high amount of water from electrode materials has a critical influence on both active materials and battery cells [3], and might affect performance or safety characteristics.

Several methods are available for the determination of water content. Karl Fischer titration method is a direct method that is suitable for testing water in gas, liquid and solid samples. The method is useful for low water content levels (< 1 %). Especially, Karl Fischer coulometric titration method is an absolute method which can determine the water content from the quantity of electricity consumed during the test. It can detect trace levels of free water (ppm level), which cannot be detected with normal drying or gravimetric methods. The Karl Fischer coulometric titration method is capable of distinguishing water levels as low as 0,000 1 %.

At present, there are 21 International Standards and/or Technical Specifications mentioning the Karl Fischer method to measure water content, of which 16 use the volumetric titration method, and 5 use the coulometric titration method. The accuracy and resolution of the volumetric method is not appropriate for electrode nanomaterials, whose water content is lower than 1 %. The sampling and measurement controls of the current coulometric method standards are not appropriate for electrode nanomaterials, which have highly hygroscopic characteristics. Therefore, the present standards are not suitable for electrode nanomaterials. This document, considering a sample's characteristic, will help to determine the water content of the electrode nanomaterials in a short time with high accuracy, and will be helpful for quality control in laboratories and industrial manufacturers.

This standardized method is intended for use in comparing the characteristics of raw materials [e.g. lithium cobalt oxide (LCO), lithium nickel cobalt aluminium oxide (NCA), lithium nickel cobalt manganese oxide (NCM), and lithium iron phosphate (LFP)] without any additives [e.g. carbon nanomaterials like carbon black (CB), carbon nanotubes or fibres] or organic binder [e.g. polyvinylidene difluoride (PVDF) or styrene-butadiene rubber (SBR)], their selection process and as a quality control method for the fully formulated electrode material, not for evaluating the electrode in end products.

¹ Numbers in square brackets refer to the Bibliography.

This is a preview of "PD IEC TS 62607-4-8:...". Click here to purchase the full version from the ANSI store.

NANOMANUFACTURING – KEY CONTROL CHARACTERISTICS –

Part 4-8: Nano-enabled electrical energy storage – Determination of water content in electrode nanomaterials, Karl Fischer method

1 Scope

This part of IEC 62607, which is a Technical Specification, specifies a test method for the determination of water content in electrode nanomaterials for nano-enabled electrical energy storage devices, using the Karl Fischer coulometric titration method.

This document includes:

- recommendations for sample preparation,
- outlines of the experimental procedures used to measure electrode nanomaterial properties, and
- methods of interpretation of results and discussion of data analysis.

NOTE This method has precision as low as 0,000 1 %. The best applicable measure range is 0,01 % to 1 %.

This document is not applicable for samples that can react with the main components of Karl Fischer reagent and produce water, or samples that can react with iodine or iodide ion.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 760, *Determination of water – Karl Fischer method (General method)*

ISO 12492, *Rubber, raw – Determination of water content by Karl Fischer method*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1

nanoscale

length range approximately from 1 nm to 100 nm

Note 1 to entry: Properties that are not extrapolations from larger sizes are predominantly exhibited in this length range.

[SOURCE: ISO/TS 80004-1:2015 [4], 2.1]