

BSI Standards Publication

Test methods for repair materials for water-leakage cracks in underground concrete structures

Part 4: Test method for adhesion on wet concrete surface



National foreword

This Published Document is the UK implementation of ISO/TS 16774-4:2023.

The UK participation in its preparation was entrusted to Technical Committee B/517/8, Protection and repair of concrete structures.

A list of organizations represented on this committee can be obtained on request to its committee manager.

Contractual and legal considerations

This publication has been prepared in good faith, however no representation, warranty, assurance or undertaking (express or implied) is or will be made, and no responsibility or liability is or will be accepted by BSI in relation to the adequacy, accuracy, completeness or reasonableness of this publication. All and any such responsibility and liability is expressly disclaimed to the full extent permitted by the law.

This publication is provided as is, and is to be used at the recipient's own risk.

The recipient is advised to consider seeking professional guidance with respect to its use of this publication.

This publication is not intended to constitute a contract. Users are responsible for its correct application.

This publication is not to be regarded as a British Standard.

© The British Standards Institution 2023 Published by BSI Standards Limited 2023

ISBN 978 0 539 13727 9

ICS 91.080.40

Compliance with a Published Document cannot confer immunity from legal obligations.

This Published Document was published under the authority of the Standards Policy and Strategy Committee on 31 May 2023.

Amendments/corrigenda issued since publication

Date Text affected

TECHNICAL

ISO/TS

This is a preview of "PD ISO/TS 16774-4:20...". Click here to purchase the full version from the ANSI store.

Second edition 2023-04-24

Test methods for repair materials for water-leakage cracks in underground concrete structures —

Part 4:

Test method for adhesion on wet concrete surface

Méthodes d'essai pour matériaux de réparation pour fissures dues à l'eau dans les structures en béton souterraines —

Partie 4: Méthode d'essai de l'adhésion sur un substrat humide



PD ISO/TS 16774-4:2023 **ISO/TS 16774-4:2023(E)**

This is a preview of "PD ISO/TS 16774-4:20...". Click here to purchase the full version from the ANSI store.



COPYRIGHT PROTECTED DOCUMENT

© ISO 2023, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office Ch. de Blandonnet 8 • CP 401 CH-1214 Vernier, Geneva, Switzerland Tel. +41 22 749 01 11 Fax +41 22 749 09 47 copyright@iso.org www.iso.org

Con	tents	Page
Forew	vord	iv
Intro	duction	v
1	Scope	
2	Normative references	1
3	Terms and definitions	1
4	Principle	1
5	Apparatus	2
6	Preparation 6.1 Test specimen assembly as artificial water-leakage crack 6.2 Ambient conditions	2
7	Procedure	
8	Expression of results	3
9	Test report 9.1 Information on the repair material of the test target 9.1.1 General 9.1.2 Other information 9.2 Information on the test	4 4
Annex	x A (informative) Example test method	5
Riblio	ngranhy	12

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 71, *Concrete, reinforced concrete and pre-stressed concrete*, Subcommittee SC 7, *Maintenance and repair of concrete structures*.

This second edition cancels and replaces the first edition (ISO/TS 16774-4:2016) which has been technically revised.

The main changes are as follows:

- ambient conditions in 6.2 and A.3.3 have been modified;
- some clarifications have been made in 9.2;
- some editorial corrections have been made.

A list of all parts in the ISO 16774 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

This document is linked to ISO/TR 16475. ISO/TR 16475 outlines six basic properties and the required performance levels of water leakage repair materials, and the ISO/TS 16774 series proposes sample testing methods that are capable of evaluating the respective properties of the repair materials.

The test methods in this document are intended to serve as references for nations that have not yet developed a test method on the six proposed required performance properties of water leakage repair materials. If other forms of test methods that are simpler, more accurate or more organized are available, such methods are recommended for use instead. Many of the dependent variables outlined in the reference test methods of this document are subject to change in accordance with the environmental conditions (temperature and humidity, chemical solution and concentration, width of movement activity, water pressure or water flow velocity, etc.) outlined in the standards used in respective countries.

For ISO/TS 16774-1, ISO/TS 16774-5 and ISO/TS 16774-6, for the purpose of objectively comparing the performance of injected repair materials, artificial cracks of same width, height, and volume were used to control the usage of repair materials for each testing cycle and enable repetition of the same test methods under the same conditions.



Test methods for repair materials for water-leakage cracks in underground concrete structures —

Part 4:

Test method for adhesion on wet concrete surface

1 Scope

This document specifies a laboratory test method for indirectly measuring the adhesion performance of repair material to wet concrete crack surfaces by qualitatively, as a pass/fail at predetermined time, against predetermined amount of weight exerted on the repair material adhesion.

NOTE This document classifies and categorizes materials that are tested into families of similar properties for the purpose of making relative comparisons with the data results.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO/TR 16475, General practices for the repair of water-leakage cracks in concrete structures

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO/TR 16475 and the following apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at https://www.iso.org/obp
- IEC Electropedia: available at https://www.electropedia.org/

3.1

water leakage repair material

grouting materials used to prevent water leakages in concrete cracks

Note 1 to entry: In this document, target ingredients are limited to injection materials outlined in ISO/TR 16475.

[SOURCE: ISO/TS 16774-2:2023, 3.1]

4 Principle

A repair material's ability to adhere to a wet leakage crack surface is one of the fundamental properties that water leakage repair materials should possess. Focus areas of repair material application are most often on concrete surfaces that are constantly wet and humid. During and after application, repair materials should be able to remain firm adhesion to concrete surface and should not fall off. This test method proposes that observing whether repair materials can retain adhesion on wet concrete surface against a constantly exerted weight can determine a repair material's adhesion performance on wet concrete surface. An example test method is provided in Annex A.