



BSI Standards Publication

Plastics — Determination of the melt mass-flow rate (MFR) and melt volume-flow rate (MVR) of thermoplastics

Part 1: Standard method

This is a preview of "BS EN ISO 1133-1:202...". [Click here to purchase the full version from the ANSI store.](#)

National foreword

This British Standard is the UK implementation of EN ISO 1133-1:2022. It is identical to ISO 1133-1:2022. It supersedes BS EN ISO 1133-1:2011, which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PRI/21, Testing of plastics.

A list of organizations represented on this committee can be obtained on request to its committee manager.

Contractual and legal considerations

This publication has been prepared in good faith, however no representation, warranty, assurance or undertaking (express or implied) is or will be made, and no responsibility or liability is or will be accepted by BSI in relation to the adequacy, accuracy, completeness or reasonableness of this publication. All and any such responsibility and liability is expressly disclaimed to the full extent permitted by the law.

This publication is provided as is, and is to be used at the recipient's own risk.

The recipient is advised to consider seeking professional guidance with respect to its use of this publication.

This publication is not intended to constitute a contract. Users are responsible for its correct application.

© The British Standards Institution 2022
Published by BSI Standards Limited 2022

ISBN 978 0 539 19777 8

ICS 83.080.20

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 September 2022.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

This is a preview of "BS EN ISO 1133-1:2022...". Click here to purchase the full version from the ANSI store.

EUROPÄISCHE NORM

July 2022

ICS 83.080.20

Supersedes EN ISO 1133-1:2011

English Version

Plastics - Determination of the melt mass-flow rate (MFR) and melt volume-flow rate (MVR) of thermoplastics - Part 1: Standard method

Plastiques - Détermination de l'indice de fluidité à chaud des thermoplastiques, en masse (MFR) et en volume (MVR) - Partie 1: Méthode normale

Kunststoffe - Bestimmung der Schmelze-Massefließrate (MFR) und der Schmelze-Volumenfließrate (MVR) von Thermoplasten - Teil 1: Allgemeines Prüfverfahren

This European Standard was approved by CEN on 25 June 2022.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

This is a preview of "BS EN ISO 1133-1:202...". [Click here to purchase the full version from the ANSI store.](#)

Contents	Page
European foreword.....	3

This is a preview of "BS EN ISO 1133-1:202...". [Click here to purchase the full version from the ANSI store.](#)

European foreword

This document (EN ISO 1133-1:2022) has been prepared by Technical Committee ISO/TC 61 "Plastics" in collaboration with Technical Committee CEN/TC 249 "Plastics" the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 2023, and conflicting national standards shall be withdrawn at the latest by January 2023.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 1133-1:2011.

Any feedback and questions on this document should be directed to the users' national standards body/national committee. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 1133-1 has been approved by CEN as EN ISO 1133-1:2022 without any modification.

This is a preview of "BS EN ISO 1133-1:202...". [Click here to purchase the full version from the ANSI store.](#)

Second edition
2022-06

Plastics — Determination of the melt mass-flow rate (MFR) and melt volume-flow rate (MVR) of thermoplastics

Part 1: Standard method

*Plastiques — Détermination de l'indice de fluidité à chaud
des thermoplastiques, en masse (MFR) et en volume (MVR)*

Partie 1: Méthode normale



Reference number
ISO 1133-1:2022(E)

© ISO 2022

This is a preview of "BS EN ISO 1133-1:202...". Click here to purchase the full version from the ANSI store.



COPYRIGHT PROTECTED DOCUMENT

© ISO 2022

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

This is a preview of "BS EN ISO 1133-1:202...". Click here to purchase the full version from the ANSI store.

Contents

	Page
Foreword	v
Introduction	vi
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	2
5 Apparatus	3
5.1 Extrusion plastometer.....	3
5.2 Accessory equipment.....	7
5.2.1 General.....	7
5.2.2 Equipment for procedure A (see Clause 8).....	8
5.2.3 Equipment for procedure B (see Clause 9): Piston displacement transducer/ timer.....	8
6 Test sample	8
6.1 Sample form.....	8
6.2 Conditioning.....	9
7 Temperature verification, cleaning and maintenance of the apparatus	9
7.1 Verification of the temperature control system.....	9
7.1.1 Verification procedure.....	9
7.1.2 Material used during temperature verification.....	10
7.2 Cleaning the apparatus.....	10
7.3 Vertical alignment of the instrument.....	10
8 Procedure A: mass-measurement method	10
8.1 Selection of temperature and load.....	10
8.2 Cleaning.....	11
8.3 Selection of sample mass and charging the cylinder.....	11
8.4 Measurements.....	12
8.5 Expression of results.....	13
8.5.1 General.....	13
8.5.2 Expression of results: standard die.....	13
8.5.3 Expression of results: half size die.....	13
9 Procedure B: displacement-measurement method	14
9.1 Selection of temperature and load.....	14
9.2 Cleaning.....	14
9.3 Minimum piston displacement distance.....	14
9.4 Selection of sample mass and charging the cylinder.....	14
9.5 Measurements.....	14
9.6 Expression of results.....	15
9.6.1 General.....	15
9.6.2 Expression of results: standard die.....	15
9.6.3 Expression of results: half size die.....	16
10 Flow rate ratio	16
11 Precision	17
12 Test report	17
Annex A (normative) Test conditions for MFR and MVR determinations	19
Annex B (informative) Conditions specified in International Standards for the determination of the melt flow rate of thermoplastic materials	21

This is a preview of "BS EN ISO 1133-1:202...". [Click here to purchase the full version from the ANSI store.](#)

Annex C (informative) Device and procedure for performing a compacted charge of material by compression	22
Annex D (informative) Precision data for polypropylene obtained from an intercomparison of MFR and MVR testing	25
Bibliography	26

This is a preview of "BS EN ISO 1133-1:202...". Click here to purchase the full version from the ANSI store.

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 5, *Physical-chemical properties*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 249, *Plastics*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This second edition cancels and replaces the first edition (ISO 1133-1:2011), of which it constitutes a minor revision. The changes are as follows:

- references to withdrawn standards in [Annex B](#) (informative), [Annex D](#) (informative) and Bibliography have been updated;
- editorial corrections.

A list of all parts in the ISO 1133 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

This is a preview of "BS EN ISO 1133-1:202...". [Click here to purchase the full version from the ANSI store.](#)

Introduction

For stable materials that are not rheologically sensitive to the time-temperature history experienced during melt flow rate testing, this document is recommended.

For materials whose rheological behaviour is sensitive to the test's time-temperature history, e.g. materials which degrade during the test, ISO 1133-2 is recommended. Also, ISO 1133-2 is considered to be particularly relevant for moisture-sensitive plastics.

NOTE At the time of publication, there is no evidence to suggest that the use of ISO 1133-2 for stable materials results in better precision in comparison with the use of this document.

This is a preview of "BS EN ISO 1133-1:202...". Click here to purchase the full version from the ANSI store.

Plastics — Determination of the melt mass-flow rate (MFR) and melt volume-flow rate (MVR) of thermoplastics —

Part 1: Standard method

WARNING — Persons using this document should be familiar with normal laboratory practice, if applicable. This document does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any regulatory requirements.

1 Scope

This document specifies two procedures for the determination of the melt mass-flow rate (MFR) and the melt volume-flow rate (MVR) of thermoplastic materials under specified conditions of temperature and load. Procedure A is a mass-measurement method. Procedure B is a displacement-measurement method. Normally, the test conditions for measurement of melt flow rate are specified in the material standard with a reference to this document. The test conditions normally used for thermoplastics are listed in [Annex A](#).

The MVR is particularly useful when comparing materials of different filler content and when comparing filled with unfilled thermoplastics. The MFR can be determined from MVR measurements, or vice versa, provided the melt density at the test temperature is known.

This document is also possibly applicable to thermoplastics for which the rheological behaviour is affected during the measurement by phenomena such as hydrolysis (chain scission), condensation and cross-linking, but only if the effect is limited in extent and only if the repeatability and reproducibility are within an acceptable range. For materials which show significantly affected rheological behaviour during testing, this document is not appropriate. In such cases, ISO 1133-2 applies.

NOTE The rates of shear in these methods are much smaller than those used under normal conditions of processing, and therefore it is possible that data obtained by these methods for various thermoplastics will not always correlate with their behaviour during processing. Both methods are used primarily in quality control.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>