

This is a preview of BS 6744:2023. [Click here to purchase the full version from the ANSI store.](#)

**BS 6744:2023**



**BSI Standards Publication**

## **Stainless steel bars – Reinforcement of concrete – Requirements and test methods**

**bsi.**

This is a preview of BS 6744:2023. [Click here to purchase the full version from the ANSI store.](#)

**Publishing and copyright information**

The BSI copyright notice displayed in this document indicates when the document was last issued.

© The British Standards Institution 2023

Published by BSI Standards Limited 2023

ISBN 978 0 539 23701 6

ICS 77.140.20

The following BSI references relate to the work on this document:

Committee reference ISE/104

Draft for comment 22/30461535 DC

**Amendments/corrigenda issued since publication**

Date	Text affected
------	---------------

---

This is a preview of BS 6744:2023. [Click here to purchase the full version from the ANSI store.](#)

<b>CONTENTS</b>	<b>Page</b>
<b>Foreword</b>	<b>III</b>
1 Scope	1
2 Normative references	1
3 Terms, definitions and symbols	1
<i>Figure 1 — 0.2% proof test</i>	2
<i>Figure 2 — Typical stress-strain curve (relation) for stainless reinforcing</i>	5
<i>Table 1 — Symbols</i>	6
4 Designation	7
5 Standard diameters	7
<i>Table 2 — Standard diameters</i>	7
6 Dimensions, mass and tolerances	8
6.1 Nominal cross-sectional area and mass per metre run	8
<i>Table 3 — Nominal cross-sectional area of reinforcing steel and nominal mass per metre run</i>	8
<i>Table 4 — Tolerances on mass per metre run</i>	8
6.2 Length	9
7 Steelmaking process	9
8 Chemical composition	9
8.1 Cast analysis	9
8.2 Product analysis	9
9 Surface quality	9
10 Surface geometry	9
10.1 General	9
<i>Table 5 — Chemical composition (cast analysis) % by mass of typical, commercially available     BS EN 10088 stainless reinforcing steel designations<sup>A)</sup></i>	9
10.2 Relative rib area	10
<i>Table 6 — Minimum relative rib area, <math>f_{Rmin}</math></i>	10
<i>Table 7 — Ranges for the rib parameters</i>	11
10.3 Geometry of rib	11
11 Conditions of supply	11
12 Mechanical and physical properties	11
12.1 Selection of test samples for conformity testing	11
12.2 Test reports	12
12.3 Test certificate	12
12.4 Retests	12
12.5 Tensile properties	12
<i>Table 8 — Strength and ductility properties</i>	13
12.6 Bendability	13
<i>Table 9 — Bend test formers</i>	14
12.7 Bonding strength (surface geometry)	14
12.8 Fatigue characteristics	14
12.9 Strength at elevated temperature (tensile strength)	14
12.10 Chemical composition and durability	14
12.11 Weldability	14
12.12 Additional test requirements	15
13 Product identification	15
13.1 Product marking	15
13.2 Product labelling	15

This is a preview of BS 6744:2023. [Click here to purchase the full version from the ANSI store.](#)

<b>Annex A</b>	(normative) <b>Test method for determining the corrosion resistance of stainless reinforcing steel in chloride contaminated concrete</b>	<b>16</b>
	<i>Figure A.1 — Geometry of the specimens</i>	17
<b>Annex B</b>	(informative) <b>Guidance on durability</b>	<b>18</b>
	<i>Table B.1 — Prescriptive guidance advice</i>	20
	<i>Figure B.1 — Example predictive model indicating where carbon steel reinforcement can be replaced by stainless steel reinforcement for a given chloride surface content, design life and reinforcement depth</i>	22
<b>Annex C</b>	(informative) <b>Guidance on magnetic properties</b>	<b>23</b>
<b>Annex D</b>	(informative) <b>Guidance on coefficients of thermal expansion</b>	<b>24</b>
	<i>Table D.1 — Comparative thermal coefficient of expansion data</i>	24
<b>Annex E</b>	(informative) <b>Design guidance: constitutive relationship</b>	<b>24</b>
	<i>Figure E.1 — Idealized design curve from BS EN 1992-1-1:2004+A1:2014</i>	25
	<i>Table E.1 — Young's modulus for stainless reinforcing steel</i>	25
	<i>Figure E.2 — The constitutive law of stainless reinforcing steel</i>	26
	<i>Figure E.3 — Example of design model for stainless reinforcing steel</i>	27
<b>Annex F</b>	(informative) <b>Guidance on welding</b>	<b>27</b>
<b>Annex G</b>	(normative) <b>Performance at elevated temperatures</b>	<b>28</b>
<b>Annex H</b>	(informative) <b>Quality assurance</b>	<b>28</b>
	<i>Table H.1 — Acceptability index, <math>k</math>, as a function of the number of test results, <math>n</math>, for a reliable failure rate of 5% (pass = 0.95) at a probability of 90% (<math>1 - \alpha = 0.90</math>)</i>	29
<b>Annex I</b>	(informative) <b>High-strength bars</b>	<b>31</b>
	<b>Bibliography</b>	<b>32</b>

### Summary of pages

This document comprises a front cover, an inside front cover, pages I to IV, pages 1 to 33, an inside back cover and a back cover.

This is a preview of BS 6744:2023. [Click here to purchase the full version from the ANSI store.](#)

## Foreword

### Publishing information

This British Standard is published by BSI Standards Limited, under licence from The British Standards Institution, and came into effect on 28 February 2023. It was prepared by Technical Committee ISE/104, *Concrete Reinforcing and Pre-Stressing Steels*. A list of organizations represented on this committee can be obtained on request to the committee manager.

### Supersession

This British Standard supersedes BS 6744:2016, which is withdrawn.

### Information about this document

This new edition of BS 6744 incorporates technical changes only. It does not represent a full review or revision of the document, which will be undertaken in due course. The changes have been made to correct errors and omissions, particularly those relating to the lack of instruction relating to the procedure required if a test fails.

Attention is drawn to the fact that compliance with this document might involve the use of patents applied to steel designation 1.4162 (see [3.1.24](#)). The patent holder agrees to make the material available for production of stainless reinforcing steel bars on reasonable and accessible and non-discriminatory terms. Information on designation 1.4162 may be obtained from: Outokumpu Stainless Ltd, Europa Link, Sheffield, South Yorkshire S9 1TZ.

This standard was revised so that it can be used in conjunction with [BS 8666](#), *Scheduling, dimensioning, bending and cutting of steel reinforcement for concrete – Specification*, but also to take into account the requirements of Eurocode (EC) 2 (specifically BS EN 1992-1-1 and BS EN 1992-1-2) and the Construction Products Regulations (CPR) [1] with respect to constitutive relationship and durability. It has also been revised to act as the national application standard for BS EN 104031, *Steel for the reinforcement of concrete – Stainless steels* (in preparation).

The decision was taken to remove other uses of steel in concrete, which means that plain bars and grades 200 MPa and ribbed bars above grade 500 MPa are no longer covered by this standard. These products are covered by other standards. This is with the exception of 500 MPa bar and 650 MPa ribbed bar which are now in an informative Annex ([Annex I](#)). The standard is open to other strength grades of ribbed bar on the basis that the designers know that these are outside normal UK practice and, once over 600 MPa, outside EC2.

Informative annexes have been prepared to give guidance on durability, magnetic properties, coefficients of thermal expansion, constitutive relationship, welding, performance at elevated temperatures and quality assurance. As far as is possible, the revision has been written to reflect the requirements of [BS 4449](#).

The test method in [Annex A](#) is based on the method in BS EN 480-14 adapted by Schönning, Randström and Adair for determining a critical chloride threshold level for stainless steel rebar [2] and that in *Testing for chloride threshold levels of stainless reinforcing bar* [3].

Copyright is claimed on [Figure B.1](#). Copyright holders are Ove Arup & Partners Ltd, 13 Fitzroy Street, London W1T 4BQ.

**Product certification.** Users of this British Standard are advised to consider the desirability of third-party certification of product conformity to this British Standard. Appropriate conformity attestation arrangements are described in BS EN ISO/IEC 17065. Users seeking assistance in

This is a preview of BS 6744:2023. [Click here to purchase the full version from the ANSI store.](#)

enquiries to the relevant association.

This publication can be withdrawn, revised, partially superseded or superseded. Information regarding the status of this publication can be found in the Standards Catalogue on the BSI website at [bsigroup.com/standards](https://bsigroup.com/standards), or by contacting the Customer Services team.

Where websites and webpages have been cited, they are provided for ease of reference and are correct at the time of publication. The location of a webpage or website, or its contents, cannot be guaranteed.

### **Use of this document**

It has been assumed in the preparation of this British Standard that the execution of its provisions will be entrusted to appropriately qualified and experienced people, for whose use it has been produced.

### **Presentational conventions**

Where words have alternative spellings, the preferred spelling of the *Shorter Oxford English Dictionary* is used (e.g. “organization” rather than “organisation”).

### **Contractual and legal considerations**

This publication has been prepared in good faith, however no representation, warranty, assurance or undertaking (express or implied) is or will be made, and no responsibility or liability is or will be accepted by BSI in relation to the adequacy, accuracy, completeness or reasonableness of this publication. All and any such responsibility and liability is expressly disclaimed to the full extent permitted by the law.

This publication is provided as is, and is to be used at the recipient’s own risk.

The recipient is advised to consider seeking professional guidance with respect to its use of this publication.

This publication is not intended to constitute a contract. Users are responsible for its correct application.

**Compliance with a British Standard cannot confer immunity from legal obligations.**

This is a preview of BS 6744:2023. [Click here to purchase the full version from the ANSI store.](#)

## 1 Scope

This British Standard specifies requirements and test methods for solid stainless steel bars used for the reinforcement of concrete. It is applicable to ribbed stainless reinforcing steel bars in grade 500.

It is applicable to bars in which the ribs have been formed by the cold working or hot rolling processes.

*NOTE* [Annex A](#) specifies a test method for determining the corrosion resistance of stainless reinforcing steel in chloride contaminated concrete. Informative annexes give guidance on durability ([Annex B](#)), magnetic properties ([Annex C](#)), coefficients of thermal expansion ([Annex D](#)), constitutive relationship ([Annex E](#)), welding ([Annex F](#)), performance at elevated temperatures ([Annex G](#)) and quality assurance ([Annex H](#)).

This British Standard is not applicable to stainless reinforcing steel bars produced from material whose metallurgical history is not known and fully documented.

It is not applicable to other uses of steel in concrete, such as plain bars and grades 200 MPa and ribbed bars above grade 500 MPa, which are covered by other standards. This is with the exception of 500 MPa bar and 650 MPa ribbed bar which are now in an informative annex ([Annex I](#)). The standard is open to other strength grades of ribbed bar on the basis that the designers know that these are outside normal UK practice and, once over 600 MPa, outside [BS EN 1992](#) (EC2).

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes provisions, or limits the application, of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

[BS 8666](#), *Scheduling, dimensioning, bending and cutting of steel reinforcement for concrete – Specification*

BS EN 196-1, *Methods of testing cement – Part 1: Determination of strength*

BS EN 1993-1-2:2005, *Eurocode 3 – Design of steel structures – Part 1-2: General rules – Structural fire design*

BS EN 10088 (all parts), *Stainless steels*

BS EN ISO 148-1, *Metallic materials – Charpy pendulum impact test – Part 1: Test method*

BS EN ISO 3651-2, *Determination of resistance to intergranular corrosion of stainless steels – Part 2: Ferritic, austenitic and ferritic-austenitic (duplex) stainless steels – Corrosion test in media containing sulfuric acid*

BS EN ISO 6892-2, *Metallic materials – Tensile testing – Part 2: Method of test at elevated temperature*

BS EN ISO 15630-1:2010, *Steel for the reinforcement and prestressing of concrete – Test methods – Part 1: Reinforcing bars, wire rod and wire*

## 3 Terms, definitions and symbols

### 3.1 Terms and definitions

For the purposes of this British Standard, the terms, definitions and symbols given in BS EN 10088 (all parts), BS EN ISO 15630-1 and the following apply.