



# TECHNICAL SPECIFICATION

---

**Guidelines for qualifying PV modules, components and materials for operation at high temperatures**

This is a preview of IEC/TS 63126 Ed. 2.0 en:2025. Click here to purchase the full version from the ANSI store.

FOREWORD.....	3
INTRODUCTION.....	5
1 Scope.....	7
2 Normative references .....	7
3 Terms and definitions .....	8
3.1 Terms and definitions.....	8
3.2 Sheet-related definitions .....	10
4 Modifications to the IEC 61215 series.....	10
4.1 General.....	10
4.2 Hot-spot endurance test (MQT 09).....	11
4.3 UV preconditioning test (MQT 10).....	11
4.4 Thermal cycling test (MQT 11).....	11
4.5 Bypass diode testing (MQT 18).....	11
5 Modifications to the IEC 61730 series.....	12
5.1 IEC 61730-1 .....	12
5.2 IEC 61730-2 .....	12
5.2.1 General .....	12
5.2.2 Hot-spot endurance test (MST 22).....	12
5.2.3 Bypass diode thermal test (MST 25).....	12
5.2.4 Materials creep test (MST 37).....	13
5.2.5 Thermal cycling test (MST 51).....	13
5.2.6 UV test (MST 54).....	13
5.2.7 Dry heat conditioning (MST 56) .....	13
6 Modifications to component standards .....	13
6.1 Polymeric packaging material testing requirements .....	13
6.1.1 Test procedures for optical durability of polymer packaging materials .....	13
6.1.2 Polymeric backsheets and frontsheets.....	14
6.2 Junction boxes according to IEC 62790 .....	15
6.3 Connectors for DC application in photovoltaic systems according to IEC 62852.....	15
6.4 Electric cables for photovoltaic systems with a voltage rating of 1,5 kV DC according to IEC 62930.....	16
7 Test modification summary .....	16
8 Reporting .....	18
Annex A (informative) Determination of temperature level.....	19
A.1 General.....	19
A.2 Modelling .....	19
A.3 98 <sup>th</sup> percentile temperatures ( $T_{98}$ ) .....	23
A.4 Guidance on module temperature for locations worldwide .....	25
A.5 Guidance to system design specific modifications .....	28
A.6 Site specific concerns .....	29
A.7 Guidance on module temperature for several locations .....	29
Bibliography.....	32
Figure A.1 – Open-rack or rack-mounted configuration (open) .....	21

This is a preview of IEC/TS 63126 Ed. 2.0 en:2025. [Click here to purchase the full version from the ANSI store.](#)

Figure A.3 – Insulated-backsheet configuration.....	22
Figure A.4 – Variety of standoff distances [3].....	22
Figure A.5 – Exponential decay fit to data from Fuentes [11], Formula (A.2) .....	23
Figure A.6 – Histogram and cumulative distribution function (CDF) of module temperature for Riyadh, Saudi Arabia .....	24
Figure A.7 – Time series from the temperature model for Riyadh, Saudi Arabia .....	25
Figure A.8 – Minimum standoff distance for a module estimated to achieve a 98 <sup>th</sup> percentile temperature of 70 °C and to qualify for Level 0 .....	27
Figure A.9 – Minimum standoff distance for a module estimated to achieve a 98 <sup>th</sup> percentile temperature of 80 °C and to qualify for Level 1 or Level 0.....	27
Figure A.10 – 98 <sup>th</sup> percentile temperature for an open-rack, or thermally unrestricted, glass superstrate, polymer backsheet module.....	30
Figure A.11 – 98 <sup>th</sup> percentile temperature for a close-roof mounted glass superstrate, glass backsheet module.....	30
Figure A.12 – 98 <sup>th</sup> percentile temperature for insulated-back glass superstrate, polymer backsheet module .....	31
Table 1 – UV and thermal exposure conditions for backsheets and frontsheets.....	14
Table 2 – Test modification summary .....	16
Table 3 – Parameters for module temperature model according to Formula (A.1).....	20

## Guidelines for qualifying PV modules, components and materials for operation at high temperatures

### FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) IEC draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). IEC takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, IEC had not received notice of (a) patent(s), which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at <https://patents.iec.ch>. IEC shall not be held responsible for identifying any or all such patent rights.

IEC TS 63126 has been prepared by IEC technical committee 82: Solar photovoltaic energy systems. It is a Technical Specification.

This second edition cancels and replaces the first edition published in 2020. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition.

- a) Updated the Introduction and Scope to clarify the applicability of this document.
- b) Defined "Level 0" as that qualified for in the IEC 61730 series and the IEC 61215 series.
- c) For the purposes of minimizing testing needs, it is explicitly stated if a test or sequence is passed for a higher Level that it passes for lower levels too.
- d) Backsheet weathering was changed to match what is in IEC 62788-2-1. For all three levels, the test condition is A3 with 4 000 h on the front side and 2 000 h on the back side.

This is a preview of IEC/TS 63126 Ed. 2.0 en:2025. Click here to purchase the full version from the ANSI store.

for exposure using A3 for longer times or using A3 with a dark insulator on the back are described.

- f) The UV test of MST 54 is now only applied to the front side exposure in sequence B of IEC 61730. Previously, it was modified as part of IEC 61215 MQT 10 which is an equivalent exposure to MST 54.
- g) Modified the backsheets testing for longer duration for frontside exposure and for the use of A3 for all levels.
- h) For IEC 62788-7-1 for the optical transmittance of encapsulants, a longer exposure using the A3 condition is outlined in this document, but the original A4 and A5 options were not modified. A third option to insulate the backside with a dark light absorbing material to achieve elevated temperatures was also added.
- i) The higher thermal cycling (TC) testing for Level 1 and Level 2 will only apply to the 200 TC leg of IEC 61730 and IEC 61215.
- j) For sequence C of IEC 61730, the UV preconditioning test (MST 54) will no longer be modified as the 50 TC of this sequence is not modified.
- k) For sequence B of IEC 61730, the higher temperature for the UV exposure (MST 54) dose will only be applied to the frontsheet of a module. The backsheets exposure will not be changed.
- l) Relative to IEC 61215, the high temperature modification of the TC test only applies to sequence D and MQT 10 (UV preconditioning) is not modified, i.e. sequence C of IEC 61215 is not changed.
- m) Improved method for estimating the  $T_{98}$  temperature. This includes a method utilizing an effective standoff distance for quick estimate of the system temperature. Or it can be used to estimate a minimum standoff distance for a given geographic location.
- n) The testing for the junction box standard, IEC 62790 was clarified to explicitly state the upper ambient temperature for testing. Here ambient testing temperature for Level 2 was also reduced from 105 °C to 100 °C.
- o) Changed the modifications to IEC 62852 to specify the ambient testing temperature instead of the ULT. Ambient test temperatures of 85 °C, 90 °C and 100 °C are used for Level 0, 1, and 2, respectively.

The text of this Technical Specification is based on the following documents:

Draft	Report on voting
82/2401/DTS	82/2472/RVDTS

Full information on the voting for its approval can be found in the report on voting indicated in the above table.

The language used for the development of this Technical Specification is English.

This document was drafted in accordance with ISO/IEC Directives, Part 2, and developed in accordance with ISO/IEC Directives, Part 1 and ISO/IEC Directives, IEC Supplement, available at [www.iec.ch/members\\_experts/refdocs](http://www.iec.ch/members_experts/refdocs). The main document types developed by IEC are described in greater detail at [www.iec.ch/publications](http://www.iec.ch/publications).

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under [webstore.iec.ch](http://webstore.iec.ch) in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn, or
- revised.

This is a preview of IEC/TS 63126 Ed. 2.0 en:2025. [Click here to purchase the full version from the ANSI store.](#)

Originally, the IEC 61215 series, the IEC 61730 series, IEC 62790 and IEC 62852 were considered suitable for an environmental temperature range of at least  $-40\text{ }^{\circ}\text{C}$  to  $+40\text{ }^{\circ}\text{C}$ . For open-rack modules operating in such conditions a 98<sup>th</sup>-percentile module operating temperature of  $70\text{ }^{\circ}\text{C}$  or less is obtained. This environmental temperature range encompasses many locations and installation styles in these locations. As an example, it has been determined that thermally unrestricted, or open-rack-style structures, in most cases do not result in 98<sup>th</sup>-percentile module operating temperatures exceeding  $70\text{ }^{\circ}\text{C}$  and, as such, the originating standards are suitable as written. Cases where the module operating temperatures exceeds  $70\text{ }^{\circ}\text{C}$  at the 98<sup>th</sup> percentile typically occur with roof-parallel or building-integrated roof top applications in climates with local environmental temperatures that exceed  $40\text{ }^{\circ}\text{C}$ .

This document is written for two purposes: to provide modified testing conditions for modules that will be deployed in climates that either have a higher environmental air temperature than  $40\text{ }^{\circ}\text{C}$  or for module installation methods that restrict cooling, or both, which are likely to result in higher operating temperatures than anticipated in the originating standards. This work will also aid in providing an alternative definition of "rack mount" in the context of the IEC 61215 series and IEC 61730 series. This term was initially used as a placeholder to restrict the scope of PV module type testing for those installation styles that permit open and unrestricted cooling from all surfaces of a PV module. Now that the testing has matured, there is a desire to refine definitions for the range of applicability of these standards.

This document defines high temperature environment use requirements but does not include applications designed to combine photovoltaic and thermal energy applications. These requirements are being refined and in part incorporated into other standards. It is not necessarily cost effective for module materials to comply with Level 1 or Level 2 requirements defined in this document, unless the module temperature is expected to exceed  $70\text{ }^{\circ}\text{C}$  at the 98<sup>th</sup> percentile. Primarily, this will only be necessary in building applied applications in hot climates. Vertical building facades are not likely to operate at these high temperatures because of reduced in plane irradiance and good free convection on the outer surface. Module materials capable of temperature Level 1 or temperature Level 2 are expected to impose higher expectations of endurance and cost than normal modules.

Component standard IEC 62930 is considered to be adequate for modules operating at high temperatures without modification due to requiring cable to have a  $120\text{ }^{\circ}\text{C}$  or greater thermal endurance at a 20 000 h correlation lifetime. A guide for cable correction factors at higher cable ambient temperatures is given in IEC 62930:2017, Table A.4. Similarly, IEC 62979 [1]<sup>1</sup> is considered adequate for bypass diode thermal runaway determination due to testing temperatures of  $90\text{ }^{\circ}\text{C}$  for roof-mounted modules and  $75\text{ }^{\circ}\text{C}$  for "rack mounted" modules.

Similar to electric cables, IEC 61730-1 requires a relative thermal index (RTI), thermal index (TI), or relative thermal endurance (RTE) of  $90\text{ }^{\circ}\text{C}$  or larger. A module operating in an environment and installation style resulting in a 98<sup>th</sup> percentile temperature of  $70\text{ }^{\circ}\text{C}$  requires an RTI, TI, or RTE safety factor of  $+20\text{ }^{\circ}\text{C}$  to establish a 25-year lifetime when the polymer has a minimum activation energy of 46 kJ/mol and the correlation lifetime is 20 000 h. This work approximately applies that safety factor of  $+20\text{ }^{\circ}\text{C}$  for polymer RTI, TI, or RTE when the 98<sup>th</sup> percentile operating temperature is above  $70\text{ }^{\circ}\text{C}$ .

---

<sup>1</sup> Numbered in square brackets refer to the Bibliography.

This is a preview of IEC/TS 63126 Ed. 2.0 en:2025. [Click here to purchase the full version from the ANSI store.](#)

temperatures and resulted in two categories of high temperature operation, temperature Level 1 and temperature Level 2. These categories are defined within this document and it is relevant to indicate that Level 2 temperatures were not found in field data, but can result from insulated substrate modules on pitched roofs facing the sun when ambient air temperature exceeds 40 °C. This can be most consistent with building-integrated PV module roofs and, to allow for this possibility, the temperature Level 2 category remains in this document.

In Annex A, methods are given for estimating when a particular system design will need higher levels of qualification. Short of actual measurement at a particular site, one cannot precisely estimate the 98<sup>th</sup> percentile temperature. However, the suggested methods give a rough approximation of when Level 1 and Level 2 qualification are likely to be needed.

This is a preview of IEC/TS 63126 Ed. 2.0 en:2025. [Click here to purchase the full version from the ANSI store.](#)

This document defines additional testing requirements for photovoltaic (PV) modules deployed under conditions leading to higher module temperature which are beyond the scope of IEC 61215-1 and IEC 61730-1 and the relevant component standards, IEC 62788-1-7, IEC 62788-2-1, IEC 62790 and IEC 62852. The testing conditions specified in IEC 61215-2 and IEC 61730-2 (and the relevant component standards IEC 62788-1-7, IEC 62788-2-1, IEC 62790 and IEC 62852) assumed that these standards are applicable for module deployment where the 98<sup>th</sup> percentile temperature ( $T_{98}$ ), that is the temperature that a module would be expected to exceed for 175,2 h per year, is less than 70 °C.

NOTE 175,2 h represents 2 % of a total year as some thermal failure modes are a function of time at temperature and not sensitive to day-only or night-only exposure.

Hybrid PV and thermal systems are out of scope of this document. Guidance on the selection of meteorological data for use in estimating  $T_{98}$  is outside the scope of this document and it is important to give it careful consideration. Annex A provides a method for estimating the temperature rating for PV modules without installation- or location-specific verification. With this, suitable installation practices and long-term durability testing can be prescribed. More accurate prescription of the temperature rating including local assessment and verification is outside the scope of this document. The effects of climate change are uncertain and not in the scope of this document. The intent of this specification is to address issues with higher temperatures but not for extended durability beyond that assessed in the IEC 61215 series or IEC 61730 series.

This document defines two temperature regimes, temperature Level 1 and temperature Level 2, which were designed considering deployment in environments with mounting configurations such that the  $T_{98}$  is less than or equal to 80 °C for temperature Level 1, and less than or equal to 90 °C for temperature Level 2. This document provides recommended additional testing conditions within the IEC 61215 series, IEC 61730 series, IEC 62788-1-7, IEC 62788-2-1, IEC 62790 and IEC 62852 for module operation in temperature Levels 1 and 2. Successfully passing a higher Level for a test, sequence of tests, or complete testing for a higher Level is an implied passing of the relevant lower-Level testing. For example, passing 200 thermal cycles for Level 2 is considered passing Level 0 and Level 1 for 200 thermal cycles.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 61215 (all parts), *Terrestrial photovoltaic (PV) modules - Design qualification and type approval*

IEC 61215-2:2021, *Terrestrial photovoltaic (PV) modules - Design qualification and type approval - Part 2: Test procedures*

IEC 61730 (all parts), *Photovoltaic (PV) module safety qualification*

IEC 61730-1, *Photovoltaic (PV) module safety qualification - Part 1: Requirements for construction*

IEC 61730-2, *Photovoltaic (PV) module safety qualification - Part 2: Requirements for testing*

IEC TS 61836, *Solar photovoltaic energy systems - Terms, definitions and symbols*

This is a preview of IEC/TS 63126 Ed. 2.0 en:2025. [Click here to purchase the full version from the ANSI store.](#)

*Encapsulants - Test procedure of optical durability*

IEC 62788-2-1, *Measurement procedures for materials used in photovoltaic modules – Part 2-1: Polymeric materials - Frontsheets and backsheets - Safety requirements*

IEC TS 62788-7-2, *Measurement procedures for materials used in photovoltaic modules – Part 7-2: Environmental exposures - Accelerated weathering tests of polymeric materials*

IEC 62790, *Junction boxes for photovoltaic modules - Safety requirements and tests*

IEC 62852, *Connectors for DC-application in photovoltaic systems - Safety requirements and tests*

IEC 62930:2017, *Electric cables for photovoltaic systems with a voltage rating of 1,5 kV DC*