



IPC-9202

Material and Process Characterization/Qualification Test Protocol for Assessing Electrochemical Performance

Developed by the IPC Surface Insulation Resistance Task
Group (5-32b) of the Cleaning and Coating Committee (5-30) of IPC

Users of this publication are encouraged to participate in the
development of future revisions.

Contact:

IPC
3000 Lakeside Drive, Suite 309S
Bannockburn, Illinois
60015-1249
Tel 847615.7100
Fax 847615.7105

Table of Contents

<p>1 Scope/Introduction1</p> <p>1.1 Terms and Definitions1</p> <p>1.1.1 Unprocessed Control1</p> <p>1.1.2 Process Characterization1</p> <p>1.1.3 Process Qualification1</p> <p>2 APPLICABLE DOCUMENTS1</p> <p>3 TEST SPECIMENS2</p> <p>3.1 IPC-B-52 Standard Test Assembly2</p> <p>3.2 Materials of Construction4</p> <p>4 SAMPLE SIZES4</p> <p>4.1 Process Characterizations4</p> <p>4.2 Process Qualifications4</p> <p>5 APPARATUS AND MATERIALS4</p> <p>5.1 Manufacturing Equipment4</p> <p>5.2 Ionic Analysis Tests4</p> <p>5.3 Surface Insulation Resistance (SIR) Tests4</p> <p>6 PROCESSING OF TEST VEHICLES5</p> <p>6.1 Preparation of Test Vehicles5</p> <p>6.2 Manufacturing Processes5</p> <p>7 SPECIMEN PREPARATION FOR TESTING5</p> <p>7.1 Solder Shorts5</p> <p>7.2 Identify Vehicles5</p> <p>7.3 Segmenting the Test Specimen5</p> <p>7.4 Storage5</p> <p>7.5 Shipping to Third Party Testers5</p> <p>7.6 Preparation for Hard Wire Attach5</p> <p>7.7 Process Qualification Preparation5</p>	<p>8 TEST METHODOLOGY5</p> <p>8.1 Visual Examinations5</p> <p>8.2 Ionic Analysis Tests5</p> <p>8.3 SIR Tests5</p> <p>8.3.1 Pre-Test Validation – Measurement Systems5</p> <p>8.3.2 Test Conditions and Measurement Frequency5</p> <p>8.3.3 Post-SIR Visual Examination6</p> <p>9 ACCEPTANCE CRITERIA6</p> <p>9.1 SIR Tests6</p> <p>9.2 Ionic Analysis Tests6</p> <p>10 REPORTING6</p> <p>10.1 Minimum Report Elements6</p> <p>11 NOTES7</p> <p>11.1 Condensation7</p> <p>11.2 Drip Shields7</p> <p>11.3 Optical Examination7</p> <p>11.4 Connectors vs. Hard Wire7</p> <p>11.5 Cable Shielding7</p> <p>11.6 Verification Vehicle8</p> <p>11.7 Design Files8</p> <p>12 HELPFUL REFERENCES8</p> <p>TABLES</p> <p>Table 3-1 Bill of Materials for IPC-B-52 Test Assembly4</p> <p>Table 8-1 SIR Testing Parameters6</p> <p>FIGURES</p> <p>Figure 3-1 IPC-B-52 Standard Test Assembly – Main SIR Board Patterns2</p> <p>Figure 3-2 IPC-B-52 Test Board Top Side and Component Locations3</p> <p>Figure 3-3 IPC-B-52 Test Board Bottom Side3</p>
---	---

Material and Process Characterization/Qualification Test Protocol for Assessing Electrochemical Performance

1 Scope/Introduction This Material and Process Characterization/Qualification Test records changes in Surface Insulation Resistance (SIR) on a representative sample of a printed circuit assembly (PCA). It quantifies any deleterious effects that might arise from solder flux or other process residues left on external surfaces after soldering, which can cause unwanted electro-chemical reactions that grossly affect reliability.

It uses test vehicles that are intended to be representative of the electronic circuits that are in production. It is a test yielding both quantitative and qualitative data.

This test may be used for *Process Qualification*, demonstrating that a proposed manufacturing process or process change can produce hardware with acceptable end-item performance related to cleanliness. Changes may involve any assembly process step, or a change in the printed board supplier, solder mask or metallization, soldering material supplier, conformal coating, etc. The test vehicle construction will vary depending upon the type of change being evaluated.

NOTE: The decision to levy this protocol on individual manufacturing sites **shall** be As Agreed Between User and Supplier (AABUS). See IPC-9203 for further guidance (As of the publication of this document, IPC-9203 is under development. Contact the IPC for status and availability). Vehicles must be prepared at the manufacturer's (User's) location using production processes and equipment whenever possible. Care must be taken to ensure that the processed test vehicles are kept free from any secondary contamination while in transit to the test site. Testing of the prepared vehicles can be performed by the user or at a suitable independent laboratory.

There is no single test that can guarantee acceptable electrochemical performance for all products, applications, and in-service environments. While there are several methods that may be used to determine materials and process compatibility, this test protocol may be used to satisfy electrochemical compatibility. IPC-J-STD-001 does not require testing to this specific method to qualify a manufacturing process.

It is strongly recommended that a subset of the unpopulated, unprocessed coupons be tested for SIR before investing the time and money to manufacture the test vehicles. If the unprocessed controls do not return acceptable SIR results because of some undiscovered fault in the design or construction of the vehicles, the populated PCAs are likely to fail also.

This test may also be used for *Process Characterizations*, including development of new processes or improvements to an existing process.

This test protocol is specific to the IPC-B-52 standard test assembly. The use of alternative test vehicles and associated pass-fail requirements **shall** be AABUS.

The IPC-B-52 standard test assembly contains both surface mount and through-hole technologies. Only the applicable portions of the IPC-B-52 assembly are processed, i.e. only the surface mount patterns are processed for a surface mount only assembly process; however, *all* surface mount patterns must be processed.

1.1 Terms and Definitions

1.1.1 Unprocessed Control A test vehicle that has not been exposed to candidate assembly manufacturing material/processes. These are in the "as-received" condition from the supplier.

1.1.2 Process Characterization A comparative examination of the interaction of materials and process parameters. Example: A comparison of different solder masks, or a comparison of cleaning processes.

1.1.3 Process Qualification The generation of "objective evidence" for the purposes of demonstrating materials and process compatibility for an assembly standard (e.g., IPC-J-STD-001).

2 APPLICABLE DOCUMENTS

2.1 IPC¹

IPC-A-24-G Surface Insulation Resistance Artwork

IPC-A-52-G Cleanliness and Residue Evaluation Test Board Artwork

IPC-TM-650 Test Methods Manual²

1. www.ipc.org

2. Current and revised IPC Test Methods are available on the IPC Web site (www.ipc.org/html/testmethods.htm)