

ANSI Internat Doc Sec

Glass and glassware — Analysis of extract solutions —

Part 1:

Determination of silicon dioxide by molecular absorption spectrometry

Verre et verrerie — Analyse des solutions d'attaque —

Partie 1: Dosage du dioxyde de silicium par spectrométrie d'absorption moléculaire



Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 10136-1 was prepared by Technical Committee ISO/TC 48, *Laboratory glassware and related apparatus*, Sub-Committee SC 5, *Quality of glassware*.

ISO 10136 consists of the following parts, under the general title *Glass and glassware — Analysis of extract solutions*:

- *Part 1: Determination of silicon dioxide by molecular absorption spectrometry*
- *Part 2: Determination of sodium oxide and potassium oxide by flame spectrometric methods*
- *Part 3: Determination of calcium oxide and magnesium oxide by flame atomic absorption spectrometry*
- *Part 4: Determination of aluminium oxide by molecular absorption spectrometry*
- *Part 5: Determination of iron(III) oxide by molecular absorption spectrometry and flame atomic absorption spectrometry*
- *Part 6: Determination of boron(III) oxide by molecular absorption spectrometry*

Annex A of this part of ISO 10136 is for information only.

© ISO 1993

All rights reserved. No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case Postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

This is a preview of "ISO 10136-1:1993". [Click here to purchase the full version from the ANSI store.](#)

Introduction

The determination of silica (SiO_2) in durability extract solutions has not, hitherto, been included in classifications of glass or glassware according to chemical resistance. Indeed, in many applications the concentrations of silica found in such extract solutions, normally very low, are not significant and are of little interest. There are occasions where such releases could be important, for example from glassware used in the determination of small concentrations of silica in solutions or, in some cases, releases from medical and pharmaceutical ware. Then again, in examining the properties of new glass compositions it could be an advantage to know the full analysis of the durability extract solutions.

Technical Committee 2, Chemical Durability and Analysis, of the International Commission on Glass (ICG), investigated two procedures for determining silica (see [6] in annex A) by the molecular absorption spectrometric technique. Both were based on the formation of colour complexes in the presence of ammonium molybdate, one using the yellow colour of the complex formed, the other using the blue colour produced when a suitable reducing agent is added. In collaborative experimental work, twelve laboratories analysed silica in two synthetic solutions and in extract solutions produced by the test described in ISO 4802[3][4]. It was agreed that whilst determinations using the yellow complex were more consistent, they were also less sensitive and, since the concentrations of silica in extract solutions are normally very low, the blue complex method was preferred.

The results of investigations on turbidities, especially in grain test solutions, showed that acidification to dissolve possible hydroxides and/or carbonates is necessary prior to the analytical determination. This is achieved by using spectroscopic buffer solutions, which are normally strongly acidic, or by addition of acids.

This is a preview of "ISO 10136-1:1993". Click here to purchase the full version from the ANSI store.

Glass and glassware — Analysis of extract solutions —

Part 1:

Determination of silicon dioxide by molecular absorption spectrometry

1 Scope

This part of ISO 10136 specifies an analytical procedure, using molecular absorption spectrometry, for measuring the concentrations of silicon, expressed as silicon dioxide or silica (SiO_2), released into extract solutions during hydrolytic resistance test procedures.

This part of ISO 10136 applies to the analysis of extract solutions obtained from any kind of glass or glassware, including laboratory and pharmaceutical ware made, for example, from borosilicate glass (such as borosilicate glass 3.3 according to ISO 3585), neutral glass, or soda-lime-silica glass as defined in ISO 4802^[3]^[4], food and drink packaging ware, tableware and kitchenware. The extract solution may be obtained from glass articles, for example according to ISO 4802, or from glass as material, for example when tested according to ISO 719^[1] or ISO 720^[2]. In addition, it may be applied to the extract solutions produced by any method for measuring the hydrolytic resistance of glass or glassware.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this part of ISO 10136. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this part of ISO 10136 are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 385-2:1984, *Laboratory glassware — Burettes — Part 2: Burettes for which no waiting time is specified.*

ISO 648:1977, *Laboratory glassware — One-mark pipettes.*

ISO 835-1:1981, *Laboratory glassware — Graduated pipettes — Part 1: General requirements.*

ISO 835-2:1981, *Laboratory glassware — Graduated pipettes — Part 2: Pipettes for which no waiting time is specified.*

ISO 835-3:1981, *Laboratory glassware — Graduated pipettes — Part 3: Pipettes for which a waiting time of 15 s is specified.*

ISO 1042:1983, *Laboratory glassware — One-mark volumetric flasks.*

ISO 3585:1991, *Borosilicate glass 3.3 — Properties.*

ISO 3696:1987, *Water for analytical laboratory use — Specification and test methods.*

ISO 3819:1985, *Laboratory glassware — Beakers.*

ISO 6955:1982, *Analytical spectroscopic methods — Flame emission, atomic absorption, and atomic fluorescence — Vocabulary.*

ISO 7056:1981, *Plastics laboratory ware — Beakers.*