

This is a preview of "ISO 10545-12:1995". Click here to purchase the full version from the ANSI store.

STANDARD

10545-12

First edition
1995-11-15

Ceramic tiles —

Part 12:

Determination of frost resistance

Carreaux et dalles céramiques —

Partie 12: Détermination de la résistance au gel



Reference number
ISO 10545-12:1995(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 10545-12 was prepared by Technical Committee ISO/TC 189, *Ceramic tile*.

ISO 10545 consists of the following parts, under the general title *Ceramic tiles*:

- *Part 1: Sampling and basis for acceptance*
- *Part 2: Determination of dimensions and surface quality*
- *Part 3: Determination of water absorption, apparent porosity, apparent relative density and bulk density*
- *Part 4: Determination of modulus of rupture and breaking strength*
- *Part 5: Determination of impact resistance by measurement of coefficient of restitution*
- *Part 6: Determination of resistance to deep abrasion for unglazed tiles*
- *Part 7: Determination of resistance to surface abrasion for glazed tiles*
- *Part 8: Determination of linear thermal expansion*

© ISO 1995

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case Postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

This is a preview of "ISO 10545-12:1995". [Click here to purchase the full version from the ANSI store.](#)

- *Part 9: Determination of resistance to thermal shock*
- *Part 10: Determination of moisture expansion*
- *Part 11: Determination of crazing resistance for glazed tiles*
- *Part 12: Determination of frost resistance*
- *Part 13: Determination of chemical resistance*
- *Part 14: Determination of resistance to stains*
- *Part 15: Determination of lead and cadmium given off by glazed tiles*
- *Part 16: Determination of small colour differences*
- *Part 17: Determination of coefficient of friction*

This is a preview of "ISO 10545-12:1995". Click here to purchase the full version from the ANSI store.

Ceramic tiles —

Part 12: Determination of frost resistance

1 Scope

This part of ISO 10545 specifies a method for determining the frost resistance of all ceramic tiles intended for use in freezing conditions in the presence of water.

2 Principle

After impregnation with water, submission of the tiles to a cycle between + 5 °C and – 5 °C, all the sides of the tiles being exposed to freezing during a minimum of 100 freeze-thaw cycles.

3 Apparatus and materials

3.1 Drying oven, capable of being operated at (110 ± 5) °C.

Microwave, infrared or other drying systems may be used provided that it has been determined that the same results are obtained.

3.2 Balance, accurate to 0,01 % of the mass of a test specimen.

3.3 Apparatus for impregnation with water after evacuation, by means of a vacuum pump capable of lowering the air pressure by (60 ± 4) kPa in a tank containing the tiles.

3.4 Freezer, capable of freezing at least 10 tiles having a minimum total surface area of 0,25 m², supported in such a manner that the tiles shall be separated.

3.5 Chamois leather.

3.6 Water, maintained at a temperature of (20 ± 5) °C.

3.7 Thermocouple, or another suitable temperature measuring device.

4 Test specimens

4.1 Sample

A minimum area of 0,25 m² and not less than 10 whole tiles shall be used. The tiles shall be free from defects. Relevant defects are cracks, crazing, holes, nipped edges and nipped corners.

If tiles with defects have to be tested, the defects shall be marked with a permanent stain prior to the test and these defects shall be examined after testing.

4.2 Preparation of test specimens

The tiles shall be dried in the oven (3.1) adjusted to (110 ± 5) °C, until constant mass is reached, i.e. until the difference between two successive weighings at intervals of 24 h is less than 0,01 %. The dry mass of each tile (m_1) shall be recorded.

5 Impregnation with water

5.1 After cooling to ambient temperature, place the tiles vertically in the dry vacuum tank (3.3) with no contact between them and no contact with the vacuum tank.