

This is a preview of "ISO 11337:2023". [Click here to purchase the full version from the ANSI store.](#)

Third edition
2023-01

Plastics — Polyamides — Determination of ϵ -caprolactam and ω -lauro lactam by gas chromatography

*Plastiques — Polyamides — Détermination du ϵ -caprolactame et du
 ω -lauro lactame par chromatographie en phase gazeuse*



Reference number
ISO 11337:2023(E)

© ISO 2023

This is a preview of "ISO 11337:2023". Click here to purchase the full version from the ANSI store.



COPYRIGHT PROTECTED DOCUMENT

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

This is a preview of "ISO 11337:2023". [Click here to purchase the full version from the ANSI store.](#)

Contents

Page

Foreword.....	iv
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Method A: Extraction method.....	1
4.1 Principle.....	1
4.2 Reagents.....	1
4.3 Apparatus and materials.....	2
4.4 Preparation of test sample.....	3
4.5 Procedure.....	4
4.5.1 Test portion.....	4
4.5.2 Extraction.....	4
4.5.3 Preparation of internal-standard solution.....	4
4.5.4 Preparation of sample solution.....	4
4.5.5 Preparation of calibration solution.....	4
4.5.6 Gas-chromatographic analysis of sample and calibration solutions.....	4
4.5.7 Evaluation of gas chromatographic peaks.....	5
4.6 Expression of results.....	5
4.7 Precision.....	5
4.8 Test report.....	6
5 Method B: Dissolution method.....	6
5.1 Principle.....	6
5.2 Reagents.....	6
5.3 Apparatus.....	7
5.4 Preparation of internal-standard solutions.....	8
5.4.1 General.....	8
5.4.2 Internal standard for unextracted polyamide 6.....	8
5.4.3 Internal standard for extracted polyamide 6.....	8
5.4.4 Internal standard for polyamide 12.....	8
5.4.5 Preparation of calibration solutions.....	9
5.4.6 Calibration.....	10
5.5 Procedure.....	10
5.5.1 Preparation and injection of sample solution.....	10
5.5.2 Evaluation of gas-chromatographic peaks.....	10
5.5.3 Solvent recovery.....	10
5.6 Expression of results.....	11
5.7 Precision.....	11
5.8 Test report.....	11

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 9, *Thermoplastic materials*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 249, *Plastics*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This third edition cancels and replaces the second edition (ISO 11337:2010), which has been technically revised.

The main changes are as follows:

- isopropanol has been added as suitable internal standard for method A;
- the use of packed and capillary columns has been indicated specifically;
- the specification of suitable detectors has been opened.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.