

STANDARD

11503

First edition
1995-07-15

ANSI Internat Doc Sec

**Paints and varnishes — Determination of
resistance to humidity (intermittent
condensation)**

*Peintures et vernis — Détermination de la résistance à l'humidité (par
condensation intermittente)*



Reference number
ISO 11503:1995(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 11503 was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 9, *General test methods for paints and varnishes*.

Annex A forms an integral part of this International Standard.

© ISO 1995

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization

Case Postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

This is a preview of "ISO 11503:1995". [Click here to purchase the full version from the ANSI store.](#)

Introduction

There is seldom a direct relationship between the resistance of organic coatings to the action of humidity and the resistance to deterioration in other environments. This is because the effect of each of the several factors influencing the progress of deterioration varies greatly with the conditions encountered. Therefore, the results obtained in this test should not be regarded as a direct guide to the resistance of the tested coatings in all environments where these coatings may be used. Also, performance of different coatings in the test should not be taken as a direct guide to the relative performance of these coatings in service. Nevertheless, the method described gives a means of checking that the quality of a paint or paint system is being maintained.

This is a preview of "ISO 11503:1995". Click here to purchase the full version from the ANSI store.

Paints and varnishes — Determination of resistance to humidity (intermittent condensation)

1 Scope

This International Standard is one of a series of standards dealing with the sampling and testing of paints, varnishes and related products.

It specifies a test method for determining under standard conditions the resistance of a single coat or a multi-coat system of paint or related material to intermittent water condensation. The method includes the testing of coatings on non-porous and on porous substrates.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 1512:1991, *Paints and varnishes — Sampling of products in liquid or paste form*.

ISO 1513:1992, *Paints and varnishes — Examination and preparation of samples for testing*.

ISO 1514:1993, *Paints and varnishes — Standard panels for testing*.

ISO 2808:1991, *Paints and varnishes — Determination of film thickness*.

ISO 3270:1984, *Paints and varnishes and their raw materials — Temperatures and humidities for conditioning and testing*.

ISO 3696:1987, *Water for analytical laboratory use — Specification and test methods*.

ISO 4628-2:1982, *Paints and varnishes — Evaluation of degradation of paint coatings — Designation of intensity, quantity and size of common types of defect — Part 2: Designation of degree of blistering*.

ISO 8335:1987, *Cement-bonded particleboards — Boards of Portland or equivalent cement reinforced with fibrous wood particles*.

3 Principle

Coated specimens are placed in a cabinet or chamber containing a heated, saturated mixture of air and water vapour. The temperature of the cabinet or chamber is maintained at $(40 \pm 3) ^\circ\text{C}$. At 98 % to 100 % relative humidity, the very small temperature difference between the specimen and the surrounding vapour causes the formation of condensation on the specimens.

This is an intermittent condensation test and after a period of time under these conditions the conditions in the cabinet or chamber are cycled to give $(23 \pm 5) ^\circ\text{C}$ and $(50 \pm 20) \%$ relative humidity, i.e. dry conditions.

Water permeates the coating at rates that are dependent upon the characteristics of the coating. Any effects such as colour change, blistering, loss of adhesion, softening or embrittlement are observed and reported using criteria previously agreed between the interested parties, these criteria usually being of a subjective nature.