

This is a preview of "ISO 11844-1:2006". [Click here to purchase the full version from the ANSI store.](#)

First edition  
2006-03-15

---

---

## **Corrosion of metals and alloys — Classification of low corrosivity of indoor atmospheres —**

### **Part 1: Determination and estimation of indoor corrosivity**

*Corrosion des métaux et alliages — Classification de la corrosivité  
faible des atmosphères d'intérieur —*

*Partie 1: Détermination et estimation de la corrosivité des atmosphères  
d'intérieur*



Reference number  
ISO 11844-1:2006(E)

© ISO 2006

This is a preview of "ISO 11844-1:2006". [Click here to purchase the full version from the ANSI store.](#)

**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

© ISO 2006

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

This is a preview of "ISO 11844-1:2006". Click here to purchase the full version from the ANSI store.

## Contents

Page

<b>Foreword</b> .....	<b>iv</b>
<b>Introduction</b> .....	<b>v</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>2</b>
<b>4 Symbols and abbreviations</b> .....	<b>2</b>
<b>5 Classification of corrosivity</b> .....	<b>3</b>
<b>5.1 General</b> .....	<b>3</b>
<b>5.2 Categories of indoor corrosivity</b> .....	<b>3</b>
<b>6 Determination of indoor atmospheric corrosivity</b> .....	<b>3</b>
<b>7 Characterization of indoor atmospheres with respect to indoor corrosivity</b> .....	<b>3</b>
<b>7.1 General</b> .....	<b>3</b>
<b>7.2 Estimation of indoor corrosivity</b> .....	<b>4</b>
<b>Annex A (informative) Relation between ISO, IEC and ISA classification systems</b> .....	<b>6</b>
<b>Annex B (informative) Outdoor and indoor concentrations of some of the most important pollutants in different types of environments</b> .....	<b>9</b>
<b>Annex C (informative) General characterisation of metal corrosion in indoor atmospheres</b> .....	<b>10</b>
<b>Annex D (informative) Guideline for estimation of indoor corrosivity</b> .....	<b>13</b>
<b>Bibliography</b> .....	<b>16</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 11844-1 was prepared by Technical Committee ISO/TC 156, *Corrosion of metals and alloys*.

ISO 11844 consists of the following parts, under the general title *Corrosion of metals and alloys — Classification of low corrosivity of indoor atmospheres*:

- *Part 1: Determination and estimation of indoor corrosivity*
- *Part 2: Determination of corrosion attack in indoor atmospheres*
- *Part 3: Measurement of environmental parameters affecting indoor corrosivity*

This is a preview of "ISO 11844-1:2006". [Click here to purchase the full version from the ANSI store.](#)

## Introduction

Metals, alloys and metallic coatings are subject to atmospheric corrosion under the impact of air humidity, especially when gaseous and solid substances of atmospheric pollution co-impact. Corrosivity data are of fundamental importance for derivation of suitable corrosion protection, or for evaluation of serviceability of metal elements of a product.

ISO 9223 classifies the atmospheric environment into 5 corrosivity categories.

Low-corrosivity indoor atmospheres are indoor atmospheres with C 1 (very low) or C 2 (low) corrosivity categories according to ISO 9223.

The classification in ISO 9223 is too broad for some purposes in low-corrosivity indoor atmospheres, e.g. places where electronic devices, sophisticated technical products, or works of art and historical objects are stored.

For such purposes, it is necessary to subdivide the corrosivity categories C 1 (very low) and C 2 (low) into indoor corrosivity categories in this part of ISO 11844.

The evaluation of low-corrosivity indoor atmospheres can be accomplished by direct determination of corrosion attack of selected metals (see ISO 11844-2) or by measurement of environmental parameters (see ISO 11844-3) which may cause corrosion on metals and alloys.

This part of ISO 11844 describes general procedures for derivation and estimation of indoor corrosivity categories.

A general approach to classification of corrosivity in indoor atmospheres is given in the scheme shown in Figure 1.

This is a preview of "ISO 11844-1:2006". [Click here to purchase the full version from the ANSI store.](#)




Figure 1 — Scheme for classification of low corrosivity in indoor atmospheres