

This is a preview of "ISO 12091:1995". [Click here to purchase the full version from the ANSI store.](#)

First edition
1995-12-01

Structured-wall thermoplastics pipes — Oven test

Tubes en matières thermoplastiques à parois structurées — Essai à l'étuve



Reference number
ISO 12091:1995(E)

This is a preview of "ISO 12091:1995". [Click here to purchase the full version from the ANSI store.](#)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 12091 was prepared by Technical Committee ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*, Subcommittee SC 5, *General properties of pipes, fittings and valves of plastic materials and their accessories — Test methods and basic specifications*.

Annex A forms an integral part of this International Standard. Annexes B and C are for information only.

© ISO 1995

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case Postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

This is a preview of "ISO 12091:1995". [Click here to purchase the full version from the ANSI store.](#)

Structured-wall thermoplastics pipes — Oven test

1 Scope

This International Standard specifies a method for assessing the pipe wall homogeneity of non-smooth, structured-wall thermoplastics pipes by inspection of the effects of heating in an oven.

The method is not applicable to the testing of pipes with a smooth external surface.

NOTE 1 This test does not include measurement of the longitudinal reversion (see annex C).

2 Definitions

For the purposes of this International Standard, the following definitions apply:

2.1 wall separation: Separation between the layers in multilayer designs.

NOTE 2 Wall separation is normally recognized as the formation of visible bubbles in the surface layer of the pipe. Separation of layers at the cut ends is not considered to constitute a failure.

2.2 blister: Separation of a pipe wall layer internally in the form of a bubble.

3 Principle

A piece of pipe of given length is heated in an oven at a specified temperature for a specified length of time.

After the heating period, the surfaces of the pipe are examined and any physical defects such as cracks, blisters or wall separation are noted. Cracks and blisters are expressed as a percentage of the wall thickness. Wall separation is expressed as a percentage of the pipe circumference.

4 Apparatus

4.1 Air-circulation oven, thermostatically controlled, with a heating power such that it is capable of operating at the temperature specified in annex A for the material under test and re-establishing this temperature within 15 min after the introduction of the test pieces.

The oven shall be equipped with a thermostat capable of maintaining the temperature to within ± 2 °C of the specified temperature.

5 Test pieces

5.1 The sampling procedure for obtaining test pieces shall be as specified in the referring standard.

5.2 Each test piece shall comprise a pipe of length $300 \text{ mm} \pm 20 \text{ mm}$. The test piece may be cut longitudinally into two equal-sized sections if the outside diameter is less than or equal to 400 mm, or four equal-sized sections if the outside diameter is greater than 400 mm.

NOTE 3 The referring standard should define the optional procedure for cutting the test piece into sections. This will depend on the wall structure of the pipe.

5.3 The number of test pieces shall be as specified in the referring standard. However, it is recommended to use at least three test pieces.

6 Procedure

6.1 Condition the test pieces (or test piece sections) for at least 2 h at $23 \text{ °C} \pm 2 \text{ °C}$.

6.2 Establish the oven temperature at the value specified in annex A for the material under test.

6.3 Place the test pieces in the oven in such a manner that they do not touch each other or the sides of the oven.