

This is a preview of "ISO 12900:2018". [Click here to purchase the full version from the ANSI store.](#)

Third edition
2018-11

Hard coal — Determination of abrasiveness

Houille — Détermination de l'abrasivité



Reference number
ISO 12900:2018(E)

© ISO 2018

This is a preview of "ISO 12900:2018". [Click here to purchase the full version from the ANSI store.](#)



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

This is a preview of "ISO 12900:2018". [Click here to purchase the full version from the ANSI store.](#)

Contents

| | Page |
|--|-----------|
| Foreword | iv |
| Introduction | v |
| 1 Scope | 1 |
| 2 Normative references | 1 |
| 3 Terms and definitions | 1 |
| 4 Principle | 1 |
| 5 Apparatus | 1 |
| 6 Sample preparation | 5 |
| 7 Procedure | 8 |
| 8 Calculation | 8 |
| 9 Reporting of results | 8 |
| 10 Precision of the determination | 8 |
| 11 Test report | 9 |
| Bibliography | 10 |

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 27, *Solid mineral fuels*, Subcommittee SC 5, *Methods of analysis*.

This third edition cancels and replaces the second edition (ISO 12900:2015), of which it constitutes a minor revision to provide clarification on how to operate the abrasion test machine in [Clause 7](#).

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

This is a preview of "ISO 12900:2018". [Click here to purchase the full version from the ANSI store.](#)

Introduction

The abrasiveness of coal is recognized as a factor in coal operations, from mining to utilization, requiring a standard method of measurement and evaluation, as some coals are more abrasive than others.

The interaction between coal and conveying, storage, and crushing equipment results in component wear. In particular, higher contact pressures in some coal pulverizers result in significant wear.

For the ranking or relative comparison of the abrasiveness of coals, a test was developed^[1] which standardized the following equipment variables:

- a) test equipment dimensions and tolerances;
- b) speed of rotation of wearing components;
- c) properties of the wearing components;
- d) mass of the test portion;
- e) top particle size of the test portion;
- f) duration of the test.

The abrasiveness of coal is generally a function of two factors: the physical properties of the coal, in particular, moisture content, mineral content, and mineral characteristics^{[1][2][3][4][5][6]}; the mechanics of the operations to which the coal is subjected.

NOTE Moisture contents over 10 % in the test sample after air-drying and laboratory equilibration might give anomalous results; the reason for this has not been established.

Wear on coal-pulverizing elements in industrial mills is influenced by the physical characteristics of the coal and its mineral constituents, the mechanical characteristics of the mill, including the milling pressures, alloy material properties and coal feed flow, and the operation of the mill. Abrasiveness as determined by this document has been demonstrated to provide initial empirical estimates of specific wear rates in certain types of industrial tube-ball mills, vertical spindle mills, and high-speed hammer mills^{[3][6]}, with different coefficients for each mill type.

Abrasiveness as determined by this document might be of value in providing an initial estimate of the likely wear in other applications, giving the relative effect of different coals.